Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Flooring

O-Prime SF

Solvent-Free Epoxy Primer
& Sealer for Concrete Floors



Product Description

O-Prime SF is a high-performance, two-component, solvent-free epoxy primer that penetrates and seals concrete surfaces. It is the base coat for O MIX epoxy and polyurethane floor systems and can also be applied on steel and aluminium.

Uses

- Primer for epoxy and polyurethane floor systems.
- Sealing porous concrete and screeds.
- Dust-proofing of concrete floors.
- Primer on steel and aluminium substrates.
- Base coat in O MIX floor systems ST, MD, HD and HD Pro.

Advantages

- Solvent-free, 100 % solids.
- Deep penetration, seals pores.
- Excellent adhesion: 3 N/mm².
- High mechanical strength.
- Flash point 140 °C.

Application

1. **Surface Preparation**
   Concrete ≥ 28 days, dry (< 4 %). Grind or shot blast and vacuum all dust.
2. **Mixing**
   Add all of Part B to Part A and mix 2 – 3 min below 300 rpm.
3. **Application**
   Roll 0.10 – 0.15 kg/m². Overcoat within 24 h or broadcast sand.

Consumption

0.10 – 0.15 kg/m² per coat
Two coats on very porous substrates
Depends on substrate porosity.

Packaging

5 kg sets: Part A in pail + Part B in jerrycan.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Mixing ratio (A : B)	As recommended — pre-weighed sets	—
Solids content	100 %	—
Specific gravity	1.06	ASTM D1475
Flash point	140 °C	—
Pot life (25 °C)	40 min	—
Recoat interval	10 hours (max. 24 hours)	—
Foot traffic	24 hours	—
Adhesion to concrete	3 N/mm² (concrete failure)	ASTM D4541
Compressive strength	70 N/mm²	ASTM D695
Flexural strength	50 N/mm²	ASTM D790
Tensile strength	40 N/mm²	ASTM D638

Consumption

Substrate	Coats	Consumption
Dense concrete	1	0.10 – 0.15 kg/m²
Porous concrete / screed	2	0.10 – 0.15 kg/m² per coat
Steel / aluminium	1	0.10 – 0.15 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Substrate at least 3 °C above dew point.
- Relative humidity: max. 85 %.
- Substrate moisture content: < 4 %.
- Concrete at least 28 days old, ≥ 25 N/mm², pull-off ≥ 1.5 N/mm².

Application Notes

- Mix with a slow-speed mixer below 300 rpm to avoid air entrapment.
- Apply by roller or brush; do not leave puddles.
- Apply two coats on very porous substrates.
- Overcoat within 24 hours; otherwise broadcast 0.1 – 0.4 mm quartz sand into the wet primer.
- Do not thin.

Health & Safety

- Wear nitrile gloves, safety goggles and overalls.
- Uncured epoxy may cause skin sensitisation; avoid skin and eye contact.
- Ensure good ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Clean tools with epoxy thinner before the material cures.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.