Construction Chemicals

**Product Datasheet**
Edition: 01 | Date: Nov 2026
**Flooring**




# O-Putty

Two-Component Epoxy Filler
for Concrete, Steel & Equipment

## Product Description

O-Putty is a two-component, solvent-based epoxy filler for high-performance repairs. It fills cracks, voids and surface defects in concrete, steel and equipment, dries quickly and resists heat, chemicals and bacteria. Any epoxy coating can be applied over it after light sanding.

## Uses

- Filling cracks and voids in concrete floors.
- Industrial, food and pharmaceutical floors.
- Garages, bridges and ramps.
- Repair of tanks, drums, pipes and equipment.
- Filling layer in O MIX floor systems.

## Advantages

- Fast drying.
- Resistant to heat, chemicals and bacteria.
- High compressive strength: 60 N/mm².
- Excellent adhesion to concrete and steel.
- Can be overcoated with any epoxy.

## Application

1. **Surface Preparation**
   Clean, dry and sound substrate. Remove dust, oil, rust and loose particles.
2. **Mixing**
   Mix Part A and Part B 1 : 1 by volume until uniform in colour.
3. **Application**
   Fill and level with a spatula or trowel. Sand lightly before coating.

## Consumption

**0.25 – 0.30 kg/m²**
As a skim / filling layer
Higher on rough or damaged surfaces.

## Packaging

5 kg sets (Part A + Part B), metal tins.

## Storage & Shelf Life

12 months in original, unopened packaging.
Store dry and cool, away from heat and ignition sources.

## Technical Data

*Typical values at 25 °C*

| Property | Typical Value | Test Method |
|---|---|---|
| **Mixing ratio (A : B)** | 1 : 1 by volume | — |
| **Colour** | White grey | — |
| **Pot life (25 °C)** | 60 min | — |
| **Drying time** | 24 hours | — |
| **Full cure** | 7 days | — |
| **Compressive strength** | 60 N/mm² | ASTM D695 |
| **Flexural strength** | 30 N/mm² | ASTM D790 |
| **Shelf life** | 12 months | — |

## Consumption

| Use | Consumption |
|---|---|
| **Skim / filling layer in floor systems** | 0.25 – 0.30 kg/m² |
| **Crack and void filling** | According to volume of defect |

*Consumption is theoretical and varies with substrate porosity, profile and application method.*

## Application Conditions

- Ambient and substrate temperature: +10 °C to +35 °C.
- Substrate at least 3 °C above dew point.
- Relative humidity: max. 85 %.
- Substrate moisture content: < 4 %.

## Application Notes

- Mix equal volumes of Part A and Part B on a clean board until uniform.
- Apply with a steel spatula or trowel; press well into cracks.
- Allow 24 hours drying, then sand lightly before overcoating.
- Keep away from flames — contains solvent.

## Health & Safety

- Contains solvent: keep away from sparks, flames and smoking.
- Wear gloves, goggles and overalls; use a mask in enclosed areas.
- Ensure good ventilation.

## First Aid & Cleaning

- Eyes: rinse with clean water for 15 minutes and seek medical advice.
- Skin: wash with soap and water.
- Clean tools with epoxy thinner before the material cures.

*The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.*