Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Repair and Grouting Materials



Cemix Crete

Self-Compacting
Cementitious Micro-Concrete

Product Description

Cemix Crete is a self-compacting, cement-based micro-concrete for large-volume grouting and deep repairs. It flows into place without vibration and achieves high strength.

Uses

- Grouting under heavy machine bases.
- Strengthening of foundations.
- Deep section repairs.
- Bridge bearings.

Advantages

- Self-compacting; no vibration.
- 28-day strength ≥ 65 MPa.
- Large-volume placement.
- Non-shrink.
- Just add water.

Application

1. **Surface Preparation**
   Remove weak concrete; roughen; pre-wet to SSD; seal formwork.
2. **Mixing**
   Add 11 – 14 % water and mix 3 – 5 minutes with a forced-action mixer.
3. **Placing**
   Pour continuously from one side to avoid air entrapment; cure immediately.

Consumption

12 – 13 L
yield per 25 kg bag
Approx. 2.3 kg of powder per litre of void.

Packaging

25 kg bags.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Water demand	11 – 14 %	—
Density	2.3 kg/L	—
Setting time	4 – 6 hours	—
Compressive strength, 7 days	≥ 45 MPa	—
Compressive strength, 28 days	≥ 65 MPa	—
Application temperature	+5 °C to +40 °C	—

Consumption

Item	Value
Yield per 25 kg bag	12 – 13 L
Bags per m³	approx. 80

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Application temperature: +5 °C to +40 °C.
- Substrate pre-wetted to SSD.
- Formwork sealed and rigid.

Application Notes

- Use a forced-action mixer.
- Do not add water beyond the maximum.
- Pour continuously from one side.
- Cure with wet hessian or curing compound.

Health & Safety

- Wear gloves, safety goggles and a dust mask when mixing.
- Contains cement; alkaline when wet. Avoid skin and eye contact.
- Avoid inhaling dust.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: wash with soap and water; cement is alkaline when wet.
- Inhalation of dust: move to fresh air.
- Ingestion: rinse mouth and seek medical advice.
- Clean tools and mixers with water immediately after use.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.