Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Repair and Grouting Materials

Epogrout

Water-Repellent Epoxy Grout
for Underwater & Marine Repairs



Product Description

Epogrout is a two-component, water-repellent epoxy grout and repair compound for underwater and marine works. It is used for grouting under machine bases, fixing bolts and reinforcement under water, filling cracks and grouting acid-resistant tiles. It is resistant to fungi and bacteria.

Uses

- Underwater and marine repairs.
- Piers and jetties.
- Fixing bolts and rebars under water.
- Grouting under machine bases.
- Crack filling and acid-resistant tile joints.

Advantages

- Cures under water.
- Compressive strength 88.4 N/mm².
- Very low shrinkage: 0.07 %.
- Resists fungi, bacteria and chemicals.
- 0.5 – 30 mm thickness.

Application

1. **Surface Preparation**
   Remove marine growth, weak concrete and rust; clean steel.
2. **Mixing**
   Add Part B to Part A (12 : 1 by weight) and mix at 400 – 500 rpm.
3. **Application**
   Place by trowel or pour; aggregate may be added up to 2 : 1 for thick sections.

Consumption

approx. 2.0 kg/m²
per mm thickness
Density 1.95 kg/L.

Packaging

20 kg sets (18.46 kg A + 1.54 kg B) and 5 kg sets (4.62 kg + 0.38 kg).

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Mixing ratio (A : B)	12 : 1 by weight	—
Density	1.95 kg/L	—
Viscosity	3000 mPa·s	—
Pot life	60 min	—
Initial cure	8 hours	—
Load cure	24 hours	—
Full hardness	7 days	—
Compressive strength	88.4 N/mm²	—
Tensile strength	15 N/mm²	—
Shear strength	14 N/mm²	—
Shrinkage	0.07 %	—
Water absorption	0.45 %	—
Min. temperature	+15 °C	—

Consumption

Thickness	Consumption
1 mm	approx. 2.0 kg/m²
10 mm	approx. 20 kg/m²
Thick sections	Extend with aggregate up to 2 : 1

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Minimum temperature: +15 °C.
- Surfaces may be wet or submerged.

Application Notes

- Mix at 400 – 500 rpm.
- Minimum application temperature +15 °C.
- For thick sections add dry aggregate up to 2 : 1.
- Place continuously to avoid cold joints.

Health & Safety

- Wear chemical-resistant gloves, safety goggles and overalls.
- Uncured resin may cause skin sensitisation; avoid skin and eye contact.
- Ensure good ventilation in enclosed areas.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: remove contaminated clothing and wash with soap and water; do not use solvents on skin.
- Inhalation: move to fresh air; seek medical advice if symptoms persist.
- Ingestion: do not induce vomiting; seek medical advice immediately.
- Clean tools with the recommended thinner before the material cures.