Construction Chemicals

Product Datasheet
Edition: 01 | Date: Nov 2026
Repair and Grouting Materials



O-Patch C

Fibre-Reinforced Polymer-Modified Repair Mortar

Product Description

O-Patch C is a fibre-reinforced, polymer-modified cementitious repair mortar for vertical and overhead repairs of beams, columns, slabs and soffits. It is applied in 5 – 40 mm layers and usually needs no bonding agent.

Uses

- Beams and columns.
- Slabs and soffits.
- Patching and levelling.
- Spalled concrete.

Advantages

- Vertical and overhead application.
- 5 – 40 mm per layer.
- 28-day strength ≥ 45 MPa.
- Bond strength ≥ 2.0 MPa.
- Fibre-reinforced.

Application

1. **Surface Preparation**
   Remove damaged concrete; clean and treat rebars; pre-wet to SSD.
2. **Mixing**
   Add 13 – 15 % water and mix 3 minutes to a uniform paste.
3. **Application**
   Apply by trowel or hand in 5 – 40 mm layers; cure.

Consumption

1.8 – 2.0 kg/m²
per mm thickness

Packaging

25 kg bags.

Storage & Shelf Life

12 months in original, unopened packaging. Store dry at +5 °C to +35 °C, away from direct sunlight.

Technical Data

Typical values at 25 °C

Property	Typical Value	Test Method
Density	2.0 – 2.1 kg/L	—
Water demand	13 – 15 %	—
Pot life	30 – 40 min	—
Setting time	3 – 5 hours	—
Compressive strength, 7 days	≥ 30 MPa	—
Compressive strength, 28 days	≥ 45 MPa	—
Flexural strength	≥ 7 MPa	—
Bond strength	≥ 2.0 MPa	—
Layer thickness	5 – 40 mm	—

Consumption

Thickness	Consumption
10 mm	18 – 20 kg/m²
20 mm	36 – 40 kg/m²

Consumption is theoretical and varies with substrate porosity, profile and application method.

Application Conditions

- Application temperature: +5 °C to +40 °C.
- Substrate SSD.

Application Notes

- Protect exposed rebars with O-Zinc I where specified.
- Apply in layers of 5 – 40 mm.
- Scratch each layer before the next.
- Cure for at least 3 days.

Health & Safety

- Wear gloves, safety goggles and a dust mask when mixing.
- Contains cement; alkaline when wet. Avoid skin and eye contact.
- Avoid inhaling dust.

First Aid & Cleaning

- Eyes: rinse immediately with plenty of clean water for at least 15 minutes and seek medical advice.
- Skin: wash with soap and water; cement is alkaline when wet.
- Inhalation of dust: move to fresh air.
- Ingestion: rinse mouth and seek medical advice.
- Clean tools and mixers with water immediately after use.

The information in this datasheet is based on laboratory tests and practical experience and is given in good faith. Users should verify product suitability for their specific application. O MIX reserves the right to update this information without prior notice.