




Pevalit

G5 light

Cement Plaster



APPLICATION

- Plaster based on cement.
- For plastering walls and ceilings, in indoor and outdoor environments.
- Usage on facades, basements, baths, rooms, etc.
- Adaptable for all base layers, such as baked bricks, clay bricks, limestone or concrete blocks, etc.
- Sprayed by hand or by machine.
- Before use in places of smooth and gasbeton concrete, binding liquid or PEVALIT-G2 needs to be used.

Layer Thickness	Consumption	Surface Covered with 25kg PEVALIT - G5 Light
10 mm	approx. 17 kg/m ²	approx. 1.5 kg/m ²
15 mm	approx. 25 kg/m ²	approx. 1 kg/m ²
20 mm	approx. 32 kg/m ²	approx. 0.8 kg/m ²

- Sanding:** From 0-1.5 mm.
- Layer thickness:** between 0.8 and 4 cm.
- Dry mass density:** 1050/1250 kg/1m³
- Steam permeability coefficient:** ca.23.
- Norm:** MKC EN 998-1/Kop: 2006.
- Pressure durability (after 28 days):** CS I, ca. 3.2 N/mm².
- Purpose and Water absorption:** GP, W0.
- Temperature conductivity:** 0,75 W/mK.
- Reaction to fire:** A1.
- Work temperatures:** +5°C - +30°C.
- Mixing with water:** with approximately 7.5 l/25kg.
- Material color:** Grey.
- Packaging:** 25 kg.
- Best before:** In the original packaging 12 months, in a warehouse without moisture.