



Pevalit Stir 10

Adhesive for
insulating facades



APPLICATION

- Used in thermo insulation facade systems.
- Adhesion of insulation panels in facades.
- Leveling of insulation panels and covering those with a reinforcing mesh, thickness of 4 to 8 mm.
- Insulation panels should be of expanded polystyrene (Styrofoam), or from mineral fibers.
- Usage in layers of indoor or outdoor environments.

TECHNICAL PARAMETERS

- Sanding: From 0-1.0 mm.
- Dry mass density: 1500-1900 kg/m³
- Norm: MKC EN ETAG 004, ETA-11/0340
- Work temperatures: +5°C - +30°C.
- Mixing with water: approximately 4 min., with around 26-28% water/25kg.
- Working time in container: Up to 4 hours after mixing.
- Spending: for panel adhesion 4-5 kg/m²; for covering panels with reinforcing mesh 4-5 kg/m²
- Adhesion (separation) from the layers of concrete: After 28 days 0.3 N/mm²
- Adhesion (separation) from the layers of polystyrene: After 28 days 0.08 N/mm²
- Material color: Grey.
- Packaging: 25 kg.
- Best before: In the original packaging 12 months, in a warehouse without moisture.