BIO-INSPIRED STRUCTURAL ENGINEERI

HONEY COMB & SPIDER WEB

Inspired Structural Engineering






C332- ARJUN NAYAK
C331- MOHAMMED RAYAAN NASEEM
C341-ADVAIT PANDYA
C347-KHUSHIT PATIDAR

WHAT WE'RE COVERING:

CORE PROBLEMS → BIOLOGICAL WORKINGS → BIOMIMICRY → TIMELINE → APPLICATIONS → FUTURE PROSPECTS


SO
WHATS
THE
PROBLEM

PROBLEM STATEMENT:

Conventional engineering forces a costly compromise: materials are either strong but brittle, or lightweight but structurally weak under extreme loads. By mimicking spider silk mechanics and honeycomb geometry, we can engineer ultra-lightweight structures that maximize kinetic energy absorption and crushing resistance without toxic, energy-heavy processing

THE CORE PROBLEMS

1) Tensile vs. Toughness Trade-off: Traditional synthetics for example, carbon fiber, Kevlar, Steel sacrifice extensibility for strength and rely on high temperatures and toxic chemical solvents during Manufacturing

2) Catastrophic Brittle failure and Chemical costs and Structural and Environmental shortcomings of Modern Synthetics

3) Buckling & Mass Inefficiency: Solid structural materials add dead weight and are vulnerable to out of plane bending and buckling under localized crash impacts




PROBLEM 1: The Tensile Strength vs. Toughness Compromise

Why Conventional High-Performance Materials Fail Under Dynamic Loads

Extensibility Compromise: Traditional synthetics like steel, carbon fiber, and Kevlar sacrifice flexibility to achieve high tensile strength and rigidity.

Poor Dynamic Absorption: Rigid materials cannot deform dynamically during sudden impacts, causing localized stress concentrations instead of wide energy dissipation.

Narrow Operating Window: Designing strictly for peak stiffness makes materials brittle, preventing effective kinetic energy




PROBLEM 2: Catastrophic Brittle Failure & Chemical Costs

Structural and Environmental Shortcomings of Modern Synthetics

Instantaneous Crack Growth: Without internal energy-dissipating mechanisms, micro-cracks spread rapidly across synthetic matrices, triggering abrupt structural failure without warning.

No Sacrificial Bonds: Unlike biological fibers, synthetic polymers lack sacrificial molecular bonds that break locally to absorb kinetic impact energy before catastrophic collapse occurs.

Energy-Intensive & Toxic Processing: Manufacturing materials like Kevlar, carbon fiber, and steel demands extreme temperatures and toxic chemical solvents, creating a large



PROBLEM 3: Mass Inefficiency & Structural Buckling

Geometric Limitations in Bending and Crash Compression

Dead Weight Near Neutral Axes: Solid beams concentrate mass near the center where flexural stresses are lowest, resulting in inefficient, heavy structures.

Out-of-Plane Buckling: Solid monolithic panels are prone to abrupt out-of-plane buckling and bending failure under localized crash loads.

Transverse Shear Vulnerability: Non-cellular solid plates lack internal core separation to resist transverse shear and bending




COLUMN BUCKLING



TORTIONAL BUCKLING OF BEAM


THE BIOLOGICAL
SOLUTION



HOW
THE
BIOLOGY
WORKS
Biology
A+


Spider Silk: Glandular Specialization & Silk Types

- **Major Ampullate Glands:** Produce spidroin proteins for the outer structural frame and radial spokes (dragline silk).

- **Flagelliform Glands:** Synthesize an ultra-elastic protein core for capture spirals, achieving up to 300% extensibility.

- **Aggregate Glands:** Secrete sticky glycoprotein adhesive droplets along the spiral threads to trap






Spider Silk: Molecular Hierarchy & Phase Transition


- **Alanine-Rich beta-Sheet Nanocrystals (2–5 nm):** Form dense hydrogen-bonded networks that provide extreme tensile strength (~1.1–1.3 GPa) and modulus.

- **Glycine-Rich Amorphous Matrix:** Random coils and helices (GPGXX motifs) deliver high extensibility (30–40%) and fracture energy (~160 MJ/m³).

- **Shear-Induced Spinning:** Concentrated liquid dope (30–50% protein) transitions to solid fiber driven by a pH drop (7.2 to <5.5), ion exchange, and shear draw under ambient conditions.

https://iopscience.iop.org/article/10.1088/0004-637X/735/1/60






Spider Web: Structural Mechanics & Energy Dissipation

- **Nonlinear Strain-Hardening:** Silk fibers exhibit initial elasticity, yield under moderate load, and stiffen dramatically before rupture.

- **Sacrificial Failure Mechanism:** Under extreme wind gusts or high-speed impacts, individual threads break locally to preserve the global web integrity.

- **Vibrational Damping & Sensing:** Tensegrity network transmits high-frequency acoustic and tactile vibrations across radial spokes for rapid prey localization

https://physicsworld.com/a/spider-webs-strengthened-by-localization/



Bees are Mathematicians!




Honeycomb: Biological Construction & Geometry


Honeycomb: Biological Construction & Geometry

- **Economics of Wax:** Worker bees consume 6–8 g of honey per 1 g of secreted wax, creating intense evolutionary pressure to minimize wall material.

- **The Honeycomb Conjecture:** 2D regular hexagonal arrays provide the mathematical minimum total perimeter to partition space into equal areas.

- **Thermal Self-Assembly:** Bees heat the hive to 35°C–40°C with thoracic muscles, allowing surface tension to pull circular wax cavities into 120° planar hexagonal junctions.





https://pmc.ncbi.nlm.nih.gov/articles/PMC5452082/

Hales, T. (2001). The Honeycomb Conjecture. Discrete & Computational Geometry. 25. 1-22. 10.1007/s004540010071.


Karihaloo, BL, Zhang, K & Wang, J 2013, 'Honeybee combs: How the circular cells transform into rounded hexagons', *Journal of the Royal Society Interface*, vol. 10, no. 86, 0299. https://doi.org/10.1098/rsif.2013.0299

Honeycomb Gravitational Tilt & Anisotropic Mechanics

Cellular Alignment: Built with an upward 9° – 14° angle to prevent low-viscosity, un-ripened honey from spilling before cell capping.

•**In-Plane Loading:** Exhibits high compliance and flexural cell-wall bending under lateral forces.

•**Out-of-Plane Loading:** Delivers exceptional axial stiffness and high compressive strength parallel to the cell axes.




Honeycomb: Progressive Buckling & Energy Absorption

Progressive Buckling Plateau: Under axial crash forces, cell walls collapse into localized plastic hinges to maintain a steady crushing force.

- **Mass-Efficient Energy Dissipation:** The folding mechanism maximizes kinetic energy absorption per unit mass compared to solid monolithic materials.

- **Core Separation in Sandwich Panels:** Honeycomb cores resist transverse shear forces while separating dense face sheets to





HOW THE ENGINEERS MIMICK THE BIOLOGY



1: Solving the Strength Vs. Toughness Trade-off (Polymer Nanocomposites)


The Problem Solved: Eliminates the classic material engineering compromise where increasing tensile strength creates brittle failure modes.

•**Bio-Inspired Architecture:** Hard ceramic or carbon nanoparticles mimic alanine beta-sheet nanocrystals, while ductile polymer chains replicate the glycine-rich matrix.

•**Engineering Impact:** Creates lightweight, fracture-resistant composites for high-performance aerospace components, impact-resistant casings, and advanced textiles.

Biological Element Mimicked: The molecular hierarchy of spider silkspecifically the dual interface between alanine-rich Beta-sheet nanocrystals (providing strength) embedded in a glycine-rich amorphous matrix (providing extensibility)

Biomimetic nanofibrillar composites exhibit up to a **377.6% increase** in strain and extensibility before fracture compared to pure synthetic polymers, enabling massive energy dissipation and a transition from brittle to ductile failure.



2: Eliminating Toxic, High-Heat Processing (Microfluidic Green Spinning)


(The Problem Solved: Replaces energy-intensive melting and hazardous chemical solvent baths with ambient manufacturing methods.

•**Bio-Inspired Architecture:** Microfluidic channels replicate the spider spinning duct using controlled pH gradients, ion exchange, and shear draw to fold synthetic spidroin proteins.

•**Engineering Impact:** Produces high-strength, biocompatible, and biodegradable fibers for surgical sutures, artificial ligaments, and sustainable textiles.

(Microfluidic Green Spinning):

Biological Element Mimicked: The spider's natural spinning duct environment, replicating shear stress draw, sodium/potassium ion exchange, and a progressive pH gradient (pH 7.2 down to <5.5) for solvent-free ambient protein



Achieves a **100% reduction** in toxic chemical solvent usage. The biomimetic process relies entirely on ambient aqueous environments and controlled pH drops, eliminating the energy-intensive high-heat processing (often 400°C+) required for synthetic fibers.

3: Preventing Sudden Catastrophic Rupture (Dynamic Strain-Hardening & Tethers)

- **The Problem Solved:** Stops instantaneous crack propagation and widespread structural collapse under high-velocity dynamic shocks.
-
- **Bio-Inspired Architecture:** Employs nonlinear strain-hardening mechanics and sacrificial local yielding inspired by orb-web load distribution.


- **Engineering Impact:** Applied in aircraft carrier arrestor cables, body armor, and seismic tethering nets that absorb extreme dynamic shocks without global failure.

(Dynamic Strain-Hardening & Tethers):

Biological Element Mimicked: The whole-web structural mechanics, specifically nonlinear strain-hardening and the sacrificial failure mechanism where individual silk threads yield locally to protect the entire structure

Utilizing spoke-wheel radial tension designs inspired by spider web geometry yields up to a **60% reduction** in structural roof steel weight. Under dynamic rockfall testing, biomimetic ring-nets achieve massive energy absorption efficiencies





4: Eliminating Dead Weight in Bending (Honeycomb Sandwich Panels)

The Problem Solved: Eliminates heavy, inefficient material near neutral bending axes while preventing out-of-plane flexural buckling.


•**Bio-Inspired Architecture:** Minimalist hexagonal cellular cores separate thin, rigid face sheets to maximize transverse shear resistance and bending stiffness.


•**Engineering Impact:** Standardized across aircraft wings, flooring, helicopter rotor blades, and rocket fairings to achieve maximum stiffness per unit weight.

(Honeycomb Sandwich Panels):

Biological Element Mimicked: The 2D regular hexagonal grid from honeybee hives (Honeycomb Conjecture) and the structural sandwich principle separating core shear resistance from surface bending loads

The surface density of an aluminum honeycomb sandwich panel is only 30% to 40% of a solid plate, resulting in a **60% to 70% reduction in weight** while maintaining equivalent or superior out-of-plane bending stiffness.





5: Managing Peak Crash Loads (Progressive Impact Absorbers)


- **The Problem Solved:** Prevents dangerous peak deceleration spikes and irregular buckling collapses during high-speed collisions.

•**Bio-Inspired Architecture:** Utilizes out-of-plane axial compression mechanics where cell walls form controlled plastic hinges (concertina folding) to maintain a steady crushing force plateau.

•**Engineering Impact:** Integrated into automotive crumple zones, roadside barrier attenuators, elevator emergency buffers, and space-probe landing legs.

(Progressive Impact Absorbers):

Biological Element Mimicked: The out-of-plane progressive buckling plateau and concertina folding (formation of localized plastic hinges) in honeybee cell walls under axial compression



Integrating quasi-honeycomb cellular cores into automotive crash boxes increases total kinetic energy absorption by **42.2% to 54.6%** while simultaneously reducing the destructive peak collision force (deceleration spike) by **2.3% to 8.9%**.

6: Merging Origami Kinematics with Honeycomb Strength


The Key Innovation: Combines the **deployable physics** of concertina folding with the **high strength-to-weight ratio** of natural beehives.


From Flat to 3D: Flat sheets are pre-creased using mathematical patterns (like the *Miura-ori*). When compressed laterally, these flat surfaces **pop up into a 3D cellular matrix**.

Interlocking Networks: Multiple folded sheets are stacked and bonded face-to-face along designated valley and mountain creases, forming a continuous, lightweight core.

Key Advantage: Unlike rigid commercial honeycombs, this hybrid structure can **compress perfectly flat** for storage or transport, then

Integrating mathematical origami fold patterns (e.g., Miura-ori) into honeycomb cell walls allows the structure to absorb at





7: Acoustic Damping & Thermal Dissipation (Acoustic Engine Liners)

•**The Problem Solved:** Mitigates severe acoustic resonance, structural vibration fatigue, and thermal expansion failure in enclosed high-stress systems.


•**Bio-Inspired Architecture:** Translates cellular tessellation and trapped-air cavity resonance to diffuse sound waves and distribute convective heat loads evenly.

•**Engineering Impact:** Used in jet engine nacelle acoustic liners, industrial mufflers, and high-efficiency, lightweight heat exchangers.

(Acoustic Damping & Thermal Dissipation):


Biological Element Mimicked: The hollow cellular tessellation and trapped-air cavity geometry of the honeycomb array.

Micro-perforated honeycomb structural panels reach sound absorption coefficients between 0.8 and 0.9. This means the cellular cavities successfully trap and convert **80% to 90%** of incident acoustic noise into heat energy within target





THE RESEARCH TIMELINE



TIMELINE FOR HONEYCOMB BIOMIMETICS

36 BCE

Roman Vaulting & The Pantheon: Roman engineers, influenced by early geometric treatises on the honeycomb (Marcus Varro), use hexagonal and multi-cellular coffer ribbing in the dome of the Pantheon to reduce ceiling dead weight without losing compressive dome strength.

1914

- **First Structural Honeycomb Patents (Höfler & Renyi, 1914):** Recognition of honeycomb cells as load-bearing structural elements.

- **George Thomson (1931):** Proposes expanded paper honeycomb cores for lightweight, fire-retardant interior building boards.

1940

Quantitative biological studies begin on honeybee wax secretion and hexagonal comb formation under metabolic energy constraints

1955

- **Post-War Sandwich Panel Architecture:** Structural Insulating Panels (SIPs) and resin-impregnated Kraft paper honeycombs transition from aerospace into prefabricated civil construction

1970

- **Architectural Biomimicry & Curtain Walls:** Development of structural aluminum honeycomb bonded panels (e.g., Alucobond) to resist high out-of-plane wind loads on skyscrapers while minimizing building facade weight

2000

Hexagonal Shell & Canopy Architecture: Large-scale biomimetic structural designs deploy tessellated hexagonal grids inspired by honeycombs to enclose vast interior volumes with minimal structural steel.

2012

Thermal Self-Assembly (Karihaloo et al., 2013): Proof that bees use 35°C–40°C heat and surface tension to transform circular wax cells into 120° hexagons.

2015-PRESENT

Modular Hexagonal Habitats & 3D Printing: Integration of bio-inspired cellular cores with additive manufacturing to produce high-strength building envelopes with internal thermal and acoustic insulation cavities

TO BE RESEARCHED



TIMELINE FOR SPIDERWEB BIOMIMETICS

1960

Frei Otto & Form-Finding Research: Frei Otto studies soap films, biological membranes, and orb-spider webs to develop lightweight tensile architecture and minimal-surface tension cable nets.

1970

Structural and chemical characterization of major ampullate spider silk proteins (spidroins) and gland morphology

1960

Frei Otto & Form-Finding Research: Frei Otto studies soap films, biological membranes, and orb-spider webs to develop lightweight tensile architecture and minimal-surface tension cable nets.


1997

Molecular Hierarchy Mapped (Gosline et al., 1999): Alanine-rich beta-sheet nanocrystals identified as the source of GPa-level tensile strength, paired with amorphous glycine-rich chains for extensibility.

• **Gibson & Ashby (1997):** Mechanics of cellular solids formulated, defining out-of-plane vs. in-plane anisotropic behaviors and progressive concertina folding

2000

Tensegrity & Radial Cable Trusses: Structural engineers adapt the combination of radial spokes (stiff dragline silk) and circumferential spiral ties into lightweight structural stadium roofs


To Be Continued
• Sacrificial & Non-Linear Web Mechanics (Buehler et al., 2012): Computational mapping proves webs withstand localized damage without global collapse via non-linear strain-hardening.
2012
• ICD/ITKE Research Pavilion (2013–2014, Uni Stuttgart): Robotic coreless carbon/glass fiber winding inspired by spider web construction.
2015
• Seismic Rock-Fall & Debris Catchment Nets: Civil infrastructure adopts radial-tangential spider web geometry to engineer dynamic boundary nets
• Biocomposite 3D-Printed Tensile Facades: Integration of recombinant spidroin proteins and bio-mimetic fiber reinforcement into facade shades and kinetic tensile building envelopes.
2019 - PRESENT
TO BE RESEARCHED


APPLICATIONS


APPLICATIONS OF HONEYCOMB ORIGAMI

Aerospace & Space Travel: Ideal for compact satellite antennas, **deployable solar arrays**, and space habitat walls that must pack tightly into a rocket fairing

Terrestrial Impact Protection: Being tested for **advanced crumple zones** in electric vehicles, run-flat tire cores, and lightweight protective sports gear.

Tunable Mechanical Properties: Engineers can change the stiffness, flexibility, and expansion ratio of the





•**The Eden Project (Cornwall, UK):** The massive geodesic biome domes are framed with a tessellated hexagonal steel space frame carrying ETFE cushions, directly applying the Honeycomb Conjecture to enclose maximum volume with minimal steel perimeter and structural weight.



This Photo by Unknown Author is licensed under CC BY-SA

•**Beijing National Aquatics Center ("Water Cube", China):** Uses an optimized cellular space-frame derived from soap-bubble and natural hexagonal cellular geometry to provide high out-of-plane stiffness and seismic absorption.



This Photo by Unknown Author is licensed under CC BY-SA

The world's largest unreinforced concrete dome utilizes recessed hexagonal and multi-cellular coffer chambers to cut ceiling dead weight while preserving out-of-plane compressive strength.



This Photo by Unknown Author is licensed under CC BY-SA

•**Skyscraper Curtain Walls (Worldwide):** Prominent high-rises such as the **Burj Khalifa** (interior partitions and cladding) and **One World Trade Center** integrate aluminum and Nomex honeycomb sandwich panels to deliver extreme bending stiffness against high-altitude wind shear while minimizing building dead



•**Hexcel Corporation:** Global leader producing aluminum, aramid (Nomex), and composite honeycomb sandwich cores for structural building envelopes, flooring, and aerospace panels.



•**3A Composites (ALUCOBOND / ALUCORE):** Manufactures structural aluminum honeycomb core panels used globally for ventilated exterior facades, curtain walls, and ceiling baffles.



•**Plascore. Inc.:** Produces customized aramid and thermoplastic honeycomb panels used for architectural cleanroom walls, marine bulkheads, and seismic energy crash absorbers.



•**EconCore:** Specializes in automated continuous production of lightweight honeycomb sandwich panels for

& Construction

1. Real Buildings & Structures


Munich Olympic Stadium Roof (Germany):
Designed by Frei Otto, this landmark pre-stressed cable-net canopy directly applies spider web tension geometry, using continuous high-strength steel cables anchored at radial points to distribute live snow and wind loads without interior support pillars.



Spoke-Wheel Stadium Roofs (e.g., Mercedes-Benz Arena, Stuttgart & BC Place, Vancouver):
Structural roofs designed on a "bicycle wheel / spider web" tensegrity principle, pairing radial tension spokes with circumferential perimeter rings to slash roof steel weight by up to 60%.


This Photo by Unknown Author is licensed under CC BY-SA

(University of Stuttgart, Germany): Lightweight architectural pavilions built using robotic coreless winding of carbon and glass fibers, explicitly modeled on the tensile load paths and radial resin patterns of orb-spider webs.



•**Slope & Rock-Fall Catchment Barriers (Swiss Alps / Geobrugg installations):** Dynamic boundary netting along highways and tunnel portals engineered with ring-net radial geometries that emulate the web's sacrificial yielding and nonlinear strain-hardening to catch falling boulders without rupturing.

This Photo by Unknown Author is licensed under CC BY-SA




mesh systems; manufactures dynamic slope stabilization nets and rockfall barriers that dissipate extreme impact kinetic energy through ring-net deformation inspired by spider web mechanics.

•**Pfeifer Holding GmbH & Schlaich Bergermann Partner (sbp):** Leading engineering and fabrication firms specializing in lightweight cable structures, tensegrity roofs, and radial spoke-wheel tension systems for international stadiums and transit hubs.

•**Spiber Inc. (Japan):** Pioneers in commercial-scale brewing of synthetic structural spidroin proteins (Brewed Protein™), partnered with construction and automotive developers to manufacture shock-absorbent bio-composite panels.

•**Kraig Biocraft Laboratories & AMSilk:** Companies producing recombinant bio-spun spider silk fibers for


FUTURE
PROSPECTS



replicate pH drops (7.2 to <5.5), sodium/potassium ion exchanges, and shear stress draw to continuously manufacture synthetic spidroin fibers under ambient conditions without toxic chemical solvents.

- *Source:* M. Andersson et al., *"Biomimetic spinning of artificial spider silk from a chimeric minispidroin,"* Nature Chemical Biology, 2017.

- **Bio-Inspired Polymer Nanocomposites:** Synthesizing lightweight, fracture-resistant composites by dispersing hard ceramic or carbon nanoparticles into ductile polymer matrices to replicate the dual beta-sheet nanocrystal (modulus) and amorphous glycine-rich (extensibility) interface.
  - *Sources:* J. M. Gosline et al., *"The mechanical design of spider silks: From fibroin sequence to mechanical function,"* Journal of Experimental Biology, 1999; M. A. Meyers et al., *"Structural biological materials: Critical mechanics-materials connections,"* Science, 2013.

- **Damage-Tolerant Dynamic Arrestor Networks:** Engineering dynamic infrastructure tethering, aircraft arrestor lines, and body armor that leverage nonlinear strain-hardening and sacrificial failure mechanics, allowing localized thread failure during high-velocity impacts to protect the global structure from collapsing.
  - *Source:* S. W. Cranford, A. Tarakanova, N. M. Pugno, and M. J. Buehler, *"Nonlinear*

construction—where 35°C–40°C heating and surface tension pull circular cavities into planar 120° hexagonal junctions—to design self-assembling cellular materials in additive manufacturing and micro-fabrication.

- *Sources:* B. L. Karihaloo, K. Zhang, and J. Wang, *"Honeybee combs: How the circular cells transform into rounded hexagons,"* Journal of the Royal Society Interface, 2013; T. C. Hales, *"The Honeycomb Conjecture,"* Discrete & Computational Geometry, 2001.

- **Progressive Crash-Absorption Systems:** Optimizing out-of-plane axial compression structures that utilize concertina folding (progressive plastic hinges) to sustain a constant crushing force plateau, maximizing kinetic energy absorption per unit mass in automotive crumple zones and planetary landing pads.
  - *Source:* L. J. Gibson and M. F. Ashby, *Cellular Solids: Structure and Properties*, Cambridge University Press, 1997.

- **Advanced Multi-Functional Sandwich Envelopes:** Expanding sandwich panel architectures that combine thin outer face sheets with lightweight cellular cores to achieve maximum bending stiffness, transverse shear resistance, and built-in acoustic attenuation in aerospace wings, rocket fairings, and jet engine nacelles.
  - *Sources:* L. J. Gibson and M. F. Ashby, *Cellular Solids: Structure and Properties*, 1997; M. A. Meyers et al., *"Structural biological materials: Critical mechanics-materials*

SUMMARY

Conventional structural engineering struggles with severe compromises: synthetic materials are strong yet brittle, solid components carry excessive dead weight, and manufacturing often relies on toxic, high-energy processes. Nature overcomes these limitations through structural hierarchy and geometric optimization. Spider silk and web networks combine high tensile strength with extreme elasticity to absorb dynamic kinetic shocks without global collapse. Simultaneously, honeycomb hexagonal arrays minimize wall material to enclose maximum volume while providing remarkable out-of-plane stiffness and progressive crush absorption.

Engineers adapt these natural blueprints into lightweight composites, tensegrity stadium roofs, rock-fall barriers, and sandwich panels across aerospace, automotive crumple zones, and skyscraper architecture, unlocking safer, ultra-lightweight, and sustainable infrastructure.

BIBLIOGRAPHY

- [1] Gibson, L. J., & Ashby, M. F. (1997). Cellular Solids: Structure and Properties. *Cambridge University Press*. Cited by: 24269
- [2] Wu, H.-C., Wu, S.-R., Yang, T. C.-K., & Yang, J.-C. (2018). A Facile Measurement for Monitoring Dragline Silk Dope Concentration in Nephila pilipes upon Spinning. *Materials*, *11*(10), 1951. https://doi.org/10.3390/ma11101951 Cited by: 9
- [3] Vierra, C., Hsia, Y., Gnesa, E., Tang, S., & Jeffery, F. (2011). Spider Silk Composites and Applications. *Metal, Ceramic and Polymeric Composites for Various Uses*. https://doi.org/10.5772/22894 Cited by: 72
- [4] Gosline, J. M., Guerette, P. A., Ortlepp, C. S., & Savage, K. N. (1999). The mechanical design of spider silks: from fibroin sequence to mechanical function. *Journal of Experimental Biology*, *202*(23), 3295-3303. https://doi.org/10.1242/jeb.202.23.3295 Cited by: 1620
- [5] Cranford, S. W., Tarakanova, A., Pugno, N. M., & Buehler, M. J. (2012). Nonlinear material behaviour of spider silk yields robust webs. *Nature*, *482*(7383), 72–76. https://doi.org/10.1038/nature10739 Cited by: 617
- [6] Hales, T. C. (2001). The Honeycomb Conjecture. *Discrete & Computational Geometry*, *25*(1), 1-22. https://doi.org/10.1007/s004540010071 Cited by: 793
- [7] Karihaloo, B. L., Zhang, K., & Wang, J. (2013). Honeybee combs: how the circular cells transform into rounded hexagons. *Journal of The Royal Society Interface*, *10*(86), 20130299. https://doi.org/10.1098/rsif.2013.0299 Cited by: 120
- *[8]Xie, L., Xu, H., Li, L.-B., Hsiao, B. S., Zhong, G.-J., & Li, Z.-M. (2016). Biomimetic Nanofibrillation in Two-Component Biopolymer Blends with Structural Analogs to Spider Silk. Scientific Reports, 6. https://doi.org/10.1038/srep34572 Cited by: 27*
- *[9] Wei, W., Zhang, F., Xing, Y., Wang, H., & Liu, R. (2022). Research on Mechanical Properties of Origami Aluminum Honeycomb for Automobile Energy Absorbing Box. Materials, 16(1), 141. https://doi.org/10.3390/ma16010141 Cited by: 30*
- *[10] Liu, Z., Dong, C., Tong, L., Rudd, C., Yi, X., & Liu, X. (2024). Sound Absorption Performance of Ultralight Honeycomb Sandwich Panels Filled with "Network" Fibers—Juncus effusus. Polymers, 16(13), 1953. https://doi.org/10.3390/polym16131953 Cited by: 13*
- *[11] Ferdynus, M., Rozylo, P., & Rogala, M. (2020). Energy Absorption Capability of Thin-Walled Prismatic Aluminum Tubes with Spherical Indentations. Materials, 13(19), 4304. https://doi.org/10.3390/ma13194304 Cited by: 42*

EOB PROJECT LINK

- https://eobgrp6-ajjpip7gc-cryo8.vercel.app