



BMA 401 T-70 Maleic Resin

Product Description:

BMA 401 T-70 is a Maleic Resin which offers excellent gloss and gloss retention and hardness and very good surface and deep drying properties.

Characteristics and Advantages:

- Excellent gloss and gloss retention
- Excellent hardness
- Very good surface and deep drying

Uses:

- Nitro cellulose enamels and paints
- Wood coatings
- Traffic paints

Technical Properties:

Physical data in liquid state at 25°C

These data are measured for each for by our QC lab before its release.					
Unit	Value	Test method			
Gardner	Max 10	ASTM D1544			
mPa.s (cP)	40-60	ASTM D1545			
mg KOH/g	Max 35	ASTM D1639			
wt%	70±1	ASTM D1259			
	Toluene				
	Unit Gardner mPa.s (cP) mg KOH/g	Unit Value Gardner Max 10 mPa.s (cP) 40-60 mg KOH/g Max 35 wt% 70±1			

Typical Properties

These data are not subject to routine monitoring or part of the specifications; they are only reported for a better product description.

Properties	Unit	Value	Test method
Density (at 23°C)	g/cm³	1.036	ASTM D1475
Flash point (open cup)	°C	5	ASTM D92
Dilutabilita (lutamatical)			

Dilutability (Internal test method)

White Spirit	0	Butyl Acetate	•
Xylene	•	Acetone	•
Toluene	•		

Compatibility (ASTM D6887 @T=160°C)

Saturated Polyesters	Compatible	Long Oil Alkyds	Incompatible
Medium Oil Alkyds	Incompatible	Amino Resin	Compatible
Short Oil Alkyds	Compatible	Acrylic Resin	Compatible

Product safety and Environmental protection:

The usual protective measures employed during the handling of Maleic Resins should be observed. Further product safety information can be obtained from our Material Safety Data Sheet which is available on request.

Packaging: 200 kg (net) in steel drums

Storage: Store in a cool place below 25 °C and away from moisture and direct sunlight. Under above mentioned storage conditions, the shelf life of the resin will be at least 6 months ex-works.

Disclaimer: The information and in particular the recommendations relating to the application and use of Bonyan Kala Chemie products are given in good faith based on our current knowledge and expertise of the products when properly stored, handled and used under normal conditions within their shelf life. In practice, the differences in materials, chemistries and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request or can be accessed from www.bonyankala.com.

DS253/052021/00