

Dibasic Lead Stearate (DBLS) SCI -150- DBLS

DBLS imparts excellent stability to the compounds due to its high free Lead content. The fine particle distribution size ensures better dispersion imparting higher stability. It also provides lubricating action at high temperatures as it does not melt in normal service conditions.

SCI-150-DBLS is being extensively used in manufacture of rigid PVC compounds, extrusion injection moulding, calendaring operation, conduits and cable and other plasticized PVC products. It helps to obtain long production runs at a higher production rate when used in conjunction with other lubricants and stabilisers such as TBLS, LS, CS and DBLP

Physical and Chemical Properties

Description	Soft White powder, insoluble in water, no combustibility, no corrosiveness; Soluble in heated Acetate Ammonium and Nitric Acid.
Chemical Formula	$2\text{PbO} \cdot \text{Pb}(\text{C}_{17}\text{H}_{35}\text{COO})_2$
CAS RNo	56189-09-4
Lead Content(as PbO)	54-55%
Specific Gravity	1.9 – 2.2
Molecular Weight	1219.87 g/mol
Moisture	1% Max.
Particle Size (Microns)	63 (230 Mesh) (Finer material available on request)
Packing	25 Kg HDPE Bag with Liner.

Samples and Further Technical details available on request

Stabplast's products are manufactured under strict process parameters and standardized procedures to provide finest quality product every time

