



STEEL FRAMING LLC

#### Corporate Headquarters

15 Salt Creek Lane, Suite 412  
Hinsdale, IL 60521  
Phone: 1.630.616.1850  
Fax: 1.630.568.5979  
info@mrsteelframing.com

#### Production Facility

201 Mississippi St Dock #Q40  
Gary, IN 46402  
Phone: 1.630.616.1850  
Fax: 1.219.886.3341  
info@mrsteelframing.com

## GREEN Benefits & Recycled Content

March 18, 2024

Project:

MRI Steel Framing is committed to supplying quality products that contribute to developing greener building projects as well as sustainability and environmental management.

MRI Steel Framing has an Environmental Product Declaration (EPD), Number SCS-EPD-08959, covering our Cold-Formed Steel Framing Products, which conforms to ISO 14025, 14040, 14044, and ISO 21930. This EPD is a Product Specific Type III and has a Cradle to Gate scope. More specifically, this Type III EPD has been externally reviewed following ISO 14071 and externally verified, and as such, is eligible to contribute 150% of a product for the purposes of LEED® credits under the LEED® v4.1 standard.

The MRI Steel Framing Environmental Product Declaration (EPD) can help your building project qualify for the following LEED® v4.1 for BD+C points:

#### MATERIALS AND RESOURCES CREDIT (MR)

- Environmental Product Declarations - Up to 2 Points
- Sourcing of Raw Materials - Up to 2 Points
- Material Ingredients - Up to 2 Points
- Construction and Demolition Waste Management - Up to 2 Points

#### INDOOR ENVIRONMENTAL QUALITY CREDIT (EQ)

- Low-Emitting Materials - Up to 3 Points
- Construction Indoor Air Quality Management Plan - Up to 1 Point
- Indoor Air Quality Assessment - Up to 2 Points

MRI Steel Framing products and accessories are manufactured from steel coil (100% by weight) containing 19.8% post-consumer recycled content and 14.4% post-industrial/pre-consumer recycled content for a total of 34.2% recycled content. These calculations are based upon information provided by the Steel Recycling Institute on minimum BOF (Basic Oxygen Furnace) steel recycled content.

In addition to the above mentioned EPD and LEED® information, MRI Steel Framing also has a Health Product Declaration (HPD) with a Unique Identifier Number of 27459 covering our full line of Interior Framing, Structural Framing, Slotted Deflection Track and Accessories; MasterSpec 05.40.00 and 09.22.16.

**Product Category:** 05.40.00 - Cold-Formed Metal Framing

**Product Name:** 550S162-43

**Available Finish:** G60, G90

\*Other standard coatings referenced in ASTM A1003

**Web Depth:** 5-1/2 in

**Flange Width:** 1-5/8 in

**Design Thickness:** 0.0451 in

**Gauge:** 43 mils or 18

**Yield stress, Fy:** 50 ksi

**Weight:** 1.44 lb/ft


**Gross Section Properties**

Cross sectional area (A)	0.424 in <sup>2</sup>
Moment of inertia (Ix)	1.884 in <sup>4</sup>
Section Modulus (Sx)	0.685 in <sup>3</sup>
Radius of gyration (Rx)	2.107 in
Gross moment of inertia (Iy)	0.145 in <sup>4</sup>
Gross Radius of gyration (Ry)	0.584 in

**Effective Section Properties**

Moment of inertia for deflection (Ix)	in <sup>4</sup>
Section modulus (Sx)	in <sup>3</sup>
Allowable bending moment (Ma)	In-k
Allowable bending moment from distortional buckling (Mad)	In-k
Allowable strong axis shear away from punch-out (Vag)	lb
Allowable strong axis shear at punch out (Vanet)	lb

- Calculated properties are based on AISI S100-16/S240-20, North American Specification for Design of Cold-Formed Steel Structural Members and meets the requirements of the IBC 2021 Building Code.
- The centerline bend radius is based on inside corner radii shown in thickness chart.
- Effective properties incorporate the strength increase from the cold work of forming as applicable per AISI A7.2.
- Tabulated gross properties are based on full-unreduced cross section of the studs, away from punchouts.
- For deflection calculations, use the effective moment of inertia.
- Allowable moment includes cold-work of forming.
- For the steels that have both 33 and 50 ksi listing, if the design is based on 50 ksi, the 50 ksi steel needs to be specified. (ex. 3.625S137 16-50 (50 ksi))



**Torsional Properties**

St. Venant torsion constant (J x 1000)	0.288 in <sup>4</sup>
Warping constant (Cw)	0.905 in <sup>6</sup>
Distance from shear center to neutral axis (Xo)	-1.103 in
Distance from shear center to mid-plane of web (m)	0.691 in
Radii of gyration (Ro)	2.449 in
Torsional flexural constant (β)	0.797
Unbraced Length (Lu)	41.2 in

**Additional Information**

MRI Steel Framing, LLC is an SFIA member. MRI acts in accordance with the product and quality standards required by the SFIA program.

MRI meets or exceeds ASTM C955, A653, and A1003.

Current LEED credits available upon request