


05.40.00 (Cold-Formed Metal Framing)





362TTS137-30 (33ksi, G40)


3-5/8" (TTS) TRAKLOC® Track with 1-3/8" leg - 30 mils (20ga DW)

Coating: G40 Color Code: Pink

Geometric Properties

Web depth: 3.625 in Thickness: 30 mils (20ga DW) Leg width: 1.375 in Design Thickness: 0.0312 in Yield strength, Fy: 33 ksi Min. steel thickness: 0.0296 in


min oto	
Gross Section Properties of Full Section, Strong Axis	
Cross sectional area (A)	0.199 in ²
Member weight per foot of length	0.676 lb/ft
Moment of inertia (lx)	0.419 in ⁴
Radius of gyration (Rx)	1.452 in
Gross moment of inertia (ly)	0.036 in ⁴
Gross radius of gyration (Ry)	0.423 in
Effective Section	Properties
Effective Area (Ae)	0.089 in ²
Moment of inertia for deflection (lx)	0.347 in ⁴
Section modulus (Sx)	0.153 in ³
Allowable bending moment (Mal)	3031 in-lbs
Allowable shear force in web (Vag)	758 lb
Torsional Pro	perties
St. Venant torsional constant (J x 1000)	0.0645 in ⁴
Warping constant (Cw)	0.087 in ⁶
Distance from shear center to neutral axis (Xo)	-0.757 in
Radii of gyration (Ro)	1.691 in
Torsional flexural constant (Beta)	0.800



- Effective properties incorporate the strength increase from the cold-work of forming as applicable per AISI A7.2.
- For deflection calculations, use the effective moment of inertia.
- Allowable moment includes cold-work of forming.

Code Approvals & Performance Standards

- AISI S100-12 North American Specification for the Design of Cold-Formed Steel Framing Structural Members
- AISI S220-11 North American Standard for Cold-Formed Steel Framing Nonstructural Members
 - o (Compliant to ASTM C645, but IBC replaced with AISI S220 in IBC 2015)
 - Section A4 Material Chemical & mechanical requirements (Referencing ASTM A1003/A1003M)
 - Section A5 Corrosion Protection (Referencing ASTM A653/A653M)
 - Section C Installation (Referencing ASTM C754)
- ICC-ES ESR-1464 TRAKLOC
- SDS For ASTM A1003 Steel Framing Products For Interior Framing, Exterior Framing and Clips/Accessories







Sustainability Credits For more details and LEED letters contact Technical Services at 888-437-3244 or visit clarkdietrich.com/LEED.

- LEED v4.1 MR Credit: Environmental Product Declarations: EPD (1 point) - Sourcing of Raw Materials (up to 2 points) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points)
- LEED v4 MR Credit: Building Product Disclosure and Optimization: EPD (1 point) Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) -Innovation Credit (up to 2 points).