Product Category: 05.40.00 - Cold-Formed Metal Framing   **Product Name:** 600SLT350-33

Available Finish: G60

(G40/G90 coatings available upon request)

*Other standard coatings referenced in ASTM A1003

Web Depth:	6 in
Flange Width:	3-1/2 in
Slot Width:	2-1/2 in
Design Thickness:	0.0346 in
Gauge:	33 mils or 20G ST
Yield stress, Fy:	33 ksi
Weight:	1.530 lb/ft

Gross Section Properties

|	
Cross sectional area (A)	0.450 in²
Moment of inertia (Ix)	0.583 in⁴
Section Modulus (Sx)	0.000 in³
Radius of gyration (Rx)	1.138 in
Gross moment of inertia (Iy)	2.882 in⁴
Gross Radius of gyration (Ry)	2.532 in

Effective Section Properties

Moment of inertia for deflection (Ix)	1.051 in⁴
Section modulus (Sx)	0.260 in³
Allowable bending moment (Ma)	4.29 In-k
Allowable bending moment from distortional buckling (Mad)	0 In-k
Allowable strong axis shear away from punch-out (Vag)	0 lb
Allowable strong axis shear at punch out (Vanet)	0 lb

Torsional Properties

St. Venant torsion constant (J x 1000)	NA in⁴
Warping constant (Cw)	NA in⁶
Distance from shear center to neutral axis (Xo)	NA in
Distance from shear center to mid-plane of web (m)	NA in
Radii of gyration (Ro)	NA in
Torsional flexural constant (β)	NA

- Gross properties calculated at the gross section, away from slots.
- Web depth taken as nominal depth + (2 x thickness) + inside corner radius.
- Effective properties based on the 2007 NASPEC with 2010 Supplement and the following: net flange on tension side; effective flange on compression side, ignoring steel below the slot; effective web per NASPEC B2.3; Ωb = 2.0 per AISI S100-16/S240-20, A1.2; meets the requirements of the IBC 2021 Building Code.
- Effective properties are not available for 6" x 18-mil products. Web h/t > 260.

Additional Information

MRI Steel Framing, LLC is an SFIA member. MRI acts in accordance with the product and quality standards required by the SFIA program.

MRI meets or exceeds ASTM C955, A653, and A1003.

Current LEED credits available upon request