

**Product Category:** 05.40.00 - Cold-Formed Metal Framing

**Product Name:** 362SLT350-33

**Available Finish:** G60

(G40/G90 coatings available upon request)

\*Other standard coatings referenced in ASTM A1003

**Web Depth:** 3-5/8 in

**Flange Width:** 3-1/2 in

**Slot Width:** 2-1/2 in

**Design Thickness:** 0.0346 in

**Gauge:** 33 mils or 20G ST

**Yield stress, Fy:** 33 ksi

**Weight:** 1.250 lb/ft

**Gross Section Properties**

|                               |                       |
|-------------------------------|-----------------------|
| Cross sectional area (A)      | 0.367 in <sup>2</sup> |
| Moment of inertia (Ix)        | 0.495 in <sup>4</sup> |
| Section Modulus (Sx)          | 0.000 in <sup>3</sup> |
| Radius of gyration (Rx)       | 1.161 in              |
| Gross moment of inertia (Iy)  | 0.981 in <sup>4</sup> |
| Gross Radius of gyration (Ry) | 1.634 in              |


**Effective Section Properties**

|   |                       |
|---|-----------------------|
| Moment of inertia for deflection (Ix)                     | 0.312 in <sup>4</sup> |
| Section modulus (Sx)                                      | 0.144 in <sup>3</sup> |
| Allowable bending moment (Ma)                             | 2.38 In-k             |
| Allowable bending moment from distortional buckling (Mad) | 0 In-k                |
| Allowable strong axis shear away from punch-out (Vag)     | 0 lb                  |
| Allowable strong axis shear at punch out (Vanet)          | 0 lb                  |

**Torsional Properties**

|  |                    |
|--|--------------------|
| St. Venant torsion constant (J x 1000)             | NA in <sup>4</sup> |
| Warping constant (Cw)                              | NA in <sup>6</sup> |
| Distance from shear center to neutral axis (Xo)    | NA in              |
| Distance from shear center to mid-plane of web (m) | NA in              |
| Radii of gyration (Ro)                             | NA in              |
| Torsional flexural constant (β)                    | NA                 |

- Gross properties calculated at the gross section, away from slots.
- Web depth taken as nominal depth + (2 x thickness) + inside corner radius.
- Effective properties based on the 2007 NASPEC with 2010 Supplement and the following: net flange on tension side; effective flange on compression side, ignoring steel below the slot; effective web per NASPEC B2.3; Ωb = 2.0 per AISI S100-16/S240-20, A1.2; meets the requirements of the IBC 2021 Building Code.
- Effective properties are not available for 6" x 18-mil products. Web h/t > 260.



**Additional Information**

MRI Steel Framing, LLC is an SFIA member. MRI acts in accordance with the product and quality standards required by the SFIA program.

MRI meets or exceeds ASTM C955, A653, and A1003.

Current LEED credits available upon request