

**Product Category:** 05.40.00 - Cold-Formed Metal Framing

**Product Name:** 400S300-43

**Available Finish:** G60, G90

\*Other standard coatings referenced in ASTM A1003

**Web Depth:** 4 in

**Flange Width:** 3 in

**Design Thickness:** 0.0451 in

**Gauge:** 43 mils or 18

**Yield stress, Fy:** 50 ksi

**Weight:** 1.67 lb/ft

**Gross Section Properties**

Cross sectional area (A)	0.492 in <sup>2</sup>
Moment of inertia (Ix)	1.400 in <sup>4</sup>
Section Modulus (Sx)	0.700 in <sup>3</sup>
Radius of gyration (Rx)	1.687 in
Gross moment of inertia (Iy)	0.617 in <sup>4</sup>
Gross Radius of gyration (Ry)	1.120 in

**Effective Section Properties**

Moment of inertia for deflection (Ix)	in <sup>4</sup>
Section modulus (Sx)	in <sup>3</sup>
Allowable bending moment (Ma)	In-k
Allowable bending moment from distortional buckling (Mad)	In-k
Allowable strong axis shear away from punch-out (Vag)	lb
Allowable strong axis shear at punch out (Vanet)	lb

- Calculated properties are based on AISI S100-16/S240-20, North American Specification for Design of Cold-Formed Steel Structural Members and meets the requirements of the IBC 2021 Building Code.
- The centerline bend radius is based on inside corner radii shown in thickness chart.
- Effective properties incorporate the strength increase from the cold work of forming as applicable per AISI A7.2.
- Tabulated gross properties are based on full-unreduced cross section of the studs, away from punchouts.
- For deflection calculations, use the effective moment of inertia.
- Allowable moment includes cold-work of forming.
- For the steels that have both 33 and 50 ksi listing, if the design is based on 50 ksi, the 50 ksi steel needs to be specified. (ex. 3.625S137 16-50 (50 ksi))



**Torsional Properties**

St. Venant torsion constant (J x 1000)	0.334 in <sup>4</sup>
Warping constant (Cw)	2.282 in <sup>6</sup>
Distance from shear center to neutral axis (Xo)	-2.608 in
Distance from shear center to mid-plane of web (m)	1.503 in
Radii of gyration (Ro)	3.302 in
Torsional flexural constant (β)	0.376
Unbraced Length (Lu)	73.9 in

**Additional Information**

MRI Steel Framing, LLC is an SFIA member. MRI acts in accordance with the product and quality standards required by the SFIA program.

MRI meets or exceeds ASTM C955, A653, and A1003.

Current LEED credits available upon request