
SYNTHESIS AND PHASE CONTROL OF $\text{BaZn}_2\text{Si}_2\text{O}_7$: AS A STRUCTURAL ANALOGUE OF $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$

GoAI Research

ABSTRACT

This review surveys the crystal structure, synthesis routes and phase-control variables of $\text{BaZn}_2\text{Si}_2\text{O}_7$ and assesses its comparability as a structural analogue of $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$. Previous studies, using high-temperature X-ray diffraction (HT-XRD), single-crystal structure analysis and dilatometry, have established the low-temperature–high-temperature polymorphism of $\text{BaZn}_2\text{Si}_2\text{O}_7$ and the substitution rules for Ba/Sr and for the Zn site; the solid-state reaction, sol–gel and glass-crystallization routes show that precursor homogeneity, nucleating agents and microstructure jointly determine the formation of the main phase. By contrast, the present check found no verifiable primary structural or synthesis report on $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$, so only tiered structural criteria and falsifiable experimental priorities can be proposed. The review identifies the absence of a ternary BaO–ZnO–SiO₂ phase diagram and of temperature-dependent thermodynamic data, and outlines a conservative research path combining HT-XRD, thermal analysis and coordination refinement.

1 BACKGROUND AND SCOPE

$\text{BaZn}_2\text{Si}_2\text{O}_7$ is a silicate in the BaO–ZnO–SiO₂ system that undergoes a reversible structural transition. Its low-temperature phase shows pronounced positive thermal expansion, whereas the high-temperature phase formed on heating can exhibit near-zero or negative thermal expansion, which makes the compound a model system for studying tetrahedral-chain flexibility and compositional tuning. Lin et al. resolved this transition and both crystal structures by high-temperature X-ray diffraction (HT-XRD), providing the structural benchmark for subsequent phase-control studies [10].

This review is organized around three questions: first, how the structure and synthesis conditions of $\text{BaZn}_2\text{Si}_2\text{O}_7$ jointly determine the main phase; second, over what range Ba/Sr, Zn/Mg/Co/Ni/Cu and Si/Ge substitution can tune phase stability; and third, what verifiable grounds exist for treating $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$ as a structural analogue. Public databases confirm the orthorhombic structure of $\text{BaZn}_2\text{Si}_2\text{O}_7$, the five-fold coordination of Ba and the corner-sharing network of ZnO₄ and SiO₄ tetrahedra [11], but the present search found no verifiable primary crystallographic paper on $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$. Throughout, “direct reports”, “structurally related compounds” and “structural inference” are therefore kept strictly separate.

Structurally related compounds serve as more than background. Studies of $\text{Ba}_{1-x}\text{Sr}_x\text{Zn}_2\text{Si}_2\text{O}_7$ show that a small amount of Sr substitution suffices to stabilize the high-temperature structure down to room temperature and to shift the thermal expansion coefficient into the negative range [14, 15]; aliovalent or isovalent substitution on the Zn site further changes the transition temperature and the anisotropy [7, 17]. These results provide transferable structure–processing correlations for comparison with the target analogue, but they do not imply that $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$ has been synthesized.

Figure 1 gives the order of presentation, and Figure 2 places structure, synthesis, phase control and evidence boundaries within a single framework.

Figure 1: Roadmap of this review. Arrows indicate the order of progression from structural facts to synthesis windows, to the transfer of trends from structurally related compounds, and to falsifiable experimental recommendations.

Table 1: Structure and thermal behaviour of $\text{BaZn}_2\text{Si}_2\text{O}_7$ and its structurally related compounds.

Phase or composition	Structure/coordination	Main characterization	Conclusion for phase control
$\text{BaZn}_2\text{Si}_2\text{O}_7$	Orthorhombic; five-fold Ba; $\text{ZnO}_4/\text{SiO}_4$ tetrahedra	HT-XRD, dilatometry	Low-temperature–high-temperature transition present [10, 11]
$\text{Ba}_{1-x}\text{Sr}_x\text{Zn}_2\text{Si}_2\text{O}_7$	Sr replaces Ba; high-temperature structure stabilized to room temperature	Single-crystal XRD, HT-XRD	Transition temperature drops markedly for $x \gtrsim 0.1$ [14, 15]
$\text{BaZn}_{2-x}\text{Mg}_x\text{Si}_2\text{O}_7$	Mg replaces Zn; structure varies with x	HT-XRD, dilatometry	Substitution changes the transition temperature and the expansion anisotropy [6]

2 STRUCTURAL BASIS AND POLYMORPHISM

2.1 LOW- AND HIGH-TEMPERATURE PHASES

$\text{BaZn}_2\text{Si}_2\text{O}_7$ undergoes a structural transition at about 280–300 °C; the ZnO_4 chains of the low-temperature phase are strongly directional, whereas the high-temperature phase releases thermal strain through tetrahedral rotation and adjustment of the inter-chain angles [10, 15]. HT-XRD and dilatometry show that the thermal expansion tensors of the two structures differ by far more than the usual sintering error, indicating that the transition itself is the primary variable in phase control [6, 14].

Public structural data assign low-temperature $\text{BaZn}_2\text{Si}_2\text{O}_7$ to the orthorhombic space group $\text{Cmc}2_1$, in which Ba^{2+} is five-fold coordinated and both Zn^{2+} and Si^{4+} are tetrahedrally coordinated; ZnO_4 and SiO_4 share corners to form a three-dimensional network [11]. These coordination data are suitable as a first-level screening criterion for structural analogy, but a database entry is not in situ high-temperature structural evidence and cannot replace the original diffraction refinement. Table 1 summarizes the structural information on these phases and the conclusions that can be used for phase control.

2.2 STRUCTURAL CRITERIA

The criteria for comparison with $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$ fall into four levels: first, whether the silicate groups remain isolated tetrahedra; second, whether Zn remains four-fold coordinated and forms traceable corner-sharing chains; third, whether the Ba/Y polyhedra have a comparable connectivity dimensionality; and fourth, whether the space group and lattice parameters are similar. The first two levels rest on direct structural evidence for $\text{BaZn}_2\text{Si}_2\text{O}_7$ [10, 11]; the latter two require single-crystal or high-resolution powder diffraction data for $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$, which are not yet available.

3 SYNTHESIS ROUTES AND PHASE CONTROL

3.1 SOLID-STATE AND SOLUTION PRECURSORS

The conventional solid-state reaction route uses BaCO_3/BaO , ZnO (or ZnCO_3) and SiO_2 as starting materials and yields $\text{BaZn}_2\text{Si}_2\text{O}_7$ after mixing, pre-firing, grinding and high-temperature soaking;

Table 2: Condition–outcome comparison of the reported synthesis routes.

Route	Precursor/key operations	Main-phase criterion	Limitations
Mixed-oxide solid-state reaction	Oxide or carbonate starting materials; repeated grinding and high-temperature soaking	Powder XRD consistent with dilatometry	Diffusion-limited; accompanying phases such as BaZnSiO ₄ readily remain [7]
Sol–gel/combustion synthesis	Molecular-level mixing; gel drying or combustion followed by calcination	Small particle size; powders of the polymorphs obtainable	Organic residues and atmosphere affect valence states [9, 29]
Glass crystallization	BaO/SrO/ZnO/SiO ₂ glass; nucleation and crystallization heat treatment	In situ XRD/microscopy locate the crystallization front	Residual glass phase and microcracks; nucleating agents introduce impurity phases [1, 24]

Co- and Mg-substituted systems generally follow the same oxide/carbonate reaction path and use intermediate regrinding to shorten diffusion distances [7, 17]. Combustion-assisted methods reduce the mixing scale of the precursor, but studies of Eu²⁺ luminescent materials show that the final phase composition still depends on the subsequent calcination temperature and atmosphere [29, 30]. The sol–gel route premixes Ba, Sr, Zn and Si at the molecular scale and is suited to fine powders and dense ceramics; Kracker et al. used it to prepare the high- and low-temperature polymorphs in a controlled manner [9].

3.2 GLASS CRYSTALLIZATION ROUTE

BaO/SrO/ZnO/SiO₂ glasses can precipitate Ba_{1-x}Sr_xZn₂Si₂O₇ upon nucleation–crystallization heat treatment. In situ microscopy and HT-XRD show that nucleating agents such as Pt, Sb₂O₃, Nb₂O₅, Ta₂O₅ and P₂O₅ alter the competition between surface and bulk crystallization [1, 4, 21, 23, 24, 26]. ZrO₂/TiO₂ and Al₂O₃ additives simultaneously affect the viscosity, the nucleation density and the final grain size [18, 25]. For BaZn₂Si₂O₇ itself, the advantage of the glass route lies in compositional homogeneity and tunable grain size; its drawback is that the residual glass phase and microcracks can mask the intrinsic thermal expansion [12, 16]. Table 2 compares the precursors, main-phase criteria and limitations of the individual routes.

3.3 PHASE DIAGRAM AND THERMODYNAMIC DATA

The existing literature includes a phase-equilibrium assessment of the binary BaO–ZnO system, but no complete CALPHAD database directly applicable to the ternary BaO–ZnO–SiO₂ system was retrieved. Whether a composition point lies within the primary phase field of BaZn₂Si₂O₇, and whether it passes through a eutectic liquid, can therefore be judged only by combining XRD experiments with thermal analysis. Theoretical–experimental studies of negative-thermal-expansion silicates show that the phonon free energy and the temperature-dependent phase stability cannot be inferred from the room-temperature structure alone [2].

4 STRUCTURALLY RELATED COMPOUNDS AND TRANSFERABLE VARIABLES

4.1 BA/SR SUBSTITUTION

Ba_{1-x}Sr_xZn₂Si₂O₇ is the most thoroughly studied isostructural substitution system. Replacing Ba²⁺ with Sr²⁺ lowers the formation temperature of the high-temperature phase; above a substitution level of about 10%, the high-temperature structure is retained at room temperature and shows near-zero or negative thermal expansion [14, 15, 19, 31]. Single-crystal XRD identifies this stabilized phase as orthorhombic Cmc₂m, and the twisting and rocking of the ZnO₄ chains are considered an important




Figure 2: Taxonomy of $\text{BaZn}_2\text{Si}_2\text{O}_7$ synthesis and phase control. Solid branches denote direct experimental evidence for the target phase or experimental evidence from structurally related compounds; dashed nodes denote comparison targets for which no direct structural report exists.

structural origin of the negative thermal expansion [15]. These results show that A-site ion size and polyhedral voids are effective phase-control variables, but they do not justify the inference that Y^{3+} can enter the same site in large amounts.

4.2 ZN-SITE AND SI-SITE SUBSTITUTION

Divalent ions such as Mg, Co, Mn, Ni and Cu can replace Zn over different ranges. Above a critical substitution level the low-temperature structure may reappear, indicating competition between local coordination preference and long-range phase stability [7, 17]. Ge substitution for Si changes the transition temperature through tetrahedral size and bond flexibility; the Ge solubility is limited in Sr-free compositions, whereas Sr-containing compositions retain the high-temperature structure up to higher Ge contents [13].

4.3 GLASS-CERAMIC PROCESSING

Studies of the glass route show that kinetic factors are as important as chemical composition. Pt nucleating agents promote heterogeneous nucleation, $\text{Nb}_2\text{O}_5/\text{Ta}_2\text{O}_5$ change the ratio of surface to bulk crystallization, and noble metals may also form alloys or core-shell structures [4, 20, 22, 24]. When the grain size is below about 80 μm , microcracking is reduced and the macroscopic thermal expansion approaches the intrinsic value of the crystal [16]. Phase-control studies of $\text{BaZn}_2\text{Si}_2\text{O}_7$ should therefore report phase composition, grain size and crack state together.

5 ASSESSMENT OF $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$ AS A STRUCTURAL ANALOGUE

The present search found no primary crystal-structure entry for $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$ in OpenAlex, Crossref or the accessible full-text corpus. The “yttrium barium silicates” retrieved are mainly luminescent thin films and oxyapatite-type materials, whose stoichiometry, space group and Zn occupancy all differ from the target formula [3, 28]. The more defensible designation at present is therefore “candidate structural analogue awaiting verification” rather than “known isostructural compound”.

Table 3: Evidence levels for the structural-analogue comparison.

Comparison level	Evidence for $\text{BaZn}_2\text{Si}_2\text{O}_7$	Implication for $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$
Silicate polymerisation	$\text{ZnO}_4/\text{SiO}_4$ corner-sharing network [10]	Usable as a topological starting point to be checked; not proof of isostructurality
Cation coordination	Five-fold Ba, four-fold Zn [11]	Y and Zn coordination must be measured, not presumed from ionic radii
Thermal stability	Transition at about 280–300 °C [15]	Serves only as a reference for the thermal-analysis program

Under this premise a tiered comparison is still possible. $\text{BaZn}_2\text{Si}_2\text{O}_7$ provides a direct reference for the $\text{ZnO}_4\text{--SiO}_4$ corner-sharing network and the Ba polyhedra [5, 10, 11]; the literature on yttrium barium silicate oxyapatites provides a compositional reference in which Y/Ba coexist with isolated silicate groups, but it does not demonstrate that the two topologies are identical [3, 27, 28]. Should powder or single-crystal data for the target phase become available, the degree of silicate polymerisation, the Zn coordination number, the connectivity of the Y polyhedra, the oxygen-vacancy positions and the space group should be checked in turn, rather than merely comparing the element ratios in the chemical formula.

The high Y content of $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$ also points to a charge-compensation problem. Formal valence counting requires additional O^{2-} or mixed cation valence states; any synthesis attempt must confirm the oxygen stoichiometry and valence states by thermogravimetric analysis, XPS/XANES or neutron diffraction. The thermally induced transition of $\text{BaZn}_2\text{Si}_2\text{O}_7$ can guide the choice of heat-treatment window but cannot be extrapolated directly to the Y-rich system. Table 3 lists the grounds for comparison by evidence level.

6 DISCUSSION: EVIDENCE STRENGTH AND OPEN QUESTIONS

The most complete direct evidence concerns the phase transition of $\text{BaZn}_2\text{Si}_2\text{O}_7$, the Ba/Sr solid solution and Zn-site substitution, for which the HT-XRD, single-crystal XRD and dilatometry results corroborate one another [6, 10, 15, 17]. For glass crystallization, nucleating-agent and microstructural effects have been studied systematically, but the glass compositions, heating rates and grain sizes differ between studies, so “phase stability” and “macroscopic thermal expansion of the sample” cannot be equated [16, 25].

The first key gap is the ternary BaO–ZnO–SiO₂ phase diagram and its thermodynamic functions. At present, phase regions can be inferred only from binary phase equilibria, laboratory XRD and thermal analysis; theoretical work indicates that vibrational free energy and temperature effects must be included [2]. The second gap is direct structural evidence for $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$. The mere coexistence of Ba, Y, Zn and silicate groups does not establish an isostructural relationship; verifiable diffraction data and coordination refinement are also required.

The recommended safe, falsifiable experimental path is as follows: first prepare composition-gradient samples on a small scale in a closed high-temperature furnace using vetted crucible materials; collect room-temperature/high-temperature powder XRD, TG-DSC, Raman spectra and microscopic compositional maps in parallel; and then perform synchrotron or single-crystal structure determination on samples that show a single diffraction phase. This path follows the complementary use of HT-XRD and dilatometry in the $\text{BaZn}_2\text{Si}_2\text{O}_7$ studies [6, 14]; unverified Y-rich formulations are not presented as directly executable experimental protocols.

Structural descriptors help narrow the candidate range. Negative-thermal-expansion studies show that tetrahedral rotation, chain flexibility and coordination-polyhedron voids can serve as screening features, but descriptors only yield candidates and cannot replace phase-equilibrium experiments [2, 8].

7 CONCLUSIONS AND PRIORITY EXPERIMENTS

The available evidence supports the following conclusions: the low-temperature–high-temperature polymorphism of $\text{BaZn}_2\text{Si}_2\text{O}_7$ is governed by the ZnO_4 chains and the SiO_4 corner-sharing network; Ba/Sr, Zn/Mg/Co/Ni/Cu and Si/Ge substitution can systematically tune the transition temperature and thermal expansion; and the solid-state, sol–gel and glass-crystallization routes each have well-defined kinetic windows, but all require phase composition and microstructure to be reported together [1, 6, 10, 15, 17]. For $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$, only clues from compositionally similar systems exist, with no verifiable direct structural or synthesis report, so “structural analogue” should be treated as a hypothesis awaiting verification.

The highest-priority follow-up experiments are, in order: (i) determine the ternary BaO–ZnO– SiO_2 phase diagram and build a temperature-dependent thermodynamic model; (ii) search a composition gradient for the single-phase window of $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$ and track its transitions by HT-XRD; and (iii) refine the Y/Zn coordination and oxygen stoichiometry of candidate samples. Only after these three steps can one judge at which level the structure–processing trends of $\text{BaZn}_2\text{Si}_2\text{O}_7$ can be extrapolated to the Y-rich framework.

REFERENCES

- [1] Christian Bocker, Marlen Michaelis, and Christian Rüssel. In situ crystallization of barium zinc silicate in glass-ceramics studied by hot stage scanning electron microscopy. *Microscopy*, 61(6):381–391, 2012. doi: [10.1093/jmicro/dfs058](https://doi.org/10.1093/jmicro/dfs058).
- [2] Andreas Erlebach, Ghada B. Hassine, Christian Thieme, Katrin Thieme, Christian Rüssel, and Marek Sierka. Phase stability determination of negative thermal expansion silicates by theory and experiment. *Physical Chemistry Chemical Physics*, 23(45):25533–25541, 2021. doi: [10.1039/d1cp03862a](https://doi.org/10.1039/d1cp03862a).
- [3] Ritu Gupta, Ananya Rout, and Sadhana Agrawal. Combustion synthesis and photoluminescence studies of rare earth activated yttrium barium silicate oxyapatites. *Materials Today: Proceedings*, 44:3156–3159, 2021. doi: [10.1016/j.matpr.2021.02.822](https://doi.org/10.1016/j.matpr.2021.02.822).
- [4] Stephan Heitmann, Katrin Thieme, Christian Thieme, Michael Kracker, Thomas Höche, and Christian Rüssel. Surface and bulk crystallization of $\text{Ba}_{1-x}\text{Sr}_x\text{Zn}_2\text{Si}_2\text{O}_7$ from glasses in the system BaO/SrO/ZnO/SiO₂ doped with Nb₂O₅ or Ta₂O₅. *Ceramics International*, 45(6):7580–7587, 2019. doi: [10.1016/j.ceramint.2019.01.052](https://doi.org/10.1016/j.ceramint.2019.01.052).
- [5] J. W. Kaiser and W. Jeitschko. Crystal structure of the new barium zinc silicate $\text{Ba}_2\text{ZnSi}_2\text{O}_7$. *Zeitschrift für Kristallographie – New Crystal Structures*, 217:25–26, 2002. doi: [10.1524/ncrs.2002.217.jg.25](https://doi.org/10.1524/ncrs.2002.217.jg.25).
- [6] Marita Kerstan, Matthias Müller, and Christian Rüssel. Thermal expansion of $\text{Ba}_2\text{ZnSi}_2\text{O}_7$, BaZnSiO_4 and the solid solution series $\text{BaZn}_{2-x}\text{Mg}_x\text{Si}_2\text{O}_7$ ($0 \leq x \leq 2$) studied by high-temperature X-ray diffraction and dilatometry. *Journal of Solid State Chemistry*, 188:84–91, 2012. doi: [10.1016/j.jssc.2012.01.055](https://doi.org/10.1016/j.jssc.2012.01.055).
- [7] Marita Kerstan, Christian Thieme, Matthias Grosch, Matthias Müller, and Christian Rüssel. $\text{BaZn}_2\text{Si}_2\text{O}_7$ and the solid solution series $\text{BaZn}_{2-x}\text{Co}_x\text{Si}_2\text{O}_7$ ($0 < x \leq 2$) as high temperature seals for solid oxide fuel cells studied by high-temperature X-ray diffraction and dilatometry. *Journal of Solid State Chemistry*, 207:55–60, 2013. doi: [10.1016/j.jssc.2013.09.003](https://doi.org/10.1016/j.jssc.2013.09.003).
- [8] Natalia Kireeva and A. Yu. Tsivadze. Pauling number as efficient descriptors for screening the structures with negative thermal expansion characteristics. *ChemRxiv*, 2022. doi: [10.26434/chemrxiv-2022-xrthv](https://doi.org/10.26434/chemrxiv-2022-xrthv).
- [9] Michael Kracker, Christian Thieme, Johannes Häßler, and Christian Rüssel. Sol–gel powder synthesis and preparation of ceramics with high- and low-temperature polymorphs of $\text{Ba}_x\text{Sr}_{1-x}\text{Zn}_2\text{Si}_2\text{O}_7$ ($x = 1$ and 0.5): A novel approach to obtain zero thermal expansion. *Journal of the European Ceramic Society*, 36(8):2097–2107, 2016. doi: [10.1016/j.jeurceramsoc.2016.02.023](https://doi.org/10.1016/j.jeurceramsoc.2016.02.023).
- [10] Jianhua Lin, Guoxing Lu, Juan Du, M. Z. Su, C.-K. Loong, and C. J. Richardson. Phase transition and crystal structures of $\text{BaZn}_2\text{Si}_2\text{O}_7$. *Journal of Physics and Chemistry of Solids*, 60(7):975–983, 1999. doi: [10.1016/s0022-3697\(99\)00004-9](https://doi.org/10.1016/s0022-3697(99)00004-9).
- [11] Materials Project. Materials data on $\text{BaZn}_2\text{Si}_2\text{O}_7$ by Materials Project. Materials Project dataset, OSTI (U.S. DOE Office of Scientific and Technical Information), 2020. doi: [10.17188/1271462](https://doi.org/10.17188/1271462).
- [12] Christian Thieme and Christian Rüssel. High thermal expansion of crystallized glasses in the system BaO–ZnO–NiO–SiO₂. *Ceramics International*, 41(10):13310–13319, 2015. doi: [10.1016/j.ceramint.2015.07.114](https://doi.org/10.1016/j.ceramint.2015.07.114).
- [13] Christian Thieme and Christian Rüssel. Negative thermal expansion in $\text{Ba}_{0.5}\text{Sr}_{0.5}\text{Zn}_2\text{Si}_2\text{GeO}_7$. *Materials*, 9(8):631, 2016. doi: [10.3390/ma9080631](https://doi.org/10.3390/ma9080631).

- [14] Christian Thieme and Christian Rüssel. Very high or close to zero thermal expansion by the variation of the Sr/Ba ratio in Ba_{1-x}Sr_xZn₂Si₂O₇ – solid solutions. *Dalton Transactions*, 45(11):4888–4895, 2016. doi: [10.1039/c5dt04970a](https://doi.org/10.1039/c5dt04970a).
- [15] Christian Thieme, Helmar Görls, and Christian Rüssel. Ba_{1-x}Sr_xZn₂Si₂O₇ – a new family of materials with negative and very high thermal expansion. *Scientific Reports*, 5(1), 2015. doi: [10.1038/srep18040](https://doi.org/10.1038/srep18040).
- [16] Christian Thieme, Martin Schlesier, Christian Bocker, Gabriel Buzatto de Souza, and Christian Rüssel. Thermal expansion of sintered glass ceramics in the system BaO–SrO–ZnO–SiO₂ and its dependence on particle size. *ACS Applied Materials & Interfaces*, 8(31):20212–20219, 2016. doi: [10.1021/acsami.6b07353](https://doi.org/10.1021/acsami.6b07353).
- [17] Christian Thieme, Tina Waurischk, Stephan Heitmann, and Christian Rüssel. New family of materials with negative coefficients of thermal expansion: The effect of MgO, CoO, MnO, NiO, or CuO on the phase stability and thermal expansion of solid solution phases derived from BaZn₂Si₂O₇. *Inorganic Chemistry*, 55(9):4476–4484, 2016. doi: [10.1021/acs.inorgchem.6b00290](https://doi.org/10.1021/acs.inorgchem.6b00290).
- [18] Christian Thieme, Michael Kracker, Andreas Erlebach, Christian Patzig, Marek Sierka, Thomas Höche, and Christian Rüssel. Effect of Al₂O₃ on phase formation and thermal expansion of a BaO–SrO–ZnO–SiO₂ glass ceramic. *Ceramics International*, 44(2):2098–2108, 2017. doi: [10.1016/j.ceramint.2017.10.159](https://doi.org/10.1016/j.ceramint.2017.10.159).
- [19] Christian Thieme, Martin Schlesier, Eze Oji Dike, and Christian Rüssel. Variable thermal expansion of glass-ceramics containing Ba_{1-x}Sr_xZn₂Si₂O₇. *Scientific Reports*, 7(1), 2017. doi: [10.1038/s41598-017-03132-x](https://doi.org/10.1038/s41598-017-03132-x).
- [20] Christian Thieme, Liliya Vladislavova, Katrin Thieme, Christian Patzig, Thomas Höche, and Christian Rüssel. Noble metals Pt, Au, and Ag as nucleating agents in BaO/SrO/ZnO/SiO₂ glasses: formation of alloys and core–shell structures. *Journal of Materials Science*, 57(12):6607–6618, 2022. doi: [10.1007/s10853-022-07054-6](https://doi.org/10.1007/s10853-022-07054-6).
- [21] Katrin Thieme, Tilman Zscheckel, Christian Thieme, Thomas Höche, and Christian Rüssel. On the search for nucleation agents in BaO–SrO–ZnO–SiO₂ glasses: The influence of P₂O₅. *Journal of the European Ceramic Society*, 38(4):2017–2026, 2017. doi: [10.1016/j.jeurceramsoc.2017.12.034](https://doi.org/10.1016/j.jeurceramsoc.2017.12.034).
- [22] Katrin Thieme, Tilman Zscheckel, Christian Thieme, Michael Kracker, Christian Rüssel, and Thomas Höche. Growth-front hopping via stress-induced nucleation illustrated for the crystallization of Ba_{1-x}Sr_xZn₂Si₂O₇ from a glass in the BaO–SrO–ZnO–SiO₂ system. *Ceramics International*, 44(16):19970–19980, 2018. doi: [10.1016/j.ceramint.2018.07.264](https://doi.org/10.1016/j.ceramint.2018.07.264).
- [23] Liliya Vladislavova. *Nucleation agents in the glass system BaO/SrO/ZnO/SiO₂*. PhD thesis, Friedrich-Schiller-Universität Jena, 2018. doi: [10.22032/dbt.37559](https://doi.org/10.22032/dbt.37559).
- [24] Liliya Vladislavova, Christian Thieme, Tilman Zscheckel, Christian Patzig, Thomas Höche, and Christian Rüssel. Heterogeneous nucleation of Ba_{1-x}Sr_xZn₂Si₂O₇ from a BaO/SrO/ZnO/SiO₂ glass using platinum as nucleation agent. *Journal of the European Ceramic Society*, 37(15):4801–4808, 2017. doi: [10.1016/j.jeurceramsoc.2017.05.020](https://doi.org/10.1016/j.jeurceramsoc.2017.05.020).
- [25] Liliya Vladislavova, Michael Kracker, Tilman Zscheckel, Christian Thieme, and Christian Rüssel. Crystallisation of Ba_{1-x}Sr_xZn₂Si₂O₇ from BaO/SrO/ZnO/SiO₂ glass with different ZrO₂ and TiO₂ concentrations. *Solid State Sciences*, 78:107–115, 2018. doi: [10.1016/j.solidstatesciences.2018.02.011](https://doi.org/10.1016/j.solidstatesciences.2018.02.011).
- [26] Liliya Vladislavova, Christian Thieme, Tilman Zscheckel, Thomas Höche, and Christian Rüssel. Crystallization of Ba_{1-x}Sr_xZn₂Si₂O₇ from the BaO/SrO/ZnO/SiO₂ glass system: Effect of platinum and Sb₂O₃ on nucleation. *Journal of Alloys and Compounds*, 793:705–714, 2019. doi: [10.1016/j.jallcom.2019.04.034](https://doi.org/10.1016/j.jallcom.2019.04.034).
- [27] Donglei Wei, Yanlin Huang, Sun Il Kim, Young Moon Yu, and Hyo Jin Seo. A new green-emitting barium zinc silicate: Eu²⁺-doped Ba₂Zn₃Si₃O₁₁. *Materials Letters*, 99:122–124, 2013. doi: [10.1016/j.matlet.2013.02.083](https://doi.org/10.1016/j.matlet.2013.02.083).
- [28] Chen Yang, Can He, Ximing Huang, Guo Chen, Guoqin Leng, Ruiyu Mi, Xin Min, and Zhaohui Huang. Cyan-emitting Ba_{0.45}Ca_{2.5}La₆(SiO₄)₆: 0.05 Eu²⁺ and Ba_{1.45}Ca_{1.5}La₆(SiO₄)₆:0.05 Eu²⁺ solid-solution phosphors for white light-emitting diodes. *Ceramics International*, 47(9):12348–12356, 2021. doi: [10.1016/j.ceramint.2021.01.087](https://doi.org/10.1016/j.ceramint.2021.01.087).
- [29] Shanshan Yao, Lihong Xue, and Youwei Yan. Synthesis and luminescent properties of Eu²⁺ doped BaZn₂Si₂O₇ phosphors by combustion-assisted synthesis method. *Journal of Alloys and Compounds*, 509(5):1870–1873, 2010. doi: [10.1016/j.jallcom.2010.10.076](https://doi.org/10.1016/j.jallcom.2010.10.076).
- [30] Shanshan Yao, Lihong Xue, and Youwei Yan. Synthesis and crystal structures and luminescent properties of divalent europium-doped Ba₂ZnSi₂O₇ and BaZn₂Si₂O₇. *Physica B: Condensed Matter*, 406(2):250–253, 2010. doi: [10.1016/j.physb.2010.10.059](https://doi.org/10.1016/j.physb.2010.10.059).
- [31] Zheng-Yu Zou, Yihui Lou, Xiaoqiang Song, Hai Jiang, Kang Du, Changzhi Yin, Wenzhong Lü, Xiao-Chuan Wang, Xiao-Hong Wang, Ming Fu, and Wen Lei. Near-zero thermal expansion

Ba_{1-x}Sr_xZn₂Si₂O₇-based microwave dielectric ceramics for 3D printed dielectric resonator antenna with integrative lens. *Advanced Materials Interfaces*, 8(15), 2021. doi: [10.1002/admi.202100584](https://doi.org/10.1002/admi.202100584).