

BaZn₂Si₂O₇ 的合成与相控制：作为 Ba₅Y₁₂Zn[O(SiO₄)]₈ 的结构类似物

GoAI Research · 2026

摘要。本文综述 BaZn₂Si₂O₇ 的晶体结构、合成路线和相控制变量，并评估其作为 Ba₅Y₁₂Zn[O(SiO₄)]₈ 结构类似物的可比性。已有研究通过高温衍射、单晶结构分析和热膨胀测量建立了 BaZn₂Si₂O₇ 的低温—高温多晶型及 Ba/Sr、Zn 位替位规律；固相、溶胶—凝胶和玻璃析晶路线揭示了前驱体均匀性、成核剂和微结构对主相的共同影响。公开检索未发现 Ba₅Y₁₂Zn[O(SiO₄)]₈ 的可验证原始结构或合成报道，因此本文仅提出分层判据和可证伪实验优先级。

BaZn₂Si₂O₇ 综述路线



阅读顺序：事实 → 比较 → 可证伪建议

图1 行文路线图：结构事实→合成窗口→近邻迁移→实验建议。

1 研究背景与范围

BaZn₂Si₂O₇ 是 BaO–ZnO–SiO₂ 体系中具有可逆结构转变的硅酸盐。其低温相表现出显著正热膨胀，加热后形成的高温相可呈近零或负热膨胀。本文区分直接报道、近邻体系和结构推断；Ba₅Y₁₂Zn[O(SiO₄)]₈ 的精确式未检出可核验原始条目。 [1,6–8,15]

2 结构基础与多晶型

Lin 等通过高温衍射解析了 BaZn₂Si₂O₇ 的相变。公开结构数据给出正交 Cmc2₁、Ba 五配位以及 ZnO₄/SiO₄ 角共享网络。相变温区约为 280–300 °C；ZnO₄ 链的转动和链间角度调整解释了膨胀张量的突变。 [1,6,7,15]

相或组成	结构与表征	相控制结论
BaZn ₂ Si ₂ O ₇	正交；Ba 五配位、ZnO ₄ /SiO ₄ 四面体；高温 XRD	存在低温—高温转变
Ba _{1-x} Sr _x Zn ₂ Si ₂ O ₇	Sr 替 Ba；单晶 XRD、HT-XRD	x≈0.1 以上可稳定高温结构
BaZn _{2-x} Mg _x Si ₂ O ₇	Mg 替 Zn；HT-XRD、膨胀测量	替位改变相变温度和各向异性

3 合成路线与相控制

固相与溶液前驱体

混合 BaCO₃/BaO、ZnO（或 ZnCO₃）和 SiO₂，经预烧、研磨和高温保温可获得目标相；Co、Mg 替位沿用氧化物/碳酸盐反应。燃烧辅助法缩短混合尺度，溶胶—凝胶法有利于制备细粉，但后续煅烧气氛仍决定最终相。 [2-5,9]

玻璃析晶

BaO/SrO/ZnO/SiO₂ 玻璃经成核—晶化热处理析出 Ba_{1-x}Sr_xZn₂Si₂O₇。Pt、Sb₂O₃、Nb₂O₅、Ta₂O₅ 和 P₂O₅ 改变表面/体析晶竞争；晶粒和微裂纹会掩盖本征膨胀。 [10,12,13,20-25,27,31]

相图与热力学

BaO–ZnO 二元关系已有评估，但未检索到完整 BaO–ZnO–SiO₂ 三元 CALPHAD 数据。组成点是否经过共晶液相需结合实验 XRD、TG–DSC 和温度相关自由能分析。 [17]

4 近邻体系与可迁移变量

Ba/Sr 替位是最成熟的同型近邻：少量 Sr 可把高温结构稳定至室温并产生近零/负热膨胀。Mg、Co、Mn、Ni、Cu 替 Zn，以及 Ge 替 Si，会改变四面体尺寸、链柔性 and 相变温度。玻璃路线还显示成核剂、升温速率、晶粒尺寸和微裂纹必须同时报告。 [3,7-11,18,19,22,26,30,32]




图2 BaZn₂Si₂O₇ 分类框架。虚线为结构化学比较，不表示同构。

5 Ba₅Y₁₂Zn[O(SiO₄)]₈ 的类似物判读

“钇钡硅酸盐”检索结果主要是发光薄膜和氧基磷灰石，化学计量、空间群和 Zn 占位均不等同于目标式。可比较的层级应依次为硅酸根聚合度、Zn 配位、Y/Ba 多面体连接、氧空位位置和空间群；目前只有前两层具有 BaZn₂Si₂O₇ 的直接参照。 [15,28-30,32]

6 讨论与开放问题

最充分的证据来自 $\text{BaZn}_2\text{Si}_2\text{O}_7$ 相变及 Ba/Sr、Zn 位固溶；玻璃析晶的动力学结果受组成和微结构差异影响。首要缺口是三元相图和温度相关热力学函数，其次是 $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$ 的直接结构。推荐在经安全审查的条件下开展组成梯度、小规模封闭式热处理，并同步采集室温/高温 XRD、TG-DSC、Raman 和显微成分图；候选单相再做配位精修。 [1,3,6,7,10,12,13,17,26]

7 结论与优先实验

$\text{BaZn}_2\text{Si}_2\text{O}_7$ 的多晶型由 ZnO_4 链和 SiO_4 角共享网络控制，阳离子替位与玻璃工艺可系统调节相变和热膨胀。 $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$ 仍是待验证候选。优先顺序为：测定 BaO-ZnO-SiO₂ 三元相图；寻找 Y-rich 单相窗口并追踪高温转变；完成 Y/Zn 配位和氧计量精修。 [1,3,6,7,17,26]

参考文献

完整、经核查的 32 条文献见随附 *references.bib*；正文引用键与该文件一一对应。

1. **lin1999phase**. Jianhua Lin and Guoxing Lu and Juan Du and M. Z. Su and C.-K. Loong and C. J. Richardson (1999). *Phase transition and crystal structures of $\text{BaZn}_2\text{Si}_2\text{O}_7$* . DOI: 10.1016/s0022-3697(99)00004-9
2. **kerstan2013bazn2si2o7**. Marita Kerstan and Christian Thieme and Matthias Grosch and Matthias Müller and Christian Rüssel (2013). *$\text{BaZn}_2\text{Si}_2\text{O}_7$ and the solid solution series $\text{BaZn}_{2-x}\text{Co}_x\text{Si}_2\text{O}_7$ (0. DOI: 10.1016/j.jssc.2013.09.003*
3. **thieme2016new**. Christian Thieme and Tina Waurischk and Stephan Heitmann and Christian Rüssel (2016). *New Family of Materials with Negative Coefficients of Thermal Expansion: The Effect of MgO, CoO, MnO, NiO, or CuO on the Phase Stability and Thermal Expansion of Solid Solution Phases Derived from $\text{BaZn}_2\text{Si}_2\text{O}_7$* . DOI: 10.1021/acs.inorgchem.6b00290
4. **yao2010synthesis**. Shanshan Yao and Lihong Xue and Youwei Yan (2010). *Synthesis and luminescent properties of Eu^{2+} doped $\text{BaZn}_2\text{Si}_2\text{O}_7$ phosphors by combustion-assisted synthesis method*. DOI: 10.1016/j.jallcom.2010.10.076
5. **yao2010synthesisx**. Shanshan Yao and Lihong Xue and Youwei Yan (2010). *Synthesis and crystal structures and luminescent properties of divalent europium-doped $\text{Ba}_2\text{ZnSi}_2\text{O}_7$ and $\text{BaZn}_2\text{Si}_2\text{O}_7$* . DOI: 10.1016/j.physb.2010.10.059
6. **kerstan2012thermal**. Marita Kerstan and Matthias Müller and Christian Rüssel (2012). *Thermal expansion of $\text{Ba}_2\text{ZnSi}_2\text{O}_7$, BaZnSiO_4 and the solid solution series $\text{BaZn}_{2-x}\text{Mg}_x\text{Si}_2\text{O}_7$ ($0 \leq x \leq 2$) studied by high-temperature X-ray diffraction and dilatometry*. DOI: 10.1016/j.jssc.2012.01.055
7. **thieme2015ba1**. Christian Thieme and Helmar Görls and Christian Rüssel (2015). *$\text{Ba}_1-x\text{Sr}_x\text{Zn}_2\text{Si}_2\text{O}_7$ - A new family of materials with negative and very high thermal expansion*. DOI: 10.1038/srep18040
8. **thieme2016very**. Christian Thieme and Christian Rüssel (2016). *Very high or close to zero thermal expansion by the variation of the Sr/Ba ratio in $\text{Ba}_{1-x}\text{Sr}_x\text{Zn}_2\text{Si}_2\text{O}_7$ - solid solutions*. DOI: 10.1039/c5dt04970a
9. **kracker2016sol**. Michael Kracker and Christian Thieme and Johannes Häßler and Christian Rüssel (2016). *Sol-gel powder synthesis and preparation of ceramics with high- and low-temperature polymorphs of $\text{Ba}_{1-x}\text{Sr}_x\text{Zn}_2\text{Si}_2\text{O}_7$ ($x = 1$ and 0.5): A novel approach to obtain zero thermal expansion*. DOI: 10.1016/j.jeurceramsoc.2016.02.023
10. **thieme2016thermal**. Christian Thieme and Martin Schlesier and Christian Bocker and Gabriel Buzatto de Souza and Christian Rüssel (2016). *Thermal Expansion of Sintered Glass Ceramics in the System BaO-SrO-ZnO-SiO_2 and Its Dependence on Particle Size*. DOI: 10.1021/acsami.6b07353
11. **thieme2016negative**. Christian Thieme and Christian Rüssel (2016). *Negative Thermal Expansion in $\text{Ba}_0.5\text{Sr}_0.5\text{Zn}_2\text{Si}_2\text{GeO}_7$* . DOI: 10.3390/ma9080631
12. **vladislavova2017heterogeneous**. Liliya Vladislavova and Christian Thieme and Tilman Zscheckel and Christian Patzig and Thomas Höche and Christian Rüssel (2017). *Heterogeneous nucleation of $\text{Ba}_{1-x}\text{Sr}_x\text{Zn}_2\text{Si}_2\text{O}_7$ from a BaO/SrO/ZnO/SiO_2 glass using platinum as nucleation agent*. DOI: 10.1016/j.jeurceramsoc.2017.05.020
13. **vladislavova2018crystallisation**. Liliya Vladislavova and Michael Kracker and Tilman Zscheckel and Christian Thieme and Christian Rüssel (2018). *Crystallisation of $\text{Ba}_{1-x}\text{Sr}_x\text{Zn}_2\text{Si}_2\text{O}_7$ from BaO/SrO/ZnO/SiO_2 glass with different ZrO_2 and TiO_2 concentrations*. DOI: 10.1016/j.solidstatesciences.2018.02.011
14. **thieme2015high**. Christian Thieme and Christian Rüssel (2015). *High thermal expansion of crystallized glasses in the system BaO-ZnO-NiO-SiO_2* . DOI: 10.1016/j.ceramint.2015.07.114
15. **available2020materials**. None Available (2020). *Materials Data on $\text{BaZn}_2\text{Si}_2\text{O}_7$ by Materials Project*. DOI: 10.17188/1271462
16. **thieme2016cheminform**. Christian Thieme and Tina Waurischk and Stephan Heitmann and Christian Ruessel (2016). *ChemInform Abstract: New Family of Materials with Negative Coefficients of Thermal Expansion: The Effect of MgO, CoO, MnO, NiO, or CuO on the Phase Stability and Thermal Expansion of Solid Solution Phases Derived from $\text{BaZn}_2\text{Si}_2\text{O}_7$* . DOI: 10.1002/chin.201628006
17. **erlebach2021phase**. Andreas Erlebach and Ghada B. Hassine and Christian Thieme and Katrin Thieme and Christian Rüssel and Marek Sierka (2021). *Phase stability determination of negative thermal expansion silicates by theory and experiment*. DOI: 10.1039/d1cp03862a
18. **zou2021near**. Zheng - Yu Zou and Yihui Lou and Xiaoqiang Song and Hai Jiang and Kang Du and Changzhi Yin and Wenzhong Lü and Xiao - Chuan Wang and Xiao - Hong Wang and Ming Fu and Wen Lei (2021). *Near - Zero Thermal Expansion $\text{Ba}_{1-x}\text{Sr}_x\text{Zn}_2\text{Si}_2\text{O}_7$ - Based Microwave Dielectric Ceramics for 3D Printed Dielectric Resonator Antenna with Integrative Lens*. DOI: 10.1002/admi.202100584
19. **thieme2017variable**. Christian Thieme and Martin Schlesier and Eze Oji Dike and Christian Rüssel (2017). *Variable thermal expansion of glass-ceramics containing $\text{Ba}_{1-x}\text{Sr}_x\text{Zn}_2\text{Si}_2\text{O}_7$* . DOI: 10.1038/s41598-017-03132-x
20. **vladislavova2019crystallization**. Liliya Vladislavova and Christian Thieme and Tilman Zscheckel and Thomas Höche and Christian

- Rüssel (2019). *Crystallization of Ba1-xSrxZn2Si2O7 from the BaO/SrO/ZnO/SiO2 glass system: Effect of platinum and Sb2O3 on nucleation*. DOI: 10.1016/j.jallcom.2019.04.034
21. **heitmann2019surface**. Stephan Heitmann and Katrin Thieme and Christian Thieme and Michael Kracker and Thomas Höche and Christian Rüssel (2019). *Surface and bulk crystallization of Ba1-xSrxZn2Si2O7 from glasses in the system BaO/SrO/ZnO/SiO2 doped with Nb2O5 or Ta2O5*. DOI: 10.1016/j.ceramint.2019.01.052
 22. **thieme2018growth**. Katrin Thieme and Tilman Zscheckel and Christian Thieme and Michael Kracker and Christian Rüssel and Thomas Höche (2018). *Growth-front hopping via stress-induced nucleation illustrated for the crystallization of Ba1-xSrxZn2Si2O7 from a glass in the BaO-SrO-ZnO-SiO2 system*. DOI: 10.1016/j.ceramint.2018.07.264
 23. **thieme2017on**. Katrin Thieme and Tilman Zscheckel and Christian Thieme and Thomas Höche and Christian Rüssel (2017). *On the search for nucleation agents in BaO-SrO-ZnO-SiO2 glasses: The influence of P2O5*. DOI: 10.1016/j.jeurceramsoc.2017.12.034
 24. **thieme2017effect**. Christian Thieme and Michael Kracker and Andreas Erlebach and Christian Patzig and Marek Sierka and Thomas Höche and Christian Rüssel (2017). *Effect of Al2O3 on phase formation and thermal expansion of a BaO-SrO-ZnO-SiO2 glass ceramic*. DOI: 10.1016/j.ceramint.2017.10.159
 25. **vladislavova2018nucleation**. Liliya Vladislavova (2018). *Nucleation agents in the glass system BaO/SrO/ZnO/SiO2*. DOI: 10.22032/dbt.37559
 26. **kireeva2022pauling**. Natalia Kireeva and A. Yu. Tsivadze (2022). *Pauling Number as Efficient Descriptors for Screening the Structures with Negative Thermal Expansion Characteristics*. DOI: 10.26434/chemrxiv-2022-xrthv
 27. **thieme2022noble**. Christian Thieme and Liliya Vladislavova and Katrin Thieme and Christian Patzig and Thomas Höche and Christian Rüssel (2022). *Noble metals Pt, Au, and Ag as nucleating agents in BaO/SrO/ZnO/SiO2 glasses: formation of alloys and core-shell structures*. DOI: 10.1007/s10853-022-07054-6
 28. **yang2021cyan**. Chen Yang and Can He and Ximing Huang and Guo Chen and Guoqin Leng and Ruiyu Mi and Xin Min and Zhaohui Huang (2021). *Cyan-emitting Ba0.45Ca2.5La6(SiO4)6: 0.05 Eu2+ and Ba1.45Ca1.5La6(SiO4)6:0.05 Eu2+ solid-solution phosphors for white light-emitting diodes*. DOI: 10.1016/j.ceramint.2021.01.087
 29. **gupta2021combustion**. Ritu Gupta and Ananya Rout and Sadhana Agrawal (2021). *Combustion synthesis and photoluminescence studies of rare earth activated Yttrium Barium silicate Oxyapatites*. DOI: 10.1016/j.matpr.2021.02.822
 30. **kaiser2002crystal**. J. W. Kaiser and W. Jeitschko (2002). *Crystal structure of the new barium zinc silicate Ba2ZnSi2O7*. DOI: 10.1524/ncrs.2002.217.jg.25
 31. **bocker2012in**. Christian Bocker and Marlen Michaelis and Christian Rüssel (2012). *In situ crystallization of barium zinc silicate in glass-ceramics studied by hot stage scanning electron microscopy*. DOI: 10.1093/jmicro/dfs058
 32. **wei2013a**. Donglei Wei and Yanlin Huang and Sun Il Kim and Young Moon Yu and Hyo Jin Seo (2013). *A new green-emitting barium zinc silicate: Eu2+-doped Ba2Zn3Si3O11*. DOI: 10.1016/j.matlet.2013.02.083