
SYNTHESIS AND PHASE CONTROL OF $\text{BaZn}_2\text{Si}_2\text{O}_7$ AS A STRUCTURAL ANALOGUE OF $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$

GoAI Research

ABSTRACT

We review the crystal structure, synthesis routes, and phase-control variables of $\text{BaZn}_2\text{Si}_2\text{O}_7$ and assess how far it can serve as a structural analogue of $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$. High-temperature X-ray diffraction (HT-XRD), single-crystal structure analysis, and dilatometry have established the low-temperature–high-temperature polymorphism of $\text{BaZn}_2\text{Si}_2\text{O}_7$ and the substitution rules for Ba/Sr and for the Zn site, and the solid-state, sol–gel, and glass-crystallization routes show that precursor homogeneity, nucleating agents, and microstructure jointly govern formation of the main phase. For $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$, by contrast, our check found no verifiable primary structural or synthesis report, so we can offer only tiered structural criteria and falsifiable experimental priorities. We identify the missing ternary BaO–ZnO–SiO₂ phase diagram and temperature-dependent thermodynamic data as the key gaps and outline a conservative path that combines HT-XRD, thermal analysis, and coordination refinement.


1 BACKGROUND AND SCOPE

$\text{BaZn}_2\text{Si}_2\text{O}_7$ is a silicate in the BaO–ZnO–SiO₂ system that undergoes a reversible structural transition. Its low-temperature phase shows pronounced positive thermal expansion, whereas the high-temperature phase that forms on heating can show near-zero or negative thermal expansion, which makes the compound a model system for studying tetrahedral-chain flexibility and compositional tuning. Lin et al. resolved the transition and both crystal structures by high-temperature X-ray diffraction (HT-XRD), providing the structural benchmark for the phase-control studies that followed [10].

This review is organized around three questions: how the structure and synthesis conditions of $\text{BaZn}_2\text{Si}_2\text{O}_7$ jointly determine the main phase; how far Ba/Sr, Zn/Mg/Co/Ni/Cu, and Si/Ge substitution can tune phase stability; and what verifiable grounds exist for treating $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$ as a structural analogue. Public databases confirm that $\text{BaZn}_2\text{Si}_2\text{O}_7$ is orthorhombic, that Ba is five-coordinate, and that the ZnO_4 and SiO_4 tetrahedra form a corner-sharing network [11], but our search turned up no verifiable primary crystallographic paper on $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$. Throughout, we therefore keep “direct reports”, “structurally related compounds”, and “structural inference” strictly apart.

The structurally related compounds are more than background. Work on $\text{Ba}_{1-x}\text{Sr}_x\text{Zn}_2\text{Si}_2\text{O}_7$ shows that a small amount of Sr is enough to stabilize the high-temperature structure down to room temperature and to push the thermal expansion coefficient into the negative range [14, 15], and aliovalent or isovalent substitution on the Zn site further shifts the transition temperature and the anisotropy [7, 17]. These findings supply transferable structure–processing correlations against which the target analogue can be compared; they do not imply that $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$ has been synthesized.

Figure 1 lays out the order in which these topics are treated, and Figure 2 places structure, synthesis, phase control, and evidence boundaries in a single framework.



Reading order: facts → comparison → falsifiable proposals

Figure 1: Roadmap of this review. Arrows trace the progression from structural facts to synthesis windows, to trends transferred from structurally related compounds, and finally to falsifiable experimental recommendations.

Table 1: Structure and thermal behavior of $\text{BaZn}_2\text{Si}_2\text{O}_7$ and its structurally related compounds.

Phase or composition	Structure and coordination	Characterization	Implication for phase control
$\text{BaZn}_2\text{Si}_2\text{O}_7$	Orthorhombic; five-coordinate Ba; $\text{ZnO}_4/\text{SiO}_4$ tetrahedra	HT-XRD, dilatometry	Low- to high-temperature transition present [10, 11]
$\text{Ba}_{1-x}\text{Sr}_x\text{Zn}_2\text{Si}_2\text{O}_7$	Sr on the Ba site; high-temperature structure retained to room temperature	Single-crystal XRD, HT-XRD	Transition temperature drops sharply for $x \gtrsim 0.1$ [14, 15]
$\text{BaZn}_{2-x}\text{Mg}_x\text{Si}_2\text{O}_7$	Mg on the Zn site; structure varies with x	HT-XRD, dilatometry	Substitution shifts the transition temperature and the expansion anisotropy [6]

2 STRUCTURAL BASIS AND POLYMORPHISM

2.1 LOW- AND HIGH-TEMPERATURE PHASES

$\text{BaZn}_2\text{Si}_2\text{O}_7$ transforms at roughly 280–300 °C. In the low-temperature phase the ZnO_4 chains are strongly directional, whereas the high-temperature phase relieves thermal strain by rotating its tetrahedra and adjusting the angles between chains [10, 15]. HT-XRD and dilatometry show that the thermal expansion tensors of the two structures differ by far more than the usual scatter introduced by sintering, which makes the transition itself the primary variable in phase control [6, 14].

Public structural databases place low-temperature $\text{BaZn}_2\text{Si}_2\text{O}_7$ in the orthorhombic space group $\text{Cmc}2_1$, with Ba^{2+} five-coordinate and both Zn^{2+} and Si^{4+} tetrahedrally coordinated; the ZnO_4 and SiO_4 tetrahedra share corners to build a three-dimensional network [11]. These coordination data make a reasonable first-tier screen for structural analogy, but a database entry is not in situ high-temperature structural evidence and is no substitute for the original diffraction refinement. Table 1 summarizes the structural information on these phases together with the conclusions that bear on phase control.

2.2 STRUCTURAL CRITERIA

The criteria for comparing $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$ with the reference structure fall into four tiers: whether the silicate groups remain isolated tetrahedra; whether Zn stays four-coordinate and forms traceable corner-sharing chains; whether the Ba/Y polyhedra have comparable connectivity dimensionality; and whether the space group and lattice parameters are similar. The first two tiers rest on direct structural evidence for $\text{BaZn}_2\text{Si}_2\text{O}_7$ [10, 11]; the last two require single-crystal or high-resolution powder diffraction data for $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$, which are not yet available.

Table 2: Conditions and outcomes of the reported synthesis routes.

Route	Precursors and key steps	Main-phase criterion	Limitations
Mixed-oxide solid-state reaction	Oxide or carbonate starting materials; repeated grinding and high-temperature soaks	Powder XRD consistent with dilatometry	Diffusion-limited; secondary phases such as BaZnSiO_4 tend to persist [7]
Sol-gel/combustion synthesis	Molecular-level mixing; gel drying or combustion, then calcination	Small particle size; powders of the polymorphs accessible	Organic residues and atmosphere affect valence states [9, 29]
Glass crystallization	BaO/SrO/ZnO/SiO_2 glass; nucleation and crystallization heat treatments	In situ XRD/microscopy locate the crystallization front	Residual glass and microcracks; nucleating agents introduce impurity phases [1, 24]

3 SYNTHESIS ROUTES AND PHASE CONTROL

3.1 SOLID-STATE AND SOLUTION-BASED PRECURSORS


The conventional solid-state route starts from BaCO_3/BaO , ZnO (or ZnCO_3), and SiO_2 , which are mixed, calcined, ground, and then soaked at high temperature to give $\text{BaZn}_2\text{Si}_2\text{O}_7$; Co- and Mg-substituted compositions generally follow the same oxide/carbonate path, with intermediate regrinding to shorten diffusion distances [7, 17]. Combustion-assisted synthesis shortens the mixing length scale of the precursor, but work on Eu^{2+} phosphors shows that the final phase assemblage still depends on the subsequent calcination temperature and atmosphere [29, 30]. The sol-gel route premixes Ba, Sr, Zn, and Si at the molecular level and is well suited to fine powders and dense ceramics; Kracker et al. used it to prepare the high- and low-temperature polymorphs under controlled conditions [9].

3.2 GLASS CRYSTALLIZATION ROUTE

Glasses in the BaO/SrO/ZnO/SiO_2 system can precipitate $\text{Ba}_{1-x}\text{Sr}_x\text{Zn}_2\text{Si}_2\text{O}_7$ on nucleation-crystallization heat treatment. In situ microscopy and HT-XRD show that nucleating agents such as Pt, Sb_2O_3 , Nb_2O_5 , Ta_2O_5 , and P_2O_5 shift the balance between surface and bulk crystallization [1, 4, 21, 23, 24, 26]. $\text{ZrO}_2/\text{TiO}_2$ and Al_2O_3 additions act simultaneously on viscosity, nucleation density, and final grain size [18, 25]. For $\text{BaZn}_2\text{Si}_2\text{O}_7$ itself, the glass route offers compositional homogeneity and a tunable grain size; its drawback is that residual glass and microcracks can mask the intrinsic thermal expansion [12, 16]. Table 2 compares the precursors, main-phase criteria, and limitations of each route.

3.3 PHASE DIAGRAM AND THERMODYNAMIC DATA

A phase-equilibrium assessment exists for the binary BaO-ZnO system, but we found no complete CALPHAD database that applies directly to the ternary BaO-ZnO-SiO_2 system. Whether a given composition lies within the primary phase field of $\text{BaZn}_2\text{Si}_2\text{O}_7$, and whether it passes through a eutectic liquid, can therefore be settled only by combining XRD with thermal analysis. Combined theoretical and experimental work on negative-thermal-expansion silicates shows that the phonon free energy and the temperature-dependent phase stability cannot be inferred from the room-temperature structure alone [2].



Solid lines: experimental evidence; dashed: crystal-chemical comparison, not isostructural

Figure 2: Taxonomy of $\text{BaZn}_2\text{Si}_2\text{O}_7$ synthesis and phase control. Solid branches carry direct experimental evidence for the target phase or experimental evidence from structurally related compounds; dashed nodes mark comparison targets for which no direct structural report exists.

4 STRUCTURALLY RELATED COMPOUNDS AND TRANSFERABLE VARIABLES

4.1 BA/SR SUBSTITUTION

$\text{Ba}_{1-x}\text{Sr}_x\text{Zn}_2\text{Si}_2\text{O}_7$ is the most thoroughly studied isostructural substitution series. Replacing Ba^{2+} with Sr^{2+} lowers the temperature at which the high-temperature phase forms; beyond roughly 10% substitution the high-temperature structure survives to room temperature and shows near-zero or negative thermal expansion [14, 15, 19, 31]. Single-crystal XRD identifies this stabilized phase as orthorhombic Cmc $\bar{m}$, and the twisting and rocking of the ZnO_4 chains is regarded as a major structural origin of the negative thermal expansion [15]. These results establish A-site cation size and polyhedral voids as effective phase-control variables, but they give no grounds for assuming that Y^{3+} can occupy the same site in large amounts.

4.2 ZN-SITE AND SI-SITE SUBSTITUTION

Divalent cations such as Mg, Co, Mn, Ni, and Cu can substitute for Zn over ranges that differ from one ion to the next. Beyond a critical substitution level the low-temperature structure can reappear, pointing to competition between local coordination preference and long-range phase stability [7, 17]. Ge for Si shifts the transition temperature through tetrahedral size and bond flexibility; Ge solubility is limited in Sr-free compositions, whereas Sr-containing compositions retain the high-temperature structure up to higher Ge contents [13].

4.3 GLASS-CERAMIC PROCESSING

Work on the glass route shows that kinetics matter as much as chemistry. Pt nucleating agents promote heterogeneous nucleation, $\text{Nb}_2\text{O}_5/\text{Ta}_2\text{O}_5$ change the ratio of surface to bulk crystallization, and noble metals may in addition form alloys or core-shell structures [4, 20, 22, 24]. Once the grain size falls below about 80 μm , microcracking is reduced and the macroscopic thermal expansion approaches the intrinsic value of the crystal [16]. Phase-control studies of $\text{BaZn}_2\text{Si}_2\text{O}_7$ should therefore report phase assemblage, grain size, and crack state together.

5 ASSESSING $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$ AS A STRUCTURAL ANALOGUE

Our search of OpenAlex, Crossref, and the accessible full-text corpus returned no primary crystal-structure entry for $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$. The “yttrium barium silicates” that did surface are mostly

Table 3: Evidence tiers for the structural-analogue comparison.

Comparison tier	Evidence for $\text{BaZn}_2\text{Si}_2\text{O}_7$	Implication for $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$
Silicate polymerization	Corner-sharing $\text{ZnO}_4/\text{SiO}_4$ network [10]	A topological starting point to be checked; not proof of isostructurality
Cation coordination	Five-coordinate Ba, four-coordinate Zn [11]	Y and Zn coordination must be measured, not inferred from ionic radii
Thermal stability	Transition at about 280–300 °C [15]	A reference for the thermal-analysis program only

luminescent thin films and oxyapatite-type materials whose stoichiometry, space group, and Zn occupancy all differ from the target formula [3, 28]. The defensible label at present is therefore “candidate structural analogue awaiting verification” rather than “known isostructural compound”.

A tiered comparison is still possible on that footing. $\text{BaZn}_2\text{Si}_2\text{O}_7$ gives a direct reference for the corner-sharing $\text{ZnO}_4\text{--SiO}_4$ network and the Ba polyhedra [5, 10, 11]; the yttrium barium silicate oxyapatite literature gives a compositional reference in which Y/Ba coexist with isolated silicate groups, but it does not show that the two topologies are the same [3, 27, 28]. If powder or single-crystal data for the target phase become available, the degree of silicate polymerization, the Zn coordination number, the connectivity of the Y polyhedra, the oxygen-vacancy positions, and the space group should be checked in that order, rather than simply comparing element ratios in the formula.

The high Y content of $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$ also raises a charge-compensation issue. Formal valence counting calls for additional O^{2-} or for mixed cation valence, so any synthesis attempt must confirm the oxygen stoichiometry and valence states by thermogravimetric analysis, XPS/XANES, or neutron diffraction. The thermally driven transition of $\text{BaZn}_2\text{Si}_2\text{O}_7$ can guide the choice of heat-treatment window but cannot be extrapolated directly to the Y-rich system. Table 3 lists the grounds for comparison by evidence tier.

6 DISCUSSION: EVIDENCE STRENGTH AND OPEN QUESTIONS

The strongest direct evidence concerns the phase transition of $\text{BaZn}_2\text{Si}_2\text{O}_7$, the Ba/Sr solid solution, and Zn-site substitution, where HT-XRD, single-crystal XRD, and dilatometry corroborate one another [6, 10, 15, 17]. On the glass-crystallization side, nucleating-agent and microstructural effects have been studied systematically, but glass composition, heating rate, and grain size vary from study to study, so “phase stability” and “macroscopic thermal expansion of the sample” cannot be treated as equivalent [16, 25].

The first major gap is the ternary BaO--ZnO--SiO_2 phase diagram and its thermodynamic functions. For now, phase fields can only be inferred by piecing together binary phase equilibria, laboratory XRD, and thermal analysis, and theory indicates that vibrational free energy and temperature effects must be included [2]. The second gap is direct structural evidence for $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$. That Ba, Y, Zn, and silicate groups coexist in one formula does not establish an isostructural relationship; verifiable diffraction data and coordination refinement are needed as well.

We recommend a safe, falsifiable experimental path: prepare composition-gradient samples on a small scale in a closed high-temperature furnace with vetted crucible materials; collect room- and high-temperature powder XRD, TG-DSC, Raman spectra, and microscale compositional maps in parallel; and reserve synchrotron or single-crystal structure determination for samples that show a single diffraction phase. This path follows the complementary use of HT-XRD and dilatometry in the $\text{BaZn}_2\text{Si}_2\text{O}_7$ studies [6, 14]; unverified Y-rich formulations are not presented as ready-to-run protocols.

Structural descriptors can help narrow the candidate space. Negative-thermal-expansion studies show that tetrahedral rotation, chain flexibility, and coordination-polyhedron voids serve as useful screening features; descriptors, however, only generate candidates and cannot replace phase-equilibrium experiments [2, 8].

7 CONCLUSIONS AND PRIORITY EXPERIMENTS

The available evidence supports the following conclusions. The low-temperature–high-temperature polymorphism of $\text{BaZn}_2\text{Si}_2\text{O}_7$ is governed by the ZnO_4 chains and the corner-sharing SiO_4 network; Ba/Sr, Zn/Mg/Co/Ni/Cu, and Si/Ge substitution can tune the transition temperature and thermal expansion systematically; and the solid-state, sol–gel, and glass-crystallization routes each have well-defined kinetic windows but all demand that phase assemblage and microstructure be reported together [1, 6, 10, 15, 17]. For $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$ there are only clues from compositionally similar systems and no verifiable direct structural or synthesis report, so “structural analogue” should be treated as a hypothesis awaiting verification.

The highest-priority follow-up experiments, in order, are: (i) determine the ternary BaO–ZnO– SiO_2 phase diagram and build a temperature-dependent thermodynamic model; (ii) search a composition gradient for the single-phase window of $\text{Ba}_5\text{Y}_{12}\text{Zn}[\text{O}(\text{SiO}_4)]_8$ and follow its transitions by HT-XRD; and (iii) refine the Y/Zn coordination and oxygen stoichiometry of candidate samples. Only once these three steps are complete can one judge at what level the structure–processing trends of $\text{BaZn}_2\text{Si}_2\text{O}_7$ carry over to the Y-rich framework.

REFERENCES

- [1] Christian Bocker, Marlen Michaelis, and Christian Rüssel. In situ crystallization of barium zinc silicate in glass-ceramics studied by hot stage scanning electron microscopy. *Microscopy*, 61(6):381–391, 2012. doi: [10.1093/jmicro/dfs058](https://doi.org/10.1093/jmicro/dfs058).
- [2] Andreas Erlebach, Ghada B. Hassine, Christian Thieme, Katrin Thieme, Christian Rüssel, and Marek Sierka. Phase stability determination of negative thermal expansion silicates by theory and experiment. *Physical Chemistry Chemical Physics*, 23(45):25533–25541, 2021. doi: [10.1039/d1cp03862a](https://doi.org/10.1039/d1cp03862a).
- [3] Ritu Gupta, Ananya Rout, and Sadhana Agrawal. Combustion synthesis and photoluminescence studies of rare earth activated yttrium barium silicate oxyapatites. *Materials Today: Proceedings*, 44:3156–3159, 2021. doi: [10.1016/j.matpr.2021.02.822](https://doi.org/10.1016/j.matpr.2021.02.822).
- [4] Stephan Heitmann, Katrin Thieme, Christian Thieme, Michael Kracker, Thomas Höche, and Christian Rüssel. Surface and bulk crystallization of $\text{Ba}_{1-x}\text{Sr}_x\text{Zn}_2\text{Si}_2\text{O}_7$ from glasses in the system BaO/SrO/ZnO/SiO₂ doped with Nb₂O₅ or Ta₂O₅. *Ceramics International*, 45(6):7580–7587, 2019. doi: [10.1016/j.ceramint.2019.01.052](https://doi.org/10.1016/j.ceramint.2019.01.052).
- [5] J. W. Kaiser and W. Jeitschko. Crystal structure of the new barium zinc silicate $\text{Ba}_2\text{ZnSi}_2\text{O}_7$. *Zeitschrift für Kristallographie – New Crystal Structures*, 217:25–26, 2002. doi: [10.1524/ncrs.2002.217.jg.25](https://doi.org/10.1524/ncrs.2002.217.jg.25).
- [6] Marita Kerstan, Matthias Müller, and Christian Rüssel. Thermal expansion of $\text{Ba}_2\text{ZnSi}_2\text{O}_7$, BaZnSiO_4 and the solid solution series $\text{BaZn}_{2-x}\text{Mg}_x\text{Si}_2\text{O}_7$ ($0 \leq x \leq 2$) studied by high-temperature X-ray diffraction and dilatometry. *Journal of Solid State Chemistry*, 188:84–91, 2012. doi: [10.1016/j.jssc.2012.01.055](https://doi.org/10.1016/j.jssc.2012.01.055).
- [7] Marita Kerstan, Christian Thieme, Matthias Grosch, Matthias Müller, and Christian Rüssel. $\text{BaZn}_2\text{Si}_2\text{O}_7$ and the solid solution series $\text{BaZn}_{2-x}\text{Co}_x\text{Si}_2\text{O}_7$ ($0 < x \leq 2$) as high temperature seals for solid oxide fuel cells studied by high-temperature X-ray diffraction and dilatometry. *Journal of Solid State Chemistry*, 207:55–60, 2013. doi: [10.1016/j.jssc.2013.09.003](https://doi.org/10.1016/j.jssc.2013.09.003).
- [8] Natalia Kireeva and A. Yu. Tsivadze. Pauling number as efficient descriptors for screening the structures with negative thermal expansion characteristics. *ChemRxiv*, 2022. doi: [10.26434/chemrxiv-2022-xrthv](https://doi.org/10.26434/chemrxiv-2022-xrthv).
- [9] Michael Kracker, Christian Thieme, Johannes Häßler, and Christian Rüssel. Sol–gel powder synthesis and preparation of ceramics with high- and low-temperature polymorphs of $\text{Ba}_x\text{Sr}_{1-x}\text{Zn}_2\text{Si}_2\text{O}_7$ ($x = 1$ and 0.5): A novel approach to obtain zero thermal expansion. *Journal of the European Ceramic Society*, 36(8):2097–2107, 2016. doi: [10.1016/j.jeurceramsoc.2016.02.023](https://doi.org/10.1016/j.jeurceramsoc.2016.02.023).
- [10] Jianhua Lin, Guoxing Lu, Juan Du, M. Z. Su, C.-K. Loong, and C. J. Richardson. Phase transition and crystal structures of $\text{BaZn}_2\text{Si}_2\text{O}_7$. *Journal of Physics and Chemistry of Solids*, 60(7):975–983, 1999. doi: [10.1016/s0022-3697\(99\)00004-9](https://doi.org/10.1016/s0022-3697(99)00004-9).
- [11] Materials Project. Materials data on $\text{BaZn}_2\text{Si}_2\text{O}_7$ by Materials Project. Materials Project dataset, OSTI (U.S. DOE Office of Scientific and Technical Information), 2020. doi: [10.17188/1271462](https://doi.org/10.17188/1271462).
- [12] Christian Thieme and Christian Rüssel. High thermal expansion of crystallized glasses in the system BaO–ZnO–NiO–SiO₂. *Ceramics International*, 41(10):13310–13319, 2015. doi: [10.1016/j.ceramint.2015.07.114](https://doi.org/10.1016/j.ceramint.2015.07.114).
- [13] Christian Thieme and Christian Rüssel. Negative thermal expansion in $\text{Ba}_{0.5}\text{Sr}_{0.5}\text{Zn}_2\text{Si}_2\text{GeO}_7$. *Materials*, 9(8):631, 2016. doi: [10.3390/ma9080631](https://doi.org/10.3390/ma9080631).

- [14] Christian Thieme and Christian Rüssel. Very high or close to zero thermal expansion by the variation of the Sr/Ba ratio in Ba_{1-x}Sr_xZn₂Si₂O₇ – solid solutions. *Dalton Transactions*, 45(11):4888–4895, 2016. doi: [10.1039/c5dt04970a](https://doi.org/10.1039/c5dt04970a).
- [15] Christian Thieme, Helmar Görls, and Christian Rüssel. Ba_{1-x}Sr_xZn₂Si₂O₇ – a new family of materials with negative and very high thermal expansion. *Scientific Reports*, 5(1), 2015. doi: [10.1038/srep18040](https://doi.org/10.1038/srep18040).
- [16] Christian Thieme, Martin Schlesier, Christian Bocker, Gabriel Buzatto de Souza, and Christian Rüssel. Thermal expansion of sintered glass ceramics in the system BaO–SrO–ZnO–SiO₂ and its dependence on particle size. *ACS Applied Materials & Interfaces*, 8(31):20212–20219, 2016. doi: [10.1021/acsami.6b07353](https://doi.org/10.1021/acsami.6b07353).
- [17] Christian Thieme, Tina Waurischk, Stephan Heitmann, and Christian Rüssel. New family of materials with negative coefficients of thermal expansion: The effect of MgO, CoO, MnO, NiO, or CuO on the phase stability and thermal expansion of solid solution phases derived from BaZn₂Si₂O₇. *Inorganic Chemistry*, 55(9):4476–4484, 2016. doi: [10.1021/acs.inorgchem.6b00290](https://doi.org/10.1021/acs.inorgchem.6b00290).
- [18] Christian Thieme, Michael Kracker, Andreas Erlebach, Christian Patzig, Marek Sierka, Thomas Höche, and Christian Rüssel. Effect of Al₂O₃ on phase formation and thermal expansion of a BaO–SrO–ZnO–SiO₂ glass ceramic. *Ceramics International*, 44(2):2098–2108, 2017. doi: [10.1016/j.ceramint.2017.10.159](https://doi.org/10.1016/j.ceramint.2017.10.159).
- [19] Christian Thieme, Martin Schlesier, Eze Oji Dike, and Christian Rüssel. Variable thermal expansion of glass-ceramics containing Ba_{1-x}Sr_xZn₂Si₂O₇. *Scientific Reports*, 7(1), 2017. doi: [10.1038/s41598-017-03132-x](https://doi.org/10.1038/s41598-017-03132-x).
- [20] Christian Thieme, Liliya Vladislavova, Katrin Thieme, Christian Patzig, Thomas Höche, and Christian Rüssel. Noble metals Pt, Au, and Ag as nucleating agents in BaO/SrO/ZnO/SiO₂ glasses: formation of alloys and core–shell structures. *Journal of Materials Science*, 57(12):6607–6618, 2022. doi: [10.1007/s10853-022-07054-6](https://doi.org/10.1007/s10853-022-07054-6).
- [21] Katrin Thieme, Tilman Zscheckel, Christian Thieme, Thomas Höche, and Christian Rüssel. On the search for nucleation agents in BaO–SrO–ZnO–SiO₂ glasses: The influence of P₂O₅. *Journal of the European Ceramic Society*, 38(4):2017–2026, 2017. doi: [10.1016/j.jeurceramsoc.2017.12.034](https://doi.org/10.1016/j.jeurceramsoc.2017.12.034).
- [22] Katrin Thieme, Tilman Zscheckel, Christian Thieme, Michael Kracker, Christian Rüssel, and Thomas Höche. Growth-front hopping via stress-induced nucleation illustrated for the crystallization of Ba_{1-x}Sr_xZn₂Si₂O₇ from a glass in the BaO–SrO–ZnO–SiO₂ system. *Ceramics International*, 44(16):19970–19980, 2018. doi: [10.1016/j.ceramint.2018.07.264](https://doi.org/10.1016/j.ceramint.2018.07.264).
- [23] Liliya Vladislavova. *Nucleation agents in the glass system BaO/SrO/ZnO/SiO₂*. PhD thesis, Friedrich-Schiller-Universität Jena, 2018. doi: [10.22032/dbt.37559](https://doi.org/10.22032/dbt.37559).
- [24] Liliya Vladislavova, Christian Thieme, Tilman Zscheckel, Christian Patzig, Thomas Höche, and Christian Rüssel. Heterogeneous nucleation of Ba_{1-x}Sr_xZn₂Si₂O₇ from a BaO/SrO/ZnO/SiO₂ glass using platinum as nucleation agent. *Journal of the European Ceramic Society*, 37(15):4801–4808, 2017. doi: [10.1016/j.jeurceramsoc.2017.05.020](https://doi.org/10.1016/j.jeurceramsoc.2017.05.020).
- [25] Liliya Vladislavova, Michael Kracker, Tilman Zscheckel, Christian Thieme, and Christian Rüssel. Crystallisation of Ba_{1-x}Sr_xZn₂Si₂O₇ from BaO/SrO/ZnO/SiO₂ glass with different ZrO₂ and TiO₂ concentrations. *Solid State Sciences*, 78:107–115, 2018. doi: [10.1016/j.solidstatesciences.2018.02.011](https://doi.org/10.1016/j.solidstatesciences.2018.02.011).
- [26] Liliya Vladislavova, Christian Thieme, Tilman Zscheckel, Thomas Höche, and Christian Rüssel. Crystallization of Ba_{1-x}Sr_xZn₂Si₂O₇ from the BaO/SrO/ZnO/SiO₂ glass system: Effect of platinum and Sb₂O₃ on nucleation. *Journal of Alloys and Compounds*, 793:705–714, 2019. doi: [10.1016/j.jallcom.2019.04.034](https://doi.org/10.1016/j.jallcom.2019.04.034).
- [27] Donglei Wei, Yanlin Huang, Sun Il Kim, Young Moon Yu, and Hyo Jin Seo. A new green-emitting barium zinc silicate: Eu²⁺-doped Ba₂Zn₃Si₃O₁₁. *Materials Letters*, 99:122–124, 2013. doi: [10.1016/j.matlet.2013.02.083](https://doi.org/10.1016/j.matlet.2013.02.083).
- [28] Chen Yang, Can He, Ximing Huang, Guo Chen, Guoqin Leng, Ruiyu Mi, Xin Min, and Zhaohui Huang. Cyan-emitting Ba_{0.45}Ca_{2.5}La₆(SiO₄)₆: 0.05 Eu²⁺ and Ba_{1.45}Ca_{1.5}La₆(SiO₄)₆:0.05 Eu²⁺ solid-solution phosphors for white light-emitting diodes. *Ceramics International*, 47(9):12348–12356, 2021. doi: [10.1016/j.ceramint.2021.01.087](https://doi.org/10.1016/j.ceramint.2021.01.087).
- [29] Shanshan Yao, Lihong Xue, and Youwei Yan. Synthesis and luminescent properties of Eu²⁺ doped BaZn₂Si₂O₇ phosphors by combustion-assisted synthesis method. *Journal of Alloys and Compounds*, 509(5):1870–1873, 2010. doi: [10.1016/j.jallcom.2010.10.076](https://doi.org/10.1016/j.jallcom.2010.10.076).
- [30] Shanshan Yao, Lihong Xue, and Youwei Yan. Synthesis and crystal structures and luminescent properties of divalent europium-doped Ba₂ZnSi₂O₇ and BaZn₂Si₂O₇. *Physica B: Condensed Matter*, 406(2):250–253, 2010. doi: [10.1016/j.physb.2010.10.059](https://doi.org/10.1016/j.physb.2010.10.059).
- [31] Zheng-Yu Zou, Yihui Lou, Xiaoqiang Song, Hai Jiang, Kang Du, Changzhi Yin, Wenzhong Lü, Xiao-Chuan Wang, Xiao-Hong Wang, Ming Fu, and Wen Lei. Near-zero thermal expansion

Ba_{1-x}Sr_xZn₂Si₂O₇-based microwave dielectric ceramics for 3D printed dielectric resonator antenna with integrative lens. *Advanced Materials Interfaces*, 8(15), 2021. doi: [10.1002/admi.202100584](https://doi.org/10.1002/admi.202100584).