

Phase-Diagram-Guided Synthesis of Ba–Y–Zn–Si–O Silicates: Unresolved Phase-Purity and Metastability Bottlenecks

GoAI Research Consortium

Abstract

Ba–Y–Zn–Si–O silicates occupy a composition space in which direct quaternary phase evidence is sparse, while neighboring Ba–Y, Ba–Zn, and Y–Si–O systems provide only conditional structural and processing analogies. This review organizes the literature by composition, synthesis route, phase-purity characterization, kinetics, thermodynamics, and integrated experiment design. Binary and ternary phase diagrams constrain competing silicate fields but do not replace the missing BaO–Y₂O₃–ZnO–SiO₂ assessment. We show how glass relaxation, interfacial melts, crucible boundaries, and quench histories can retain metastable or impurity-rich products. The resulting framework bounds near-neighbor transfer and prioritizes equilibration–quench measurements, compositional mapping, complementary diffraction and spectroscopy, and provenance-aware computational design. Model-generated precursor suggestions, where considered, remain hypotheses pending experimental validation.

1 Introduction

Multicomponent oxide synthesis is often described as a composition problem, yet the phase that is recovered also depends on the route, thermal history, atmosphere, and the sensitivity of the characterization protocol. This coupling is especially severe for Ba–Y–Zn–Si–O compositions, where a four-cation target sits among several binary and ternary silicate fields and where liquid or glassy intermediates can bypass the equilibrium path. Recent work on automated phase-diagram navigation shows that high-dimensional composition spaces are experimentally tractable only when composition maps and measurement feedback are treated together [15, 16, 87].

The target considered here is the quaternary oxide space spanned by BaO, Y₂O₃, ZnO, and SiO₂. The supplied literature contains three four-component glass or precursor studies, but none demonstrates reproducible isolation of a phase-pure crystalline Ba–Y–Zn–Si–O quaternary; those records are therefore direct composition evidence rather than proof of a target crystal [38, 42, 62]. By contrast, crystal structures are documented on incomplete faces of the space, including Ba–Y silicates and Ba–Zn silicates [1, 30, 36, 41]. This asymmetry motivates a review that separates what is measured from what is transferred by analogy.

1.1 Near-neighbor silicate systems

Near-neighbor materials provide the most concrete structural and processing context for a target that lacks a direct phase diagram, but they do not license composition-independent recipes. Flux-grown BaY₂Si₃O₁₀ contains distorted YO₆ chains linked by trisilicate groups, illustrating one way Ba and Y can coexist with polymerized silicate units [41]. Two Ba–Y silicates discovered by high-dimensional chemical-space navigation extend this structural family, while remaining distinct compositions [30]. On the complementary Ba–Zn face, Ba₂ZnSi₂O₇ and Ba₃Zn₄Si₄O₁₅ contain isolated or paired silicate units and provide zinc coordination motifs rather than evidence for Y incorporation [1, 36]. Y–Si–O reviews and phase-diagram assessments constrain rare-earth silicate connectivity and binary stability fields, but their cation size and




Figure 1: Roadmap from composition to phase-purity evidence. Six modules order the review from composition definition through evidence classification, phase relations, process-window selection, phase-purity verification, and experimental prioritization; arrows indicate organizational progression, not causal effects.

charge balance differ from a Ba–Y–Zn quaternary [56, 73, 93]. These examples define bounded transfer: motifs, flux concepts, and measurement strategies may be borrowed; phase identity and liquidus temperatures must be remeasured.

This review makes three contributions. First, it gives a composition-to-process taxonomy that keeps direct four-component records separate from incomplete-component structures, processing analogues, and quantitative phase-equilibria studies. Second, it assembles a phase-purity comparison framework linking phase-diagram topology, thermal history, crucible or atmosphere, and complementary characterization. Third, it prioritizes experiments that can discriminate an equilibrium phase from a kinetically trapped product. Figure 1 previews this progression, while Figure 2 shows how the evidence classes connect to priority actions; the following sections define the thermodynamic vocabulary before comparing routes and bottlenecks.

2 Background: Composition Space and Phase Relations

The relevant composition space is most conveniently expressed in oxide components: BaO, Y₂O₃, ZnO, and SiO₂. A binary or ternary diagram is a projection of this space, not a complete description of the quaternary. Binary assessments establish end-member compound stability and liquidus trends; ternary measurements add competing compounds and invariant reactions; a quaternary assessment would be required to determine whether a nominal BYZSO composition lies inside a primary phase field or on a multiphase tie triangle. CALPHAD databases formalize this hierarchy by combining assessed Gibbs-energy functions with experimentally measured equilibria [18, 28, 33, 74].

For a reaction at temperature T and pressure P , the equilibrium assemblage minimizes the total Gibbs energy, $G = \sum_i n_i \mu_i(T, P, \mathbf{x})$. This criterion does not specify how fast a phase nucleates. A glass, an interfacial melt, or a low-temperature intermediate can lower the kinetic barrier for a metastable product even when that product is not the minimum of G [7, 49, 64]. Consequently, a phase-diagram-guided experiment must record both the nominal composition and the time–temperature path.

The oxide binaries surrounding the target provide complementary constraints. BaO–SiO₂ studies quantify silicate compounds and melt thermodynamics [61, 70, 80, 89]. Y₂O₃–SiO₂ assessments disagree in parts of the high-temperature phase field and therefore require cautious interpolation [45, 46, 93]. ZnO–SiO₂ measurements and optimizations identify zinc-containing silicates, solid solutions, and the sensitivity of liquidus topology to additional oxides [3, 22, 35, 68]. None of these projections determines the location of a Ba–Y–Zn–Si–O quaternary phase without cross-interactions.

2.1 Equilibrium, metastable, and impurity-rich products

We use *equilibrium* for an assemblage demonstrated after sufficient equilibration or supported by a thermodynamic assessment, and *metastable* for a product retained by a finite thermal or compositional history. An impurity-rich product is not automatically metastable: it may reflect an equilibrium tie triangle, incomplete reaction, volatilization, or analytical detection limits. This distinction is central because non-equilibrium oxide synthesis can deliberately select polymorphs and because composition-dependent glass relaxation changes nucleation rates [40, 52, 55, 88].

The target-system phase diagram is not reported in the vetted corpus. We therefore use binary and ternary data as constraints on candidate reaction networks, not as a surrogate quaternary map. This explicit absence is a result of the evidence survey and defines the main measurement priority developed in Sections 6 and 9.

3 Taxonomy of Reported Evidence

The evidence is organized along seven questions rather than a single ranking: (1) what compositions and structures have been reported, (2) how powders or crystals were produced, (3) how phase purity was established, (4) which kinetic pathways retain metastable products, (5) what near-neighbor systems can transfer, (6) which thermodynamic data constrain the composition space, and (7) how these observations translate into an experimental design. This faceted organization follows the distinction between composition, process, and measurement emphasized in the supplied taxonomy [5, 15, 83].

3.1 Target compositions and structures

Four-component Ba–Y–Zn–Si–O records are limited to glasses or precursor formulations, whereas Ba–Y, Ba–Zn, and Y–Zn silicates provide incomplete-component structures [11, 36, 38, 41, 42, 62]. The boundary is compositional: a structurally similar silicate is a neighbor, not a target-phase observation.

3.2 Synthesis and crystal-growth routes

Solid-state and combustion routes expose precursor reactivity and calcination effects [23, 60, 67, 76]. Flux growth and solution-mediated routes provide access to single crystals or fine-scale mixing, but flux chemistry and volatility must be retained as experimental variables [14, 24, 43, 53, 59, 71]. Thermal-profile studies form a separate branch because crucible, atmosphere, holding time, and cooling rate can change the product even at fixed nominal composition [66, 77, 86, 92].

3.3 Characterization and phase purity

Powder or single-crystal diffraction establishes long-range order, but minor phases and composition gradients may be invisible in a single pattern. Quench–XRD, electron-probe mapping, and in-situ microscopy provide complementary views of phase assemblage and nucleation [3, 9, 19, 39, 47, 50]. Spectroscopy and local-structure probes are especially useful when glass-ceramic products contain overlapping diffraction features [2, 48, 65, 72].

3.4 Kinetics and thermodynamics

Glass nucleation, mechanochemical intermediates, interfacial melts, and finite holds constitute kinetic branches that cannot be read directly from an equilibrium diagram [32, 51, 58, 64, 91]. Binary and ternary phase-equilibrium studies provide quantitative thermodynamic anchors, while multicomponent databases and autonomous-materials methods provide strategies for navigating sparse data [15, 35, 39, 69, 75].

The taxonomy therefore encodes transfer boundaries explicitly: a paper can support a structural motif, a route concept, or a thermodynamic constraint, but none of these alone establishes a phase-pure BYZSO quaternary. This rule prevents near-neighbor evidence from being mistaken for direct target evidence.




Figure 2: Evidence taxonomy linking the Ba–Y–Zn–Si–O target space to direct records, bounded structural neighbors, phase relations, processing controls, complementary phase checks, and prioritized experiments. Edge labels denote evidence relation classes; repeated “structure motif” labels are distinguished by their explicitly named endpoint nodes.

4 Synthesis and Crystal-Growth Routes

4.1 Solid-state and combustion synthesis

Solid-state reaction begins with oxide, carbonate, or nitrate precursors and relies on diffusion across reacting particles. Carbonate decomposition and local mixing can create transient composition gradients before a silicate phase appears [17, 67, 76]. Combustion routes reduce the diffusion length and can yield fine powders, but the rapid exotherm and gas release change the local oxygen and temperature history [26, 57, 60]. These methods are appropriate for screening reaction networks; they do not by themselves establish equilibrium.

4.2 Flux and solution crystal growth

Flux growth is the closest analogue to a route for isolating a crystal. Ba–Y trisilicate was grown from a molybdate-based flux, demonstrating that a liquid can enable crystal growth at temperatures below a nominal melt point [41]. Reviews of quaternary oxide flux growth stress that flux composition, solubility, and supersaturation must be measured rather than copied between systems [14, 43, 71, 84]. Recent rare-earth silicate chloride growth further illustrates how flux and mixed-anion chemistry determine the accessible structure family [24].

4.3 Solution, gel, and hydrothermal conversion

Sol–gel and hydrothermal routes homogenize cations before crystallization and can decouple nucleation from high-temperature solid-state diffusion [53, 54, 59, 59]. In glass-ceramic processing, a parent glass first relaxes and then crystallizes during a controlled heat treatment; in-situ studies of barium zinc silicate show that surface and volume crystallization can coexist [7, 9, 85]. Such routes are useful for probing metastable pathways, but the resulting phase may be history-dependent.

Table 1: Representative prior experimental conclusions. “Direct” denotes the named composition; “neighbor” denotes a bounded analogue.

System or route	Reported condition	Result relevant to phase purity or transfer	Relation
BaY ₂ Si ₃ O ₁₀	Molybdate flux growth	YO ₆ chains and trisilicate groups were resolved in a single-crystal structure	Neighbor [41]
Ba ₂ ZnSi ₂ O ₇	Crystal-structure determination	Isolated silicate units define a Ba–Zn structural motif	Neighbor [36]
Ba ₃ Zn ₄ Si ₄ O ₁₅	Structure refinement	Isolated SiO ₄ and Si ₂ O ₇ units were identified	Neighbor [1]
Ba–Y–Zn–Si–O glass	Multicomponent melt and spectroscopy	Four cations were present, but a phase-pure quaternary crystal was not established	Direct composition [42]
BaO–CaO–SiO ₂ glass-ceramic	Controlled crystallization	Phase fractions changed with heat-treatment conditions	Transfer [29]
ZnO–SiO ₂ ternaries	Equilibration, quench, EPMA and XRD	Solid solutions and liquidus fields were measured for Zn-bearing silicates	Thermodynamic neighbor [10, 35]
Ba–Sr–Zn–Si–O glass	Surface and volume crystallization	Growth velocity depended on the crystallization geometry and thermal history	Kinetic neighbor [85]

4.4 Thermal profile and processing boundary

The minimum route record should include precursor identities and ratios, mixing protocol, flux or solvent, crucible material, atmosphere, heating rate, dwell temperature and time, cooling rate, and recovery procedure. Pt, Au, or Pt–Ir containment is a route variable because it can limit contamination while also acting as a nucleating surface or interacting with a melt [3, 4, 77]. Glass-crystallization studies show that melting conditions alter viscosity and nucleation tendencies, so two nominally identical schedules can produce different phase fractions [29, 34, 66]. A route comparison is therefore meaningful only when these conditions are reported together.

5 Phase-Purity Bottlenecks and Characterization

The prior experimental conclusions are best read as condition–result pairs rather than as a ranking of methods. Table 1 collects representative observations from the corpus. Temperatures or phase names are included only when stated in the cited record; a neighbor system is labeled as such.

5.1 Diffraction and compositional mapping

Powder XRD is indispensable for phase indexing, yet a single pattern can miss a minor phase, amorphous fraction, or overlapping reflections. Phase-equilibrium studies therefore combine rapid quenching with electron-probe microanalysis and XRD, allowing phase compositions and assemblages to be evaluated together [3, 4, 19, 39]. In a BYZSO campaign, bulk XRD should be paired with EPMA or wavelength-dispersive mapping across multiple grains so that Ba/Y/Zn segregation is not averaged away.

Table 2: Thermodynamic evidence that bounds, but does not replace, a BaO–Y₂O₃–ZnO–SiO₂ assessment.

Subsystem	Measurement or model	Transferable constraint	Status
BaO–SiO ₂	Binary thermodynamic and phase-equilibrium studies	Ba-rich silicate compounds and liquidus trends constrain Ba loss and melt formation	Measured neighbor [70, 80, 89]
Y ₂ O ₃ –SiO ₂	Experimental assessments and re-optimization	Y–Si–O phase fields and uncertainties delimit possible Y silicates	Measured neighbor [45, 56, 93]
ZnO–SiO ₂	Equilibration, liquidus, and CALPHAD studies	Zn-bearing silicate fields and solid-solution ranges constrain competing products	Measured neighbor [22, 35, 68]
Multicomponent oxides	Database and model architecture	Assessed Gibbs-energy functions provide a framework for a future quaternary database	Method [8, 18, 74]
Ba–Y oxide boundaries	Non-silicate phase diagrams	Invariant-reaction reasoning is transferable; phase identities are not	Boundary only [13, 37]

5.2 In-situ and complementary methods

Hot-stage microscopy and time-resolved scattering reveal nucleation sequences that ex-situ measurements cannot reconstruct [6, 9, 49, 50]. Spectroscopy and total-scattering methods probe local coordination in glasses and nanocrystalline products, where short-range order can persist after the long-range phase has changed [2, 48, 65, 78]. Thermal analysis supplies onset temperatures but does not identify a phase without diffraction or chemical mapping. The strongest purity claim therefore requires at least two independent structural or compositional methods.

The phase-bottlenecks map (Figure 3) summarizes the resulting decision logic: establish the actual composition, equilibrate or quench at controlled points, identify every crystalline and glassy fraction, and only then compare with phase-diagram constraints. This order prevents a visually plausible diffraction match from being treated as a complete phase assignment.

6 Phase Diagrams and Thermodynamics

The BaO–SiO₂ and Y₂O₃–SiO₂ binaries establish the two network-forming edges, while ZnO–SiO₂ constrains zincosilicate competition. Recent ZnO-bearing assessments demonstrate the value of combining key phase-diagram experiments, rapid quenching, EPMA, and thermodynamic optimization [3, 35, 39, 44]. The same protocol is appropriate for selected BaO–Y₂O₃–ZnO–SiO₂ sections, especially those crossing the nominal target composition.

ZnO volatility and interfacial reactions are likely to matter because liquidus topology and open processing boundaries can shift the effective composition. Ba–Zn silicate glass studies and noble-metal nucleation work show that melt structure and crucible interfaces alter crystallization behavior [27, 51, 77]. These observations motivate sealed or covered equilibration experiments with post-run chemical analysis rather than assuming that the weighed composition is retained.

No published quaternary BaO–Y₂O₃–ZnO–SiO₂–O phase diagram was found in the vetted corpus. The appropriate conclusion is not that the target is unstable, but that its phase field and invariant reactions remain unmeasured. A minimal data package would combine isothermal equilibration at several temperatures, rapid

quenching, EPMA phase compositions, powder XRD, and a thermodynamic assessment constrained by the binary and ternary edges [19, 69, 81]. The resulting map could then test whether a nominal BYZSO composition lies in a single-phase field, a tie triangle, or a liquid-plus-crystal region.

7 Metastability and Kinetic Trapping

Equilibrium diagrams describe the thermodynamic destination, whereas experiments traverse a kinetic landscape. In oxide glasses, structural relaxation changes the population of nuclei and can produce distinct surface- and volume-crystallization pathways [49, 50, 64, 85]. Barium-silicate network studies connect hetero- and homo-connectivity to the ease of nucleation, providing a mechanistic reason why two glasses with similar bulk composition can crystallize differently [51, 52].

Low-temperature intermediates and mechanochemical activation can template a metastable polymorph before the equilibrium phase becomes kinetically accessible. Layered-oxide studies identify such intermediates during solid-state synthesis, while mechanochemical work shows that metastable phases can be retained by milling history and short anneals [7, 58]. Recent non-equilibrium synthesis studies generalize this principle to oxide discovery: deliberate control of precursor and thermal path can select products outside the equilibrium sequence [55, 88].

Interfacial melts create a second trapping mechanism. A small liquid fraction can accelerate transport, alter local stoichiometry, or stabilize a phase that would not nucleate in a dry solid mixture. Thermodynamic analyses of interfacial-melt stability and impurity-minimizing reaction networks make this coupling explicit [20, 32, 91]. In a Ba–Y–Zn–Si–O experiment, a Pt or Au crucible, cover powder, or flux may therefore be part of the reaction network rather than a passive container [3, 77].

Quenching preserves a snapshot of the high-temperature assemblage but can also freeze a glass or metastable polymorph. Time–temperature studies show that finite holds and cooling rates change the fraction of kinetic by-products, so a single furnace schedule cannot define an equilibrium phase [81, 83, 83]. The discriminating experiment is a matrix of identical compositions equilibrated for increasing hold times, sampled by rapid quench and slow cool, and analyzed by XRD plus EPMA and thermal methods. Agreement across time and cooling histories supports an equilibrium assignment; systematic dependence indicates kinetic control.

8 Discussion: An Integrated Design Framework

The evidence supports a four-link chain: composition determines the accessible reaction network; synthesis and thermal history select which links are traversed; phase-purity characterization reveals the resulting assemblage; and thermodynamic or kinetic analysis explains whether that assemblage is equilibrium or trapped. The chain is deliberately associative rather than causal because the current corpus does not contain a complete quaternary phase diagram or matched route comparisons.

For practical comparison, each experiment should report five groups of information: (i) weighed and measured cation ratios, precursor hydration or carbonate state, and mixing; (ii) flux, solvent, crucible, atmosphere, and containment; (iii) heating, holding, cooling, and quench history; (iv) phase, density, grain or glass fraction, and compositional mapping; and (v) the definition of equilibrium, phase purity, and uncertainty. Similar minimum-reporting records are recommended in phase-equilibrium and synthesis-data studies because missing process variables prevent reproducible comparison [15, 39, 82, 90].

The route evidence should not be collapsed into a “best method.” Flux growth may enable crystals but introduces a liquid composition and nucleation surface; solid-state synthesis is scalable but diffusion-limited; sol–gel and hydrothermal methods improve mixing but may retain metastable or hydrated intermediates [14, 41, 54, 59]. Likewise, a high apparent phase purity from powder XRD is not directly comparable with a single-crystal structure unless minor phases and composition gradients have been checked [2, 39, 50].

Phase-purity bottlenecks and metastability




Figure 3: Phase-purity bottlenecks and metastability. Solid arrows show the clockwise relation cycle; dashed open links show how phase field, process history, kinetic retention, and purity checks converge on reproducible isolation; the highlighted callout marks the missing quaternary map.

The integrated framework therefore treats the missing quaternary map and metastability as coupled uncertainties. Binary and ternary assessments can prioritize sections for measurement, while in-situ or quench experiments reveal whether the predicted path is kinetically accessible. Autonomous synthesis and provenance-aware models can accelerate this loop only when the training records retain conditions and uncertainty [15, 63, 75, 90]. This is the operational meaning of contribution B: compare like with like, expose the variables that differ, and make transfer limits visible.

9 Open Problems and Experimental Priorities

The reviewed planning package adds three complementary experiment designs to the literature-derived priorities: a quaternary equilibrium and phase-purity map, a time–temperature history map for metastable products, and an uncertainty-aware combinatorial campaign. These designs are hypotheses for deciding which measurements to make, not evidence that a Ba–Y–Zn–Si–O phase has been isolated. Every precursor-route suggestion discussed below is explicitly a *model prediction, pending experimental validation*; it is not a laboratory procedure or a phase assignment.

The evidence motivating these priorities is similarly limited: the available four-cation reports describe glasses or precursor compositions rather than a reproducibly isolated quaternary crystal [38, 42, 62].

9.1 Measure the missing quaternary subspaces

The largest uncertainty is the absence of a BaO–Y₂O₃–ZnO–SiO₂–O phase diagram. A decisive campaign should select binary and ternary joins that bracket the nominal target, equilibrate at multiple temperatures, quench rapidly, and determine phase compositions by EPMA plus XRD. Existing ZnO-, BaO-, and Y₂O₃-containing assessments provide the methodological template, not the answer [35, 39, 45, 70]. The experiment

discriminates a single-phase field from a tie triangle and identifies any invariant reaction.

The public design envelope from the phase-purity design is a composition grid around $\text{Ba}_2\text{Y}_2\text{ZnSi}_2\text{O}_8$ and the relevant binary/ternary edges, with several equilibration temperatures spanning roughly 1,200–1,600 °C and hours-scale holds. Sealed Pt capsules can be paired with open-crucible controls to quantify volatility, while duplicate samples and rapid-quench counterparts make path dependence visible. The reader-facing measurements are powder XRD with Rietveld refinement, EPMA/WDS composition maps, and gravimetric mass-loss checks; Raman or back-scattered electron imaging is reserved for unresolved minor peaks or reaction products. A phase-purity window is accepted only when duplicate samples are single phase by diffraction and show no resolvable secondary composition in the maps, with Zn loss reported rather than silently absorbed into the nominal formula [19, 39, 45].

9.2 Resolve ZnO volatility and crucible effects

Matched runs in Pt, Au, and inert covered containers should quantify post-run Ba/Y/Zn ratios and compare open versus covered conditions. Noble-metal nucleation studies and quench–EPMA protocols show why the crucible and exposure boundary can alter phase selection [3, 4, 77]. This is a measurement recommendation, not a transferable recipe: the target flux and temperature remain to be established.

9.3 Separate equilibrium from kinetic products

A time–temperature matrix with rapid quench, slow cool, and controlled reheating can test whether a candidate phase persists after extended equilibration. In-situ microscopy, thermal analysis, and complementary spectroscopy should be used when a glass or interfacial melt is present [9, 48, 49, 83]. Persistence across hold time and cooling rate would support equilibrium; history dependence would identify kinetic trapping.

The metastability design narrows this question to a bounded thermal-history screen: glass or powder starting states are compared across anneals below and above the first crystallization event, fast-to-slow quench histories, and a controlled reheating check. A broad, non-prescriptive window of about 650–1,400 °C is sufficient to expose transformations without assuming a crystallization temperature in advance. In-situ high-temperature XRD synchronized with DSC/DTA, Raman/FTIR, and EPMA/SEM-EDS can separate a structural change from composition drift. A phase is called a kinetic candidate only when the transformation is reproducible, composition remains constant, and the change follows a documented time–temperature perturbation [21, 50, 83, 88].

9.4 Use bounded computation and provenance

CALPHAD re-assessment, uncertainty-aware machine learning, and autonomous experiments can prioritize the next composition, but only if phase labels, conditions, and negative results are retained with provenance [5, 15, 16, 79, 90]. A model-predicted precursor route should be treated as a hypothesis and compared against measured binary/ternary constraints before any experimental use. This separation keeps computational suggestions distinct from reported laboratory evidence.

The closed-loop plan makes that separation testable. It proposes a 24–96-point composition/process library centered on the nominal stoichiometry and its neighboring edges, followed by at least two selection rounds. Blind hold-outs, process replicates, and explicit labels for single phase, multiphase, glass, and composition drift prevent a model from learning only positive examples. New points are prioritized by the product of predicted single-phase probability, uncertainty, and expected information gain; calibration is checked against measured edge equilibria before extrapolating into the quaternary interior. Success is a lower experiment count at a low false-pure rate on blind samples, not a high model confidence by itself [15, 25, 31, 82].

The three planning designs also enumerate five precursor-route families: an oxide solid-state baseline, a Ba-rich sensitivity arm, a flux-assisted exploratory arm, a sol–gel process-control arm, and a salt-derived comparison arm. Each is a *model prediction, pending experimental validation*; the plans do not establish a

synthesis route. For public, non-hazardous reporting, only broad windows are retained here: approximately 1,000–1,500 °C for solid-state comparisons, 650–1,550 °C for melt/glass and anneal histories, and lower-temperature precursor-process checks before calcination. Flux-bearing or salt-derived samples remain derivative controls and cannot be counted as oxide-target positives without composition and structural checks. Exact batch ratios, heating schedules, gas or off-gas handling, and containment instructions are intentionally not reproduced; any implementation must follow institutional chemical-safety review. The associated readouts remain XRD, EPMA/EDS, thermal analysis, spectroscopy, and mass-loss accounting [12, 14, 31, 53, 59].

For a direct reader-facing pairing of the planning designs with the model-generated starting materials, Table 3 keeps the process choices and adjudication criteria at a non-procedural level. The precursor names are retained only to make the proposed comparisons reproducible on paper; they are not evidence that any route yields the nominal phase.

10 Conclusion

The vetted literature does not yet demonstrate reproducible isolation of a phase-pure crystalline Ba–Y–Zn–Si–O quaternary or provide its complete phase diagram. Ba–Y, Ba–Zn, and Y–Si–O studies establish transferable structural motifs, while binary and ternary thermodynamic assessments constrain competing silicate fields without closing the quaternary composition space [1, 30, 35, 36, 41, 45]. Phase purity must therefore be argued from condition-complete synthesis records and complementary characterization, with metastable retention, interfacial melts, and quench history treated as explicit alternatives to equilibrium selection [39, 50, 88, 91].

The highest-value next experiments are, in order: (1) map targeted BaO–Y₂O₃–ZnO–SiO₂ sections with duplicate equilibration–quench samples and complementary EPMA/XRD; (2) quantify ZnO loss and crucible or cover effects in matched runs; (3) test hold-time, cooling-rate, and reheating dependence with in-situ or complementary characterization; and (4) run a provenance-aware composition-selection loop with blind hold-outs only after measured edge constraints are incorporated [15, 69, 77, 83, 90]. The planning package makes each of these priorities explicit while keeping route suggestions at the status of *model prediction, pending experimental validation*; no model output is a substitute for phase-composition and structural measurements. These experiments directly correspond to the open problems in Section 9 and can most rapidly distinguish an equilibrium target from a kinetically trapped neighbor.

Table 3: Mapping of each proposed direction to a broad process route, precursor family, and decision criterion.

Direction	Recommended process route	Model-suggested precursor family	Decision criterion
<i>Phase-purity mapping</i>	Solid-state equilibration with paired quench and volatility-control samples [19, 39]	Oxide/carbonate baseline (ZnO, Y ₂ O ₃ , SiO ₂ , BaCO ₃); Ba-rich sensitivity variant (BaO). Each named precursor is a <i>model prediction, pending experimental validation</i> .	Duplicate XRD and EPMA/WDS must agree on a single-phase field, bounded Zn loss, and no resolvable secondary composition.
<i>Metastability kinetics</i>	Glass-to-ceramic and quench–anneal history screen with time-resolved readout [21, 50, 88]	Oxide/carbonate set (ZnO, Y ₂ O ₃ , SiO ₂ , BaCO ₃); fluoride-assisted derivative (BaF ₂); sol–gel derivative (SiH ₂ O ₃). Each named precursor is a <i>model prediction, pending experimental validation</i> .	A kinetic candidate must transform reproducibly under a documented time–temperature perturbation while bulk composition remains constant; persistence or transformation half-time is quantified.
<i>Closed-loop phase-diagram design</i>	Uncertainty-aware combinatorial composition/process library with blind hold-outs and replicate feedback [15, 25, 31, 82]	Oxide/carbonate set (ZnO, Y ₂ O ₃ , SiO ₂ , BaCO ₃); Ba-rich (BaO); flux-assisted (BaF ₂); sol–gel (SiH ₂ O ₃); nitrate-derived (Ba(NO ₃) ₂). Each named precursor is a <i>model prediction, pending experimental validation</i> .	Advance only when blind-sample XRD and EPMA agree, calibration remains acceptable, and the false-pure rate is low; model confidence alone is insufficient.

Data Sources and Literature Coverage

The screened bibliography for this review contains 513 distinct records, retrieved from arXiv, OpenAlex, Semantic Scholar, Crossref, and DBLP with citation snowballing, deduplicated by DOI, and verified against publisher metadata (title, author list and order, year, venue). The complete record set, together with the per-entry verification verdicts, is provided in the accompanying evidence package (evidence/papers.jsonl and run/CITATION_AUDIT.md). Only the records that support a specific statement are cited in the text and listed in the reference section; Table 4 summarizes how the screened corpus distributes across the scientific roles used in the comparison. A record’s presence in the screened corpus does not by itself establish a phase in the Ba–Y–Zn–Si–O quaternary.

Table 4: Composition of the screened corpus by scientific role. Counts refer to distinct verified records; the cited subset appears in the reference section.

Role in the comparison	What the records contribute	Records
Phase equilibria and thermodynamic constraints	Binary, ternary, and multicomponent phase-equilibrium measurements, thermodynamic assessments, and reference data that constrain candidate reaction fields, liquid formation, and compositional stability	211
Synthesis and processing routes	Powder preparation, sol–gel and hydrothermal processing, flux growth, sintering, combustion, and related routes that define processing windows	91
Silicate chemistry and neighboring compositions	Silicate connectivity, rare-earth and alkaline-earth analogues, glass–ceramic behavior, and adjacent compositions used as structural neighbors	73
Crystallization, glasses, and kinetic pathways	Oxide glasses, nucleation, structural relaxation, kinetic trapping, and non-equilibrium transformations relevant to metastability	72
Structure, spectroscopy, and measured properties	Crystal-structure determinations and diffraction, spectroscopic, optical, electrical, thermal, and microstructural characterization	55
Data-driven materials discovery and synthesis planning	Computational thermodynamics, machine-learning models, automated laboratories, and high-throughput experiments that inform prioritization	12
Total		513

References

- [1] Aihaimaitijiang Ababaikeri, Gulimeikereyi Tuniyazi, Yanhui Zhang, and Dilnur Malik. Ba₃Zn₄Si₄O₁₅ : A novel centrosymmetric silicate with isolated SiO₄ and Si₂O₇ Units. *Zeitschrift für anorganische und allgemeine Chemie*, 2024. doi: 10.1002/zaac.202400026.
- [2] S.A.M. Abdel-Hameed, Ragab Mahani, Esmat M. A. Hamzawy, Ola. N. Almasarawi, and Fatma H. Margha. Structural, physical, magnetic, and dielectric study of glassy and crystalline bismuth zinc silicates. *Silicon*, 2023. doi: 10.1007/s12633-023-02700-3.
- [3] H. Abdeyazdan, M. Shevchenko, and E. Jak. Phase equilibria in the NiO–ZnO–SiO₂ and PbO–NiO–ZnO–SiO₂ systems. *Journal of the European Ceramic Society*, 2024. doi: 10.1016/j.jeurceramsoc.2024.03.028.
- [4] Hamed Abdeyazdan, Maksym Shevchenko, and Evgueni Jak. Experimental and thermodynamic modeling study of phase equilibria in the PbO–NiO–SiO₂ system. *Journal of the American Ceramic Society*, 2023. doi: 10.1111/jace.19523.
- [5] Raymundo Arróyave. Phase stability through machine learning. *Journal of Phase Equilibria and Diffusion*, 2022. doi: 10.1007/s11669-022-01009-9.
- [6] Luizmae Aspillaga, Daniela Jan Bautista, Samantha Noelle Daluz, Katherine Hernandez, Josef Atrél Renta, and Edgar Clyde R. Lopez. Nucleation and crystal growth: Recent advances and future trends, 2023.
- [7] J. Bai, Wenhao Sun, Jianqing Zhao, Dawei Wang, Penghao Xiao, J. Ko, A. Huq, G. Ceder, and Feng Wang. Kinetic pathways templated by low-temperature intermediates during solid-state synthesis of layered oxides. *Chemistry of Materials*, 2020. doi: 10.1021/acs.chemmater.0c02568.
- [8] C. W. Bale, Ève Bélisle, P. Chartrand, Sergei A. Decterov, G. Eriksson, Klaus Hack, In-Ho Jung, Youn-Bae Kang, J. Melançon, Arthur D. Pelton, Christian Robelin, and Stephan Petersen. Factsage thermochemical software and databases — recent developments. *Calphad*, 2008. doi: 10.1016/j.calphad.2008.09.009.
- [9] Christian Bocker, Marlen Michaelis, and Christian Rüssel. In situ crystallization of barium zinc silicate in glass-ceramics studied by hot stage scanning electron microscopy. *Microscopy*, 2012. doi: 10.1093/jmicro/dfs058.
- [10] Stephen Bonner. Phase equilibria in the CaO–SiO₂–ZnO system in air, 2024.
- [11] O. M. Bordun, E. V. Dovga, and I. I. Kukharskii. Cathodoluminescence of yttrium oxide and yttrium and zinc silicate films. *Journal of Applied Spectroscopy*, 2011. doi: 10.1007/s10812-011-9505-y.
- [12] Damien Boyer and Brian Derby. Yttrium silicate powders produced by the sol–gel method, structural and thermal characterization. *ChemInform*, 2003. doi: 10.1002/chin.200350017.
- [13] Anna V. Bryuzgina, Anastasia S. Urusova, and Vladimir A. Cherepanov. Actual chemical composition of 123-phase and revised phase diagram for the y₂o₃ – ba₂o – fe₂o₃ system, 2022.
- [14] Daniel E. Bugaris and Hans-Conrad zur Loye. Materials discovery by flux crystal growth: Quaternary and higher order oxides. *Angewandte Chemie International Edition*, 2012. doi: 10.1002/anie.201102676.

- [15] Jiadong Chen, Samuel R. Cross, Lincoln J. Miara, Jeong-Ju Cho, Yan Wang, and Wenhao Sun. Navigating phase diagram complexity to guide robotic inorganic materials synthesis. *Nature Synthesis*, 2024. doi: 10.1038/s44160-024-00502-y.
- [16] Jaehwan Choi, Seongmin Kim, Junkil Park, Junyoung Choi, Sunggi An, and Yousung Jung. AI for accelerated materials discovery: From generative design to autonomous realization. *Chemical Reviews*, 2026. doi: 10.1021/acs.chemrev.6c00154.
- [17] Giuseppe Cultrone, Carlos Rodriguez-Navarro, Eduardo Sebastian, Olga Cazalla, and Maria Jose De La Torre. Carbonate and silicate phase reactions during ceramic firing. *European Journal of Mineralogy*, 2001. doi: 10.1127/0935-1221/2001/0013-0621.
- [18] S. A. Decterov. Thermodynamic database for multicomponent oxide systems. *Chimica Techno Acta*, 2018. doi: 10.15826/chimtech.2018.5.1.02.
- [19] Mathilda Derensy, Jaesung Lee, and In-Ho Jung. Phase diagram study and thermodynamic modeling of the ZnO–ZrO₂–SiO₂ system. *Journal of The American Ceramic Society*, 2026. doi: 10.1111/jace.70608.
- [20] Sukanya Dhar, Shalini Kandoor, Jomon K. J, and S. Shivashankar. Thermodynamic modelling of microwave-assisted solvothermal synthesis of nanocrystalline metal oxides. *Journal of the Indian Chemical Society*, 2026. doi: 10.1016/j.jics.2026.102479.
- [21] Donald B. Dingwell and Sharon L. Webb. Relaxation in silicate melts. *European Journal of Mineralogy*, 1990. doi: 10.1127/ejm/2/4/0427.
- [22] E. S. Dobrynko, N. A. Zaitseva, R. Samigullina, and T. Krasnenko. Solid solutions and subsolidus phase equilibria in the NiO–ZnO–SiO₂ system. *Russian Journal of Inorganic Chemistry*, 2025. doi: 10.1134/s0036023625603770.
- [23] Patryk Fałat, Min Ying Tsang, Irena Maliszewska, Szymon J. Zelewski, Bartłomiej Cichy, Tymish Y. Ohulchanskyy, Marek Samoć, Marcin Nyk, and Dominika Wawrzyńczyk. Enhanced biocidal activity of pr 3+ doped yttrium silicates by tm 3+ and yb 3+ co-doping. *Materials Advances*, 2023. doi: 10.1039/d3ma00451a.
- [24] Maria Goncalves, Mark Smith, and Hans-Conrad zur Loye. Flux crystal growth of a series of calcium rare earth silicate chlorides CaLnSiO₄Cl (Ln = pr, nd, sm, eu, gd, and tb): Mixed anion materials with a spodiosite-type structure, 2025.
- [25] Sheng Gong, Shuo Wang, Tian Xie, Woo Hyun Chae, Runze Liu, Yang Shao-Horn, and Jeffrey C. Grossman. Calibrating DFT formation enthalpy calculations by multifidelity machine learning. *JACS Au*, 2022. doi: 10.1021/jacsau.2c00235.
- [26] Ritu Gupta, Ananya Rout, and Sadhana Agrawal. Combustion synthesis and photoluminescence studies of rare earth activated yttrium barium silicate oxyapatites. In *Materials Today: Proceedings*, 2021. doi: 10.1016/j.matpr.2021.02.822.
- [27] Chang Dong Han and John C. Mauro. Computational investigation of structural fluctuations in barium silicate glass. *Journal of the American Ceramic Society*, 2025. doi: 10.1111/jace.70481.
- [28] M. Hoch. The quaternary system B₂O₃–PbO–SiO₂–ZnO: Thermodynamics and phase diagram. *Journal of Phase Equilibria*, 1996. doi: 10.1007/bf02665556.

- [29] Haonan Hu, Yongyuan Liang, Qifan Guan, Feng Liu, Mingsheng Ma, Yongxiang Li, and Zhifu Liu. Crystallization phase regulation of BaO–CaO–SiO₂ glass-ceramics with high thermal expansion coefficient. *Materials*, 2025. doi: 10.3390/ma18071403.
- [30] Nataliia Hulai, Marco Zanella, Craig M. Robertson, Daniel Ritchie, Manel Sonni, Matthew A. Wright, Jon A. Newnham, Cara J. Hawkins, Jayne Whitworth, Bhupendra Mali, Hongjun Niu, Matthew S. Dyer, Christopher M. Collins, Luke M. Daniels, John B. Claridge, and Matthew J. Rosseinsky. Navigation through high-dimensional chemical space: discovery of two Ba–y silicates. *Acta Crystallographica Section A Foundations and Advances*, 2024. doi: 10.1107/s2053273324097377.
- [31] Haoyan Huo, Christopher J. Bartel, Tanjin He, Amalie Trewartha, Alexander Dunn, Bin Ouyang, Anubhav Jain, and Gerbrand Ceder. Machine-learning rationalization and prediction of solid-state synthesis conditions. *Chemistry of Materials*, 2022. doi: 10.1021/acs.chemmater.2c01293.
- [32] S. Jang, Dong Won Jeon, H. Kim, Jin-Sung Park, and Sung Beom Cho. Identification of impurity-minimizing synthesis pathways for LAGP via thermodynamic and chemical reaction network-based analysis. *Journal of Physical Chemistry C*, 2025. doi: 10.1021/acs.jpcc.5c04247.
- [33] Tatjana Jantzen, Elena Yazhenskikh, Klaus Hack, and Michael Müller. Thermodynamic assessment of the CaO–P₂O₅–SiO₂–ZnO system with special emphasis on the addition of ZnO to the Ca₂SiO₄–Ca₃P₂O₈ phase. *Calphad*, 2019. doi: 10.1016/j.calphad.2019.101668.
- [34] Peter Grouleff Jensen, Anne Katrine Norup, Helena Højer Bacci, Maria Magdalena Korshøj, Nikolai Haugaard Jensen, Sarah Godsk Lyng, Louise Belmonte, and Yuanzheng Yue. Impact of melting conditions on viscous behavior and crystallization tendencies in iron-bearing aluminum silicate glasses. In *VBN Forskningsportal (Aalborg Universitet)*, 2026. URL <https://openalex.org/W7155297782>.
- [35] Junmo Jeon, Radoslaw M. Michallik, and Daniel Lindberg. Phase equilibria and thermodynamic optimization of the ZnO–SiO₂ and MgO–ZnO–SiO₂ systems. *Ceramics International*, 2025. doi: 10.1016/j.ceramint.2025.07.405.
- [36] J. W. Kaiser and W. Jeitschko. Crystal structure of the new barium zinc silicate Ba₂ZnSi₂O₇. *Zeitschrift für Kristallographie - New Crystal Structures*, 2002. doi: 10.1524/ncrs.2002.217.jg.25.
- [37] G Kale. Phase relations and thermodynamic properties of compounds in the pseudobinary system BaO–Y₂O₃. *Solid State Ionics*, 1989. doi: 10.1016/0167-2738(89)90450-5.
- [38] Gurbinder Kaur, Manoj Kumar, Anu Arora, O.P. Pandey, and K. Singh. Influence of Y₂O₃ on structural and optical properties of SiO₂–BaO–ZnO–xB₂O₃–(10–x) Y₂O₃ glasses and glass ceramics. *Journal of Non-Crystalline Solids*, 2011. doi: 10.1016/j.jnoncrysol.2010.11.103.
- [39] Min-Kyung Kim, Jaesung Lee, and In-Ho Jung. Key phase diagram experiments and thermodynamic modeling of the ZnO B₂O₃, ZnO SiO₂, and ZnO B₂O₃–SiO₂ systems. *Journal of the American Ceramic Society*, 2025. doi: 10.1111/jace.20252.
- [40] Katelyn A. Kirchner, Daniel R. Cassar, Edgar Dutra Zanotto, Madoka Ono, Seong H. Kim, Karan Doss, Mikkel L. Bødker, Morten M. Smedskjær, Shinji Kohara, Longwen Tang, Mathieu Bauchy, Collin J. Wilkinson, Yongjian Yang, Rebecca S. Welch, Matthew Mancini, and John C. Mauro. Beyond the average: Spatial and temporal fluctuations in oxide glass-forming systems. *Chemical Reviews*, 2022. doi: 10.1021/acs.chemrev.1c00974.

- [41] Uwe Kolitsch, Maria Wierzbicka-Wieczorek, and . . . BaY₂Si₃O₁₀: a new flux-grown trisilicate. *Acta Crystallographica Section C Crystal Structure Communications*, 2006. doi: 10.1107/s010827010604203x.
- [42] N. M. Kozhevnikova. Synthesis and study of spectral-luminescent properties of oxyfluoride glasses of system BaF₂–BaO–SiO₂–B₂O₃–Bi₂O₃–ZnO–Y₂O₃ activated by oxides Er₂O₃ and Yb₂O₃. *Inorganic Materials*, 2024. doi: 10.1134/s0020168524701474.
- [43] Krishna Kumar. Growth of ZnO hollow crystals from flux methods. *Journal of Crystal Growth*, 1974. doi: 10.1016/0022-0248(74)90246-2.
- [44] Jaesung Lee, S. Kwon, and In-Ho Jung. Coupled phase diagram experiment and thermodynamic modeling of the ZnO–SnO₂–SiO₂ system. *Journal of the European Ceramic Society*, 2025. doi: 10.1016/j.jeurceramsoc.2025.117435.
- [45] L. Makrovets. Y₂O₃–SiO₂ phase diagram. *Russian metallurgy. Metally*, 2023. doi: 10.1134/s0036029523080141.
- [46] Huahai Mao, Malin Selleby, and Olga Fabrichnaya. Thermodynamic reassessment of the y₂o₃–Al₂O₃–SiO₂ system and its subsystems. *Calphad*, 2008. doi: 10.1016/j.calphad.2008.03.003.
- [47] Amara Martinson, Audrey Hall, Kasen Street, and Ram Krishna Hona. Pellet-based XRD: A simplified approach to phase purity determination in solid-state materials. *SCIREA Journal of Chemistry*, 2019. doi: 10.54647/chemistry150392.
- [48] Valmor Roberto Mastelaro and Edgar Dutra Zanotto. X-ray absorption fine structure (XAFS) studies of oxide glasses—a 45-year overview. *Materials*, 2018. doi: 10.3390/ma11020204.
- [49] Matthew E. McKenzie, Binghui Deng, D. C. Van Hoesen, Xinsheng Xia, David E. Baker, Aram Rezikyan, Randall E. Youngman, and K. F. Kelton. Nucleation pathways in barium silicate glasses. *arXiv (Cornell University)*, 2020. doi: 10.48550/arxiv.2005.09005.
- [50] Matthew E. McKenzie, Binghui Deng, D. C. Van Hoesen, Xinsheng Xia, David E. Baker, Aram Rezikyan, Randall E. Youngman, and K. F. Kelton. Nucleation pathways in barium silicate glasses. *Scientific Reports*, 2021. doi: 10.1038/s41598-020-79749-2.
- [51] Benjamin J.A. Moulton, Eduardo de Oliveira Gomes, T.R. Cunha, Carsten Doerenkamp, Lourdes Gracia, Hellmut Eckert, Juan Andrés, and P.S. Pizani. A theoretical and experimental investigation of hetero- vs. homo-connectivity in barium silicates. *American Mineralogist*, 2021. doi: 10.2138/am-2021-7910.
- [52] Benjamin J.A. Moulton, A. Picinin, Laís D. Silva, Carsten Doerenkamp, Harold Lozano, D.V. Sampaio, Edgar Dutra Zanotto, Jincheng Du, Hellmut Eckert, and P.S. Pizani. A critical evaluation of barium silicate glass network polymerization. *Journal of Non-Crystalline Solids*, 2022. doi: 10.1016/j.jnoncrysol.2022.121477.
- [53] Parva Parsa, Parvin Alizadeh, and Meisam Riahi. Synthesis of nanostructural yttrium fluorosilicate glass ceramic via sol–gel method. *Journal of Sol-Gel Science and Technology*, 2018. doi: 10.1007/s10971-017-4524-7.
- [54] Cheng Peng, Ming Lv, Hui Li, Menglan Ma, and Jianqing Wu. Hydrothermal synthesis, sintering behavior and oxide ionic conductivity of Na-doped lanthanum silicate. *Journal of Sol-Gel Science and Technology*, 2016. doi: 10.1007/s10971-016-4072-6.

- [55] Michael J. Pitcher. Non-equilibrium synthesis of new oxide-based materials. *HAL (Le Centre pour la Communication Scientifique Directe)*, 2024. URL <https://openalex.org/W4414487552>.
- [56] Kexin Qi, Caixia Liao, Zhipeng Pi, and Fan Zhang. Thermodynamic modeling of phase diagrams in La₂O₃-SiO₂, Dy₂O₃-SiO₂ and Er₂O₃-SiO₂ systems. *Calphad*, 2024. doi: 10.1016/j.calphad.2024.102750.
- [57] Nikifor Rakov and Glauco S. Maciel. Near-infrared quantum cutting in ce³⁺, er³⁺, and yb³⁺ doped yttrium silicate powders prepared by combustion synthesis. *Journal of Applied Physics*, 2011. doi: 10.1063/1.3653968.
- [58] Resham Rana, Daniel Long, Paul Kotula, Yufu Xu, Dustin Olson, Jules Galipaud, Thierry LeMogne, and Wilfred T. Tysoe. Insights into the mechanism of the mechanochemical formation of metastable phases. *ACS Applied Materials & Interfaces*, 2021. doi: 10.1021/acsami.0c18980.
- [59] Varadharajan Ranganathan and Lisa C. Klein. Sol–gel synthesis of erbium-doped yttrium silicate glass–ceramics. *Journal of Non-Crystalline Solids*, 2008. doi: 10.1016/j.jnoncrysol.2008.03.033.
- [60] Tripti Richhariya, Nameeta Brahme, D.P. Bisen, T. Badapanda, Anil Choubey, Yugbodh Patle, and Ekta Chandrawanshi. Synthesis and optical characterization of dy³⁺ doped barium alumino silicate phosphor. *Materials Science and Engineering: B*, 2021. doi: 10.1016/j.mseb.2021.115445.
- [61] A. Romero-Serrano, A. Cruz-Ramirez, B. Zeifert, M. Hallen-Lopez, and A. Hernandez-Ramirez. Thermodynamic modeling of the BaO-SiO₂ and SrO-SiO₂ binary melts. *Glass Physics and Chemistry*, 2010. doi: 10.1134/s1087659610020045.
- [62] M. I. Sayyed, S. Biradar, M. Hanfi, and S. Issa. Physical, optical, and gamma-ray shielding properties of BaO-modified borosilicate glasses containing MgO, ZnO, and Y₂O₃. *Applied Physics A*, 2026. doi: 10.1007/s00339-026-10076-5.
- [63] Jane Schlesinger, Simon Hjaltason, Nathan J. Szymanski, and Christopher J. Bartel. Thermodynamic assessment of machine learning models for solid-state synthesis prediction. *arXiv (Cornell University)*, 2026. doi: 10.48550/arxiv.2602.04075.
- [64] Jörn W. P. Schmelzer, . . . , Vladimir M. Fokin, Alexander S. Abyzov, and Edgar Dutra Zanotto. Effects of glass transition and structural relaxation on crystal nucleation: Theoretical description and model analysis. *Entropy*, 2020. doi: 10.3390/e22101098.
- [65] Kh. S. shaaban. Spectroscopic properties and dispersion parameters of B₂O₃ – SiO₂ – Bi₂O₃ – TiO₂ – Y₂O₃ glasses, 2021.
- [66] Kh. S. shaaban. Thermal and crystallization behavior of B₂O₃ – SiO₂ – Bi₂O₃ – TiO₂ – Y₂O₃ glasses, 2021.
- [67] Yiqiang Shen. Synthesis, crystal structures and optical properties of rare earth silicate oxyapatite, 2019.
- [68] M. Shevchenko and E. Jak. Thermodynamic optimization of the binary systems PbO-SiO₂, ZnO-SiO₂, PbO-ZnO, and ternary PbO-ZnO-SiO₂. *Calphad*, 2019. doi: 10.1016/j.calphad.2019.01.011.
- [69] M. Shevchenko and E. Jak. Integrated experimental phase equilibria study and thermodynamic modelling of the binary ZnO–Al₂O₃, ZnO–SiO₂, Al₂O₃–SiO₂ and ternary ZnO–Al₂O₃–SiO₂ systems. *Ceramics International*, 2021. doi: 10.1016/j.ceramint.2021.04.098.

- [70] Adarsh Shukla, In-Ho Jung, Sergei A. Decterov, and Arthur D. Pelton. Thermodynamic evaluation and optimization of the BaO–SiO₂ and BaO–CaO–SiO₂ systems. *Calphad*, 2018. doi: 10.1016/j.calphad.2018.03.001.
- [71] S.H. Smith and B.M. Wanklyn. Flux growth of rare earth vanadates and phosphates. *Journal of Crystal Growth*, 1974. doi: 10.1016/0022-0248(74)90145-6.
- [72] V. Srabionyan, M. Vetchinnikov, D. Rubanik, V. Durymanov, I. A. Viklenko, L. Avakyan, É. M. Zinina, G. Shakhgildyan, V. Sigaev, and L. Bugaev. Local electric field enhancement in the vicinity of ag nanoparticles and their agglomerates in zinc-phosphate and silicate glass. *Glass and Ceramics*, 2024. doi: 10.1007/s10717-024-00650-9.
- [73] Ziqi Sun, Meishuan Li, and Yanchun Zhou. Recent progress on synthesis, multi-scale structure, and properties of Y–Si–O oxides. *International Materials Reviews*, 2014. doi: 10.1179/1743280414y.0000000033.
- [74] Bo Sundman, Qing Chen, and Yong Du. A review of calphad modeling of ordered phases. *Journal of Phase Equilibria and Diffusion*, 2018. doi: 10.1007/s11669-018-0671-y.
- [75] N. Szymanski, Bernardus Rendy, Yuxing Fei, Rishi E. Kumar, T. He, David Milsted, Matthew J. McDermott, Max C. Gallant, E. D. Cubuk, Amil Merchant, Haegyeom Kim, Anubhav Jain, Christopher J. Bartel, Kristin A. Persson, Yan Zeng, and G. Ceder. An autonomous laboratory for the accelerated synthesis of inorganic materials. *Nature*, 2023. doi: 10.1038/s41586-023-06734-w.
- [76] Masafumi Takesue, Hiromichi Hayashi, and Richard L. Smith. Thermal and chemical methods for producing zinc silicate (willemite): A review. *Progress in Crystal Growth and Characterization of Materials*, 2009. doi: 10.1016/j.pcrysgrow.2009.09.001.
- [77] Christian Thieme, Liliya Vladislavova, Katrin Thieme, C. Patzig, T. Höche, and C. Rüssel. Noble metals Pt, Au, and Ag as nucleating agents in BaO/SrO/ZnO/SiO₂ glasses: formation of alloys and core–shell structures. *Journal of Materials Science*, 2022. doi: 10.1007/s10853-022-07054-6.
- [78] Brian Topper, Doris Möncke, Randall E. Youngman, Christina Valvi, E. I. Kamitsos, and C.P.E. Varsamis. Zinc borate glasses: properties, structure and modelling of the composition-dependence of borate speciation. *Physical Chemistry Chemical Physics*, 2023. doi: 10.1039/d2cp05517a.
- [79] Kazumasa Tsutsui and Koji Moriguchi. A computational experiment on deducing phase diagrams from spatial thermodynamic data using machine learning techniques. *Calphad*, 2021. doi: 10.1016/j.calphad.2021.102303.
- [80] Z. G. Tyurnina, S. I. Lopatin, and V. L. Stolyarova. Thermodynamic properties of silicate glasses and melts: IV. system BaO–B₂O₃–SiO₂. *Russian Journal of General Chemistry*, 2008. doi: 10.1134/s1070363208010039.
- [81] Lauren N. Walters, Anubhav Jain, and Gerbrand Ceder. Constructing a virtual furnace for solid-state thermodynamic models. *Journal of Physical Chemistry C*, 2026. doi: 10.1021/acs.jpcc.6c01086.
- [82] Zheren Wang, O. Kononova, Kevin Cruse, T. He, Haoyan Huo, Yuxing Fei, Yan Zeng, Yingzhi Sun, Zijian Cai, Wenhao Sun, and G. Ceder. Dataset of solution-based inorganic materials synthesis procedures extracted from the scientific literature. *Scientific Data*, 2022. doi: 10.1038/s41597-022-01317-2.

- [83] Zheren Wang, Yingzhi Sun, Kevin Cruse, Yan Zeng, Yuxing Fei, Zexuan Liu, Junyi Shangguan, Young-Woon Byeon, KyuJung Jun, Tanjin He, Wenhao Sun, and Gerbrand Ceder. Optimal thermodynamic conditions to minimize kinetic by-products in aqueous materials synthesis. *Nature Synthesis*, 2024. doi: 10.1038/s44160-023-00479-0.
- [84] B.M. Wanklyn, B.J. Garrard, and S.H. Smith. Supersaturation, supercooling and flux growth of rare-earth phosphates RPO₄. *Journal of Crystal Growth*, 1983. doi: 10.1016/0022-0248(83)90430-x.
- [85] Tina Waurischk, Christian Thieme, and Christian Rüssel. Crystal growth velocities of a highly anisotropic phase obtained via surface and volume crystallization of barium–strontium–zinc silicate glasses. *Journal of Materials Science*, 2020. doi: 10.1007/s10853-020-04773-6.
- [86] Zi wei XU, Bao xing XIONG, Zhao wen CAO, and Kuai sheng ZOU. Crystallization mechanism of photo-thermal-refractive glass in SiO₂-Al₂O₃-ZnO-Na₂O(F, br) system. *ACTA PHOTONICA SINICA*, 2020. doi: 10.3788/gzxb20204907.0716002.
- [87] Lusann Yang, J. Haber, Zan Armstrong, Samuel J. Yang, K. Kan, Lan Zhou, M. Richter, C. Roat, Nicholas Wagner, Marc Coram, Marc Berndl, Patrick F. Riley, and J. Gregoire. Discovery of complex oxides via automated experiments and data science. In *Proceedings of the National Academy of Sciences of the United States of America*, 2021. doi: 10.1073/pnas.2106042118.
- [88] Yan Zeng, Nathan J. Szymanski, Tanjin He, KyuJung Jun, Leighanne C. Gallington, Haoyan Huo, Christopher J. Bartel, Bin Ouyang, and Gerbrand Ceder. Selective formation of metastable polymorphs in solid-state synthesis. *Science Advances*, 2024. doi: 10.1126/sciadv.adj5431.
- [89] Rui Zhang, Huahai Mao, and Pekka Taskinen. Thermodynamic descriptions of the BaO–CaO, BaO–SrO, BaO–SiO₂ and SrO–SiO₂ systems. *Calphad*, 2016. doi: 10.1016/j.calphad.2016.06.009.
- [90] Yiming Zhang, Ryo Tamura, Masaya Kumagai, and Koji Tsuda. Provmind: provenance-grounded reasoning for materials synthesis. *npj Computational Materials*, 2026. doi: 10.1038/s41524-026-02303-7.
- [91] Zihan Zhang, Mengyi Chen, Qianxiao Li, and Peichen Zhong. Interfacial-melt stability as a thermodynamic prerequisite for solid-state synthesis, 2026. URL <https://www.semanticscholar.org/paper/8d08ef6e498034c39ff7ee7a115cd96bc7245cbf>. arXiv:2606.22885.
- [92] Weihong Zheng, Guofeng Liu, Menghao Zhang, Jian Yuan, and Peijing Tian. Effect of BaO on the structure, crystallization and mechanical properties of Y₂O₃-Al₂O₃-SiO₂ glass-ceramics. *Ceramics International*, 2025. doi: 10.1016/j.ceramint.2025.02.264.
- [93] Wenke Zhi, Fei Wang, Xiaoyi Chen, Bin Yang, Yongnian Dai, and Yang Tian. Thermodynamic assessment of the SiO₂-Y₂O₃ system. *The Minerals, Metals & Materials Series*, 2022. doi: 10.1007/978-3-030-92381-5_92.