

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/S)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
1/10/2025	Kwanghee Han	Cr	13.5%	19%	0.48	4nm	83.84%
Notes:							
1/10	Kwanghee Han	Al	31%	77%	1	60nm	82.173%
Notes:							
1/13	George Trivies	Al	28%	43.6%	0.61	20nm	80.54%
Notes:							
1/14	Ashish	Ge	5%	13%	0.3	25nm	80.43
Notes:							
1/15	Sreerag	Pi	13% 13%	17%	0.45	20nm	
Notes:							
1/15	Sreerag	Au	30%	45.5%	0.75	200nm	77.32%
Notes:							
1/16	Maya Goldpwr	Cr	10.6%	15.1%	0.24	6.6nm 8nm	
Notes:							
1/16	Maya Goldpwr	Au	27%	43.5%	0.56	50.3nm	76.61%
Notes:							
01/16	Padma Padmakishan	Cr	13%	18.3%	0.5	7nm	76.51%
Notes:							
01/16	Padma Padmakishan	Au	30%	48.1%	1	50nm	75.30%
Notes:							
01/21	Ashish	Ge	3%	5.3%	0.5	25nm	96.83%
Notes:							
01/21	Ashish	Au	32%	48%	0.5	50nm	95.99%
Notes:							

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/s)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
01/21	Serena Zachariah	Ag	8.4	11.5	0.5	40	95.55%
Notes:							
01/22	Zezheng Zhu	Al ₂ O ₃	3%	11%	2.74	25	95.43%
Notes:							
01/22	Padma Padhakrishnan	Cr	4.3%	7.2%	0.5	9	95.35%
Notes:							
01/22	Padma Padhakrishnan	Au	33%	51%	1	50	94.20%
Notes:							
01/23	Rishabh Kaul	Ag	8.5 r.	11.5	0.5	50	93.68%
Notes:							
01/24/25	Ashish	Cr	5.0%	8%	0.45	20nm	93.59%
Notes:							
1/26/25	Trivikas	Au	29.1%	46.6%	0.52	20nm	93.14%
Notes:							
1/27/25	Ashish	Cr	6%	10%	0.6	30nm	93.02%
Notes:							
1/27/25	Wenjun Deng	Cr	6%	10.4%	0.2	15nm	92.93%
Notes:							
1/29/25	Wenjun Deng	Au	29.5%	50.7%	1	55nm	91.01%
Notes:							
1/30/25	M. Feinstein	Au	29.3%	46.2%	0.5	20nm	91.05%
Notes:							
1/31/25	Serena Zachariah	Ag	9%	12%	0.7	40nm	90.69%
Notes:							