

February 2025

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/S)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
02/03/25	Melissa Mikalsen	Ti	13%	17.5% 17.5%	0.4	10 10	90.63%
Notes:							
02/03/25	Melissa Mikalsen	Au	29.6 %	45.5%	0.5	30	89.83%
Notes:							
02/03/15	Yajun Gao	Al ₂ O ₃	15%	9.0%	0.28	25nm	89.74%
Notes:							
02/05/25	Wenjun Deng	Cr	6%	11.5%	0.2	15nm	89.62%
Notes:							
02/05/25	Wenjun Deng	Au	30%	50.7 %	1	55nm	88.32%
Notes:							
02/06	Ashish	Ti	12%	18%	0.4	3nm	88.31%
Notes:							
02/06	Ashish	AU	30%	46%	0.5	17nm	88.02%
Notes:							
02/06	Ashish	Co	9%	14.5%	0.5	20nm	87.93%
Notes:							
02/06	Ashish	Al ₂ O ₃	9%	18%	0.3	20nm	87.88%
Notes:							
2/6	George Triviers	Al	30%	46.2%	0.5	20nm	87.46%
Notes:							
3/17	Kwonghee Han	Cr	12%	15.3%	0.54	4nm	87.39%
Notes:							
3/17	Kwonghee Han	Al	30%	51.3%	1.01	52nm	86.15%
Notes:							

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/s)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
02/07/25	Rishabh Kaun	Ag	8.8	11.4	0.5	50 nm	85.61 %
Notes:							
02/08/25	Melissa Mikalsen	Ti	11.0 %	16.0 %	0.43	10 nm	85.57 %
Notes:							
02/08/25	Melissa Mikalsen	Au	30 %	46.5 %	0.66	50 nm	84.68 %
Notes:							
02/10/25	Sichao Yu	Ag	10 %	16 %	2.5	200 nm	82.91 %
Notes:							
2/10/25	Kwanghee Han	Cr	13 %	15 %	0.47	4 nm	82.85 %
Notes:							
2/10/25	Kwanghee Han	Au	30 %	50 %	1.06	60 nm	81.62 %
Notes:							
2/10/25	Melissa Mikalsen	Ti	12.1 %	14.1 %	0.49	10 nm	81.57 %
Notes:							
2/10/25	Melissa Mikalsen	Au	28.0 %	46.5 %	0.68	50 nm	80.61 %
Notes:							
02/11/25	Melissa Mikalsen	Ti	12.0 %	14.5 %	0.47	10 nm	80.55 %
Notes:							
02/11/25	Melissa Mikalsen	Au	31 %	46.4 %	0.70	50 nm	79.70 %
Notes:							
02/11/25	Yajun Gao	Cr	13 %	14.7 %	0.30	28 nm	79.54 %
Notes:							
02/12/25	Melissa Mikalsen	Ti	9 %	15.5 %	0.35	5 nm	78.34 %
Notes:							

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (A/S)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
11/02/25	Padma Radhakrishnan	Cr	13.5%	15%	0.5	7	79.46%
Notes:							
11/02/25	Padma Radhakrishnan	Au	30%	48.5%	1	50	78.37%
Notes:							
18/02	Ashish	Al ₂ O ₃	2.5%	8.5%	0.5	50	97.85%
Notes:							
02/18	Reaz	Cr	didn't complete			80	
Notes:							
02/18	Rishabh Kaur	Ag	9.2	11	0.45	50	97.25%
Notes:							
02/18	Yajun Gao	Cr	5%	7.3%	0.6	100%	96.29%
Notes:							
02/19	Padma Radhakrishnan	Cr	10% (showed negative values belows) then went to 0A/s again. second threshold ~16%	20.1% hard to stabilize	0.5	7	96.04%
Notes:							
02/19	Padma Radhakrishnan	Au	33%	48%	1	50	94.80%
Notes:							
2/19	Reaz Uddin	Cr	12.6%	19.7%	0.3	5	94.74%
Notes:							
2/19	Reaz Uddin	Ag	9%	13.2%	1	100	93.68%
Notes:							
2/20	Rishabh Kaur	Ag	9.5%	11.6%	0.5	50	
Notes:							
2/20	George Tmika	Ag	32.5%	43.3%	0.5	20	92.71%
Notes:							

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/s)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
02/20/25	Emmanuel Hanzel	Ag	8%	12%	0.8	100	91.75
Notes:							
2/22/25	Guangyu Han	Cr	16%	19.5%	0.2	15nm	91.63%
Notes:							
~	~	Au	30%	49.3%	1	55nm	90.21%
Notes:							
2/22/25	Licheng Xiao	Cr	16%	20%	0.5	10nm	90.15%
Notes:							
2/23/25	Licheng Xiao	Au	32%	45.2%	0.5	100nm	88.64%
Notes:							
2/23/25	Rishabh Kaur	Ag	10.0	10.5	0.35	10 nm	
Notes:							
2/24/25	Kolmakov	Cr	12%	20%	0.16	5nm	
Notes:							
2/24/25	Kolmakov	Au	30%	47%	0.55	102nm	86.75%
Notes:							
2/24/25	Kwanghee Han	Cr	13.5%	25%	0.53	5nm	80.63%
Notes:							
2/24/25	Kwanghee Han	Ag	31%	51.2%	0.90	40nm	85.68%
Notes:							
2/24/25	Jacob Issakson	Ti	11%	18%	0.57	10nm	85.59%
Notes:							
2/24/25	Jacob Issakson	Au	31.5%	49.5%	0.69	50nm	84.97
Notes:							

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/S)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
2/24/25	Guangyu Han	Cr	18%	23%	0.2	15	84.39%
Notes:							
~	~	Au	30%	52%	1	150	81.91%
Notes:							
2/24/25	George Trivizas	Au	31.6%	46.7%	0.5	20	81.54%
Notes:							
2/25/25	Nansheng Deng	Ti	11%	15%	0.3	4	81
Notes:							
		Au	33%	51%	1.1	46	80.44%
Notes:							
02/25/25	Rishabh HK	Ag	10	11.2	0.6	50 nm	80.02%
Notes:							
02/26/25	Yajun	Al ₂ O ₃	2.1%	7.7%	0.35	22 nm	79.88%
Notes:							
02/28/25	Longyao	Ge	8.0%	19 20 %	1	100 nm	97.29%
Notes:							
02/28/25	Rishabh Kaur	Ag	10%	12%	0.8	150 nm	96.42%
Notes:							
3/3/25	George Trivizas	Au	33.1%	43.1%	0.5	20 nm	95.45%
Notes:							
3/4/25	Yajun Gao	Cr	1%	2%	0.2	10 nm	
Notes:							
~	~	Au	31.4%	47%	1	60 nm	93.43%
Notes:							