

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/s)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
3/5/2025	Nansheng Deng	Ti	12%	17%	0.6 Å/s	4	
Notes:							
3/5/2025	~	Au	31%	47%	0.9 Å/s	46	
Notes:							
3/5/25	Rishabh Kuvra	Ag	10	12	0.6	40 nm	
Notes:							
3/6/25	Ashish	Al ₂ O ₃	1%	10%	0.7	50 nm	91.80
Notes:							
3/7/25	Kwanghee Han	Cr	4%	10.7%	0.5	4 nm	91.50
Notes:							
3/7/25	Kwanghee Han	Ag	31%	78.8%	1.05	60 nm	89.9%
Notes:							
3/7/25	Nansheng Deng	Ti	11%	17%	0.7 Å/s	4	
Notes:							
3/7/25	~	Au	31%	47%	0.9 Å/s	46	88.73%
Notes:							
3/8/25	Nansheng Deng	Cr	7%	10.1%	0.2	5	88.68%
Notes:							
3/8/25	~	Au	30%	48.5%	1	20	87.87%
Notes:							
3/10/25	Kwanghee Han	Cr	9%	12%	0.5	4	87.80%
Notes:							
3/10/25	Kwanghee Han	Ag	30%	48%	1.05	60	88.5%
Notes:							

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/S)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
3/11/25	Ashish	Al ₂ O ₃	1%	9%	0.45	50 nm	86.5%
Notes:							
3/11/25	Ashish	Ti	10%	16%	0.3	4 nm	86.49%
Notes:							
3/11/25	Ashish	Au	30%	44%	0.5	46 nm	85.82%
Notes:							
3/11/25	Zigao Feng	Cr	9%	11.5%	0.21	15 nm	85.74%
Notes:							
3/11/25	Zigao Feng	Au	30%	49.8%	1.04	55 nm	84.32%
Notes:							
3/12/25	Maya Colaprese	Cr	14%	16%	0.64	6 nm	84.27%
Notes:							
3/12/25	Maya Colaprese	Au	29%	48.5%	0.98	114 nm	82.71%
Notes:							
3/12/25	Yajun Gao	Cr	13.4%	14.1%	0.38	10 nm	82.62%
Notes:							
3/12/25	Yajun Gao	Au	31%	49%	1	60 nm	80.97%
Notes:							
03/12/25	Padma Padmakrishnan	Cr	11%	15.1%	0.5	7 nm	80.87%
Notes:							
03/12/25	Padma Padmakrishnan	Au	32%	49.4%	1	50 nm	79.68%
Notes:							
03/12/25	Rishabh Kaur	Ag	10	11.5	0.5	50 m	
Notes:							

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (A/S)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
3/14/25	Ze Zheng Zhn	Al ₂ O ₃	3%	14%	1.07	75	79.13%
Notes:							
—	—	Ag	10%	14%	1.9	120	77.94%
Notes:							
3/15/25	Zhn Li	Cr	16%	16.4%	0.5	90	77.81%
Notes:							
—	—	Au	32%	46.5%	0.8	120 920	65.7%
Notes:							
3/18/25	Niranyan	Ti	14%	15%	0.31	10	98.09%
Notes:							
"	"	Au	36%	45.5%	0.81	100	96.12
Notes:							
"	"	Ti	15%	15%	0.33	10	96.06%
Notes:							
"	"	Au	30%	45.3%	0.82	100	93.91%
Notes:							
03/18	Lih Jiny	Ge	14%	19.3%	1	90	93.32%
Notes:							
3/18	Wei Wang	Ag	10%	13%	9	70	92.6%
Notes:							
03/19	Ashish	Al ₂ O ₃	1%	10%	0.5	50nm	92.31%
Notes:							
03/19	Ashish	Ti	11%	15%	0.4	5nm	92.30%
03/19	Ashish	Au	30%	45%	0.85	45nm	91.62%

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/S)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
3/19/15	Salan	Cr	0.5 %	1.9	0.22	4	91.58%
Notes:							
3/19/15	Salan	Au	30 %	43.8	0.68	35.3nm	91.05%
Notes:							
3/19/15	Niranjana	Ti	9%	19%	0.4	10	91%
Notes:							
"	"	Au	21%	48%	0.74	100	88.95%
Notes:							
"	"	Ti	120%	19%	0.4	10	88.91%
Notes:							
"	"	Au	32%	50%	0.72	100	87.17%
Notes:							
3/20/15	Yajun Gao	Cr	1%	2.5%	0.27	10	
Notes:							
3/20/15	Yajun Gao	Au	33%	49.5%	1.23	85	83.8%
Notes:							
3/20/15	Yajun Gao	Cr	2.5%	4%	0.55	10	
Notes:							
3/20/15	Yajun Gao	Au	31.2%	50.5%	1.04	85	81.9%
Notes:							
7/21/15	Zhan Li	Cr	1%	8%	0.5	30	81.5%
Notes:							
~	~	Au	32%	50%	0.8	900	69.3%
Notes:							

03/23/15 Lin Jay Ge 13% 1 100 68.82%

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/S)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
03/27/25	Agneya	Ge	12.4 %	17 %	0.5	2	98.22
Notes:							
03/27/25	Ziyao Fong	Cr	25%	20%	0.25	15nm	98.09
Notes:							
03/27/25	Ziyao Fong	Au	35.0%	47%	1.06	55nm	96.52
Notes:							
03/26/25	Emmanuel	Ag	8%	11.5%	0.5	40	96.02
Notes:							
03/26/25	Yajun Gao	Cr	2%	24%	0.4	10nm	95.91%
Notes:							
03/26/25	Yajun Gao	Au	30%	46.5%	0.9	60nm	94.17%
Notes:							
03/27/25	Emmanuel	Ag	8%	11.5%	0.50	40	93.60%
Notes:							
03/27	Ashish	Al ₂ O ₃	1%	8.5	0.5	50nm	93.48%
Notes:							
03/27	Ashish	Al ₂ O ₃	1%	8.5	0.5	50nm	93.36%
Notes:							
03/27	Mohammed Dasthaheer	Ge	12.5 %	15.0 %	0.12	2nm	93.34%
Notes:							
03/27	Mohammed Dasthaheer	Ag	10 %	12.0 %	0.55	40nm	92.89 %
Notes:							
03/27	Rishabh Kumar	Ag	11 %	13 %	0.9	80 nm	92.21 %
Notes:							

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/S)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
	Andy Cruz	Ag	9.6%	12%	0.59	32	91.82
Notes:							
03/30	Lin Jing	Ge	13%	16.7%	0.4	60	91.50
Notes:							
	Lin Jing	Ge	14%	17.8%	0.4	40	91.26
Notes:							
3/3/25	Kwanghee Han	Cr	1%	3.5%	0.5	4	91.17
Notes:							
	Kwanghee Han	Au	30%	48%	0.93	60	89.82
Notes:							
3/3/25	Melissa Mikelsen	Ti	13.6%	16%	0.56	5	89.8%
Notes:							
Notes:							
3/3/25	Melissa Mikelsen	Au	30%	46.9%	0.88	50	88.92%
Notes:							
3/31/25	Vika Rutckaja	Cr	3.3%	4%	0.21	4	88.89%
Notes:							
	Vika Rutckaja	Au	29.6%	47.1%	0.72	100	87.09%
Notes:							
3/31/25	Yajun Gao	Cr	3.6%	6.9%	0.3	28	86.91%
Notes:							
04/04/25	Emmanuel	Ag	8%	11.7%	0.47	40	86.40
Notes:							
05/02/2025	Ashish	Al ₂ O ₃	11%	8.7%	0.4	50	96.90
07/10/2025	Ashok	Ag	10%	12%	0.5	38	92%
07/10/2025	Nirmal	Cr/Au	1.5% / 20%	3.6% / 42%	0.75 / 0.96	30 / 60	