

April 2025

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/S)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
04/04/25	Emmanuel	Ag	22	12%	0.6	80	85.55
Notes:							
4/4/25	Wei Wang	Ag	9%	13%	0.8	50	84.82
Notes:							
4/5/25	Guangyu Han	Cr	10% 7%	9%	0.2	15	83.04
Notes:							
4/5/25	Guangyu Han	Al	30%	50%	1	55	81.7
Notes:							
4/7/25	Rishabh Kumar	Ag	10	12.5%	0.7	200	80.07%
Notes:							
04/07/25	Ashish	Al ₂ O ₃	1%	10%	0.4	50nm	79.82%
Notes:							
04/07/25	Daria	Al ₂ O ₃	3%	18%	1.6	20nm	79.72%
Notes:							
04/07/25	Kuanghee	Cr	9%	12%	0.47	4nm	79.65%
Notes:							
4/7/25	Kuanghee	Al	32%	50%	1.09	61nm	78.44%
Notes:							
4/7/25	Yajun Gao	Cr	10.3%	13.7%	0.49	28	78.22%
Notes:							
4/8/25	M. Dasthakeer	Ge	13%	14.5%	0.12	2nm	78.2%
Notes:							
4/8/25	M. Dasthakeer	Ag	10%	11.5%	0.5	40nm	77.74%
Notes:							

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/s)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
4/8/25	Zezberg Zhu	Al ₂ O ₃	3.0%	15%	0.5	25nm	77.66
Notes:							
4/9/25	Nicholas Morin	Cr	6.5%	13.7% 14.8% 0.5	0.5	30nm	77.46%
Notes:							
4/9/25	Nicholas Morin	Au	27%	44.5%	0.5	60nm	76.22%
Notes:							
4/9/25	Wei Wang	Ti	9%	15%	0.55	5nm	76.19%
Notes:							
4/9/25	Wei Wang	Au	27%	45%	0.7	50nm	75.18%
Notes:							
4/10/25	Rinshubn K	Ag	10	11	0.5	50nm	75.82%
Notes:							
4/10/25	Ashish	Al ₂ O ₃	2%	13.6%	0.48	50nm	74.65%
Notes:							
4/10/25	Rinshubn K	Ag	9	11.5	0.7	100nm	73.85
Notes:							
4/11/25	Lin Jing	Ge	13.5	16.5	0.4	80nm	97.76
Notes:							
4/11/25	Emmanuel	Ag	8%	10.5	0.43	40	97.30
Notes:							
4/11/25	Wei Wang	Ag	9%	13%	1%	30	96.57
Notes:							
4/12/25	Nicholas Morin	Cr	0.5%	4.4%	0.5	30	96.29%
Notes:							

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/s)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
4/12/25	Nicholas Marin	Au	33%	46.6%	0.5	60	94.82%
Notes:							
4/12/25	Guanyu Han	User.	1.5%	33.2%	0.5	200	93.64%
Notes:							
4/14/25	Ziyao Feng	Cr.	5.0%	6.0%	0.20	15	95.55%
Notes:							
4/14/25	Ziyao Feng	Au	33%	49%	1.0A	55	92.01%
Notes:							
4/14/25	Yajun Gao	Cr	7%	8.2%	0.30	28	91.86%
Notes:							
4/14/25	Nicholas Marin	Au	30.5%	45.3%	0.5	60	90.59%
Notes:							
4/16/25	Emmanuel	Ag	9%	17%	2	500	85.68
Notes:							
4/16/25	Lev Berkhovskiy	Cr	1.6%	7.5%	0.58	3	85.39
Notes:							
4/16/25	Lev Berkhovskiy	Au	33%	46.5%	0.57	5	89.7
Notes:							
4/16/25	Yajun Gao	Cr	5.5%	11.9%	1	95 100	84.06%
Notes:							
4/16/25	Wenjun Deng	Cr	4.4%	11.9%	0.1A/s	5	84.02%
Notes:							
4/16/25	Wenjun Deng	Au	30 30%	36.8%	0.1A/s	25	83.61%
Notes:							

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/s)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
4/18	Zezheng Zhu	Al ₂ O ₃	3%	12%	0.6	25	83.53%
Notes:							
4/17	Ashish	Ti	10%	14.4%	0.36	5nm	83.52%.
Notes:							
4/17	Ashish	Au	30%	44%	0.55	45nm	82.86%.
Notes:							
4/17	Ashish	Al ₂ O ₃	1%	12.8%	0.6	50nm	82.74%.
Notes:							
4/17	Yajun Gao	Al ₂ O ₃	1.1%	10.5% 12%	0.44	25	82.60%
Notes:							
4/17	Melissa Mikalsen	Ti	11.5%	15.5%	0.51	5	82.55%
Notes:							
4/17	Melissa Mikalsen	Au	29%	45%	0.70	50	81.47%
Notes:							
4/18	Lih Jng	Cr	5.5%	8.5%	0.4	60	81.20%
Notes:							
4/18	Ewangee Han	Cr	10%	13.5%	0.51	4	81.14%
Notes:							
4/18	Ewangee Han	Au	30%	46%	1.01	60	79.43%
Notes:							
4/19	Wei Wang	Ag	9%	14%	0.8	60	79.11%
Notes:							
4/19	Guangyi Han	Ni/Cr	7.4%	29%	0.35	200	77.75%
Notes:							

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (A/S)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
4/22	Lin Jang	Cr	3%	3.6% 8.5%	0.4	50	97.69%
Notes:							
4/23	Melissa Mikalsen	Ti	12%	17.5%	0.43	5	97.60%
Notes:							
4/23	Melissa Mikalsen	Au	37%	49%	0.75	50	96.58%
Notes:							
4/23	Zeyu Peng	Cr	6.0%	8.3%	0.23	15	96.48%
Notes:							
4/23	Zeyu Peng	Au	31%	49%	1.16	55	94.85%
Notes:							
4/23	Yajun Gao	Cr	7.7%	10.6%	0.45	40	94.62%
Notes:							
4/24	Salwa Elhalabi	Al	11.7%	13%	0.70	100	94.38%
Notes: went to 12% for threshold & rate skyrocket. / @ same power → rate went up to 1.51 A/s							
04/24	Padma Radhakrishnan	Cr	9%	12.1%	0.5	7	94.31%
Notes:							
04/24	Padma Radhakrishnan	Au	33%	47.7%	1	50	93.29%
Notes:							
4/24	Wei Wang	Ag	9%	14%	0.76	60	92.57%
Notes:							
04/25	Emmanuel	Ag	8%	11.8%	0.5	40	91.97%
Notes:							
04/25	Wenjun Deng	Cr	7%	11.5%	0.2	15	90.88%
Notes:							
04/25	Wenjun Deng	Au	31%	48.1%	1	55	80.44%
04/26	Lin Jang	Cr	11%	13.7%	0.4	50	90.17%

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/S)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
4/28	Zygo Peng	Cr.	15.0%	17.0%	0.5A	15	90.0%
Notes:							
4/28	Zygo Peng	Au.	31.0%	49%	1.2.	55	88.95%
Notes:							
4/28	Ethan Liu	Ti	11.5%	15%	0.4A	20	88.84%
Notes:							
4/28	Ethan Liu	Al	11.5%	12%	0.8	120	88.63%
Notes:							
4/28	Ethan Liu	Ni	6%	35%	0.4	30	88.21%
Notes:							
4/28	Ethan Liu	Au	27%	49%	0.91	50	87.07%
Notes:							
04/29	Ashish	Ti	10%	14%	0.5	10	87.04%
Notes:							
04/29	Ashish	Au	30%	45%	0.8	90	85.06%
Notes:							
04/29	Ashish	Ti	11%	14%	0.33	51	84.46
Notes:							
04/29	Ashish	Au	30%	40%	0.32	45	83.81
Notes:							
04/29	Yajun	Cr	15.8%	17.7%	0.40	10	83.68
Notes:							
04/29	Yajun	Au	36.1%	40%	0.60	60	82.09%
Notes:							