

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/s)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
4/30/05	Nicholas Menner	Au	30%	48.6%	1.0	60	80.63%
Notes:							
4/30/05	Yajun Gao	Cr	15.2%	16.9%	0.23	38	80.47%
Notes:							
05/01/05	Yajun Gao	Al ₂ O ₃	2%	5.2%	0.1	25	97.92%
Notes:							
05/01/05	Yajun Gao	Ag	9.2%	13.5% 15%	1.0	60	97.03%
Notes:							
05/02/05	Andy Cruz	Au	33%	43%	0.48	30	96.11%
Notes:							
05/02/05	Serena Lachariah	Ag	8.1%	11.8%	0.5	40	95.60%
Notes:							
05/02/05	Salim Kilhadi	Ge	9.0	19.6%	0.73	30	95.33%
Notes:							
05/04/05	Lin Tong	Cr	2.5	4.2	0.5	10	95.10%
Notes:							
05/04/05	Lin Tong	Au	29.5	46.5	1	60	93.73%
Notes:							
05/04/05	Zhan Li	Cr	3.9	6.8	0.5	30	93.60%
Notes:							
05/04/05	Zhan Li	Au	31.1	45.5	1	500	86.1%
Notes:							
05/05/05	Yajun Gao	Al ₂ O ₃	1.2%	7.3%	0.17	25	86.01%
Notes:							

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/s)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
5/5/2025	Kwanghee Han	Cr	7.5	8.4	0.47	4nm	85.87%
Notes:							
5/5/2025	Kwanghee Han	Ag	30	46.5	1.05	60nm	84.55%
Notes:							
05/05/25	Padma Padhakrishnan	Cr	8%	8.9%	0.5	7nm	84.58%
Notes:							
05/05/25	Padma Padhakrishnan	Au	30.1%	45.3%	1	50nm	83.61%
Notes:							
05/05/25	Rishabh Kumar	Ag	11	13	1	150nm	82.67%
Notes:							
05/06/25	Lih Jing	Cr	8%	10.5	0.5	5nm	82.56%
Notes:							
05/06/25	Lih Jing	Ge	7%	9.5	0.4	60nm	82.26%
Notes:							
05/06/25	Sriram	Cr	8.5%	11.2%	0.33	5nm	82.28%
Notes:							
05/06/25	Sriram	Ge	11%	19%	0.66	10nm	82.21%
Notes:							
05/06/25	Sriram	Al ₂ O ₃	3%	8.5%	0.23	5nm	82.21%
Notes:							
05/06/25	Sriram	Ge	11%	22.3%	1.2 Å/s	3x Å	80.62%
Notes:							
05/06/25	Yajun	Cr	9%	10.5%	0.24 Å/s	2nm	
Notes:							

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/s)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
05/06	Yajun	Al ₂ O ₃	2.3%	9%	0.2	25	
Notes:							
05/07	Bhuiyan, Reaz Uddin	Cr	9.6%	11.9%	0.45	5	80.42%
Notes:							
05/07	Bhuiyan, Reaz U.	Ag	11%	16%	2.0	200	78.96%
Notes:							
05/07	Ashok Achikani	Ag	20.3%	22.5%	0.60	38	78.90%
Notes:							
05/07	Lin Jia	Al ₂ O ₃	1%	8.3%	0.15	20	78.32%
Notes:							
05/08	Lin Jia	Cr	9%	11.6%	0.25	5	78.27%
Notes:							
05/08	Lin Jia	Ge	14%	18%	0.4	94	77.88%
Notes:							
05/08	Yajun	Cr	10.3%	12.6%	0.25	3	77.83%
Notes:							
05/08	Yajun	Au	30%	45.9%	1	50	76.45%
Notes:							
05/08	Zeyu F.	Cr.	10.5%	13.5%	0.60	15	76.67%
Notes:							
05/08	Zeyu F.	Au	20.0%	46.0%	1.05	50	76.2%
Notes:							
05/08	Sriram	Ge	13%	21%	0.9 Å/μ	260 nm	76.87%
Notes:							

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/S)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
4/10	Lin /ing	Ge	12.5%	19.4%	0.4	63 63	73.6%
Notes:							
5/10	Lin /ing	Al ₂ O ₃	2.0%	8.5%	0.2	15	73.62%
Notes:							
5/13	Yajun Gao	Cr	0.2%	1.1%	0.25	5	97.96%
Notes:							
5/13	Yajun Gao	Au	30.3%	47.3%	1	50	96.33%
Notes:							
5/13	Surodup	Ti	14%	19%	0.95	10	96.26%
Notes:							
5/13	Surodeep	Au	33%	60%	6.80	200	93.08%
Notes:							
05/14	Ashish	Ti	10%	14%	0.26	10	91.05%
Notes:							
05/14	Ashish	Au	28%	46%	0.9	90	89.65%
Notes:							
05/15	Yajun Gao	Cr	1.7%	2.4%	0.4 0.25	5	89.59%
Notes:							
05/15	Yajun Gao	Au	30%	46.4%	1	50	87.92%
Notes:							
05/15	Zyco fang	Cr	3%	3.8%	0.35	15	87.84%
Notes:							
05/15	Zyco fang	Au	30.0%	47.0	1.14	55	86.40%
Notes:							

5/15 Nicholas Menina Cr 35% 8.3% 1.0 30 86.13%

5/15 Nicholas Menina Au 30% 46.4% 1.0 60 84.66%

5/19 Ashish Al₂O₃ 1% 8% 0.45 100 nm 84.39%

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/S)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
05/19	Yajun Gao	Al ₂ O ₃	1.0%	9%	0.4	25	84.27%
Notes:							
05/19	Lih Jing	Cr	1.8%	10.5	0.4	50	83.90%
Notes:							
5/20	Arnon Rezene	Cr	2%	10.6	.08	48	83.88%
Notes:							
5/20	Kwanghee Han	Cr	7.5%	17.5%	0.48	4.3	83.82%
Notes:							
5/20	Kwanghee Han	Al ₂	33%	51%	1.02	60	82.68%
Notes:							
5/20	Lih Jing	Cr	9.7%	14.8%	0.4	5	82.58%
Notes:							
5/20	Lih Jing	Au	30%	51%		50	81.18%
Notes:							
5/21	Maryam Barzegar	Ti	11.0% 11.0%	14.5%	0.49	5	81.10%
Notes:							
5/21	Maryam Barzegar	Au	30%	49.5%	0.75	50	80.04%
Notes:							
5/22	Yajun Gao	Cr	10.5%	15.0%	0.32	45	79.81%
Notes:							
5/22	Ziyao Feng	Cr	12.5%	15.0%	0.20	15.6	79.72%
Notes:							
5/22	Ziyao Feng	Au	22.0%	51.1%	1.00	55	78.19%
Notes:							

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/s)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
5/23	Padma Radhakrishnan	Cr	14.1%	17.7%	0.5	7	78.10%
Notes:							
5/23	Padma Radhakrishnan	Au	29%	51.1%	1	50	76.95%
Notes:							
5/23	Audre Lai	Cr	15%	18.1%	0.4	5	76.86%
Notes:							
	Audre Lai	Au	29%	50%	0.9	50	75.46%
Notes:							
05/23	Sriram	Cr	11.5%	16.1%	0.15	5	75.45%
Notes:							
05/23	Sriram	Ge	13.1%	19.5%	0.5	360nm	75.4%
Notes:							
05/24	Lin Jay	Cr	13.5%	19.4%	0.4	50	73.72%
Notes:							
05/27	Yajun Gao	Cr	14.1%	20.1%	0.4	28	73.53%
Notes:							
05/27	Erros Michail	Cr	13.0%	18.1%	0.22	2,2	73%
Notes:							
05/27	Erros Michail	Au	30%	43%	0.39	51	73%
Notes:							
05/27	Lin Jay	Ge	12%		0.4	60	72.46%
Notes:							
05/28	Yajun Gao	Cr	15.6%	20.6%	0.3	10	72.36%
Notes:							

Date	User	Material	Threshold Power (to see a rate)	Power (deposition)	Rate (Å/s)	Thickness (nm)	Crystal Monitor % (End)
Notes:							
05/28	Yajun Gao	Au	30.0%	50.1%	1.02	80	70.34%
Notes:							
05/28	Yajun Gao	Cr	15.7%	21.7%	0.4	10	
Notes:							
05/28	Yajun Gao	Au	30.9%	50.1%	0.95	80	68.53%
Notes:							
05/28	Ashish	Al ₂ O ₃	1%	10%	0.4	50	87.12%
Notes:							
05/28	Ritesh Ashish	Ti	8%	14%	0.3	5	
Notes:							
05/28	Gold Ashish	Au	30%	46%	0.6	45	86.34%
Notes:							
05/28	Lih Jiny	Al ₂ O ₃	3%	10%	0.4	50	67.51%
Notes:							
05/28	Lih Jiny	Al ₂ O ₃	3%	11.5%	0.4	50 58	67.34%
Notes:							
05/29	Radma Radhakrishnan	Cr	16%	22.8%	0.5	7	67.26%
Notes:							
05/29	Radma Radhakrishnan	Au	32.1%	49.9%	1	50	66.20%
Notes:							
5/29	Feddre Zhu	Al ₂ O ₃	3%	18%	1	25	66.12%
Notes:							
05.30	Daria Kafewa	Cr	16%	17%	0.09	5	66.09%
Notes:							