ERRATUM

Erratum to: Temperature and wavelength dependent refractive index equations for MgO-doped congruent and stoichiometric $LiNbO_3$

O. Gayer · Z. Sacks · E. Galun · A. Arie

Received: 27 July 2010 / Published online: 26 August 2010 © Springer-Verlag 2010

Erratum to: Appl Phys B (2008) 91: 343–348 DOI 10.1007/s00340-008-2998-2

In Table 1, the parameter b_1 for n_e of 1% MgO-doped SLN should be 4.677×10^{-6} . Here is again the corrected Table 1.

Table 1 Calculated Sellmeier coefficients for 5% MgO-doped congruent LiNbO₃ (CLN) and 1% MgO-doped stoichiometric LiNbO₃ (SLN), according to (2), where λ is in microns

Parameters	5% MgO-doped CLN		1% MgO-doped SLN
	$\overline{n_{\mathrm{e}}}$	n_0	n_{e}
a_1	5.756	5.653	5.078
a_2	0.0983	0.1185	0.0964
a ₃	0.2020	0.2091	0.2065
a ₄	189.32	89.61	61.16
a ₅	12.52	10.85	10.55
a ₆	1.32×10^{-2}	1.97×10^{-2}	1.59×10^{-2}
b_1	2.860×10^{-6}	7.941×10^{-7}	4.677×10^{-6}
b_2	4.700×10^{-8}	3.134×10^{-8}	7.822×10^{-8}
b_3	6.113×10^{-8}	-4.641×10^{-9}	-2.653×10^{-8}
b_4	1.516×10^{-4}	-2.188×10^{-6}	1.096×10^{-4}

The online version of the original article can be found under doi:10.1007/s00340-008-2998-2.

O. Gayer · A. Arie (⊠)

Department of Physical Electronics, School of Electrical Engineering, Tel-Aviv University, Tel-Aviv 69978, Israel e-mail: ady@eng.tau.ac.il

Z. Sacks · E. Galun

Elbit Systems, El-Op Electro-Optics Industries Ltd., Rehovot, Israel

