Micro Powders

AquaBead® 519

A specially formulated wax composite that provides immediate water repellency and weather resistance

Features and Benefits

- Imparts immediate water beading
- Provides long-lasting water repellency
- Contains lower molecular weight polymers for faster water beading in water based and solvent based penetrating stains
- Combine with silica to improve weather resistance

Composition

Hydrophobically modified synthetic wax

Recommended Addition Levels

1.0-4.0% (on total formula weight)

Systems and Applications

Water based and solvent based coatings. Industrial coatings (including metal and masonry); stains, sealers and varnishes; wood coatings; automotive polishes.

Typical Properties*

	AquaBead 519
Mean Particle Size (µm)	5.5 - 8.0
Maximum Particle Size (µm)	22.00
Melting Point °C	126 - 132
Density @ 25 °C (g/cc)	0.94
NPIRI Grind	2.0 - 3.0

This product is also available as a water based wax dispersion - Microspersion 519

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

Micro Powders

AquaPoly 511

A unique micronized oxidized polyethylene wax composite for improved scuff and mar resistance in aqueous and solvent based systems

Features and Benefits

- A synergistic blend of high molecular weight waxes including polyethylene
- Provides optimum levels of scuff and mar resistance along with excellent slip and mobility
- Easy to disperse fine powder that can be incorporated into aqueous paints, inks and coatings with high speed mixing
- Compare to AquaPolyfluo 411 (without PTFE)

Composition

Modified oxidized HDPE

Recommended Addition Levels

0.5-2.0% (on total formula weight)

Systems and Applications

Solvent and water based coatings. Industrial coatings (including plastic, metal and leather); architectural wall and trim paints; stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); coil coatings.

Typical Properties*

	AquaPoly 511
Mean Particle Size (µm)	6.0 - 8.0
Maximum Particle Size (µm)	22.00
Melting Point °C	117 - 123
Density @ 25 °C (g/cc)	0.97
NPIRI Grind	2.5 - 3.5

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

Micro Powders

TECHNICAL DATA

MicroTouch 800 Series

Highly resilient spherical polyurethane beads that can modify the tactile properties of formulated coatings and inks while improving burnish, scratch and mar resistance

Features and Benefits

- Virtually indestructible elastic particles that distort when disturbed by a physical force and then return to their original spherical shape when the force is removed
- Provide different tactile effects ranging from satiny smooth to rubbery to leathery in properly formulated coatings
- Different particle sizes available to create a unique surface "touch"
- Improves burnish and abrasion resistance
- Effective gloss reduction

Composition

Aliphatic polyurethane

Recommended Addition Levels

2.0-10.0% (higher amounts when greater tactile effects are desired) (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, vinyl and leather); architectural wall and trim paints; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; soft touch coatings; floor coatings; visual effects.

Typical Properties*

	MicroTouch 800F	MicroTouch 800VF	MicroTouch 800XF	MicroTouch 800XXF
Mean Particle Size (µm)	22.0 - 30.0	11.0 - 15.0	6.0 - 9.0	3.0 - 5.0
Maximum Particle Size (µm)	120.00	60.00	31.00	15.00
Density @ 25 °C (g/cc)	1.05	1.05	1.05	1.05

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

MPI Micro Powders

TECHNICAL DATA

MicroTouch 800 Series

Highly resilient spherical polyurethane beads that can modify the tactile properties of formulated coatings and inks while improving burnish, scratch and mar resistance

Features and Benefits

- Virtually indestructible elastic particles that distort when disturbed by a physical force and then return to their original spherical shape when the force is removed
- Provide different tactile effects ranging from satiny smooth to rubbery to leathery in properly formulated coatings
- Different particle sizes available to create a unique surface "touch"
- Improves burnish and abrasion resistance
- Effective gloss reduction

Composition

Aliphatic polyurethane

Recommended Addition Levels

2.0-10.0% (higher amounts when greater tactile effects are desired) (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, vinyl and leather); architectural wall and trim paints; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; soft touch coatings; floor coatings; visual effects.

Typical Properties*

	MicroTouch 800F	MicroTouch 800VF	MicroTouch 800XF	MicroTouch 800XXF
Mean Particle Size (µm)	22.0 - 30.0	11.0 - 15.0	6.0 - 9.0	3.0 - 5.0
Maximum Particle Size (µm)	120.00	60.00	31.00	15.00
Density @ 25 °C (g/cc)	1.05	1.05	1.05	1.05

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

Micro Powders

TECHNICAL DATA

MP-22

High performance, versatile grade of micronized synthetic wax for improved slip, scratch and rub resistance in a wide variety and paints, coatings and inks

Features and Benefits

- Imparts a high degree of lubricity and slip with rub and mar resistance
- Provides antiblocking properties
- Gives long-lasting water beading and weather resistance to exterior alkyd-based stains
- Consider MP-22C & MP-28C (spherical) for improved surface slip
- Biodegradable to OECD 302C test standard
- Not a microplastic per ECHA definitions

Composition

Synthetic wax

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, metal and masonry); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; coil coatings; powdered metals.

Typical Properties*

	MP-22	MP-22VF	MP-22XF	MP-22XXF
Mean Particle Size (µm)	7.0 - 10.0	6.0 - 8.0	4.5 - 6.5	3.75 - 5.75
Maximum Particle Size (µm)	31.00	22.00	22.00	15.56
Melting Point °C	110 - 115	110 - 115	110 - 115	110 - 115
Density @ 25 °C (g/cc)	0.93	0.93	0.93	0.93
NPIRI Grind	4.0 - 6.0	2.0 - 3.5	1.5 - 3.0	1.0 - 2.3

This product is also available as a water based wax dispersion - Microspersion 22-50

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

MP-28AL Series

Value engineered synthetic wax/aluminum oxide nanocomposites for surface durability and lubricity

Features and Benefits

- Improves scratch, scuff and mar resistance
- Adds surface slip and lubricity
- Choose XF grade for maximum gloss retention
- Choose G grade for maximum gloss reduction and burnish resistance
- Biodegradable to OECD 302C test standard
- Not a microplastic per ECHA definitions

Composition

Synthetic wax/aluminum oxide

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks, Industrial coatings (including plastic, metal and masonry); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings.

Typical Properties*

	MP-28AL-XF	MP-28AL	MP-28AL-G
Mean Particle Size (µm)	4.0 - 6.0	6.0 - 8.0	10.0 - 14.0
Maximum Particle Size (µm)	15.56	22.00	44.00
Melting Point °C	114 - 118	114 - 118	114 - 118
Density @ 25 °C (g/cc)	0.99	0.99	0.99
NPIRI Grind	1.0 - 2.0	1.5 - 3.0	N/A

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

TECHNICAL DATA

MPI Micro Powders

NyloTex Series

Micronized Nylon 66 for adding texture and surface durability to high temperature coatings

Features and Benefits

- Provides a uniform and controlled surface texture
- Imparts surface toughness and durability
- High melting point polymer is ideal for use in baking or high temperature curing systems
- Easy to disperse fine powder that can be incorporated with high speed mixing
- Adds texture in powder coatings

Composition

Nylon 66

Recommended Addition Levels

3.0% and higher depending on the level of texture desired (on total formula weight)

Systems and Applications

Water based and solvent based coatings. Industrial coatings (including metal and masonry); powder coatings; coil coatings; floor coatings.

Typical Properties*

	NyloTex 50	NyloTex 100	NyloTex 140	NyloTex 200
Mean Particle Size (µm)	160.0 - 180.0	80.0 - 100.0	45.0 - 65.0	30.0 - 50.0
Maximum Particle Size (µm)	297 (50 mesh)	149 (100 mesh)	105 (140 mesh)	74 (200 mesh)
Melting Point °C	257 - 267	257 - 267	257 - 267	257 - 267
Density @ 25 °C (g/cc)	1.14	1.14	1.14	1.14
Moisture Content	<4%	<4%	<4%	<4%

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

Micro Powders

NyloTex Series

Micronized Nylon 66 for adding texture and surface durability to high temperature coatings

Features and Benefits

- Provides a uniform and controlled surface texture
- Imparts surface toughness and durability
- High melting point polymer is ideal for use in baking or high temperature curing systems
- Easy to disperse fine powder that can be incorporated with high speed mixing
- Adds texture in powder coatings

Composition

Nylon 66

Recommended Addition Levels

3.0% and higher depending on the level of texture desired (on total formula weight)

Systems and Applications

Water based and solvent based coatings. Industrial coatings (including metal and masonry); powder coatings; coil coatings; floor coatings.

Typical Properties*

	NyloTex 50	NyloTex 100	NyloTex 140	NyloTex 200
Mean Particle Size (µm)	160.0 - 180.0	80.0 - 100.0	45.0 - 65.0	30.0 - 50.0
Maximum Particle Size (µm)	297 (50 mesh)	149 (100 mesh)	105 (140 mesh)	74 (200 mesh)
Melting Point °C	257 - 267	257 - 267	257 - 267	257 - 267
Density @ 25 °C (g/cc)	1.14	1.14	1.14	1.14
Moisture Content	<4%	<4%	<4%	<4%

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

Micro Powders

NyloTex Series

Micronized Nylon 66 for adding texture and surface durability to high temperature coatings

Features and Benefits

- Provides a uniform and controlled surface texture
- Imparts surface toughness and durability
- High melting point polymer is ideal for use in baking or high temperature curing systems
- Easy to disperse fine powder that can be incorporated with high speed mixing
- Adds texture in powder coatings

Composition

Nylon 66

Recommended Addition Levels

3.0% and higher depending on the level of texture desired (on total formula weight)

Systems and Applications

Water based and solvent based coatings. Industrial coatings (including metal and masonry); powder coatings; coil coatings; floor coatings.

Typical Properties*

	NyloTex 50	NyloTex 100	NyloTex 140	NyloTex 200
Mean Particle Size (µm)	160.0 - 180.0	80.0 - 100.0	45.0 - 65.0	30.0 - 50.0
Maximum Particle Size (µm)	297 (50 mesh)	149 (100 mesh)	105 (140 mesh)	74 (200 mesh)
Melting Point °C	257 - 267	257 - 267	257 - 267	257 - 267
Density @ 25 °C (g/cc)	1.14	1.14	1.14	1.14
Moisture Content	<4%	<4%	<4%	<4%

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

TECHNICAL DATA

Micro Powders

NyloTex Series

Micronized Nylon 66 for adding texture and surface durability to high temperature coatings

Features and Benefits

- Provides a uniform and controlled surface texture
- Imparts surface toughness and durability
- High melting point polymer is ideal for use in baking or high temperature curing systems
- Easy to disperse fine powder that can be incorporated with high speed mixing
- Adds texture in powder coatings

Composition

Nylon 66

Recommended Addition Levels

3.0% and higher depending on the level of texture desired (on total formula weight)

Systems and Applications

Water based and solvent based coatings. Industrial coatings (including metal and masonry); powder coatings; coil coatings; floor coatings.

Typical Properties*

	NyloTex 50	NyloTex 100	NyloTex 140	NyloTex 200
Mean Particle Size (µm)	160.0 - 180.0	80.0 - 100.0	45.0 - 65.0	30.0 - 50.0
Maximum Particle Size (µm)	297 (50 mesh)	149 (100 mesh)	105 (140 mesh)	74 (200 mesh)
Melting Point °C	257 - 267	257 - 267	257 - 267	257 - 267
Density @ 25 °C (g/cc)	1.14	1.14	1.14	1.14
Moisture Content	<4%	<4%	<4%	<4%

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

TECHNICAL DATA

Micro Powders

PolyTuf® 1229

A highly engineered LDPE/ceramic/nanoceramic composite for abrasion resistance and surface durability

Features and Benefits

- High performance additive for maximizing surface abrasion resistance (Taber) and film toughness
- Fortified with two types of hard, inert ceramic particles
- Low density polyethylene provides superior surface toughness, durability and mar resistance
- Ideal for walking surfaces
- PTFE-free alternative to Polyfluo 900
- Easy to disperse fine powder that can be incorporated with high speed mixing

Composition

Ceramic modified polyethylene

Recommended Addition Levels

0.5-2.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, metal and masonry); architectural wall and trim paints; stains, sealers and varnishes; floor coatings; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings; rubber additives.

Typical Properties*

	PolyTuf 1229
Mean Particle Size (µm)	9.0 - 12.0
Maximum Particle Size (µm)	31.11
Melting Point °C	110 - 113
Density @ 25 °C (g/cc)	0.97
NPIRI Grind	4.0 - 6.0

This product is also available as a water based wax dispersion - Microspersion 1229-40

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

TECHNICAL DATA

Micro Powders

PropylMatte 31

Finely micronized polypropylene for efficient matting and gloss control in paints, coatings and inks

Features and Benefits

- Provides consistent gloss reduction with no effect on coating viscosity
- Tough, high molecular weight polymer imparts burnish and abrasion resistance
- Imparts anti-slip properties
- Density (0.89) ideal for solvent based systems
- For more efficient matting with a fine microtexture, try PropylTex 325S/270S
- Adds texture in low bake (Low E) powder coatings

Composition

Polypropylene

Recommended Addition Levels

2.0-5.0% depending on the level of gloss reduction desired (on total formula weight)

Systems and Applications

Water based and solvent based coatings. Industrial coatings (including plastic, metal and leather); architectural wall and trim paints; stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings.

Typical Properties*

	PropylMatte 31
Mean Particle Size (µm)	8.0 - 12.0
Maximum Particle Size (µm)	31.00
Melting Point °C	160 - 170
Density @ 25 °C (g/cc)	0.89
NPIRI Grind	5.0 - 6.0

This product is also available as a water based wax dispersion - Microspersion 31-35

Mar-26

PropylMatte 31HD

Finely micronized densified polypropylene for consistent matting and gloss control with superior in-can stability in water based paints, coatings and inks

Features and Benefits

- Efficient gloss reduction from satin to matte finish
- Improves burnish resistance vs. silica mattifiers
- Particle density optimized to essentially eliminate flotation or settling in most water based systems
- Imparts anti-slip properties
- For more efficient matting with a fine microtexture, try PropylTex 325HD/270HD

Composition

Densified polypropylene

Recommended Addition Levels

2.0-5.0% depending on the level of gloss reduction desired (on total formula weight)

Systems and Applications

Water based and energy curable coatings and inks. Industrial coatings (including plastic, metal, masonry and leather); architectural wall and trim paints; stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); interior and exterior can and container coatings; coil coatings; floor coatings.

Typical Properties*

	PropylMatte 31HD
Mean Particle Size (µm)	8.0 - 12.0
Maximum Particle Size (µm)	31.00
Melting Point °C	160 - 170
Density @ 25 °C (g/cc)	1.07
NPIRI Grind	5.0 - 6.0

This product is also available as a water based wax dispersion - Microspersion 31HD-40

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

Micro Powders

PropylTex® 14-50 (coarse texture grades)

Extra coarse particle size grades of micronized polypropylene for adding texture, structure and anti-slip properties to a wide variety of paints and coatings

Features and Benefits

- Provides a consistent coarse textured coating surface
- Tough, high molecular weight polypropylene gives good film durability
- Does not lower COF; ideal for anti-skid surfaces
- Easy to disperse powder that can be incorporated with high speed mixing

Composition

Polypropylene

Recommended Addition Levels

3.0-10.0% (on total formula weight)

Systems and Applications

Water based, solvent based, industrial and consumer paints including masonry, stucco paints, architectural wall and trim paints; stains, sealers and varnishes; wood coatings; floor coatings.

Typical Properties*

	PropylTex 14	PropylTex 20	PropylTex 30	PropylTex 50
Mean Particle Size (µm)	375 - 450*	350 - 425*	300 - 350*	200 - 250*
Maximum Particle Size (µm)	1410 (14 mesh)	841 (20 mesh)	595 (30 mesh)	297 (50 mesh)
Melting Point °C	166 - 168	166 - 168	166 - 168	166 - 168
Density @ 25 °C (g/cc)	0.90	0.90	0.90	0.90

* NOTE THAT MEAN PARTICLE SIZE IS NOT A SPECIFICATION FOR THESE PRODUCTS. PROPYLTEX 14 IS A MADE TO ORDER PRODUCT WITH MINIMUM ORDER QUANTITIES AND EXTENDED LEAD TIMES

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

Micro Powders

PropylTex® 14-50 (coarse texture grades)

Extra coarse particle size grades of micronized polypropylene for adding texture, structure and anti-slip properties to a wide variety of paints and coatings

Features and Benefits

- Provides a consistent coarse textured coating surface
- Tough, high molecular weight polypropylene gives good film durability
- Does not lower COF; ideal for anti-skid surfaces
- Easy to disperse powder that can be incorporated with high speed mixing

Composition

Polypropylene

Recommended Addition Levels

3.0-10.0% (on total formula weight)

Systems and Applications

Water based, solvent based, industrial and consumer paints including masonry, stucco paints, architectural wall and trim paints; stains, sealers and varnishes; wood coatings; floor coatings.

Typical Properties*

	PropylTex 14	PropylTex 20	PropylTex 30	PropylTex 50
Mean Particle Size (µm)	375 - 450*	350 - 425*	300 - 350*	200 - 250*
Maximum Particle Size (µm)	1410 (14 mesh)	841 (20 mesh)	595 (30 mesh)	297 (50 mesh)
Melting Point °C	166 - 168	166 - 168	166 - 168	166 - 168
Density @ 25 °C (g/cc)	0.90	0.90	0.90	0.90

* NOTE THAT MEAN PARTICLE SIZE IS NOT A SPECIFICATION FOR THESE PRODUCTS. PROPYLTEX 14 IS A MADE TO ORDER PRODUCT WITH MINIMUM ORDER QUANTITIES AND EXTENDED LEAD TIMES

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

TECHNICAL DATA

Micro Powders

PropylTex® 100S-200S (medium texture grades)

Coarse particle size grades of micronized polypropylene for adding texture, structure and anti-slip properties to a wide variety of paints and coatings

Features and Benefits

- Provides a consistent medium textured coating surface
- Tough, high molecular weight polypropylene gives good film durability
- Does not lower COF; ideal for anti-skid surfaces
- Easy to disperse powder that can be incorporated with high speed mixing
- Adds texture in low bake (Low E) powder coatings

Composition

Polypropylene

Recommended Addition Levels

3.0-10.0% (on total formula weight)

Systems and Applications

Water based, solvent based, industrial and consumer paints including masonry, stucco paints, architectural wall and trim paints; stains, sealers and varnishes; wood coatings; floor coatings.

Typical Properties*

	PropylTex 100S	PropylTex 140S	PropylTex 200S	PropylTex 200SF
Mean Particle Size (µm)	80.0 - 100.0	45.0 - 50.0	35.0 - 45.0	25.0 - 35.0
Maximum Particle Size (µm)	149 (100 mesh)	105 (140 mesh)	74 (200 mesh)	74 (200 mesh)
Melting Point °C	160 - 170	160 - 170	160 - 170	160 - 170
Density @ 25 °C (g/cc)	0.89	0.89	0.89	0.89

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

Micro Powders

TECHNICAL DATA

PropylTex® 100S-200S (medium texture grades)

Coarse particle size grades of micronized polypropylene for adding texture, structure and anti-slip properties to a wide variety of paints and coatings

Features and Benefits

- Provides a consistent medium textured coating surface
- Tough, high molecular weight polypropylene gives good film durability
- Does not lower COF; ideal for anti-skid surfaces
- Easy to disperse powder that can be incorporated with high speed mixing
- Adds texture in low bake (Low E) powder coatings

Composition

Polypropylene

Recommended Addition Levels

3.0-10.0% (on total formula weight)

Systems and Applications

Water based, solvent based, industrial and consumer paints including masonry, stucco paints, architectural wall and trim paints; stains, sealers and varnishes; wood coatings; floor coatings.

Typical Properties*

	PropylTex 100S	PropylTex 140S	PropylTex 200S	PropylTex 200SF
Mean Particle Size (µm)	80.0 - 100.0	45.0 - 50.0	35.0 - 45.0	25.0 - 35.0
Maximum Particle Size (µm)	149 (100 mesh)	105 (140 mesh)	74 (200 mesh)	74 (200 mesh)
Melting Point °C	160 - 170	160 - 170	160 - 170	160 - 170
Density @ 25 °C (g/cc)	0.89	0.89	0.89	0.89

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

Micro Powders

PropylTex® 100S-200S (medium texture grades)

Coarse particle size grades of micronized polypropylene for adding texture, structure and anti-slip properties to a wide variety of paints and coatings

Features and Benefits

- Provides a consistent medium textured coating surface
- Tough, high molecular weight polypropylene gives good film durability
- Does not lower COF; ideal for anti-skid surfaces
- Easy to disperse powder that can be incorporated with high speed mixing
- Adds texture in low bake (Low E) powder coatings

Composition

Polypropylene

Recommended Addition Levels

3.0-10.0% (on total formula weight)

Systems and Applications

Water based, solvent based, industrial and consumer paints including masonry, stucco paints, architectural wall and trim paints; stains, sealers and varnishes; wood coatings; floor coatings.

Typical Properties*

	PropylTex 100S	PropylTex 140S	PropylTex 200S	PropylTex 200SF
Mean Particle Size (µm)	80.0 - 100.0	45.0 - 50.0	35.0 - 45.0	25.0 - 35.0
Maximum Particle Size (µm)	149 (100 mesh)	105 (140 mesh)	74 (200 mesh)	74 (200 mesh)
Melting Point °C	160 - 170	160 - 170	160 - 170	160 - 170
Density @ 25 °C (g/cc)	0.89	0.89	0.89	0.89

Mar-26

Micro Powders

PropylTex® 100S-200S (medium texture grades)

Coarse particle size grades of micronized polypropylene for adding texture, structure and anti-slip properties to a wide variety of paints and coatings

Features and Benefits

- Provides a consistent medium textured coating surface
- Tough, high molecular weight polypropylene gives good film durability
- Does not lower COF; ideal for anti-skid surfaces
- Easy to disperse powder that can be incorporated with high speed mixing
- Adds texture in low bake (Low E) powder coatings

Composition

Polypropylene

Recommended Addition Levels

3.0-10.0% (on total formula weight)

Systems and Applications

Water based, solvent based, industrial and consumer paints including masonry, stucco paints, architectural wall and trim paints; stains, sealers and varnishes; wood coatings; floor coatings.

Typical Properties*

	PropylTex 100S	PropylTex 140S	PropylTex 200S	PropylTex 200SF
Mean Particle Size (µm)	80.0 - 100.0	45.0 - 50.0	35.0 - 45.0	25.0 - 35.0
Maximum Particle Size (µm)	149 (100 mesh)	105 (140 mesh)	74 (200 mesh)	74 (200 mesh)
Melting Point °C	160 - 170	160 - 170	160 - 170	160 - 170
Density @ 25 °C (g/cc)	0.89	0.89	0.89	0.89

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

TECHNICAL DATA

Micro Powders

PropylTex® 270S Series

Micronized polypropylene for reducing gloss and adding consistent surface texture and structure to a wide variety of paints and coatings

Features and Benefits

- Provides gloss reduction with improved burnish resistance vs. silica
- Adds a mild texture effect to the coating surface
- Tough, high molecular weight polypropylene gives good durability
- Does not lower COF; ideal for anti-skid surfaces
- Narrow cut mean particle size grades available for maximum texture control
- Adds texture in low bake (Low E) powder coatings

Composition

Polypropylene

Recommended Addition Levels

2.0-5.0% depending on the level of gloss reduction desired (on total formula weight)

Systems and Applications

Water based, solvent based, industrial coatings including metal, plastics and masonry, architectural wall and trim paints; stains, sealers and varnishes; wood coatings; floor coatings.

Typical Properties*

	PropylTex 270S	PropylTex 270S-1518	PropylTex 270S-16520
Mean Particle Size (µm)	18.5 - 23.0	15.0 - 18.0	16.5 - 20.0
Maximum Particle Size (µm)	53 (270 mesh)	53 (270 mesh)	53 (270 mesh)
Melting Point °C	160 - 170	160 - 170	160 - 170
Density @ 25 °C (g/cc)	0.89	0.89	0.89

PROPYLTEX 270S-16520 IS A MADE TO ORDER PRODUCT WITH MINIMUM ORDER QUANTITIES AND EXTENDED LEAD TIMES

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

TECHNICAL DATA

Micro Powders

PropylTex® 270S Series

Micronized polypropylene for reducing gloss and adding consistent surface texture and structure to a wide variety of paints and coatings

Features and Benefits

- Provides gloss reduction with improved burnish resistance vs. silica
- Adds a mild texture effect to the coating surface
- Tough, high molecular weight polypropylene gives good durability
- Does not lower COF; ideal for anti-skid surfaces
- Narrow cut mean particle size grades available for maximum texture control
- Adds texture in low bake (Low E) powder coatings

Composition

Polypropylene

Recommended Addition Levels

2.0-5.0% depending on the level of gloss reduction desired (on total formula weight)

Systems and Applications

Water based, solvent based, industrial coatings including metal, plastics and masonry, architectural wall and trim paints; stains, sealers and varnishes; wood coatings; floor coatings.

Typical Properties*

	PropylTex 270S	PropylTex 270S-1518	PropylTex 270S-16520
Mean Particle Size (µm)	18.5 - 23.0	15.0 - 18.0	16.5 - 20.0
Maximum Particle Size (µm)	53 (270 mesh)	53 (270 mesh)	53 (270 mesh)
Melting Point °C	160 - 170	160 - 170	160 - 170
Density @ 25 °C (g/cc)	0.89	0.89	0.89

PROPYLTEX 270S-16520 IS A MADE TO ORDER PRODUCT WITH MINIMUM ORDER QUANTITIES AND EXTENDED LEAD TIMES

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

TECHNICAL DATA

Micro Powders

PropylTex® 325S Series

Micronized polypropylene for reducing gloss and adding consistent surface texture and structure to a wide variety of paints and coatings

Features and Benefits

- Provides gloss reduction with improved burnish resistance vs. silica
- Adds a mild texture effect to the coating surface
- Tough, high molecular weight polypropylene gives good durability
- Does not lower COF; ideal for anti-skid surfaces
- Narrow cut mean particle size grade available for maximum texture control
- For a finer texture, try PropylMatte 31

Composition

Polypropylene

Recommended Addition Levels

2.0-5.0% depending on the level of gloss reduction desired (on total formula weight)

Systems and Applications

Water based, solvent based, industrial coatings including metal, plastics and masonry, architectural wall and trim paints; stains, sealers and varnishes; wood coatings; floor coatings.

Typical Properties*

	PropylTex 325S	PropylTex 325S-11125
Mean Particle Size (µm)	10.0 - 15.0	11.0 - 12.5
Maximum Particle Size (µm)	44 (325 mesh)	44 (325 mesh)
Melting Point °C	160 - 170	160 - 170
Density @ 25 °C (g/cc)	0.89	0.89

PROPYLTEX 325S-11125 IS A MADE TO ORDER PRODUCT WITH MINIMUM ORDER QUANTITIES AND EXTENDED LEAD TIMES

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com