Micro Powders

TECHNICAL DATA

PolyTuf® 1229

A highly engineered LDPE/ceramic/nanoceramic composite for abrasion resistance and surface durability

Features and Benefits

- High performance additive for maximizing surface abrasion resistance (Taber) and film toughness
- Fortified with two types of hard, inert ceramic particles
- Low density polyethylene provides superior surface toughness, durability and mar resistance
- Ideal for walking surfaces
- PTFE-free alternative to Polyfluo 900
- Easy to disperse fine powder that can be incorporated with high speed mixing

Composition

Ceramic modified polyethylene

Recommended Addition Levels

0.5-2.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, metal and masonry); architectural wall and trim paints; stains, sealers and varnishes; floor coatings; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings; rubber additives.

Typical Properties*

	PolyTuf 1229
Mean Particle Size (µm)	9.0 - 12.0
Maximum Particle Size (µm)	31.11
Melting Point °C	110 - 113
Density @ 25 °C (g/cc)	0.97
NPIRI Grind	4.0 - 6.0

This product is also available as a water based wax dispersion - Microspersion 1229-40

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

Micro Powders

MicroTouch 800 Series

Highly resilient spherical polyurethane beads that can modify the tactile properties of formulated coatings and inks while improving burnish, scratch and mar resistance

Features and Benefits

- Virtually indestructible elastic particles that distort when disturbed by a physical force and then return to their original spherical shape when the force is removed
- Provide different tactile effects ranging from satiny smooth to rubbery to leathery in properly formulated coatings
- Different particle sizes available to create a unique surface "touch"
- Improves burnish and abrasion resistance
- Effective gloss reduction

Composition

Aliphatic polyurethane

Recommended Addition Levels

2.0-10.0% (higher amounts when greater tactile effects are desired) (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, vinyl and leather); architectural wall and trim paints; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; soft touch coatings; floor coatings; visual effects.

Typical Properties*

	MicroTouch 800F	MicroTouch 800VF	MicroTouch 800XF	MicroTouch 800XXF
Mean Particle Size (µm)	22.0 - 30.0	11.0 - 15.0	6.0 - 9.0	3.0 - 5.0
Maximum Particle Size (µm)	120.00	60.00	31.00	15.00
Density @ 25 °C (g/cc)	1.05	1.05	1.05	1.05

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

Micro Powders

MP-28AL Series

Value engineered synthetic wax/aluminum oxide nanocomposites for surface durability and lubricity

Features and Benefits

- Improves scratch, scuff and mar resistance
- Adds surface slip and lubricity
- Choose XF grade for maximum gloss retention
- Choose G grade for maximum gloss reduction and burnish resistance
- Biodegradable to OECD 302C test standard
- Not a microplastic per ECHA definitions

Composition

Synthetic wax/aluminum oxide

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks, Industrial coatings (including plastic, metal and masonry); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings.

Typical Properties*

	MP-28AL-XF	MP-28AL	MP-28AL-G
Mean Particle Size (µm)	4.0 - 6.0	6.0 - 8.0	10.0 - 14.0
Maximum Particle Size (µm)	15.56	22.00	44.00
Melting Point °C	114 - 118	114 - 118	114 - 118
Density @ 25 °C (g/cc)	0.99	0.99	0.99
NPIRI Grind	1.0 - 2.0	1.5 - 3.0	N/A

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

Micro Powders

PropylTex® 270S Series

Micronized polypropylene for reducing gloss and adding consistent surface texture and structure to a wide variety of paints and coatings

Features and Benefits

- Provides gloss reduction with improved burnish resistance vs. silica
- Adds a mild texture effect to the coating surface
- Tough, high molecular weight polypropylene gives good durability
- Does not lower COF; ideal for anti-skid surfaces
- Narrow cut mean particle size grades available for maximum texture control
- Adds texture in low bake (Low E) powder coatings

Composition

Polypropylene

Recommended Addition Levels

2.0-5.0% depending on the level of gloss reduction desired (on total formula weight)

Systems and Applications

Water based, solvent based, industrial coatings including metal, plastics and masonry, architectural wall and trim paints; stains, sealers and varnishes; wood coatings; floor coatings.

Typical Properties*

	PropylTex 270S	PropylTex 270S-1518	PropylTex 270S-16520
Mean Particle Size (µm)	18.5 - 23.0	15.0 - 18.0	16.5 - 20.0
Maximum Particle Size (µm)	53 (270 mesh)	53 (270 mesh)	53 (270 mesh)
Melting Point °C	160 - 170	160 - 170	160 - 170
Density @ 25 °C (g/cc)	0.89	0.89	0.89

PROPYLTEX 270S-16520 IS A MADE TO ORDER PRODUCT WITH MINIMUM ORDER QUANTITIES AND EXTENDED LEAD TIMES

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

Micro Powders

PropylMatte 31HD

Finely micronized densified polypropylene for consistent matting and gloss control with superior in-can stability in water based paints, coatings and inks

Features and Benefits

- Efficient gloss reduction from satin to matte finish
- Improves burnish resistance vs. silica mattifiers
- Particle density optimized to essentially eliminate flotation or settling in most water based systems
- Imparts anti-slip properties
- For more efficient matting with a fine microtexture, try PropylTex 325HD/270HD

Composition

Densified polypropylene

Recommended Addition Levels

2.0-5.0% depending on the level of gloss reduction desired (on total formula weight)

Systems and Applications

Water based and energy curable coatings and inks. Industrial coatings (including plastic, metal, masonry and leather); architectural wall and trim paints; stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); interior and exterior can and container coatings; coil coatings; floor coatings.

Typical Properties*

	PropylMatte 31HD
Mean Particle Size (µm)	8.0 - 12.0
Maximum Particle Size (µm)	31.00
Melting Point °C	160 - 170
Density @ 25 °C (g/cc)	1.07
NPIRI Grind	5.0 - 6.0

This product is also available as a water based wax dispersion - Microspersion 31HD-40

Mar-26

MPI Micro Powders

TECHNICAL DATA

PolyGlide 1226XF

A highly engineered HDPE/ceramic/nanoceramic composite for abrasion resistance and lubricity

Features and Benefits

- HDPE composite reinforced with hard, inert ceramic microspheres and nanoceramic platelets
- Improved Taber abrasion resistance when compared to PE/PTFE additives
- Provides slip and lubricity
- Ideal for can and container coatings; 21CFR 175.300 approved
- Effective replacement for PTFE additives
- Compare to (coarser) Polyfluo 900

Composition

HDPE/ceramic

Recommended Addition Levels

0.5-1.5% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic and metal); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; can, container, and coil coatings; rubber additives.

Typical Properties*

	PolyGlide 1226XF
Mean Particle Size (µm)	3.5 - 5.5
Maximum Particle Size (µm)	15.56
Melting Point °C	109 - 115
Density @ 25 °C (g/cc)	0.99
NPIRI Grind	1.0 - 2.0

This product is also available as a water based wax dispersion - Microspersion 1226XF-50

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

Micro Powders

MPP-620

High performance micronized polyethylene wax which provides a unique combination of surface slip, abrasion/rub resistance, and antiblocking in a wide variety of coatings and inks

Features and Benefits

- Imparts excellent abrasion, rub and mar resistance with good surface slip
- Provides excellent antiblocking properties
- Adds heat resistance
- Better resistance to solvent absorption and swelling when compared to Synthetic wax

Composition

High density polyethylene

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic and metal); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; coil coatings.

Typical Properties*

	MPP-620VF	MPP-620XF	MPP-620XXF
Mean Particle Size (µm)	5.0 - 7.0	4.5 - 5.5	4.25 - 4.75
Maximum Particle Size (µm)	22.00	22.00	12.00
Melting Point °C	120 - 124	120 - 124	120 - 124
Density @ 25 °C (g/cc)	0.96	0.96	0.96
NPIRI Grind	2.0 - 3.0	1.0 - 2.0	1.0 - 1.5

This product is also available as a water based wax dispersion - Microspersion 620VF-50

Mar-26

TECHNICAL DATA

Micro Powders

MP-28AL Series

Value engineered synthetic wax/aluminum oxide nanocomposites for surface durability and lubricity

Features and Benefits

- Improves scratch, scuff and mar resistance
- Adds surface slip and lubricity
- Choose XF grade for maximum gloss retention
- Choose G grade for maximum gloss reduction and burnish resistance
- Biodegradable to OECD 302C test standard
- Not a microplastic per ECHA definitions

Composition

Synthetic wax/aluminum oxide

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks, Industrial coatings (including plastic, metal and masonry); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings.

Typical Properties*

	MP-28AL-XF	MP-28AL	MP-28AL-G
Mean Particle Size (µm)	4.0 - 6.0	6.0 - 8.0	10.0 - 14.0
Maximum Particle Size (µm)	15.56	22.00	44.00
Melting Point °C	114 - 118	114 - 118	114 - 118
Density @ 25 °C (g/cc)	0.99	0.99	0.99
NPIRI Grind	1.0 - 2.0	1.5 - 3.0	N/A

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

TECHNICAL DATA

Micro Powders

MicroTouch 800 Series

Highly resilient spherical polyurethane beads that can modify the tactile properties of formulated coatings and inks while improving burnish, scratch and mar resistance

Features and Benefits

- Virtually indestructible elastic particles that distort when disturbed by a physical force and then return to their original spherical shape when the force is removed
- Provide different tactile effects ranging from satiny smooth to rubbery to leathery in properly formulated coatings
- Different particle sizes available to create a unique surface "touch"
- Improves burnish and abrasion resistance
- Effective gloss reduction

Composition

Aliphatic polyurethane

Recommended Addition Levels

2.0-10.0% (higher amounts when greater tactile effects are desired) (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, vinyl and leather); architectural wall and trim paints; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; soft touch coatings; floor coatings; visual effects.

Typical Properties*

	MicroTouch 800F	MicroTouch 800VF	MicroTouch 800XF	MicroTouch 800XXF
Mean Particle Size (µm)	22.0 - 30.0	11.0 - 15.0	6.0 - 9.0	3.0 - 5.0
Maximum Particle Size (µm)	120.00	60.00	31.00	15.00
Density @ 25 °C (g/cc)	1.05	1.05	1.05	1.05

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

Micro Powders

MP-28AL Series

Value engineered synthetic wax/aluminum oxide nanocomposites for surface durability and lubricity

Features and Benefits

- Improves scratch, scuff and mar resistance
- Adds surface slip and lubricity
- Choose XF grade for maximum gloss retention
- Choose G grade for maximum gloss reduction and burnish resistance
- Biodegradable to OECD 302C test standard
- Not a microplastic per ECHA definitions

Composition

Synthetic wax/aluminum oxide

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks, Industrial coatings (including plastic, metal and masonry); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings.

Typical Properties*

	MP-28AL-XF	MP-28AL	MP-28AL-G
Mean Particle Size (µm)	4.0 - 6.0	6.0 - 8.0	10.0 - 14.0
Maximum Particle Size (µm)	15.56	22.00	44.00
Melting Point °C	114 - 118	114 - 118	114 - 118
Density @ 25 °C (g/cc)	0.99	0.99	0.99
NPIRI Grind	1.0 - 2.0	1.5 - 3.0	N/A

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

Micro Powders

Superslip 6515AL

A highly engineered HDPE/EBS/aluminum oxide nanocomposite for maximum scratch, scuff and block resistance

Features and Benefits

- Maximum scratch resistance; equal to PE/PTFE additives
- HDPE/EBS composite reinforced with 300 nm aluminum oxide nanoparticles (Mohs Hardness 9)
- Good abrasion resistance with slip and lubricity
- Amide wax component provides excellent antiblocking and release properties
- Ideal for can and container coatings; 21CFR 175.300 approved

Composition

HDPE/EBS/aluminum oxide

Renewable Carbon Index

>90%

Recommended Addition Levels

0.5-1.5% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic and metal); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; can, container, and coil coatings; rubber additives.

Typical Properties*

	Superslip 6515AL
Mean Particle Size (µm)	3.5 - 5.5
Maximum Particle Size (µm)	15.56
Melting Point °C	139 - 145
Density @ 25 °C (g/cc)	0.99
NPIRI Grind	1.0 - 2.0

This product is also available as a water based wax dispersion - Microspersion 6515AL-40

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

TECHNICAL DATA

MPP-611AL

A highly engineered HDPE/aluminum oxide nanocomposite for unsurpassed scratch and scuff resistance

Features and Benefits

- Maximum scratch and scuff resistance with slip and lubricity
- HDPE composite reinforced with 300 nm aluminum oxide nanoparticles (Mohs Hardness 9)
- Easier-to-disperse nanotechnology in a safe, non-nano powder
- Composite particle density maximizes efficiency and minimizes settling
- Effective replacement for PTFE additives

Composition

HDPE/aluminum oxide

Recommended Addition Levels

0.5-1.5% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic and metal); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings; rubber additives.

Typical Properties*

	MPP-611AL
Mean Particle Size (µm)	3.5 - 5.5
Maximum Particle Size (µm)	15.56
Melting Point °C	110 - 116
Density @ 25 °C (g/cc)	0.99
NPIRI Grind	1.0 - 2.0

This product is also available as a water based wax dispersion - Microspersion 611AL-50

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

Micro Powders

MicroMatte® 1415-EZ

A multifunctional matting additive that improves soil release and dirt pickup resistance in architectural coatings

Features and Benefits

- Complex wax composite dramatically improves DPUR vs. inorganic flattening agents
- Provides efficient gloss reduction
- Improves burnish resistance
- Surface treated for easy incorporation into waterbased systems
- Particle density provides optimal in-can stability
- Not a microplastic per ECHA definitions

Composition

Densified modified synthetic wax

Recommended Addition Levels

1.0 - 4.0% (on total formula weight)

Systems and Applications

Water based architectural wall and trim paints; stains, sealers and varnishes; wood coatings.

Typical Properties*

	MicroMatte 1415-EZ
Mean Particle Size (µm)	10.0 - 15.0
Maximum Particle Size (µm)	44 (325 mesh)
Melting Point °C	136 - 140
Density @ 25 °C (g/cc)	1.06

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

Micro Powders

PropylMatte 31

Finely micronized polypropylene for efficient matting and gloss control in paints, coatings and inks

Features and Benefits

- Provides consistent gloss reduction with no effect on coating viscosity
- Tough, high molecular weight polymer imparts burnish and abrasion resistance
- Imparts anti-slip properties
- Density (0.89) ideal for solvent based systems
- For more efficient matting with a fine microtexture, try PropylTex 325S/270S
- Adds texture in low bake (Low E) powder coatings

Composition

Polypropylene

Recommended Addition Levels

2.0-5.0% depending on the level of gloss reduction desired (on total formula weight)

Systems and Applications

Water based and solvent based coatings. Industrial coatings (including plastic, metal and leather); architectural wall and trim paints; stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings.

Typical Properties*

	PropylMatte 31
Mean Particle Size (µm)	8.0 - 12.0
Maximum Particle Size (µm)	31.00
Melting Point °C	160 - 170
Density @ 25 °C (g/cc)	0.89
NPIRI Grind	5.0 - 6.0

This product is also available as a water based wax dispersion - Microspersion 31-35

Mar-26

Micro Powders

MPP-620AL-XF

A highly engineered polyethylene/aluminum oxide nanocomposite that provides slip, abrasion/rub resistance, and antiblocking

Features and Benefits

- Maximum scratch and scuff resistance with slip and lubricity
- HDPE composite reinforced with 300 nm aluminum oxide nanoparticles (Mohs Hardness 9)
- Easier-to-disperse nanotechnology in a safe, non-nano powder
- Composite particle density maximizes efficiency and minimizes settling
- Effective replacement for PTFE additives

Composition

High density polyethylene/aluminum oxide

Recommended Addition Levels

0.5-1.5% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic and metal); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings; rubber additives.

Typical Properties*

	MPP-620AL-XF
Mean Particle Size (µm)	3.5 - 5.5
Maximum Particle Size (µm)	15.56
Melting Point °C	120 - 124
Density @ 25 °C (g/cc)	1.00
NPIRI Grind	1.0 - 2.0

Mar-26

Micro Powders | 580 White Plains Road | Tarrytown, NY 10591 | 914-793-4058 | micropowders.com

TECHNICAL DATA

Micro Powders

PropylTex® 325S Series

Micronized polypropylene for reducing gloss and adding consistent surface texture and structure to a wide variety of paints and coatings

Features and Benefits

- Provides gloss reduction with improved burnish resistance vs. silica
- Adds a mild texture effect to the coating surface
- Tough, high molecular weight polypropylene gives good durability
- Does not lower COF; ideal for anti-skid surfaces
- Narrow cut mean particle size grade available for maximum texture control
- For a finer texture, try PropylMatte 31

Composition

Polypropylene

Recommended Addition Levels

2.0-5.0% depending on the level of gloss reduction desired (on total formula weight)

Systems and Applications

Water based, solvent based, industrial coatings including metal, plastics and masonry, architectural wall and trim paints; stains, sealers and varnishes; wood coatings; floor coatings.

Typical Properties*

	PropylTex 325S	PropylTex 325S-11125
Mean Particle Size (µm)	10.0 - 15.0	11.0 - 12.5
Maximum Particle Size (µm)	44 (325 mesh)	44 (325 mesh)
Melting Point °C	160 - 170	160 - 170
Density @ 25 °C (g/cc)	0.89	0.89

PROPYLTEX 325S-11125 IS A MADE TO ORDER PRODUCT WITH MINIMUM ORDER QUANTITIES AND EXTENDED LEAD TIMES

Mar-26