

PropylTex® 270S Series

Micronized polypropylene for reducing gloss and adding consistent surface texture and structure to a wide variety of paints and coatings

Features and Benefits

- Provides gloss reduction with improved burnish resistance vs. silica
- Adds a mild texture effect to the coating surface
- Tough, high molecular weight polypropylene gives good durability
- Does not lower COF; ideal for anti-skid surfaces
- Narrow cut mean particle size grades available for maximum texture control
- Adds texture in low bake (Low E) powder coatings

Composition

Polypropylene

Recommended Addition Levels

2.0-5.0% depending on the level of gloss reduction desired (on total formula weight)

Systems and Applications

Water based, solvent based, industrial coatings including metal, plastics and masonry, architectural wall and trim paints; stains, sealers and varnishes; wood coatings; floor coatings.

Typical Properties*

	<u>PropylTex 270S</u>	<u>PropylTex 270S-1518</u>	<u>PropylTex 270S-16520</u>
Mean Particle Size (µm)	18.5 - 23.0	15.0 - 18.0	16.5 - 20.0
Maximum Particle Size (µm)	53 (270 mesh)	53 (270 mesh)	53 (270 mesh)
Melting Point °C	160 - 170	160 - 170	160 - 170
Density @ 25 °C (g/cc)	0.89	0.89	0.89

PROPYLTEX 270S-16520 IS A MADE TO ORDER PRODUCT WITH MINIMUM ORDER QUANTITIES AND EXTENDED LEAD TIMES

Mar-26

PropylTex® 325S Series

Micronized polypropylene for reducing gloss and adding consistent surface texture and structure to a wide variety of paints and coatings

Features and Benefits

- Provides gloss reduction with improved burnish resistance vs. silica
- Adds a mild texture effect to the coating surface
- Tough, high molecular weight polypropylene gives good durability
- Does not lower COF; ideal for anti-skid surfaces
- Narrow cut mean particle size grade available for maximum texture control
- For a finer texture, try PropylMatte 31

Composition

Polypropylene

Recommended Addition Levels

2.0-5.0% depending on the level of gloss reduction desired (on total formula weight)

Systems and Applications

Water based, solvent based, industrial coatings including metal, plastics and masonry, architectural wall and trim paints; stains, sealers and varnishes; wood coatings; floor coatings.

Typical Properties*

	<u>PropylTex 325S</u>	<u>PropylTex 325S-11125</u>
Mean Particle Size (µm)	10.0 - 15.0	11.0 - 12.5
Maximum Particle Size (µm)	44 (325 mesh)	44 (325 mesh)
Melting Point °C	160 - 170	160 - 170
Density @ 25 °C (g/cc)	0.89	0.89

PROPYLTEX 325S-11125 IS A MADE TO ORDER PRODUCT WITH MINIMUM ORDER QUANTITIES AND EXTENDED LEAD TIMES

Mar-26

MicroTouch 800 Series

Highly resilient spherical polyurethane beads that can modify the tactile properties of formulated coatings and inks while improving burnish, scratch and mar resistance

Features and Benefits

- Virtually indestructible elastic particles that distort when disturbed by a physical force and then return to their original spherical shape when the force is removed
- Provide different tactile effects ranging from satiny smooth to rubbery to leathery in properly formulated coatings
- Different particle sizes available to create a unique surface "touch"
- Improves burnish and abrasion resistance
- Effective gloss reduction

Composition

Aliphatic polyurethane

Recommended Addition Levels

2.0-10.0% (higher amounts when greater tactile effects are desired) (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, vinyl and leather); architectural wall and trim paints; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; soft touch coatings; floor coatings; visual effects.

Typical Properties*

	<u>MicroTouch 800F</u>	<u>MicroTouch 800VF</u>	<u>MicroTouch 800XF</u>	<u>MicroTouch 800XXF</u>
Mean Particle Size (µm)	22.0 - 30.0	11.0 - 15.0	6.0 - 9.0	3.0 - 5.0
Maximum Particle Size (µm)	120.00	60.00	31.00	15.00
Density @ 25 °C (g/cc)	1.05	1.05	1.05	1.05

Mar-26

MicroTouch 800 Series

Highly resilient spherical polyurethane beads that can modify the tactile properties of formulated coatings and inks while improving burnish, scratch and mar resistance

Features and Benefits

- Virtually indestructible elastic particles that distort when disturbed by a physical force and then return to their original spherical shape when the force is removed
- Provide different tactile effects ranging from satiny smooth to rubbery to leathery in properly formulated coatings
- Different particle sizes available to create a unique surface "touch"
- Improves burnish and abrasion resistance
- Effective gloss reduction

Composition

Aliphatic polyurethane

Recommended Addition Levels

2.0-10.0% (higher amounts when greater tactile effects are desired) (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, vinyl and leather); architectural wall and trim paints; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; soft touch coatings; floor coatings; visual effects.

Typical Properties*

	<u>MicroTouch 800F</u>	<u>MicroTouch 800VF</u>	<u>MicroTouch 800XF</u>	<u>MicroTouch 800XXF</u>
Mean Particle Size (µm)	22.0 - 30.0	11.0 - 15.0	6.0 - 9.0	3.0 - 5.0
Maximum Particle Size (µm)	120.00	60.00	31.00	15.00
Density @ 25 °C (g/cc)	1.05	1.05	1.05	1.05

Mar-26

PropylMatte 31

Finely micronized polypropylene for efficient matting and gloss control in paints, coatings and inks

Features and Benefits

- Provides consistent gloss reduction with no effect on coating viscosity
- Tough, high molecular weight polymer imparts burnish and abrasion resistance
- Imparts anti-slip properties
- Density (0.89) ideal for solvent based systems
- For more efficient matting with a fine microtexture, try PropylTex 325S/270S
- Adds texture in low bake (Low E) powder coatings

Composition

Polypropylene

Recommended Addition Levels

2.0-5.0% depending on the level of gloss reduction desired (on total formula weight)

Systems and Applications

Water based and solvent based coatings. Industrial coatings (including plastic, metal and leather); architectural wall and trim paints; stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings.

Typical Properties*

	<u>PropylMatte 31</u>
Mean Particle Size (µm)	8.0 - 12.0
Maximum Particle Size (µm)	31.00
Melting Point °C	160 - 170
Density @ 25 °C (g/cc)	0.89
NPIRI Grind	5.0 - 6.0

This product is also available as a water based wax dispersion - Microspersion 31-35

Mar-26



PropylMatte 31HD

Finely micronized densified polypropylene for consistent matting and gloss control with superior in-can stability in water based paints, coatings and inks

Features and Benefits

- Efficient gloss reduction from satin to matte finish
- Improves burnish resistance vs. silica mattifiers
- Particle density optimized to essentially eliminate flotation or settling in most water based systems
- Imparts anti-slip properties
- For more efficient matting with a fine microtexture, try PropylTex 325HD/270HD

Composition

Densified polypropylene

Recommended Addition Levels

2.0-5.0% depending on the level of gloss reduction desired (on total formula weight)

Systems and Applications

Water based and energy curable coatings and inks. Industrial coatings (including plastic, metal, masonry and leather); architectural wall and trim paints; stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); interior and exterior can and container coatings; coil coatings; floor coatings.

Typical Properties*

	<u>PropylMatte 31HD</u>
Mean Particle Size (µm)	8.0 - 12.0
Maximum Particle Size (µm)	31.00
Melting Point °C	160 - 170
Density @ 25 °C (g/cc)	1.07
NPIRI Grind	5.0 - 6.0

This product is also available as a water based wax dispersion - Microspersion 31HD-40

Mar-26

Micropro 400

Modified high melt point hybrid polypropylene wax for consistent gloss control with surface slip, mar and abrasion resistance

Features and Benefits

- Improves mar, scratch and metal marking resistance
- Effective gloss control agent with good burnish resistance in low or medium gloss finishes
- Provides antiblocking properties
- Low density will keep silica matting additives in suspension
- Easy to disperse in both polar and non-polar systems

Composition

Modified polypropylene

Recommended Addition Levels

0.5-2.0% (mar and abrasion resistance); 2.0-5.0% (gloss control) (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, metal and leather); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; floor coatings.

Typical Properties*

	<u>Micropro 400</u>
Mean Particle Size (µm)	4.5 - 7.5
Maximum Particle Size (µm)	22.00
Melting Point °C	140 - 143
Density @ 25 °C (g/cc)	0.94
NPIRI Grind	2.0 - 3.5

Mar-26

Micropro 440W

Modified polypropylene wax for consistent gloss control with mar and abrasion resistance, specifically formulated for stability in water based paints and coatings

Features and Benefits

- Improves mar, scratch and metal marking resistance
- Uniform gloss reduction with good burnish resistance in low or medium gloss finishes
- Imparts a smooth surface "feel"
- Will not powder or chalk in exterior applications
- Low density will keep silica matting additives in suspension

Composition

Modified polypropylene

Recommended Addition Levels

0.5-2.0% (mar and abrasion resistance); 2.0-5.0% (gloss control) (on total formula weight)

Systems and Applications

Water based coatings and inks. Industrial coatings (including plastic, metal and leather); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; floor coatings.

Typical Properties*

	<u>Micropro 440W</u>
Mean Particle Size (µm)	7.0 - 10.0
Maximum Particle Size (µm)	31.00
Melting Point °C	150 - 156
Density @ 25 °C (g/cc)	0.97
NPIRI Grind	3.0 - 5.0

This product is also available as a water based wax dispersion - Microspersion 440W

Mar-26



MicroMatte® 1415-EZ

A multifunctional matting additive that improves soil release and dirt pickup resistance in architectural coatings

Features and Benefits

- Complex wax composite dramatically improves DPUR vs. inorganic flattening agents
- Provides efficient gloss reduction
- Improves burnish resistance
- Surface treated for easy incorporation into waterbased systems
- Particle density provides optimal in-can stability
- Not a microplastic per ECHA definitions

Composition

Densified modified synthetic wax

Recommended Addition Levels

1.0 - 4.0% (on total formula weight)

Systems and Applications

Water based architectural wall and trim paints; stains, sealers and varnishes; wood coatings.

Typical Properties*

	<u>MicroMatte 1415-EZ</u>
Mean Particle Size (µm)	10.0 - 15.0
Maximum Particle Size (µm)	44 (325 mesh)
Melting Point °C	136 - 140
Density @ 25 °C (g/cc)	1.06

Mar-26

AquaPoly 511

A unique micronized oxidized polyethylene wax composite for improved scuff and mar resistance in aqueous and solvent based systems

Features and Benefits

- A synergistic blend of high molecular weight waxes including polyethylene
- Provides optimum levels of scuff and mar resistance along with excellent slip and mobility
- Easy to disperse fine powder that can be incorporated into aqueous paints, inks and coatings with high speed mixing
- Compare to AquaPolyfluo 411 (without PTFE)

Composition

Modified oxidized HDPE

Recommended Addition Levels

0.5-2.0% (on total formula weight)

Systems and Applications

Solvent and water based coatings. Industrial coatings (including plastic, metal and leather); architectural wall and trim paints; stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); coil coatings.

Typical Properties*

	<u>AquaPoly 511</u>
Mean Particle Size (µm)	6.0 - 8.0
Maximum Particle Size (µm)	22.00
Melting Point °C	117 - 123
Density @ 25 °C (g/cc)	0.97
NPIRI Grind	2.5 - 3.5

Mar-26

MP-22

High performance, versatile grade of micronized synthetic wax for improved slip, scratch and rub resistance in a wide variety of paints, coatings and inks

Features and Benefits

- Imparts a high degree of lubricity and slip with rub and mar resistance
- Provides antiblocking properties
- Gives long-lasting water beading and weather resistance to exterior alkyd-based stains
- Consider MP-22C & MP-28C (spherical) for improved surface slip
- Biodegradable to OECD 302C test standard
- Not a microplastic per ECHA definitions

Composition

Synthetic wax

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, metal and masonry); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; coil coatings; powdered metals.

Typical Properties*

	<u>MP-22</u>	<u>MP-22VF</u>	<u>MP-22XF</u>	<u>MP-22XXF</u>
Mean Particle Size (µm)	7.0 - 10.0	6.0 - 8.0	4.5 - 6.5	3.75 - 5.75
Maximum Particle Size (µm)	31.00	22.00	22.00	15.56
Melting Point °C	110 - 115	110 - 115	110 - 115	110 - 115
Density @ 25 °C (g/cc)	0.93	0.93	0.93	0.93
NPIRI Grind	4.0 - 6.0	2.0 - 3.5	1.5 - 3.0	1.0 - 2.3

This product is also available as a water based wax dispersion - Microspersion 22-50

Mar-26

MPP-620

High performance micronized polyethylene wax which provides a unique combination of surface slip, abrasion/rub resistance, and antiblocking in a wide variety of coatings and inks

Features and Benefits

- Imparts excellent abrasion, rub and mar resistance with good surface slip
- Provides excellent antiblocking properties
- Adds heat resistance
- Better resistance to solvent absorption and swelling when compared to Synthetic wax

Composition

High density polyethylene

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic and metal); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; coil coatings.

Typical Properties*

	<u>MPP-620VF</u>	<u>MPP-620XF</u>	<u>MPP-620XXF</u>
Mean Particle Size (µm)	5.0 - 7.0	4.5 - 5.5	4.25 - 4.75
Maximum Particle Size (µm)	22.00	22.00	12.00
Melting Point °C	120 - 124	120 - 124	120 - 124
Density @ 25 °C (g/cc)	0.96	0.96	0.96
NPIRI Grind	2.0 - 3.0	1.0 - 2.0	1.0 - 1.5

This product is also available as a water based wax dispersion - Microspersion 620VF-50

Mar-26

AquaBead® 519

A specially formulated wax composite that provides immediate water repellency and weather resistance

Features and Benefits

- Imparts immediate water beading
- Provides long-lasting water repellency
- Contains lower molecular weight polymers for faster water beading in water based and solvent based penetrating stains
- Combine with silica to improve weather resistance

Composition

Hydrophobically modified synthetic wax

Recommended Addition Levels

1.0-4.0% (on total formula weight)

Systems and Applications

Water based and solvent based coatings. Industrial coatings (including metal and masonry); stains, sealers and varnishes; wood coatings; automotive polishes.

Typical Properties*

	<u>AquaBead 519</u>
Mean Particle Size (µm)	5.5 - 8.0
Maximum Particle Size (µm)	22.00
Melting Point °C	126 - 132
Density @ 25 °C (g/cc)	0.94
NPIRI Grind	2.0 - 3.0

This product is also available as a water based wax dispersion - Microspersion 519

Mar-26



Spherex™ Series

Hard, monosized spherical powders that improve surface durability with stain and moisture resistance

Features and Benefits

- Superior scratch and abrasion resistance with high coefficient of friction
- Improved stain and moisture resistance at dosages of 2.0 - 8.0%
- Spherex 200 lowers gloss and improves burnish resistance in architectural paints
- Spherex 200XF ideal for gloss reduction and surface protection in wood and leather coatings
- Improves edge coverage in powder coatings, especially on sharp corners and weld seams
- Outstanding UV stability

Composition

Acrylic

Recommended Addition Levels

0.5-8.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings. Floor coatings. Powder coatings. Leather coatings. Architectural wall and trim paints, stains, sealers and varnishes. Interior and exterior can and container coatings. Coil coatings. Wood coatings. Printing inks and OPV's.

Typical Properties*

	<u>Spherex 200</u>	<u>Spherex 200XF</u>
Mean Particle Size (µm)	18.5 - 21.5	5.5 - 6.5
Maximum Particle Size (µm)	24.00	8.00
Degradation °C	> 260	> 260
Density @ 25 °C (g/cc)	1.20	1.20

Apr-26



Spherex™ Series

Hard, monosized spherical powders that improve surface durability with stain and moisture resistance

Features and Benefits

- Superior scratch and abrasion resistance with high coefficient of friction
- Improved stain and moisture resistance at dosages of 2.0 - 8.0%
- Spherex 200 lowers gloss and improves burnish resistance in architectural paints
- Spherex 200XF ideal for gloss reduction and surface protection in wood and leather coatings
- Improves edge coverage in powder coatings, especially on sharp corners and weld seams
- Outstanding UV stability

Composition

Acrylic

Recommended Addition Levels

0.5-8.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings. Floor coatings. Powder coatings. Leather coatings. Architectural wall and trim paints, stains, sealers and varnishes. Interior and exterior can and container coatings. Coil coatings. Wood coatings. Printing inks and OPV's.

Typical Properties*

	<u>Spherex 200</u>	<u>Spherex 200XF</u>
Mean Particle Size (µm)	18.5 - 21.5	5.5 - 6.5
Maximum Particle Size (µm)	24.00	8.00
Degradation °C	> 260	> 260
Density @ 25 °C (g/cc)	1.20	1.20

Apr-26

MP-28AL Series

Value engineered synthetic wax/aluminum oxide nanocomposites for surface durability and lubricity

Features and Benefits

- Improves scratch, scuff and mar resistance
- Adds surface slip and lubricity
- Choose XF grade for maximum gloss retention
- Choose G grade for maximum gloss reduction and burnish resistance
- Biodegradable to OECD 302C test standard
- Not a microplastic per ECHA definitions

Composition

Synthetic wax/aluminum oxide

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks, Industrial coatings (including plastic, metal and masonry); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings.

Typical Properties*

	<u>MP-28AL-XF</u>	<u>MP-28AL</u>	<u>MP-28AL-G</u>
Mean Particle Size (µm)	4.0 - 6.0	6.0 - 8.0	10.0 - 14.0
Maximum Particle Size (µm)	15.56	22.00	44.00
Melting Point °C	114 - 118	114 - 118	114 - 118
Density @ 25 °C (g/cc)	0.99	0.99	0.99
NPIRI Grind	1.0 - 2.0	1.5 - 3.0	N/A

Mar-26

MP-28AL Series

Value engineered synthetic wax/aluminum oxide nanocomposites for surface durability and lubricity

Features and Benefits

- Improves scratch, scuff and mar resistance
- Adds surface slip and lubricity
- Choose XF grade for maximum gloss retention
- Choose G grade for maximum gloss reduction and burnish resistance
- Biodegradable to OECD 302C test standard
- Not a microplastic per ECHA definitions

Composition

Synthetic wax/aluminum oxide

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks, Industrial coatings (including plastic, metal and masonry); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings.

Typical Properties*

	<u>MP-28AL-XF</u>	<u>MP-28AL</u>	<u>MP-28AL-G</u>
Mean Particle Size (µm)	4.0 - 6.0	6.0 - 8.0	10.0 - 14.0
Maximum Particle Size (µm)	15.56	22.00	44.00
Melting Point °C	114 - 118	114 - 118	114 - 118
Density @ 25 °C (g/cc)	0.99	0.99	0.99
NPIRI Grind	1.0 - 2.0	1.5 - 3.0	N/A

Mar-26

MP-28AL Series

Value engineered synthetic wax/aluminum oxide nanocomposites for surface durability and lubricity

Features and Benefits

- Improves scratch, scuff and mar resistance
- Adds surface slip and lubricity
- Choose XF grade for maximum gloss retention
- Choose G grade for maximum gloss reduction and burnish resistance
- Biodegradable to OECD 302C test standard
- Not a microplastic per ECHA definitions

Composition

Synthetic wax/aluminum oxide

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks, Industrial coatings (including plastic, metal and masonry); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings.

Typical Properties*

	<u>MP-28AL-XF</u>	<u>MP-28AL</u>	<u>MP-28AL-G</u>
Mean Particle Size (µm)	4.0 - 6.0	6.0 - 8.0	10.0 - 14.0
Maximum Particle Size (µm)	15.56	22.00	44.00
Melting Point °C	114 - 118	114 - 118	114 - 118
Density @ 25 °C (g/cc)	0.99	0.99	0.99
NPIRI Grind	1.0 - 2.0	1.5 - 3.0	N/A

Mar-26

MPP-611AL

A highly engineered HDPE/aluminum oxide nanocomposite for unsurpassed scratch and scuff resistance

Features and Benefits

- Maximum scratch and scuff resistance with slip and lubricity
- HDPE composite reinforced with 300 nm aluminum oxide nanoparticles (Mohs Hardness 9)
- Easier-to-disperse nanotechnology in a safe, non-nano powder
- Composite particle density maximizes efficiency and minimizes settling
- Effective replacement for PTFE additives

Composition

HDPE/aluminum oxide

Recommended Addition Levels

0.5-1.5% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic and metal); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings; rubber additives.

Typical Properties*

	<u>MPP-611AL</u>
Mean Particle Size (µm)	3.5 - 5.5
Maximum Particle Size (µm)	15.56
Melting Point °C	110 - 116
Density @ 25 °C (g/cc)	0.99
NPIRI Grind	1.0 - 2.0

This product is also available as a water based wax dispersion - Microspersion 611AL-50

Mar-26

MPP-620AL-XF

A highly engineered polyethylene/aluminum oxide nanocomposite that provides slip, abrasion/rub resistance, and antiblocking

Features and Benefits

- Maximum scratch and scuff resistance with slip and lubricity
- HDPE composite reinforced with 300 nm aluminum oxide nanoparticles (Mohs Hardness 9)
- Easier-to-disperse nanotechnology in a safe, non-nano powder
- Composite particle density maximizes efficiency and minimizes settling
- Effective replacement for PTFE additives

Composition

High density polyethylene/aluminum oxide

Recommended Addition Levels

0.5-1.5% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic and metal); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings; rubber additives.

Typical Properties*

	<u>MPP-620AL-XF</u>
Mean Particle Size (µm)	3.5 - 5.5
Maximum Particle Size (µm)	15.56
Melting Point °C	120 - 124
Density @ 25 °C (g/cc)	1.00
NPIRI Grind	1.0 - 2.0

Mar-26

MicroKlear 418AL

Aluminum oxide modified carnauba wax for maximum scratch resistance with surface slip, clarity and gloss retention. Also useful as an additive in seed coatings

Features and Benefits

- Carnauba wax composite reinforced with 300 nm aluminum oxide nanoparticles (Mohs Hardness 9)
- Provides maximum scratch resistance with surface lubricity
- Does not adversely affect clarity or gloss
- Easier-to-disperse nanotechnology in a safe, non-nano powder
- Composite wax/aluminum oxide particle is less abrasive on processing equipment compared to free aluminum oxide
- Effective replacement for PTFE additives

Composition

Carnauba wax/aluminum oxide

Renewable Carbon Index

>95%

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, metal and leather); wood coatings; printing inks and OPV's (including flexo and gravure); interior and exterior can and container coatings; coil coatings; seed coatings.

Typical Properties*

	<u>MicroKlear 418AL</u>
Mean Particle Size (µm)	6.0 - 8.0
Maximum Particle Size (µm)	22.00
Melting Point °C	81 - 86
Density @ 25 °C (g/cc)	1.04
NPIRI Grind	2.0 - 3.5

This product is also available as a water based wax dispersion - Microspersion 418AL-40

Mar-26

Superslip 6515AL

A highly engineered HDPE/EBS/aluminum oxide nanocomposite for maximum scratch, scuff and block resistance

Features and Benefits

- Maximum scratch resistance; equal to PE/PTFE additives
- HDPE/EBS composite reinforced with 300 nm aluminum oxide nanoparticles (Mohs Hardness 9)
- Good abrasion resistance with slip and lubricity
- Amide wax component provides excellent antiblocking and release properties
- Ideal for can and container coatings; 21CFR 175.300 approved

Composition

HDPE/EBS/aluminum oxide

Renewable Carbon Index

>90%

Recommended Addition Levels

0.5-1.5% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic and metal); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; can, container, and coil coatings; rubber additives.

Typical Properties*

	<u>Superslip 6515AL</u>
Mean Particle Size (µm)	3.5 - 5.5
Maximum Particle Size (µm)	15.56
Melting Point °C	139 - 145
Density @ 25 °C (g/cc)	0.99
NPIRI Grind	1.0 - 2.0

This product is also available as a water based wax dispersion - Microspersion 6515AL-40

Mar-26

SuperGlide 1231

A value engineered ceramic-modified amide wax for superior surface durability, lubricity, and antiblocking

Features and Benefits

- Amide wax composite reinforced with hard, inert ceramic microspheres
- Excellent scratch and abrasion resistance when compared to PTFE based additives
- Adds slip, release and lubricity with an excellent surface "feel"
- High melting point to improve heat and block resistance
- Lowers COF
- Not a microplastic per ECHA definitions

Composition

Ethylene bis(stearamide)/ceramic

Renewable Carbon Index

>80%

Recommended Addition Levels

0.5-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; powdered metals.

Typical Properties*

	<u>SuperGlide 1231</u>
Mean Particle Size (µm)	5.0 - 8.0
Maximum Particle Size (µm)	22.00
Melting Point °C	141 - 146
Density @ 25 °C (g/cc)	1.00
NPIRI Grind	2.0 - 3.5

Mar-26

PolyTuf® 1229

A highly engineered LDPE/ceramic/nanoceramic composite for abrasion resistance and surface durability

Features and Benefits

- High performance additive for maximizing surface abrasion resistance (Taber) and film toughness
- Fortified with two types of hard, inert ceramic particles
- Low density polyethylene provides superior surface toughness, durability and mar resistance
- Ideal for walking surfaces
- PTFE-free alternative to Polyfluo 900
- Easy to disperse fine powder that can be incorporated with high speed mixing

Composition

Ceramic modified polyethylene

Recommended Addition Levels

0.5-2.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, metal and masonry); architectural wall and trim paints; stains, sealers and varnishes; floor coatings; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings; rubber additives.

Typical Properties*

	<u>PolyTuf 1229</u>
Mean Particle Size (µm)	9.0 - 12.0
Maximum Particle Size (µm)	31.11
Melting Point °C	110 - 113
Density @ 25 °C (g/cc)	0.97
NPIRI Grind	4.0 - 6.0

This product is also available as a water based wax dispersion - Microspersion 1229-40

Mar-26