

GraphShield 730

Micronized composite of synthetic wax and edge functionalized graphene (EFG) for improved anticorrosion in powder coatings

Features and Benefits

- Improves corrosion resistance on bare and treated cold rolled steel (CRS) when formulated with titanium dioxide or other inorganic pigments
- Black wax composite delivers graphene in an easy to use micronized powder
- Formulated with Asbury Carbons EFG technology
- 1% typically reduces mm creep by 25%
- Must be added to the premix, ideally processed above 110 ° C

Composition

Graphene/synthetic wax

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Powder coatings, industrial coatings.

Typical Properties*

	<u>GraphShield 730</u>
Mean Particle Size (µm)	8.0 - 12.0
Maximum Particle Size (µm)	31.00
Melting Point °C	108 - 113
Density @ 25 °C (g/cc)	1.24

Mar-26

MicroKlear 418AL

Aluminum oxide modified carnauba wax for maximum scratch resistance with surface slip, clarity and gloss retention. Also useful as an additive in seed coatings

Features and Benefits

- Carnauba wax composite reinforced with 300 nm aluminum oxide nanoparticles (Mohs Hardness 9)
- Provides maximum scratch resistance with surface lubricity
- Does not adversely affect clarity or gloss
- Easier-to-disperse nanotechnology in a safe, non-nano powder
- Composite wax/aluminum oxide particle is less abrasive on processing equipment compared to free aluminum oxide
- Effective replacement for PTFE additives

Composition

Carnauba wax/aluminum oxide

Renewable Carbon Index

>95%

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, metal and leather); wood coatings; printing inks and OPV's (including flexo and gravure); interior and exterior can and container coatings; coil coatings; seed coatings.

Typical Properties*

	<u>MicroKlear 418AL</u>
Mean Particle Size (µm)	6.0 - 8.0
Maximum Particle Size (µm)	22.00
Melting Point °C	81 - 86
Density @ 25 °C (g/cc)	1.04
NPIRI Grind	2.0 - 3.5

This product is also available as a water based wax dispersion - Microspersion 418AL-40

Mar-26

Micromide 520

Micronized fatty amide wax for maximum surface slip, scratch resistance and release properties

Features and Benefits

- Adds slip, release and lubricity with an excellent surface "feel"
- High melting point to improve heat and block resistance
- Lowers COF
- Reduces dust buildup on sanding belts and increases longevity in sanding sealers

Composition

Ethylene bis(stearamide) wax (EBS)

Renewable Carbon Index

>90%

Recommended Addition Levels

0.5-3.0% (on total formula weight)

Systems and Applications

Solvent based and energy curable coatings and inks. Wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; powdered metals.

Typical Properties*

	<u>Micromide 520</u>	<u>Micromide 520XF</u>
Mean Particle Size (µm)	5.0 - 8.0	3.0 - 5.0
Maximum Particle Size (µm)	22.00	15.56
Melting Point °C	141 - 146	141 - 146
Density @ 25 °C (g/cc)	0.97	0.97
NPIRI Grind	1.5 - 3.0	1.0 - 2.0

This product is also available as a water based wax dispersion - Microspersion 520

Mar-26

Micropro 400

Modified high melt point hybrid polypropylene wax for consistent gloss control with surface slip, mar and abrasion resistance

Features and Benefits

- Improves mar, scratch and metal marking resistance
- Effective gloss control agent with good burnish resistance in low or medium gloss finishes
- Provides antiblocking properties
- Low density will keep silica matting additives in suspension
- Easy to disperse in both polar and non-polar systems

Composition

Modified polypropylene

Recommended Addition Levels

0.5-2.0% (mar and abrasion resistance); 2.0-5.0% (gloss control) (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, metal and leather); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; floor coatings.

Typical Properties*

	<u>Micropro 400</u>
Mean Particle Size (µm)	4.5 - 7.5
Maximum Particle Size (µm)	22.00
Melting Point °C	140 - 143
Density @ 25 °C (g/cc)	0.94
NPIRI Grind	2.0 - 3.5

Mar-26



MicroTex[®] 580

PFAS-free biopolymer additive for powder coating texturing

Features and Benefits

- Imparts a uniform sandpaper-like surface texture when formulated in a matte polyester/acrylic system
- In polyester/epoxy and polyester/HAA systems, provides a smoother, scattered granular surface texture
- Typically added into the powder coating pre-mix before extrusion
- PTFE (PFAS) free
- Natural, sustainable, and renewable
- Biodegradable

Composition

Biopolymer

Renewable Carbon Index

100%

Recommended Addition Levels

3.0-7.0% (depending on the desired level of texture)
(on total formula weight)

Systems and Applications

Powder coatings.

Typical Properties*

MicroTex 580

Maximum Particle Size (µm)	105 (140 mesh)
Density @ 25 °C (g/cc)	1.45

Please refer to our "MicroTex 580 Formulation Guide" for more details on how to use this product

Mar-26



MicroTex[®] 950

PFAS-free additive for powder coating texturing

Features and Benefits

- Provides uniform fine texturing and gloss reduction at 4-6% dosage
- Effective in many chemistries including polyester/TGIC, polyester/HAA, and polyester/epoxy
- Best results for single digit gloss achieved at 6%
- Can provide PTFE-like texturing with low gloss
- PTFE (PFAS) free
- See Performance Study for details on product use

Composition

Modified polyolefin

Recommended Addition Levels

4.0-6.0% (depending on the desired gloss level) (on total formula weight)

Systems and Applications

Powder coatings.

Typical Properties*

	<u>MicroTex 950</u>
Maximum Particle Size (µm)	74 (200 mesh)
Density @ 25 °C (g/cc)	1.22

Mar-26

MicroTouch 800 Series

Highly resilient spherical polyurethane beads that can modify the tactile properties of formulated coatings and inks while improving burnish, scratch and mar resistance

Features and Benefits

- Virtually indestructible elastic particles that distort when disturbed by a physical force and then return to their original spherical shape when the force is removed
- Provide different tactile effects ranging from satiny smooth to rubbery to leathery in properly formulated coatings
- Different particle sizes available to create a unique surface "touch"
- Improves burnish and abrasion resistance
- Effective gloss reduction

Composition

Aliphatic polyurethane

Recommended Addition Levels

2.0-10.0% (higher amounts when greater tactile effects are desired) (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, vinyl and leather); architectural wall and trim paints; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; soft touch coatings; floor coatings; visual effects.

Typical Properties*

	<u>MicroTouch 800F</u>	<u>MicroTouch 800VF</u>	<u>MicroTouch 800XF</u>	<u>MicroTouch 800XXF</u>
Mean Particle Size (µm)	22.0 - 30.0	11.0 - 15.0	6.0 - 9.0	3.0 - 5.0
Maximum Particle Size (µm)	120.00	60.00	31.00	15.00
Density @ 25 °C (g/cc)	1.05	1.05	1.05	1.05

Mar-26

MicroTouch 800 Series

Highly resilient spherical polyurethane beads that can modify the tactile properties of formulated coatings and inks while improving burnish, scratch and mar resistance

Features and Benefits

- Virtually indestructible elastic particles that distort when disturbed by a physical force and then return to their original spherical shape when the force is removed
- Provide different tactile effects ranging from satiny smooth to rubbery to leathery in properly formulated coatings
- Different particle sizes available to create a unique surface "touch"
- Improves burnish and abrasion resistance
- Effective gloss reduction

Composition

Aliphatic polyurethane

Recommended Addition Levels

2.0-10.0% (higher amounts when greater tactile effects are desired) (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, vinyl and leather); architectural wall and trim paints; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; soft touch coatings; floor coatings; visual effects.

Typical Properties*

	<u>MicroTouch 800F</u>	<u>MicroTouch 800VF</u>	<u>MicroTouch 800XF</u>	<u>MicroTouch 800XXF</u>
Mean Particle Size (µm)	22.0 - 30.0	11.0 - 15.0	6.0 - 9.0	3.0 - 5.0
Maximum Particle Size (µm)	120.00	60.00	31.00	15.00
Density @ 25 °C (g/cc)	1.05	1.05	1.05	1.05

Mar-26

MP-22

High performance, versatile grade of micronized synthetic wax for improved slip, scratch and rub resistance in a wide variety of paints, coatings and inks

Features and Benefits

- Imparts a high degree of lubricity and slip with rub and mar resistance
- Provides antiblocking properties
- Gives long-lasting water beading and weather resistance to exterior alkyd-based stains
- Consider MP-22C & MP-28C (spherical) for improved surface slip
- Biodegradable to OECD 302C test standard
- Not a microplastic per ECHA definitions

Composition

Synthetic wax

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, metal and masonry); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; coil coatings; powdered metals.

Typical Properties*

	<u>MP-22</u>	<u>MP-22VF</u>	<u>MP-22XF</u>	<u>MP-22XXF</u>
Mean Particle Size (µm)	7.0 - 10.0	6.0 - 8.0	4.5 - 6.5	3.75 - 5.75
Maximum Particle Size (µm)	31.00	22.00	22.00	15.56
Melting Point °C	110 - 115	110 - 115	110 - 115	110 - 115
Density @ 25 °C (g/cc)	0.93	0.93	0.93	0.93
NPIRI Grind	4.0 - 6.0	2.0 - 3.5	1.5 - 3.0	1.0 - 2.3

This product is also available as a water based wax dispersion - Microspersion 22-50

Mar-26

MP-22

High performance, versatile grade of micronized synthetic wax for improved slip, scratch and rub resistance in a wide variety of paints, coatings and inks

Features and Benefits

- Imparts a high degree of lubricity and slip with rub and mar resistance
- Provides antiblocking properties
- Gives long-lasting water beading and weather resistance to exterior alkyd-based stains
- Consider MP-22C & MP-28C (spherical) for improved surface slip
- Biodegradable to OECD 302C test standard
- Not a microplastic per ECHA definitions

Composition

Synthetic wax

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, metal and masonry); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; coil coatings; powdered metals.

Typical Properties*

	<u>MP-22</u>	<u>MP-22VF</u>	<u>MP-22XF</u>	<u>MP-22XXF</u>
Mean Particle Size (µm)	7.0 - 10.0	6.0 - 8.0	4.5 - 6.5	3.75 - 5.75
Maximum Particle Size (µm)	31.00	22.00	22.00	15.56
Melting Point °C	110 - 115	110 - 115	110 - 115	110 - 115
Density @ 25 °C (g/cc)	0.93	0.93	0.93	0.93
NPIRI Grind	4.0 - 6.0	2.0 - 3.5	1.5 - 3.0	1.0 - 2.3

This product is also available as a water based wax dispersion - Microspersion 22-50

Mar-26

MP-28AL Series

Value engineered synthetic wax/aluminum oxide nanocomposites for surface durability and lubricity

Features and Benefits

- Improves scratch, scuff and mar resistance
- Adds surface slip and lubricity
- Choose XF grade for maximum gloss retention
- Choose G grade for maximum gloss reduction and burnish resistance
- Biodegradable to OECD 302C test standard
- Not a microplastic per ECHA definitions

Composition

Synthetic wax/aluminum oxide

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks, Industrial coatings (including plastic, metal and masonry); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings.

Typical Properties*

	<u>MP-28AL-XF</u>	<u>MP-28AL</u>	<u>MP-28AL-G</u>
Mean Particle Size (µm)	4.0 - 6.0	6.0 - 8.0	10.0 - 14.0
Maximum Particle Size (µm)	15.56	22.00	44.00
Melting Point °C	114 - 118	114 - 118	114 - 118
Density @ 25 °C (g/cc)	0.99	0.99	0.99
NPIRI Grind	1.0 - 2.0	1.5 - 3.0	N/A

Mar-26

MPP-611AL

A highly engineered HDPE/aluminum oxide nanocomposite for unsurpassed scratch and scuff resistance

Features and Benefits

- Maximum scratch and scuff resistance with slip and lubricity
- HDPE composite reinforced with 300 nm aluminum oxide nanoparticles (Mohs Hardness 9)
- Easier-to-disperse nanotechnology in a safe, non-nano powder
- Composite particle density maximizes efficiency and minimizes settling
- Effective replacement for PTFE additives

Composition

HDPE/aluminum oxide

Recommended Addition Levels

0.5-1.5% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic and metal); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings; rubber additives.

Typical Properties*

	<u>MPP-611AL</u>
Mean Particle Size (µm)	3.5 - 5.5
Maximum Particle Size (µm)	15.56
Melting Point °C	110 - 116
Density @ 25 °C (g/cc)	0.99
NPIRI Grind	1.0 - 2.0

This product is also available as a water based wax dispersion - Microspersion 611AL-50

Mar-26

MPP-611

High performance grade of micronized polyethylene wax for inks and coatings

Features and Benefits

- Imparts excellent rub and mar resistance with good surface slip
- Provides excellent antiblocking properties
- Good heat resistance
- Better resistance to solvent absorption and swelling when compared to Synthetic wax

Composition

High density polyethylene

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic and metal); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; coil coatings; seed coatings.

Typical Properties*

	<u>MPP-611</u>	<u>MPP-611XF</u>
Mean Particle Size (µm)	5.0 - 8.0	4.0 - 6.0
Maximum Particle Size (µm)	22.00	22.00
Melting Point °C	110 - 116	110 - 116
Density @ 25 °C (g/cc)	0.96	0.96
NPIRI Grind	2.0 - 3.0	1.0 - 2.0

This product is also available as a water based wax dispersion - Microspersion 611XF-50

Mar-26

MPP-620

High performance micronized polyethylene wax which provides a unique combination of surface slip, abrasion/rub resistance, and antiblocking in a wide variety of coatings and inks

Features and Benefits

- Imparts excellent abrasion, rub and mar resistance with good surface slip
- Provides excellent antiblocking properties
- Adds heat resistance
- Better resistance to solvent absorption and swelling when compared to Synthetic wax

Composition

High density polyethylene

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic and metal); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; coil coatings.

Typical Properties*

	<u>MPP-620VF</u>	<u>MPP-620XF</u>	<u>MPP-620XXF</u>
Mean Particle Size (µm)	5.0 - 7.0	4.5 - 5.5	4.25 - 4.75
Maximum Particle Size (µm)	22.00	22.00	12.00
Melting Point °C	120 - 124	120 - 124	120 - 124
Density @ 25 °C (g/cc)	0.96	0.96	0.96
NPIRI Grind	2.0 - 3.0	1.0 - 2.0	1.0 - 1.5

This product is also available as a water based wax dispersion - Microspersion 620VF-50

Mar-26

MPP-635

Micronized high molecular weight polyethylene wax for maximum rub and abrasion resistance in inks and coatings

Features and Benefits

- Crystalline, high melting point wax provides superior rub and abrasion resistance
- Imparts excellent antiblocking properties
- High molecular weight and hardness improves resistance to solvent absorption and swelling
- Easy to disperse fine powder that can be incorporated with high speed mixing

Composition

High density polyethylene

Recommended Addition Levels

1.0-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic and metal); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; coil coatings.

Typical Properties*

	<u>MPP-635F</u>	<u>MPP-635VF</u>	<u>MPP-635XF</u>
Mean Particle Size (µm)	8.0 - 10.0	6.0 - 8.0	4.0 - 6.0
Maximum Particle Size (µm)	31.00	22.00	22.00
Melting Point °C	123 - 125	123 - 125	123 - 125
Density @ 25 °C (g/cc)	0.97	0.97	0.97
NPIRI Grind	4.0 - 5.0	2.0 - 3.0	1.0 - 2.5

This product is also available as a water based wax dispersion - Microspersion 635F-50 & 635VF-50

Mar-26



PolyGlide 1226XF

A highly engineered HDPE/ceramic/nanoceramic composite for abrasion resistance and lubricity

Features and Benefits

- HDPE composite reinforced with hard, inert ceramic microspheres and nanoceramic platelets
- Improved Taber abrasion resistance when compared to PE/PTFE additives
- Provides slip and lubricity
- Ideal for can and container coatings; 21CFR 175.300 approved
- Effective replacement for PTFE additives
- Compare to (coarser) Polyfluor 900

Composition

HDPE/ceramic

Recommended Addition Levels

0.5-1.5% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic and metal); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; can, container, and coil coatings; rubber additives.

Typical Properties*

	<u>PolyGlide 1226XF</u>
Mean Particle Size (µm)	3.5 - 5.5
Maximum Particle Size (µm)	15.56
Melting Point °C	109 - 115
Density @ 25 °C (g/cc)	0.99
NPIRI Grind	1.0 - 2.0

This product is also available as a water based wax dispersion - Microspersion 1226XF-50

Mar-26

PolyTuf® 1229

A highly engineered LDPE/ceramic/nanoceramic composite for abrasion resistance and surface durability

Features and Benefits

- High performance additive for maximizing surface abrasion resistance (Taber) and film toughness
- Fortified with two types of hard, inert ceramic particles
- Low density polyethylene provides superior surface toughness, durability and mar resistance
- Ideal for walking surfaces
- PTFE-free alternative to Polyfluo 900
- Easy to disperse fine powder that can be incorporated with high speed mixing

Composition

Ceramic modified polyethylene

Recommended Addition Levels

0.5-2.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic, metal and masonry); architectural wall and trim paints; stains, sealers and varnishes; floor coatings; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings; rubber additives.

Typical Properties*

	<u>PolyTuf 1229</u>
Mean Particle Size (µm)	9.0 - 12.0
Maximum Particle Size (µm)	31.11
Melting Point °C	110 - 113
Density @ 25 °C (g/cc)	0.97
NPIRI Grind	4.0 - 6.0

This product is also available as a water based wax dispersion - Microspersion 1229-40

Mar-26

PropylMatte 31

Finely micronized polypropylene for efficient matting and gloss control in paints, coatings and inks

Features and Benefits

- Provides consistent gloss reduction with no effect on coating viscosity
- Tough, high molecular weight polymer imparts burnish and abrasion resistance
- Imparts anti-slip properties
- Density (0.89) ideal for solvent based systems
- For more efficient matting with a fine microtexture, try PropylTex 325S/270S
- Adds texture in low bake (Low E) powder coatings

Composition

Polypropylene

Recommended Addition Levels

2.0-5.0% depending on the level of gloss reduction desired (on total formula weight)

Systems and Applications

Water based and solvent based coatings. Industrial coatings (including plastic, metal and leather); architectural wall and trim paints; stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; coil coatings.

Typical Properties*

	<u>PropylMatte 31</u>
Mean Particle Size (µm)	8.0 - 12.0
Maximum Particle Size (µm)	31.00
Melting Point °C	160 - 170
Density @ 25 °C (g/cc)	0.89
NPIRI Grind	5.0 - 6.0

This product is also available as a water based wax dispersion - Microspersion 31-35

Mar-26



PropylTex® 100S-200S (medium texture grades)

Coarse particle size grades of micronized polypropylene for adding texture, structure and anti-slip properties to a wide variety of paints and coatings

Features and Benefits

- Provides a consistent medium textured coating surface
- Tough, high molecular weight polypropylene gives good film durability
- Does not lower COF; ideal for anti-skid surfaces
- Easy to disperse powder that can be incorporated with high speed mixing
- Adds texture in low bake (Low E) powder coatings

Composition

Polypropylene

Recommended Addition Levels

3.0-10.0% (on total formula weight)

Systems and Applications

Water based, solvent based, industrial and consumer paints including masonry, stucco paints, architectural wall and trim paints; stains, sealers and varnishes; wood coatings; floor coatings.

Typical Properties*

	<u>PropylTex 100S</u>	<u>PropylTex 140S</u>	<u>PropylTex 200S</u>	<u>PropylTex 200SF</u>
Mean Particle Size (µm)	80.0 - 100.0	45.0 - 50.0	35.0 - 45.0	25.0 - 35.0
Maximum Particle Size (µm)	149 (100 mesh)	105 (140 mesh)	74 (200 mesh)	74 (200 mesh)
Melting Point °C	160 - 170	160 - 170	160 - 170	160 - 170
Density @ 25 °C (g/cc)	0.89	0.89	0.89	0.89

Mar-26

SuperGlide 1231

A value engineered ceramic-modified amide wax for superior surface durability, lubricity, and antiblocking

Features and Benefits

- Amide wax composite reinforced with hard, inert ceramic microspheres
- Excellent scratch and abrasion resistance when compared to PTFE based additives
- Adds slip, release and lubricity with an excellent surface "feel"
- High melting point to improve heat and block resistance
- Lowers COF
- Not a microplastic per ECHA definitions

Composition

Ethylene bis(stearamide)/ceramic

Renewable Carbon Index

>80%

Recommended Addition Levels

0.5-3.0% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; interior and exterior can and container coatings; powdered metals.

Typical Properties*

	<u>SuperGlide 1231</u>
Mean Particle Size (µm)	5.0 - 8.0
Maximum Particle Size (µm)	22.00
Melting Point °C	141 - 146
Density @ 25 °C (g/cc)	1.00
NPIRI Grind	2.0 - 3.5

Mar-26

Superslip 6515AL

A highly engineered HDPE/EBS/aluminum oxide nanocomposite for maximum scratch, scuff and block resistance

Features and Benefits

- Maximum scratch resistance; equal to PE/PTFE additives
- HDPE/EBS composite reinforced with 300 nm aluminum oxide nanoparticles (Mohs Hardness 9)
- Good abrasion resistance with slip and lubricity
- Amide wax component provides excellent antiblocking and release properties
- Ideal for can and container coatings; 21CFR 175.300 approved

Composition

HDPE/EBS/aluminum oxide

Renewable Carbon Index

>90%

Recommended Addition Levels

0.5-1.5% (on total formula weight)

Systems and Applications

Water based, solvent based and energy curable coatings and inks. Industrial coatings (including plastic and metal); stains, sealers and varnishes; wood coatings; printing inks and OPV's (including flexo and gravure); powder coatings; can, container, and coil coatings; rubber additives.

Typical Properties*

	<u>Superslip 6515AL</u>
Mean Particle Size (µm)	3.5 - 5.5
Maximum Particle Size (µm)	15.56
Melting Point °C	139 - 145
Density @ 25 °C (g/cc)	0.99
NPIRI Grind	1.0 - 2.0

This product is also available as a water based wax dispersion - Microspersion 6515AL-40

Mar-26