

Adhesives and Sealants

Application Guide

PRODUCT	DESCRIPTION(system/ application)	APPLICATION NOTES
Tyzor 726	• Silicone (RTV-1) • Acrylic resin • Industrial • Electronic	• Cure Time: <5 min • Tack Free Time, minutes: 2-5 • Relative Adhesion: 1 • Skin Formation Time: 5-30 min • Other: Freezes at 25°C
Tyzor 795	• Silicone (RTV-1) • Polysiloxane • STP, MS Polymer • Automotive	• Cure Time: 12-24 h • Tack Free Time, minutes: 10-30 • Relative Adhesion: 0.95 • Skin Formation Time: 10-30 min • Other: Freezes at -30°C
Tyzor KE-6	• Silicone (RTV-1) • Polysiloxane • Acrylic resin • Construction • Industrial • Automotive	• Cure Time: 12-24 h • Tack Free Time, minutes: 10-30 • Relative Adhesion: 0.9 • Skin Formation Time: 10-30 min • Other: Freezes at -35°C
Tyzor 9000	• Polysiloxane • Epoxy • Acrylic • Polyurethane • Construction • Industrial • Automotive • Electronic	• Cure Time: 3-5min • Tack Free Time, minutes: 1-2 • Relative Adhesion: 0.25 • Skin Formation Time: 3-5 min • Other: Freezes at -40°C

The table below details which grades of Tyzor® are recommended for various adhesive and sealant systems.

System	Grade	Cure Rate	Moisture Sensitivity	Color Impact
Silicone (RTV-1)	Tyzor® 726	Moderate	Resistant	Moderate
	Tyzor® 9000	Moderate to Fast	Reactive	Low to None
	Tyzor® KE 6	Fast	Stable	Low to None
	Tyzor® BTP	Fast	Reactive	Low to None
Polyurethane	Tyzor® 9000	Moderate to Fast	Reactive	Low to None
Polysulfide	Tyzor® TE	Moderate to Fast	Stable	Moderate to Low
Natural Rubber	Tyzor® NBZ	Fast	Reactive	Low to None
	Tyzor® TPT	Fast	Reactive	Low to None
Epoxy	Tyzor® 9000	Fast	Reactive	Low to None
Acrylic (Solvent)	Tyzor® 9000	Moderate	Reactive	Low to None
	Tyzor® 726	Fast	Resistant	Moderate
	Tyzor® TOT	Fast	Reactive	Low to None
Acrylic (Water)	Tyzor® TE	Fast	Stable	Moderate to Low
	Tyzor® LA			
	Tyzor® 217			