

Application Data Sheet

Plastic Packaging for Food Contact

DESCRIPTION

Tyzor® ACTivate™ 422 is a hydrolytically stable titanate catalyst specifically designed for plastic packaging in food contact applications. Superior ligand chemistry provides the excellent melt and SSP activity required for excellent polymer color and aesthetics.

Approved for Food Contact

Tyzor® ACTivate™ catalysts complies with the requirements of US CFR177.1630 and EU Regulation 10/2011 when used in the manufacture of plastic for food contact materials.

Tyzor® ACTivate™ 422 benefits can be fine-tuned in a variety of ways to fit each manufacturer's unique requirements for a balance of manufacturing efficiency, resin quality improvements and increased resin performance in demanding bottle designs.

Application Benefits

- Improved Process Efficiency and Throughput
- Enhanced Resin Properties
- Improved Resin Performance.

Tyzor® ACTivate™ 422 is a highly active esterification catalyst that can increase esterification rates up to 20%. This allows resin manufacturers to improve diethylene glycol concentration by lowering esterification temperatures.

Tyzor® ACTivate™ 422 is a high-performance polymerization catalyst that has been shown to increase melt plant capacity by as much as 15%, substantially lowering PET manufacturing costs. Alternatively, manufacturers can choose to decrease polymerization temperatures, producing improved polymers with reduced acetaldehyde or carboxyl end group concentration for flavor-sensitive applications.

Excellent hydrolytic stability allows Tyzor® ACTivate 422 to be added to the esterification reaction wherever it is most convenient, either by addition to the PTA/MEG slurry or directly to the esterification vessel.

TYPICAL PROPERTIES

PROPERTY	TYPICAL VALUE
Flash point, °C (°F)	> 70 (158)
Specific gravity @ at 25 °C (77 °F)	1.14 - 1.18
Viscosity, cPs @ 25 °C (77 °F)	1 to 20
pH	3
Solubility	Miscible in water. Soluble in glycols and alcohols. Insoluble in hydrocarbons.



Dorf Ketal Speciality Catalysts LLC
11200 Westheimer Road – Suite 400
Houston, Texas 77042
USA

Tel: +1-713-343-2377
E-mail: tyzor@dorketal.com
www.dorketal.com

The information contained in this sheet is provided free of charge and is based on technical data that Dorf Ketal believes to be correct and reliable. It is intended for use by persons having technical skill and at their own discretion and risk. We make no warranties, express or implied, and assume no liability in connection with any of this information as the conditions of use are outside our control. In addition, none of the contents of this publication should be taken as a license to operate under, or a recommendation to infringe any patent.