

Clearlink®, Unilink® Crosslinkers and Chain Extenders



Product Guide

PRODUCT	DESCRIPTION	APPLICATION NOTES
Clearlink® 1000	Aliphatic diamine chain extender for use with aliphatic isocyanates in polyurethane and polyurea	• Produces tough, UV light-stable polyurethane and polyurea coatings with improved strength and heat resistance. • Can be applied using conventional spray techniques.
Clearlink® 1080	Aliphatic diamine chain extender for use with aliphatic isocyanates in polyurethane and polyurea	• Produces durable, UV light-stable polyurethane and polyurea coatings with improved strength and heat resistance. • Low moisture sensitivity, slower reactivity and compatibility with a wide range of polyols, co-curatives and other polyurethane chemicals. • Can be applied using conventional spray techniques.
Unilink® 1136	modified IPDA	• In aromatic systems, an extended pot life of about 15 seconds can be achieved. • In aliphatic systems, apart from longer pot life and UV stability, the final properties of the coating are attained much faster (within about 4 hours). In the event of exposure to heat, polyurea coatings made from Clearlink® 1136 can withstand temperatures of up to 90 °C thanks to their higher heat distortion temperature (HDT). • Aliphatic elastomers from 40 Shore D to 85 Shore D can be obtained by only slight variation of formula.
Unilink® 1030	Reactive proprietary liquid zirconium chelate dissolved in a reactive diol	• Unilink® 1030 is designed for use in polyurethane elastomers. It provides delayed open times in polyester polyol elastomers, and because the diol solvent reacts into the polyurethane it leaves no residue. Unilink® 1030 is selective towards the gelling reaction, generating very low water reactivity, and low color makes it particularly suitable for color-critical formulations.

PRODUCT	DESCRIPTION	APPLICATION NOTES
Unilink® 2500	Proprietary titanium chelate	Unilink® 2500 is a polyurethane gelling catalyst designed for filled and unfilled MDI-based elastomers and coatings. It is designed for use with castor oil, polybutadiene polyols or polyether polyol systems requiring short gel times. Unilink® 2500 exhibits excellent gel-time stability when blended with the polyol side of the formulation. It is suitable only for formulations containing low levels of secondary alcohols and should not be used with non-ethyleneoxide-capped polypropyleneglycol polyols and similar formulations.
Unilink® 2200	Proprietary titanium chelate	Unilink® 2200 is a polyurethane gelling catalyst designed for filled and unfilled MDI-based elastomers and coatings. Unilink® 2130 exhibits excellent gel-time stability when blended with the polyol side of the formulation. It is suitable only for formulations containing low levels of secondary alcohols and should not be used with non-ethyleneoxide-capped polypropyleneglycol polyols and similar formulations. Delivers a fast cure profile, similar to tin.
Unilink® 2130	Titanium-based polyurethane catalysts for filled and unfilled elastomers and coatings	- Slower, delayed cure profile with a snap final cure, similar to mercury, wide formulating window and tailored polyurethane properties. - Suitable for use with a wide variety of isocyanates and primary polyols. - Moisture-tolerant and excellent storage stability in polyols.
Unilink® 4100	Aromatic diamine chain extender for foams and elastomeric coatings	- Improved compressive strength, tensile, tear, dimensional stability and load-bearing properties in standard TDI slab-stock foam and high-resilience foam systems. - Reduces foam density and softens cold-molded foam. - Improves mold flow and reduces mold time. - Cures TDI and MDI coating compounds at ambient temperatures. - Can be applied by spray or pour-and-spread techniques. - Low viscosity improves handling, surface wetting, adhesion and finish.
Unilink® 4200	Aromatic diamine chain extender for foams and elastomeric coatings	- Improved compressive strength, tensile, tear, dimensional stability and load-bearing properties in standard TDI slab-stock foam and high-resilience foam systems. - Reduces foam density and softens cold-molded foam. - Improves mold flow and reduces mold time. - UNILINK® 4200 is a multifunctional chain extender for polyurethane and polyurea systems such as flexible and rigid foams, coatings, adhesives, and elastomers. Thanks to relatively low reactivity, UNILINK® 4200 can be used in TDI or MDI formulations, and cross-linking can be controlled by adding higher functioning polyols.