

DATA SHEET

No. 506/CE Revision 00 dated 10/2/2006

Mod. 03 PGQ 5.4_01 Rev. 01 del 03.09.2007



GEO RPES AG 200

Geo&tex 2000 S.p.A., Via XXV Aprile 3, I-36020 San Nazario (VI) - ITALY

07 **0799 - CPD - 15**

Non woven Geotextile manufactured from polyester fibers, needlepunched

suitable for the following applications:





EN 13249 : Characteristics required for use in the construction of roads and other trafficked areas





EN 13250 : Characteristics required for use in the construction of railways





EN 13251: Characteristics required for use in earthworks, foundations and retaining structures





EN 13252 : Characteristics required for use in drainage systems





EN 13253: Characteristics required for use in erosion control works (coastal protection, bank revetments)





EN 13254: Characteristics required for use in the construction of reservoirs and dams





EN 13255 : Characteristics required for use in the construction of canals





EN 13256 : Characteristics required for use in the construction of tunnels and underground structures





EN 13257 : Characteristics required for use in solid waste disposal





EN 13265 : Characteristics required for use in liquid waste containment projects

Functions:

F - R - F+R+S - F+S - R+S - F+R











Characteristic	Test Method	Ui	nit	Nominal Value	Tolerance
Mass per unit area	EN ISO 9864	g/i	m^2	200	± 10%
Thickness	EN ISO 9863-1	mm	2 kPa	1,00	± 20%
Wide-Width Tensile Strength	EN ISO 10319	kN/m	MD	1,00	-0,50
Wide-Width Ferishe Strength	LIN 130 10319		CMD	1,00	-0,50
Elongation	EN ISO 10319	%	MD	80	± 20
•		70	CMD	90	± 20
Static Puncture Resistance	EN ISO 12236	1	V	250	-100
Dynamic Perforation Test	EN ISO 13433	mm		45,00	+ 10,00
Characteristic Opening Size	EN ISO 12956	μm		100	± 30
Permeability normal to the Plane	EN ISO 11058	m	ı/s	0,098	-0,026
Long Term Protection Efficiency		%	300 kPa	NR	NR
	EN 13719		600 kPa	NR	NR
			1200 kPa	NR	NR
		m²/s	20 kPa	NR	NR
Water Flow Capacity in the Plane	EN ISO 12958		100 kPa	NR	NR
			200 kPa	NR	NR
Durability	EN 12224	To be covered within 1 day after installation. Predicted to be durable 5 years in			
	EN 12224	natural soils with 4 <ph<9 25="" <="" and="" soil="" td="" temperature="" ℃<=""></ph<9>			
Oxidation Resistance	EN ISO 13438	Residual Strenght		MD	NR
Oxidation Resistance	EN 130 13430			CMD	NR
Chemical Resistance	EN 14030	Residual Strenght		MD	NR
Chemical Nesistance	LIN 14030			CMD	NR
Microbiological Resistance	EN 12225	Residual Strenght		MD	NR
Microbiological Resistance	LIN 12223			CMD	NR

MD : Machine Direction - CMD : Cross Machine Direction - NR : Not Required for application

TOLERANCE ON ROLL WIDTH: ± 3 cm. TOLERANCE ON ROLL LENGHT: ± 2% IF LENGHT ≤ 200 m, ± 1% IF LENGHT > 200 m.
STANDARD CORES: PAPER, DIAMETER INNER 81mm / OUTER 89mm ± 5%. TOLERANCE ON GROSS/NET WEIGHT ± 5%.
TECNICAL DATA BASED ON STATISTIC ANALISYS ON 95% CONFIDENCE LIMIT. PRESENT DATA SHEET CAN BE MODIFIED WITHOUT PRIOR NOTICE

Issued				
Date	COM			
10/2/2006	A			

Verified				
Date	RCQ			
10/2/2006	Pade Borre			

Approved			
Date	RSGQ		
10/2/2006	BeotoEllo		



