YELLOW LEAD OXIDE

SPECIFICATIONS

Appearance : Yellow Free Flowing Powder
Boiling Point : 1470 C
Melting Point : 888 C
Solubility : Insoluble in water, soluble in acetic acid, nitric acid, alkalies

COMPOSITION

Element Range

- PbO (litharge) 99.82% minimum
- Pb (free lead) 0.15% maximum
- Pb3O4 (red lead) 0.05% maximum

Trace Elements	Maximum (%)	Typical (%)
- Fe	0.0007	0.0004
- Zn	0.0006	0.0004
- Cu	0.0004	0.0003
- Ag	0.0015	0.00006
- Bi	0.0050	< 0.0009
- As, Sb, Sn	0.0009	< 0.0004
- Ni, Te, Th, Cd	0.0006	< 0.0005
- Co, Cr, Mn, Se	0.0002	< 0.0001

PROPERTIES AND APPLICATIONS

Litharge, which is Lead Mono-Oxide (PbO) is a yellowish or reddish, odorless, heavy, earthy, water-insoluble, solid, PbO, used chiefly in the manufacture of Lead Stabilizers (Lead Steareates), pottery, lead glass, paints, enamels, and inks. Litharge is also called Lead Monoxide, Lead Oxide, Plumbous Oxide. Other use of Litharge is as intermediate used in a variety of industries like lubricants and greases, insecticides, inorganic pigments, Lead soaps, petroleum refining, rubber and PVC etc..

PRODUCT PACKAGING

25 Kg. HDPE Laminated Paper Sacks with Polythene Liners

Tepe Kimya (M) SDN. BHD.
Plo 602 Jalan MIEL 1 Off Jalan Keluli 9
81700 Pasir Gudang Johor MALAYSIA
Tel: +60 7 251 7844 Fax: +60 7 251 7848
Web: www.tepekimya.com

Tepe Kimya San. ve Tic.Ltd.Şti.
Kimyacılar Organize Sanayi Bölgesi
Melek Aras Bulvarı N:12 34959
Tepeören Tuzla Istanbul/TURKEY
Tel:+90 216 5931920 Fax:+90 216 5931925

Tepe Trade Intl. Chem Pte. Ltd.
63 Mount Sinai Drive #05-01
277116 SINGAPORE
Tel:+65 932 65813 Fax: +65 631 48 435
Email: info@tepekimya.com