Novarez TP 35

Resinous Softener/Tackifier/Homogeniser

NOVAREZ TP 35 ;

- Improves the building tack of synthetic rubber compounds
- Very good extraction resistance against aliphatic hydrocarbons and mineral oils
- Good dispersion of carbon blacks and mineral fillers
- No reduction of the low temperature flexibility
- Improve the homogeneity of polymer blends

PROPERTIES

Chemical Characteristics	:	Blend of synthetic resin
Appearance	:	Powder
Dropping Point	:	95 ° C ± 2
Storage Stability	:	3 years under cool and dry storage conditions in orginally packing
Packing	:	Paper bags containing 30 kg net
Dosage	:	5 – 15 phr

Tepe Kimya (M) SDN. BHD.
Plo 602 Jalan MIEL 1 Off Jalan Keluli 9
81700 Pasir Gudang Johor MALAYSIA
Tel: +60 7 251 7844 Fax: +60 7 251 7848
Web: www.tepekimya.com

Tepe Kimya San. ve Tic.Ltd.Şti.
Kimyacılar Organize Sanayi Bölgesi
Melek Aras Bulvarı N:12 34959
Tepeören Tuzla Istanbul/TURKEY
Tel:+90 216 5931920 Fax:+90 216 5931925

Tepe Trade Intl. Chem Pte. Ltd.
63 Mount Sinai Drive #05-01
277116 SINGAPORE
Tel:+65 932 65813 Fax: +65 631 48 435
Email: info@tepekimya.com