

Fichot 5×5 Quicksheet

This sheet is for usage with the Alain Fichot 5×5 glaze testing fixture. Each well on my fixture is measured at $2.2\text{ cm} \times 2.4\text{ cm}$ and 1 cm deep. The section for Glaze Slurry contains information for the Leach 4321 glaze at ~ 1.45 specific gravity. The section on Additions contains information on how to create bottles of addition material, generally a single colorant oxide, used to add $\sim X\%$ of colorant per drop.

Glaze Slurry

Dose each well of the Fichot 5×5 fixture with a volume of glaze slurry from the table below. The reference amount for most glazes is 0.8 mL at $\sim 0.4\text{ mm}$ thick, which is what the standard addition amounts are based on below.

Volume (mL)	Fired Thickness (mm)	Specific Gravity	Wet Mass (g)	Dry Mass (g)
0.6	0.30	1.44	0.87	0.43
0.8	0.39	1.44	1.16	0.58
1.0	0.49	1.44	1.44	0.72
1.2	0.59	1.44	1.73	0.87

Most glazes will scale linearly with specific gravity (SG). Following is the formula one can use to find dose volume for a given thickness with a new specific gravity:

$$\text{Dry Mass (g)} = 1.64 \times \text{Volume (mL)} \times (\text{SG} - 1)$$

Additions

To make a standard addition bottle add 3 g of colorant (representing $\sim 0.5\%$ colorant per 0.05 mL drop) to 50 g of distilled water. Optionally, add 0.75 g of sodium bentonite for better colorant suspension. Mix well and let sit at least 24 hours before use for materials to fully hydrate.

To verify the colorant solution is accurate, weigh 100 drops of the mixture in grams (W), let dry completely, and weigh the residue in grams (R). Use the formulas below to compute mg/drop, then convert to percentage per drop with the Dry Mass value above:

$$\text{Colorant amount in grams: } \text{mg/drop} = 10 R$$

$$\text{...with } X\text{ grams bentonite: } \text{mg/drop} = 10 R \times \frac{m_c}{m_c + X}$$

$$\text{Percentage Conversion: } \%/drop = \frac{\text{mg/drop}}{10 \times (\text{Dry Mass})}$$

$$R = \text{dry residue from 100 drops (g)}$$

$$m_c = \text{colorant added to the bottle (g)}$$

The bottle additions are targeted to add 0.5% of colorant per drop based on the 0.4 mm thick reference glaze. There are cases where one might want to use existing colorant bottles for other volumes of glaze. Following is a table that shows percentages for other amounts of glaze based on the dry mass of the Glaze Slurry.

Reference %/drop	Glaze Dry Mass (g)			
	0.43	0.58	0.72	0.87
0.2 % (1 g)	0.23 %	0.17 %	0.14 %	0.11 %
0.5 % (3 g)	0.70 %	0.52 %	0.42 %	0.34 %
1 % (6 g)	1.40 %	1.03 %	0.83 %	0.69 %