

DESCRIPTION

ALSAN FLASHING is a patented single component, polyurethane- and bitumen-based waterproofing coating used to waterproof hard-to-access upstands and other details where it is difficult to apply sheet waterproofing membranes.

RECOMMENDED SUBSTRATES

- Without primer: traditional granulated and sanded bituminous waterproofing membranes, wood, metal, prepaint metal, concrete, polyurethane membrane (TRAFIK HP) and PVC pipe (vertical partition wall only);
- With primer (ELASTOCOL 500): BUR bituminous waterproofing;
- With primer (ELASTOCOL STICK, ELASTOCOL STICK ZERO): membranes with HDPE surface.

SURFACE PREPARATION

- Surfaces must be clean, dry and free of loose particles, formwork, curing products, irregularities, slurry, etc.
- PVC pipe must be sanded with sandpaper.
- All metal surfaces must be cleaned with a non-greasy solvent such as acetone or Methyl Ethyl Ketone (MEK). Metals surfaces must be smooth, clean and uncontaminated (free of oxidized bitumen).

APPLICATION

1. MIXING

- 1.1. Mix the ALSAN FLASHING waterproofing coating for **2 to 3 minutes** to obtain a uniform consistency.

2. APPLICATION

ALSAN FLASHING is applied using a trowel, a brush or a roller. Each coat of ALSAN FLASHING must have a minimum wet film thickness of 0.8 mm (30 mils).

A. When the reinforcement is not required:

- 2.1. Apply a first coat of ALSAN FLASHING on the surface.
- 2.2. Apply the second coat of ALSAN FLASHING once the first coat has formed a surface skin (still tacky but no longer transfers to the fingers). For maximum adhesion, apply the second coat within 24 hours of the first coat.

B. Transitions, angle changes and junctions between two supports, must be reinforced using POLYFLEECE reinforcement:

- 2.1. Apply a first coat of ALSAN FLASHING on the surface.
- 2.2. Install POLYFLEECE reinforcement into the still-wet first coat of ALSAN FLASHING using a trowel, ensuring it is fully embedded in the coating.
- 2.3. Immediately apply a second coat of ALSAN FLASHING to fully saturate the POLYFLEECE reinforcement.
- 2.4. Apply a third coat of ALSAN FLASHING when the second coat has formed a surface skin (still tacky but no longer transfers to the fingers). For maximum adhesion, apply the third coat within 24 hours of the second coat.

3. AESTHETIC FINISH (OPTIONAL)

- 3.1. ALSAN FLASHING is UV resistant. It can be left exposed without protection. For aesthetic purposes, the top coat can also be covered with roofing granules or for aluminum colour with SOPRALASTIC 124 ALU waterproofing coating.

Minimum application temperature: 5 °C (41 °F)

Service temperature: -30 to 150 °C (-22 to 302 °F)



RESTRICTION

- Do not apply the product during precipitation or if rain or snow is expected within the next 12 hours.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

GENERAL INFORMATION

Specifications	ALSAN FLASHING
Available formats	3.78 L (1 US gal) 18.9 L (5 US gal)
Colour	Brown
Physical state	Liquid
Coverage ⁽¹⁾ , 3.78 L (1 US gal) 18.9 L (5 US gal)	4.6 m ² (50 ft ²) 23 m ² (250 ft ²)
Thickness, wet film dry film	0.8 mm (30 mils) 0.6 mm (24 mils)

(1): Coverage may vary depending on the condition and porosity of the substrate.

PROPERTIES

Properties	Standards	ALSAN FLASHING
Density, at 25 °C (77 °F)	-	1.07 kg/L (8.93 lb/US gal)
Solid content	-	80%
Softening point	-	150 °C (302 °F)
Ultimate elongation	ASTM D412	500%
Tensile strength	ASTM D412	3.5 MPa (508 psi)
Peel resistance ⁽²⁾	ASTM D903	400-2500 N/m (27.4 à 171.3 lbf/ft)
Tear resistance ⁽¹⁾	ASTM D5147 sec.7	337 N (76 lbf)
Peel adhesion after water immersion, concrete substrate	ASTM C836	640 - 720 N/m (43.9 – 49.3 lbf/ft)
Water vapour permeance, Dry film of 1.1 mm (43 mils) Reinforced system: Dry film of 2.7 mm (106 mils) ⁽¹⁾	ASTM E96 (Procedure B)	30 ng/Pa•s•m ² (0.47 perm) 14 ng/Pa•s•m ² (0.24 perm)
Reaction times, recoat (surface skin) ⁽³⁾ dry fully cured	-	after 2 hours (still tacky but no longer transferring to the fingers) 12 hours (remains tacky to touch) 3 days

(All values are nominal)

(1): The result is for a reinforced system: 3 coats of ALSAN FLASHING + POLYFLEECE reinforcement.

(2): Results may vary depending on the type and porosity of the substrate.

(3): For maximum adhesion apply the second and/or third coat within 24 hours of applying the previous coat.



CLEANING

- ALSAN FLASHING can be cleaned with solvents such as mineral spirits, Varsol, xylene, etc.

STORAGE AND HANDLING

- ALSAN FLASHING can be kept up to 12 months when properly stored in its original sealed containers.
- Containers must be stored in a cool, well-ventilated area, away from heat, open flames or spark sources, moisture, oxidizing agents, and direct sunlight.
- Recommended storage temperature: 0 to 35 °C (32 to 95 °F).

TESTS, CERTIFICATIONS AND EVALUATIONS

FLORIDA BUILDING CODEMIAMI-DADE COUNTY
APPROVED

FOR MORE INFORMATION, REFER TO THE INSTRUCTIONS ON THE LABEL AND RELEVANT SAFETY DATA SHEET (SDS).

