

COLPLY EF FLASHING CEMENT

TECHNICAL DATA SHEET 240809SCANE

(supersedes 230130SCANE)



COMPLEMENTARY PRODUCTS

APPLICATIONS

ROOFS

DESCRIPTION

COLPLY EF FLASHING CEMENT is an odourless polyether based adhesive. COLPLY EF FLASHING CEMENT adhesive is used to adhere SBS bituminous membranes on flashings and slope surfaces > 3 % (3/8 in per ft).

On low slopes (< 3 % [3/8 in per ft]), use COLPLY EF adhesive.

SURFACE PREPARATION

Surfaces must be dry, clean and free of oil, grease, debris or dirt.

In order to prevent moisture on sanded surfaces, it is recommended to install the cap sheet membrane on the same day as the base sheet membrane.

APPLICATION

COLPLY EF FLASHING CEMENT adhesive is applied using a 4.8 mm (3/16 in) or a 6.0 mm (1/4 in) notched trowel in order to apply a uniform coat as per the recommended coverage rate.

The minimum application temperature is 0 °C (32 °F).

RESTICTION

COLPLY EF shall not be used in combination with ELASTOCOL 500 primer.

CONSULT THE MOST UP-TO-DATE ROOFER'S GUIDE FOR MORE INFORMATION ON THE VARIOUS APPLICATION METHODS RECOMMENDED BY SOPREMA OR PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

GENERAL INFORMATION

Specifications	COLPLY EF FLASHING CEMENT
Physical state	Liquid
Colour	Brown-black
Container	13.2 L (3.5 US Gallon)

COVERAGE RATES⁽¹⁾

Use	Coverage
Typical surface <i>Sanded surface, coverboard, insulation board, CSP 3-4</i>	0.8 to 1.2 L/m ² (2.0 to 3.0 US Gallon/100 ft ²)
Granulated surface	1.2 to 1.6 L/m ² (3.0 to 4.0 US Gallon/100 ft ²)

(1) Coverage rate is approximate and may vary depending on application technique, surface roughness and application temperature.

PROPERTIES

Properties	Standards	COLPLY EF FLASHING CEMENT
Density	-	1.3 kg/L (11.2 lb/gal)
Ultimate elongation	ASTM D412	450 %
Viscosity, Brookfield at 25 °C (77 °F)	-	150 000 cP



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE : All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.

sopca-en-ca-tds-colply-ef-flashing-cement.indd

COLPLY EF FLASHING CEMENT

TECHNICAL DATA SHEET 240809SCANE

(supersedes 230130SCANE)



COMPLEMENTARY PRODUCTS

APPLICATIONS

ROOFS

PROPERTIES *(Continued)*

Properties	Standards	COLPLY EF FLASHING CEMENT
Solids by weight	-	> 99 %
V.O.C.	EPA, Method 24	15 g/L
Curing time	-	7 days*

*Curing time was determined under ideal application conditions [25 °C (77 °F) and 50% relative humidity] it will be longer at lower temperatures. Curing time will also varies on the quantity applied.
(All values are nominal)

CLEANING

Tools and uncured adhesive can be cleaned with solvents, such as mineral spirits, Varsol, Xylene, etc.

STORAGE AND HANDLING

Up to **6 months**, stored in original sealed containers. COLPLY EF FLASHING CEMENT adhesive must be stored between **5 to 40 °C (41 to 104 °F)** in a ventilated place, away from heat and direct sunlight.

For more information, refer to instructions on the container label and relevant safety data sheet (SDS).



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE : All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.