

COLPLY TRAFFIC CAP (FR)



TECHNICAL DATA SHEET **250402SCANE**

(supersedes 250129SCANE)

DESCRIPTION

COLPLY TRAFFIC CAP is a high performance cap sheet membrane composed of SBS modified bitumen and a composite reinforcement. The surface is protected by coloured granules and the underface is sanded.

For ease of installation, when installed with cold adhesive at temperatures below 0 °C (32 °F), it is recommended to use the COLPLY TRAFFIC CAP FLEX membrane.

A cap sheet membrane offering better fire resistance is available in FR version (COLPLY TRAFFIC CAP FR).

INSTALLATION

1. ADHESIVE

- 1.1. Unroll COLPLY TRAFFIC CAP or COLPLY TRAFFIC CAP FR on the adhesive previously applied using a notched squeegee.
- 1.2. Apply pressure over the whole surface using a membrane roller to ensure good contact.
- 1.3. Apply adhesive on the first 100 to 125 mm (4 to 5 in) of the end laps with a notched trowel. Weld the last 25 to 50 mm (1 to 2 in) of the end laps, using an electric hot-air welder and a membrane roller.
- 1.4. Welding must also be done on all side laps. The use of an automatic hot-air welder will increase the speed and quality of the seal.

2. SEBS HOT BITUMEN

- 2.1. Unroll COLPLY TRAFFIC CAP or COLPLY TRAFFIC CAP FR in a bed of SEBS hot bitumen (SOPRASPHALTE M) applied with a mop.

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

GENERAL INFORMATION

Specifications	COLPLY TRAFFIC CAP & COLPLY TRAFFIC CAP FR
Reinforcement	Composite
Dimensions	10 x 1 m (33 x 3.3 ft)
Selvedge width	100 mm (4 in)
Surface	Granules
Underface	Sanded



SOPREMA.CA 1 877 MAMMOUTH

NOTE : All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.
This technical data sheet applies to products sold on the Canadian market only.

COLPLY TRAFFIC CAP (FR)



TECHNICAL DATA SHEET **250402SCANE**

(supersedes 250129SCANE)

PROPERTIES

Properties	COLPLY TRAFFIC CAP & COLPLY TRAFFIC CAP FR		Standard Requirements
	BEFORE Heat Conditioning	AFTER Heat Conditioning	CSA A123.23 Type C, Grade 1
Thickness, min.	3.5 mm (138 mils)		2.8 mm (110 mils)
Selvedge thickness, min.	2.75 mm (108 mils)		1.8 mm (70 mils)
Mass per unit area, min.	4.3 kg/m ² (88 lb/100 ft ²)		2.9 kg/m ² (60 lb/100 ft ²)
Strain energy, min. MD/XD, at 23 °C ± 2 °C (73.4 °F ± 3.6 °F) at -18 °C ± 2 °C (0 °F ± 3.6 °F)	8/6.5 kN/m (46/37 lbf/in) 8/7 kN/m (46/40 lbf/in)	7/6 kN/m (40/34 lbf/in) 6.5/6 kN/m (37/34 lbf/in)	5.5 kN/m (31 lbf/in) 3.0 kN/m (17 lbf/in)
Peak load, min. MD/XD, at 23 °C ± 2 °C (73.4 °F ± 3.6 °F) at -18 °C ± 2 °C (0 °F ± 3.6 °F)	17/14 kN/m (97/80 lbf/in) 22/19 kN/m (126/108 lbf/in)	18/15 kN/m (103/86 lbf/in) 22/17 kN/m (126/97 lbf/in)	Report value Report value
Elongation at peak load, min. MD/XD, at 23 °C ± 2 °C (73.4 °F ± 3.6 °F) at -18 °C ± 2 °C (0 °F ± 3.6 °F)	55/55% 45/45%	50/50% 35/35%	Report value Report value
Ultimate elongation, MD/XD, at 23 °C ± 2 °C (73.4 °F ± 3.6 °F)	65/65%	55/55%	Report value
Dimensional stability, max. MD/XD	±0.2/±0.2%		0.5%
Low temperature flexibility, max. MD/XD	-27/-27 °C (-17/-17 °F)	-18/-18 °C (-0.4/-0.4 °F)	-18 °C (-0.4 °F)
Low temperature flexibility after UV weathering, max. MD/XD	-12/-12 °C (10/10 °F)		-12 °C (10 °F)
Compound stability	121/121 °C (250/250 °F)		min. 91 °C (195 °F)
Resistance to puncture	Pass		Pass
Granule embedment	< 2.0 g (0.07 oz)		max. 2.0 g (0.07 oz)
Fire classification, according to ULC-S107 standard	Consult the TGFUC.R19921 Canada's Underwriters Laboratories (UL) directory for more information on the classification of SOPREMA roofing systems.		N/A

(All values are nominal)

STORAGE AND HANDLING

Rolls must be stored upright, with the selvedge side on top. If the products are stored outdoors, cover them with an opaque protection cover after removal of the delivery packaging.

TESTS AND CERTIFICATIONS



TESTED
ACCORDING TO
CSA A123.23
STANDARD

FOR MORE INFORMATION, REFER TO THE INSTRUCTIONS ON THE CONTAINER LABEL AND RELEVANT SAFETY DATA SHEET (SDS).



SOPREMA.CA 1 877 MAMMOUTH

NOTE : All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.
This technical data sheet applies to products sold on the Canadian market only.