

SOPRALAP STICK

TECHNICAL DATA SHEET 240213SCANE

(supersedes 200316SCANE)



WATERPROOFING

APPLICATIONS

ROOFS

DESCRIPTION

SOPRALAP STICK is a cover strip composed of SBS modified bitumen and a composite reinforcement. The surface is sanded and the self-adhesive underface is covered with a silicone release film.

SOPRALAP STICK is designed to ensure waterproofing of the end laps on composite panels and on COLVENT base sheet membranes. It can also be used with any other base sheet with sanded surface or other applications requiring the use of a cover strip.

SURFACE PREPARATION

Surfaces must be clean, dry and free of loose particles. The membrane is installed over the substrate previously primed with one of the ELASTOCOL STICK primers.

INSTALLATION

SELF-ADHESIVE

The SOPRALAP STICK cover strip is adhered to the substrate by peeling off the silicone release film.

Once the membrane is in place, apply pressure over the whole surface using a membrane roller to ensure a complete and uniform adhesion.

Minimal application temperature: 0 °C (32 °F).

FOR COMPLETE INFORMATION ON PRODUCT INSTALLATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

GENERAL INFORMATION

Specifications	SOPRALAP STICK
Reinforcement	Composite
Dimensions	12 x 0.33 m (39.6 ft x 13 in)
Surface	Sanded
Underface	Self-adhesive, covered with a silicone release film.

(All values are nominal)



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE : All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.

sopca-en-ca-tds-sopralap-stick.indd

SOPRALAP STICK

TECHNICAL DATA SHEET 240213SCANE

(supersedes 200316SCANE)



WATERPROOFING

APPLICATIONS

ROOFS

PROPERTIES

Properties	SOPRALAP STICK		CSA A123.23 Type C, Grade 3 Requirements
	BEFORE Heat Conditioning	AFTER Heat Conditioning	
Thickness, min.	2.5 mm (98 mils)		1.8 mm (70 mils)
Selvage thickness, min.	N/A		1.8 mm (70 mils)
Mass per unit area, min.	2.8 kg/m ² (60 lb/100 ft ²)		2.2 kg/m ² (45 lb/100 ft ²)
Strain energy, min. MD/XD, at 23 °C ± 2 °C (73.4 °F ± 3.6 °F) at -18 °C ± 2 °C (0 °F ± 3.6 °F)	8/6.5 kN/m (46/37 lbf/in) 8/7 kN/m (46/40 lbf/in)	7/6 kN/m (40/34 lbf/in) 6.5/6 kN/m (37/34 lbf/in)	5.5 kN/m (31 lbf/in) 3.0 kN/m (17 lbf/in)
Peak load, min. MD/XD, at 23 °C ± 2 °C (73.4 °F ± 3.6 °F) at -18 °C ± 2 °C (0 °F ± 3.6 °F)	17/14 kN/m (97/80 lbf/in) 22/19 kN/m (126/108 lbf/in)	18/15 kN/m (103/86 lbf/in) 22/17 kN/m (126/97 lbf/in)	Report value Report value
Elongation at peak load, min. MD/XD, at 23 °C ± 2 °C (73.4 °F ± 3.6 °F) at -18 °C ± 2 °C (0 °F ± 3.6 °F)	55/55% 45/45%	50/50% 35/35%	Report value Report value
Ultimate elongation, MD/XD, at 23 °C ± 2 °C (73.4 °F ± 3.6 °F)	65/65%	55/55%	Report value
Dimensional stability, max. MD/XD	±0.2/±0.2%		0.5%
Low temperature flexibility, max. MD/XD	-27/-27 °C (-17/-17 °F)	-18/-18 °C (-0.4/-0.4 °F)	-18 °C (-0.4 °F)
Compound stability	121/121 °C (250/250 °F)		min. 91 °C (195 °F)
Resistance to puncture	Pass		Pass

(All values are nominal)

STORAGE AND HANDLING

Rolls must be stored upright, with the selvage side on top. If the products are stored outdoors, cover them with an opaque protection cover after removal of the delivery packaging.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

NOTE : All products manufactured by SOPREMA Inc. comply with the description and properties indicated in the technical data sheet that was current at the date of manufacture.