

		PT. STEEL PIPE INDUSTRY OF INDONESIA Tbk. (SPINDO)		No Form : OCC/QM21 Revisi : 1 Halaman : 1 dari 1													
CHEMICAL ANALYSIS TEST REPORT																	
Customer : PT. DPM Order Prod. No. : - Size : 34,0X4,5XL Spec : STAM 390 G Reference : JIS G 3472 Test Frequency : 3 tests		Report No. : 29/QC-SKF/III/2017 Page : 1 of 1 Date : 30/03/2017 From : Lab Technician Distribution : QC Adm. Room Temp. : 19° C															
No.	Batch Number	C	Mn	P	S	Si	Mo*	Cr	Ni*	Ti*	Al	Cu*	V*	Nb*	CE*	Result	Remark
1	5153489	0,1364	0,4745	0,0129	0,0149	0,0231	0,0027	0,0252	0,0216	0,0016	0,0404	0,0388	0,0027	0,0009	0,2257	OK	
Standard Maximum		0,25 % Max	0,30-0,90 % Max	0,035 % Max	0,035 % Max	0,35 % Max	%	%	%	%	%	%	%	%	%		

Note :

ok : Accept

rej : Reject

Prepared By,



Lab Technician

Checked By,



Karu Lab

Approved By,



Kasie QC