



PT. DHARMA POLIMETAL METALLURGICAL LABORATORY



Jl. Angsana raya Blok : A9 No:8 Delta silikon 1, Cikarang Tlp : 021-8974559 , Ext 532
Web : <http://www.dharmap.com> Email : info@dp.dharmap.com

VERIFIKASI PENGUJIAN TARIK

Page 1 of 1



Supplier Sample	PT. PERSADA SELARAS INDONESIA	Dibuat Untuk Executed for	QA DAC
Tanggal Uji Date of Testing	31.08.2016	REF. Standard Ref. Standard	JIS G 3131
Nama Sampel Sample Name	PLATE RL, HOOK SPRING, STAY AB FR CVR, STAY INNER & PLATE	Mesin Uji Testing Machine	SERVOPULSER SHIMADZU
Spesifikasi Sampel Sample Specification	SPHC, t=2.0 mm	Status Pengujian Type of Testing	NEW PROJECT
Model Type	K93A	Pelanggan Customer	PT. AHM

ACTUAL PENGUJIAN

ACTUAL						
Spesifikasi Material	Dimensi Ukur (mm)	Area (mm ²)	Max Force (N)	Batas Luluh Yield strength (N/mm ²)	Kuat Tarik Tensile strength (N/mm ²)	Regangan Elongation (%)
SPHC-P t=2.0 mm	t=2.0 w=25	50	19,100.00	274	382	38.58

STANDARD

STANDARD	Designation	Test piece	Batas Luluh Yield strength (N/mm ²)	Kuat Tarik Tensile strength (N/mm ²)	Regangan Elongation (%)
JIS G 3131	SPHC-P t=2.0 mm	No : 5	-	270 N/mm ² (min)	29 % (min)






PT. DHARMA POLIMETAL

Jl Raya Serang KM 24 Balara - Tangerang 15610. Banten - Indonesia
Telp : 62-21-5951630, ext : 162, 301 Fax : 62-21-5952615. webset : www.dharmap.com

LABORATORIUM METALLURGY



LAPORAN PENGUJIAN TARIK TENSILE TEST REPORT



Page 1 of 1

* Plate R_L stand tread

No Laporan	318/QA/LMDAC/UTM/IX/2016	Model	K93A
Report No		Type	
Tanggal uji	01.10.2016	Pelanggan	PT AHM
Date of test		Customer	
Nama sample	STAY (STAY AB FR COVER)&STAY&PLATE (STAY INNER)	Supplier Sample	PT PSI
Sample Name		Sample Supplier	
No Lot	V 60232	Status pengujian	NEW PROJECT
Lot Number		Propertis Of testing	

STANDARD					
JIS G3131	Designation	Test piece	Yield point (N/mm ²)	Tensile Strength (N/mm ²)	Elongation (%)
	SPHC	No:5	-	270 min	29 min
ACTUAL					
Spesifikasi Material	Area (mm ²)	Max Force (N)	Batas Luluh Yield strength (N/mm ²)	Kuat Tarik tensile Strength (N/mm ²)	Regangan Elongation (%)
SPHC, t=2.0 mm	47.885	16657.6	288.78	347.87	40.00
SPHC, t=2.0 mm	48.115	16630.1	287.77	345.63	39.00

Sketsa Sample
Sample Figur



Cikarang : 01.10.2016

LABORATORIUM METALLURGY

JUDGEMENT	
OK	NG

Tested By	Checked By	Approved By
SERY	MERDIANA	M.IMRAN

Laporan hasil pengujian ini hanya berlaku untuk sample yang di uji di laboratorium Metallurgi
Publikasi serta penggunaan dokumen ini atau sebagian dari padanya harus dengan izin dari laboratorium Metallurgi