


## 0079337A7

110 Delta Drive Pittsburgh, PA 15238 NAFTA Sales: (1)800-245-3984 HK Sales : (852)3102-9337

magnetics@spang.com www.mag-inc.com



| Kool Mµ MAX         | AL      |               | Coating        |                     |       |
|---------------------|---------|---------------|----------------|---------------------|-------|
| Permeability<br>(μ) | (nH/T²) | Lot<br>Number | Part<br>Number | Inductance<br>Grade | Color |
| 26                  | 68 ± 8% | XXXXXX        | 79337A7        | N/A                 | Black |

| Dimensions | Uncoated |       | Coated Limits |       |     | Packaging          |
|------------|----------|-------|---------------|-------|-----|--------------------|
| Dimensions | (mm)     | (in)  | (mm)          | (in)  |     |                    |
| OD (A)     | 132.6    | 5.219 | 134.0         | 5.274 | max | Cardboard cut-outs |
| ID (B)     | 78.60    | 3.094 | 77.19         | 3.039 | min | Box Qty= 16 pcs    |
| HT (C)     | 25.40    | 1.000 | 26.80         | 1.055 | max |                    |

| Electrical Characteristics                   |                         |     | Physical Characteristics                                       |                               |  |   |                                       |   |               |
|--|-------------------------|-----|--|-------------------------------|--|---|---------------------------------------|---|---------------|
| Watt Loss<br>@ 100 kHz, 50mT<br>max (mW/cm³) | DC Bias<br>min (A·T/cm) |     | Voltage<br>Breakdown<br>wire to wire<br>min (V <sub>AC</sub> ) | Break<br>Strength<br>min (kg) | Window<br>Area<br>W <sub>A</sub> (mm²) | Cross<br>Section<br>A <sub>e</sub> (mm <sup>2</sup> ) | Path<br>Length<br>L <sub>e</sub> (mm) | Volume<br>V <sub>e</sub> (mm <sup>3</sup> ) | Weight<br>(g) |
| 700  | 80%                     | 50% | 2000   | 113                           | 4.710                                  | 678   | 324                                   | 220,000                                     | 1.050         |
| 700  | 106                     | 227 | 2000   | 113                           | 4,710                                  | 0/0   | 324                                   | 220,000                                     | 1,250         |

|   |      | Temperature Rating |                            |                           |        |                   |                                  |
|---|------|--------------------|----------------------------|---------------------------|--------|-------------------|----------------------------------|
| Winding Length Per Turn                   |      |                    | Wound Coil Dimensions (mm) |                           |        | Curie Temp: 500°C |                                  |
| \A('' \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ \ |      | 14 <i>C</i> - C    |                            | 40% Winding Factor        | OD     | 146               | Coating Temp (Continuous up to): |
| Winding<br>Factor                         | (mm) | Winding<br>Factor  | (mm)                       | 40% Willding Factor       | HT     | 50.7              | 200°C                            |
| ractor                                    |      | Factor             |                            | Completely Full Window    | Max OD | 179               | Notes:                           |
| 0%  | 110  | 40%                | 150                        | Completely Full Window    | Max HT | 78.8              |                                  |
| 20%                                       | 130  | 45%                | 156                        | Surface Area (mm²)        |        |                   |                                  |
| 25%                                       | 135  | 50%                | 162                        |                           |        |                   |                                  |
| 30%                                       | 139  | 60%                | 173                        | Unwound Core 36,000       |        |                   |                                  |
| 35%                                       | 145  | 70%                | 187                        | 40% Winding Factor 65,000 |        |                   |                                  |

