



地址: 中国 辽宁 大连 金州新区

Add: No.18,HeBin South Road ,DengShaHe Coastal Industrial Zone,

登沙河临港工业园区 河滨南路 18 号

JinZhou District ,DaLian ,LiaoNing, Province,China.

邮编: 116105 服务电话: 0411-62693173 传真: 0411-62693094

Post code: 116105 Serve Tel: 0411-62693173 Fax: 0411-62693094

订货单位 Purchaser		订货单位代码 Customer No.	091649	记录号 Record No.	DLZJC-03-0
合同号 Contract No.		品名 Name	轴承钢	证明书号 Certificate No.	W2503-0249991
生产号 Production No.	C25BA0081DQ001	形状 Shape		入库票号 Into Depot No.	E58553334
牌号 Steel Grade	GCr15	图纸号 Drawing No.		重量(T) Weight	4.358吨
技术条件 Specification	GB/T18254-2016	冶炼方法 Melting Method	按标准	规格 (mm) Size	24
加工用途 Designated Further	冷压力加工	炉号 Heat No.	2510511770	长度(mm) Length	fixed length: 5800
交货状态 Condition of Delivery		许可证号 License No.	XK05-006-00212	件/盘数 Bundle Number	2
热处理号 Heat Treatment Na		签发日期 Date of Issue	20250329153007	支数 Piece Number	2

一、化学成分 (%) Chemical Composition (%)

1. 熔炼成分
C | 0.98 Si | 0.25 Mn | 0.34 P | 0.010 S | 0.002 Cr | 11.46 Ni | 0.07 Cu | 0.03
Mo | 0.03 Ti | 0.0017 Al | 0.016 Pb | 0.000 As | 0.00 As+Sn+Sb | 0.003

2. 产品化学成分

O | 0.00075

二、力学性能 Mechanical Property

1. 硬度 Heading

退火硬度 Hardness

205 | 198 | 197 | 201 | 205

三、微观检验 Microstructure Exammination

1. 非金属夹杂物 Non-metallic Inclusions

A粗(级)	A(Thick)(Grade)	0.0	0.0	0.0	0.0	0.0	0.0
A细(级)	A(Thin)(Grade)	0.5	0.5	0.5	0.5	0.5	0.5
B粗(级)	B(Thick)(Grade)	1.0	0.0	0.0	0.0	0.0	1.0
B细(级)	B(Thin)(Grade)	0.5	0.5	0.5	0.5	0.5	0.5
C粗(级)	C(Thick)(Grade)	0.0	0.0	0.0	0.0	0.0	0.0
C细(级)	C(Thin)(Grade)	0.0	0.0	0.0	0.0	0.0	0.0
D粗(级)	D(Thick)(Grade)	0.0	0.0	0.0	0.0	0.0	0.0
D细(级)	D(Thin)(Grade)	0.5	0.5	0.5	0.5	0.5	0.5
DS(级)	Ds(Grade)	0.0	0.0	0.0	0.0	0.0	0.0

2. 脱碳 Decarburized Layer

总脱碳层(mm) Total Decarburization(mm)

0.28 | 0.28 | 0.28 | 0.28 | 0.28

3. 显微组织 Microstructure

球化(级)	spheroidization(Grade)	2	2	2	2	2
碳化物带状(级)	Carbide Segregation(Grade)	2.0	2.0	2.0	2.0	2.0
碳化物网状(级)	Carbide Network(Grade)	2.5	2.5	2.5	2.5	2.5
碳化物液析(级)	Carbide Liquation(Grade)	0	0	0	0	0
显微孔隙	Microporosity	0	0	0	0	0

四、宏观检验 Macrostructure Exammination

1. 低倍 Macrostructure

一般疏松(级)	General Porosity(Grade)	0.5	0.5	0.5	0.5	0.5
中心疏松(级)	Central Porosity(Grade)	1.0	1.0	1.0	1.0	1.0
锭型偏析(级)	Pattern Segregation(Grade)	0.5	0.5	0.5	0.5	0.5
中心偏析	Center Segregation(Grade)	1.0	1.0	1.0	1.0	1.0

2. 断口 Fradure

断口要求 Fracture | 合格 | 合格

备注:
Note 表面质量: 合格 尺寸外形: 合格声明:
Statement经检验与试验,本产品符合合同及标准之规定
Through inspection and testing, the quality of
product conforms to the stipulations of the
related contract and standards.质量判定人:
Quality Judge:

邱飞玉

质量负责人:
Quality Manager:

李红明

