EASY MIX RATIO

CHARACTERISTICS						HANDLING PROPERTIES			TYPICAL CURED PROPERTIES						
Product	Chemistry	Thermally Conductive	Chemical Resistance	Low Viscosity	High Temp.	Mixed Viscosity (cP@25°C)	Mix Ratio by Weight	Cure Temp. Room/Heat	Temperature Range of Use	Specific Gravity	Hardness	Thermal Conductivity (W/m.K)	Dielectric Strength (V/mil)	Dielectric Constant at 1mHz	Features and Typical Applications
EASY MIX RATIO															
1265 A/B	Epoxy		Good	X		600	100:100	Heat	-40 to +65°C	1.08	25A	N/A	N/A	3.0	
1269A A/B	Epoxy		Good	X	X	5,000	100:100	Heat	-40 to +130°C	1.20	85D	0.27	430	3.8	
1497 A/B	Epoxy	X	Good		X	150,000	100:100	Heat	-65 to +155°C	1.70	80D	0.68	425	3.6	Primarily designed for ease of use in either meter mix or manual dispense operations. These products also offer a wide range of features including heat dissipation, thermal and mechanical shock, as well as thermal conductivity.
2072 A/B	Epoxy		Good	X	X	8,000	100:50	RT/HT	-40 to +130°C	1.60	89D	0.42	400	4.2	
2741LV/15LV	Epoxy		Good			30,000	400:100	RT/HT	-40 to +90°C	1.43	80D	N/A	400	3.3	
2760 A/B	Epoxy/ Polyurethane	X	Good			18,000	100:50	RT/HT	-40 to +130°C	1.55	80D	0.60	450	4.0	
3180M A/B	Epoxy		Good			15,000	100:100	RT/HT	-40 to +130°C	1.62	80D	0.40	430	4.0	
5952 A/B	Silicon	X	Poor		X	40,000	100:100	RT/HT	-65 to +260°C	2.05	75A	0.85	450	5.0	
E-1410 A/B	Epoxy	X	Good		X	35,000	100:100	Heat	-40 to +175°C	1.80	94D	0.57	N/A	4.0(3)	
S 5225 A/B	Silicone		Poor	X	X	2,420	100:100	RT/HT	-60 to +220°C	1.59	53A	N/A	450	3.0	
GENERAL PURPOSE															
One Component Systems															
A-312	Epoxy		Excellent	X		3,000	N/A	Heat	-40 to +130°C	1.14	86D	N/A	N/A	N/A	These general purpose encapsulants were designed to offer a wide range of features including thermal conductivity, mechanical shock and impact resistance, as well as thermal shock protection.
E-151-8	Epoxy		Good	X		1,100	N/A	Heat	-40 to +130°C	1.05	55D	N/A	325	3.4(3)	
Two Component Systems															
1090/11	Epoxy		Good		X	29,000	100:10.5	Heat	-55 to +155°C	0.80	82D	0.19	375	2.7	
2057/9	Epoxy		Good	X		4,000	100:6.5	RT/HT	-40 to +130°C	1.54	85D	N/A	400	4.2	
2651-40/23LV	Epoxy	X	Good	X		2,200	100:18	RT/HT	-65 to +105°C	1.40	85D	0.55	450	3.8	
2651MM/11	Epoxy	X	Good		X	13,000	100:8.5	Heat	-55 to +155°C	1.59	89D	0.60	450	3.7	
E-1400 A/B	Epoxy	X	Good			15,000	100:100	RT/HT	-65 to +105°C	1.68	75D	0.74	400	4.0	

Please call us at **1-800-832-4929** to talk to our application experts, order a free evaluation sample, or receive more information about our products.

www.emersoncuming.com

(1) Dielectric constant measured at 60Hz (2) Dielectric constant measured at 1kHz (3) Dielectric constant measured at 100Hz

Emerson & Cuming
a National Starch & Chemical Company



www.emersoncuming.com

Europe
Nijverheidsstraat 7
B-2260 Westerlo
Belgium
+(32) (0) 14 57 56 11
Fax: +(32) (0) 14 58 55 30

North America
46 Manning Road
Billerica, MA 01821
(800) 832-4929
(978) 436-9700
Fax: (978) 436-9701

Asia-Pacific
100 Kaneda, Atsugi-shi
Kanagawa-ken, 243
Japan
(81) 462-25-8815
Fax: (81) 462-22-1347

The information given and the recommendations made herein are based on our research and are believed to be accurate but no guarantee of their accuracy is made. In every case we urge and recommend that purchasers before using any product in full scale production make their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purposes under their own operating conditions. No representative of ours has any authority to waive or change the foregoing provisions but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to their needs and to the circumstances prevailing in their business. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without the authority from the owner of this patent. We also expect purchasers to use our products in accordance with the guiding principles of the Chemical Manufacturers Association's Responsible Care® program.

8901C-00-0310-3M

© 2000 National Starch and Chemical Company

Responsible Care®
A Public Commitment