PCBM-CG: A place for tired LaTeXto rest

Jarvist M. Frost

Centre for Sustainable Chemical Technologies and Department of Chemistry, University of Bath, Claverton Down, Bath BA2 7AY, UK

Received March 31, 2014; E-mail:

Abstract: Abstract. EPSRC gave us some money so we did our best to do great science, and these are our conclusions.

Lambdas

Table 1. Inner sphere reorganisation energies of Mono, Bis and Tris PC−60BM fullerenes. All units meV.

Isomer	λ_{neut}	λ_{ion}	λ_{tot}
mono	77.91	77.49	155.40
bis-C1	111.52	182.64	294.16
bis-C2	108.54	158.89	267.43
bis-C3	81.38	83.31	164.69
bis-E1	88.82	89.49	178.31
bis-T1	138.30	151.32	289.62
bis-T2	80.30	80.93	161.23
bis-T3	125.77	166.20	291.97
bis-T4	87.66	95.56	183.22
tris-E,E,E	108.42	105.41	213.84
tris-E,E,T1(1)	99.51	100.82	200.33
tris-E,E,T1(2)	94.62	98.86	193.49
tris-E,T3,T2	93.97	92.93	186.90
tris-E,T4,T2	98.54	106.46	205.00
tris-E,T4,T3	100.51	100.06	200.56
tris-T3,T3,T3	137.97	173.63	311.60
tris-T4,T3,T3	200.30	226.34	426.64
tris-T4,T4,T2	149.22	148.26	297.48
tris-T4,T4,T4	136.01	166.56	302.57

Some mobs

Table 2. Mobility by Time of Flight, with varying energetic disorder. Units are $\mathrm{cm}^2/\mathrm{Vs}$

σ	$0. \times 10^{-3}$	56×10^{-3}	121×10^{-3}
M	4.40×10^{-3}	2.72×10^{-3}	0.837×10^{-3}
B	2.27×10^{-3}	1.30×10^{-3}	0.329×10^{-3}
B-E1	1.88×10^{-3}	1.09×10^{-3}	0.277×10^{-3}
T	1.20×10^{-3}	0.589×10^{-3}	0.126×10^{-3}
T-EEE	0.623×10^{-3}	0.429×10^{-3}	0.0854×10^{-3}

Acknowledgement We acknowledge membership of the UK's HPC Materials Chemistry Consortium, which is funded by EPSRC grant EP/F067496. J.M.F. is funded by EPSRC Grant EP/K016288/1. We are grateful for the lyrical encouragment of Salt N Pepa.

Supporting Information Available: The data set and analysis codes, TrendyName, are available as a source code repository on GitHub.[1] This material is available free of charge via the Internet at `http://pubs.acs.org/`.

References

(1) WMD-Bath/StarryNight. `https://github.com/WMD-Bath/StarryNight`.