



SAMRAT POLY RESINS

Manufacturer of Coating & Composite Resins · Doraha, Ludhiana, Punjab, India

SAFETY DATA SHEET

Doc. Ref: SPR-SDS-FPP · Rev. 01 · Issue Date: 8 August 2026

FRP POLYESTER PIGMENT

High-Strength Colour Paste for FRP · UPR-Compatible · RAL & Pantone Custom Matching

THIS IS A PIGMENT PASTE, NOT A RESIN

FRP Polyester Pigment is a colour paste/colourant — it is NOT an unsaturated polyester resin, gelcoat, catalyst, or resin solution in its own right. It is intended to be blended into unsaturated polyester resin, vinyl ester resin, or gelcoat systems at a recommended 2–5% dosage by the customer. None of the resin-specific hazard information, storage warnings, or transport classification used in this company's resin product SDS documents (flammable liquid, styrene content, MEKP, UN 1866) applies to this product unless specifically stated below.

FRP Polyester Pigment is an industrial colour pigment paste for FRP/composite applications, compatible with unsaturated polyester resins (UPR), vinyl ester resins, and gelcoats. It is used for colouring FRP mouldings, tanks, pipes, panels, electrical enclosures, and automotive/boat components, and other manufacturer-approved composite applications. It is available in multiple colours (RAL, Pantone, and custom shades).

Not for use in food-contact, medical, pharmaceutical, cosmetic, children's products, or other applications unless specifically approved by the manufacturer.

SECTION 1: IDENTIFICATION

1.1 Product Identifier

Product Name	FRP Polyester Pigment
Product Type	Industrial colour pigment paste for FRP/composite applications
Chemical Family	Proprietary pigment paste (colour-dependent composition) — not a resin, catalyst, or solvent product
Product Code / Internal Reference	FPP
SDS Document Reference	SPR-SDS-FPP, Rev. 01

1.2 Relevant Identified Uses and Uses Advised Against

- Recommended use: Colouring of unsaturated polyester resin, vinyl ester resin, gelcoat, FRP mouldings, tanks, pipes, panels, electrical enclosures, automotive/boat components, and other manufacturer-approved composite applications — including FRP tanks and pipes, gelcoats for boats and automotive components, decorative and architectural panels, and electrical enclosures. For industrial/professional use only.
- Uses advised against: Food-contact, medical, pharmaceutical, cosmetic, children's products, or other applications unless specifically approved by the manufacturer; any use not confirmed with Samrat Poly Resins technical staff.

1.3 Details of the Supplier of the Safety Data Sheet

Company Name	Samrat Poly Resins
Registered Activity	Manufacturer of Coating & Composite Resins (ISO 9001:2015 certified)
Address	Oswal Road, Near GT Road, Doraha, Ludhiana — 141421, Punjab, India

GST No.	03ALBPS3446G1ZB
Website	samratpolyresins.in
Email	info@samratpolyresins.in

1.4 Emergency Telephone Number

Company Emergency Contact	+91 74638 81652
National Poison Information Centre (India)	1800-116-117 (Toll-Free, 24x7) — National Poisons Information Centre, AIIMS New Delhi

SECTION 2: HAZARD IDENTIFICATION

CLASSIFICATION NOT ESTABLISHED — COMPOSITION NOT DISCLOSED

A specific GHS classification is NOT established for this product. The manufacturer's TDS does not disclose the pigment identity, carrier/paste vehicle chemistry, or stabiliser/dispersant package — and this is a multicolour product family where composition may genuinely vary by shade (RAL, Pantone, or custom colour). Assigning a signal word or hazard statements without this data would mean guessing, which this SDS does not do.

This is NOT a flammable liquid (the UN 1866 / Class 3 classification used for this company's resin products does not apply), and it is NOT an organic peroxide (the classification used for MEKP Hardener does not apply). Beyond ruling those out, no further classification can be responsibly assigned without the actual formulation data for the specific colour supplied.

2.1 Classification of the Substance or Mixture (GHS)

Not established. Jaspal (company chemist) should confirm the actual pigment/carrier/additive composition for each colour variant supplied, so that a defensible, colour-specific classification can be assigned. Until then, this product should be handled with the general precautions in Section 2.2 and Section 8, which are prudent regardless of formal classification.

2.2 General Precautions (Pending Composition-Specific Classification)

- Avoid unnecessary skin and eye contact.
- Use in an adequately ventilated area.
- Avoid ingestion.
- Wear the PPE specified in Section 8 when handling in bulk or during extended contact.
- Mechanical processing of cured pigmented composites or dried product residue may generate particulate dust — see Section 8.

SECTION 3: COMPOSITION / INFORMATION ON INGREDIENTS

FRP Polyester Pigment is a mixture. Composition is proprietary and may vary by colour (RAL, Pantone, or custom shade) — this is a master SDS covering the product family in general terms, not a single fixed formulation.

Component	CAS No.	Concentration (% w/w)	Function
Pigment / colourant package	Varies by colour / proprietary	Manufacturer-controlled proprietary concentration	Provides colour and tinting strength. Identity may vary according to the specific RAL, Pantone, or custom colour supplied — not confirmed as titanium dioxide, iron oxide, carbon black, phthalocyanine, or any other specific compound for any given shade without manufacturer confirmation.
Carrier / paste vehicle	Proprietary / not disclosed	Manufacturer-controlled proprietary concentration	Provides paste consistency, pigment wetting, dispersion,

Component	CAS No.	Concentration (% w/w)	Function
			and compatibility with polyester/vinyl ester/gelcoat systems. NOT confirmed as styrene, unsaturated polyester resin, plasticiser, solvent, or reactive monomer — no such chemistry is disclosed in the manufacturer's TDS.
Stabiliser / dispersant additive package	Proprietary / not disclosed	Manufacturer-controlled proprietary concentration	Supports pigment dispersion, storage stability, lightfastness, and processing compatibility.

COLOUR-DEPENDENT COMPOSITION — CONFIRM WITH JASPAL PER SHADE

This composition table cannot be made more specific without manufacturer/chemist disclosure of the actual pigment identity, carrier chemistry, and additive package — and because this is a multicolour product, that disclosure may need to be done per shade rather than once for the whole family. If a specific colour is known to contain a hazardous pigment (e.g. certain heavy-metal-based colourants used industry-wide in some pigment classes), that shade may require its own composition entry and classification, separate from this general document.

SECTION 4: FIRST-AID MEASURES

4.1 Description of First-Aid Measures

Eye Contact	Rinse cautiously with clean water for several minutes. Remove contact lenses if present and easy to do — continue rinsing. Seek medical attention if irritation persists.
Skin Contact	Remove contaminated clothing. Wash affected skin thoroughly with soap and water. Seek medical attention if irritation persists.
Inhalation	Under normal paste handling, inhalation exposure is expected to be limited, but vapours or mist may occur depending on the carrier and processing method (e.g. spray application). Move the affected person to fresh air if symptoms occur. Seek medical attention for persistent irritation or symptoms.
Ingestion	Rinse mouth. Never give anything by mouth to an unconscious person. Seek medical advice if significant ingestion occurs.

4.2 Most Important Symptoms and Effects, Acute and Delayed

Not established for the complete product. Depending on the actual pigment and carrier composition (not disclosed), skin, eye, or respiratory irritation is possible from any industrial colour paste of this general type — general precautions in Sections 2 and 8 apply regardless. No aspiration hazard is asserted, as the carrier composition supporting such a classification is not confirmed.

4.3 Notes to Physician

Treat symptomatically. No specific antidote is known or indicated by available product information.

SECTION 5: FIRE-FIGHTING MEASURES

This product's fire behaviour depends on its actual carrier and pigment composition, which is not disclosed. It is a paste, heat-resistant to 180°C per the manufacturer's TDS, and no flammable solvent or reactive monomer content is confirmed — this is not expected to present the same flammable-liquid fire profile as this company's resin products, but this has not been separately tested or certified as non-flammable.

5.1 Extinguishing Media

- Suitable: Dry chemical, foam, carbon dioxide (CO2), water spray/fog for cooling containers — select based on the surrounding fire, as is standard practice for a product without a confirmed distinct flammability hazard.

5.2 Special Hazards Arising from the Substance or Mixture

Not established for the complete product. Combustion may generate carbon monoxide, carbon dioxide, and smoke, along with decomposition products specific to the actual (undisclosed) pigment/carrier system. No styrene vapours, hydrogen halides, metal fumes, or specific heavy-metal combustion products are asserted, as no such ingredients are confirmed present.

5.3 Advice for Fire-Fighters

- Use suitable protective equipment and self-contained breathing apparatus (SCBA) as a general precaution, particularly in an enclosed space or where the surrounding fire involves other chemicals.
- Cool fire-exposed containers with water spray from a safe distance if practical.

SECTION 6: ACCIDENTAL RELEASE MEASURES

6.1 Personal Precautions, Protective Equipment and Emergency Procedures

- Restrict unnecessary access to the spill area.
- Wear appropriate PPE as described in Section 8. Avoid skin and eye contact.

6.2 Environmental Precautions

- Prevent release into drains, soil, and waterways.
- Notify the relevant Pollution Control Board and site EHS personnel for any release that reaches, or is likely to reach, a drain or waterway.

6.3 Methods and Material for Containment and Cleaning Up

- Scrape or scoop bulk paste into appropriate labelled containers — this product is a paste, not a free-flowing liquid, and spill response should reflect that consistency.
- Absorb residual material with an inert absorbent where necessary. Avoid spreading pigment contamination onto adjacent surfaces.
- Clean affected surfaces using cleaning methods compatible with the actual carrier chemistry.
- Dispose through authorised waste channels — see Section 13.

SECTION 7: HANDLING AND STORAGE

7.1 Precautions for Safe Handling

- Avoid unnecessary skin and eye contact. Use clean tools to prevent contamination between batches/colours.
- Maintain good industrial hygiene. Ensure ventilation appropriate to the carrier system and application method (e.g. spray application may require additional ventilation/PPE).
- Keep away from incompatible chemicals — specific incompatibilities are not established given the undisclosed composition; use general good practice segregation from strong oxidisers, acids, and bases pending confirmation.
- Keep container tightly closed when not in use.

7.2 Conditions for Safe Storage, Including Any Incompatibilities

This product's storage requirements are based on its own manufacturer TDS data and are NOT the same as this company's resin products — the flammable-liquid storage warning used for GP Clear/Yellow/White Resin and related products (storage temperature overlapping a 31–34°C flash point) does not apply here, as no such flash point is disclosed or indicated for this product.

Storage Temperature	15–30°C, per manufacturer TDS.
Storage Conditions	Store in a cool, dry place away from direct sunlight, per manufacturer TDS. Protect from excessive heat.

Shelf Life	12 months in unopened original packaging, per manufacturer TDS.
Incompatible Materials	Not established — actual incompatibilities depend on the undisclosed pigment/carrier composition. Avoid contamination and segregate from strong oxidisers, acids, and bases as a general precaution.
Packaging Material	10 kg bottle, per manufacturer TDS. Keep tightly closed when not in use.

7.3 Specific End Use(s)

Colourant for unsaturated polyester resin, vinyl ester resin, and gelcoat systems, at a recommended dosage of 2–5% by weight per the manufacturer TDS. Refer to the product TDS (SPR-TDS-FPP) for dosage, tinting strength, and colour-matching guidance.

SECTION 8: EXPOSURE CONTROLS / PERSONAL PROTECTION

8.1 Control Parameters — Occupational Exposure Limits

No occupational exposure limit is established for this product, as its composition is not disclosed and no component-specific OEL is confirmed. Styrene exposure limits (used for this company's resin products) do NOT apply here, as styrene is not confirmed present in this pigment paste. If a specific colour is confirmed to contain an ingredient with an established OEL, that colour-specific limit should be added to this section.

8.2 Exposure Controls

- Engineering controls: Adequate general and local ventilation appropriate to the carrier system and application method — spray application, in particular, may generate mist requiring additional ventilation.
- Eye/face protection: Chemical safety glasses or goggles.
- Hand protection: Protective gloves compatible with the carrier chemistry (specific glove material not established given undisclosed composition — select based on general chemical resistance practice).
- Body protection: Protective work clothing.
- Respiratory protection: Determined by actual carrier vapour/mist generation, spray application, and dried pigment dust — not established generically; assess based on the specific application method and, where relevant, the specific colour's composition.
- General hygiene: Good hand hygiene. Wash hands and exposed skin thoroughly after handling.

DOWNSTREAM PROCESSING — DUST FROM CURED/DRIED MATERIAL ONLY

The supplied product is a paste, not a dry powder, and normal handling should not be treated as a dust exposure. However, mechanical processing of cured pigmented composites or dried product residue (sanding, grinding, cutting) may generate particulate dust. Provide appropriate local extraction, eye protection, protective clothing, and particulate respiratory protection according to the actual pigment composition and workplace exposure conditions.

SECTION 9: PHYSICAL AND CHEMICAL PROPERTIES

Appearance	Pigmented colour paste, per manufacturer TDS
Physical Form	Paste
Colour	Multicolour; RAL, Pantone, and custom shades available, per manufacturer TDS
Odour	Not established — no odour data provided in the manufacturer's TDS
pH	Not established — no product-specific pH data provided in the manufacturer's TDS
Melting / Freezing Point	Not established for the complete product
Initial Boiling Point / Range	Not established for the complete product
Flash Point	Not established — no product-specific value provided in the manufacturer's TDS. NOT assumed to fall in this company's resin flash-point range, as no such chemistry is confirmed present

Evaporation Rate	Not established for the complete product
Flammability	Not established / not classified — see Section 5
Vapour Pressure	Not established for the complete product
Vapour Density	Not established for the complete product
Relative Density / Specific Gravity	1.45 g/cm ³ , per manufacturer TDS (chemist-verified)
Solubility	Not established — depends on the actual, undisclosed carrier/pigment system
Partition Coefficient (log K_{ow})	Not established for the complete product
Auto-Ignition Temperature	Not established for the complete product
Decomposition Temperature	Not established for the complete product
Heat Resistance	Up to 180°C, per manufacturer TDS. This is a technical product-performance property (thermal stability of the colour effect in the cured composite) — it is NOT a decomposition temperature or flash point value and should not be read as one
VOC Content	Not established — no product-specific VOC data provided; NOT assumed to match this company's resin products' VOC content

Additional manufacturer technical reference data (not core SDS physical/chemical hazard properties): Light fastness 7–8 on the Blue Wool Scale; recommended dosage 2–5% by weight; tinting strength high (≥95%). These describe colour performance in the finished composite and are provided for product identification only.

SECTION 10: STABILITY AND REACTIVITY

10.1 Reactivity

Not established for the complete product. No reactive polyester/styrene chemistry or organic peroxide sensitivity is confirmed present in this pigment paste — the polymerisation hazard warnings used for this company's uncatalyzed resin products do not apply here unless the actual composition is confirmed to include such chemistry.

10.2 Chemical Stability

Stable under recommended storage conditions (Section 7). Avoid excessive heat and direct sunlight.

10.3 Possibility of Hazardous Reactions

Not established for the complete product; depends on the actual, undisclosed carrier and pigment package. Avoid contamination with incompatible chemicals as a general precaution.

10.4 Conditions to Avoid

- Excessive heat and direct sunlight during storage.
- Contamination with incompatible chemicals (not established given undisclosed composition).

10.5 Incompatible Materials

Not established for the complete product. The MEKP/organic peroxide incompatibility warnings used for this company's uncatalyzed resin products are not relevant to this pigment paste unless the actual composition is confirmed to include reactive resin chemistry.

10.6 Hazardous Decomposition Products

Not established for the complete product. Combustion may generate carbon monoxide, carbon dioxide, and smoke; specific decomposition products depend on the actual, undisclosed pigment/carrier chemistry.

SECTION 11: TOXICOLOGICAL INFORMATION

Not established for the complete product. The pigment identity, carrier/binder chemistry, and dispersant/stabiliser package are not disclosed in the manufacturer's TDS, and composition may vary by colour (RAL, Pantone, or custom shade). Styrene toxicology (used for this company's resin products) does NOT apply here, as styrene is not confirmed present. No reproductive toxicity, aspiration toxicity, chronic organ toxicity, or carcinogenicity is asserted without composition support.

11.1 Information on Toxicological Effects

Acute Toxicity — Oral/Inhalation/Dermal	Not established for the complete product
Skin Corrosion / Irritation	Not established for the complete product; general industrial colour-paste handling precautions apply (Section 8)
Serious Eye Damage / Irritation	Not established for the complete product; general precautions apply (Section 8)
Respiratory / Skin Sensitisation	Not established for the complete product
Germ Cell Mutagenicity	Not established for the complete product
Carcinogenicity	Not established for the complete product — not asserted without composition support
Reproductive Toxicity	Not established for the complete product — not asserted without composition support
STOT — Single/Repeated Exposure	Not established for the complete product
Aspiration Hazard	Not asserted — carrier composition supporting this classification is not confirmed

Where a specific colour is confirmed by the manufacturer to contain a particular pigment or additive with known toxicological data, that information should be added to this section for the relevant shade.

SECTION 12: ECOLOGICAL INFORMATION

Not established for the complete product. Styrene aquatic toxicity data (used for this company's resin products) does NOT apply here, as styrene is not confirmed present. Ecological characteristics depend on the actual, undisclosed pigment and carrier composition, and may vary by colour.

12.1 General Precaution

Prevent release into drains, soil, groundwater, and surface water, consistent with good practice for any industrial chemical product regardless of formal ecological classification.

12.2 Persistence, Bioaccumulation, and Other Effects

Not established for the complete product. A formal PBT/vPvB assessment has not been performed.

SECTION 13: DISPOSAL CONSIDERATIONS

13.1 Waste Treatment Methods

- Dispose through authorised industrial/hazardous waste handlers where applicable to the actual composition of the colour supplied.
- Do not discharge concentrated pigment paste into drains or waterways. Prevent uncontrolled environmental release.
- Empty containers may retain pigment/carrier residue. Handle contaminated packaging appropriately.
- Follow applicable local, state, and national waste requirements. This is a pigment paste for waste-classification purposes, not flammable resin waste — do not apply this company's resin waste guidance without confirming it is appropriate for the actual composition.

SECTION 14: TRANSPORT INFORMATION

TRANSPORT — NOT A RESIN, NOT AN ORGANIC PEROXIDE

Based on the available product information (paste physical form; no flammable liquid, reactive monomer, or organic peroxide chemistry disclosed), this product does not appear to meet the criteria for a dangerous goods classification under standard transport provisions. This has NOT been separately confirmed by the manufacturer in a formal transport declaration, and colour-specific formulations should be verified individually if their composition varies materially. Do not use UN 1866 / RESIN SOLUTION / Class 3 / Packing Group III for this product — that classification belongs to this company's resin products and does not apply here. Do not use UN 3105 / Organic Peroxide Type D / Class 5.2 — that belongs to MEKP Hardener, a separate product.

UN Number	Not applicable — not indicated as dangerous goods based on available product information (see callout above)
Transport Classification	Not regulated as dangerous goods for transport under applicable provisions, based on available product classification — pending manufacturer confirmation
Special Precautions for User	Transport in tightly closed, properly labelled containers to prevent leakage and contamination.

SECTION 15: REGULATORY INFORMATION

15.1 India

- General workplace chemical-safety requirements under the Factories Act, 1948 and applicable State Factory Rules apply to industrial handling of this product, as they would to any industrial chemical mixture.
- This product is not subject to the styrene-specific occupational exposure requirements, flammable-liquid handling/storage rules, or organic peroxide provisions applied to this company's resin and MEKP products, as none of that chemistry is confirmed present.
- Users must comply with all applicable local, state, national, and transport regulations for the actual composition of the colour supplied.

15.2 Claims Not Made

This SDS does NOT claim that this product (or any specific colour) is heavy-metal-free, lead-free, cadmium-free, chromium-free, RoHS-compliant, REACH-registered, food-contact safe, toy-safety compliant, or automotive-compliance certified. Any such claim requires actual manufacturer test/specification documentation for the specific colour in question, which is not included in the general TDS reviewed for this SDS.

SECTION 16: OTHER INFORMATION

Abbreviations

CAS = Chemical Abstracts Service · FRP = Fibre-Reinforced Plastic · GHS = Globally Harmonized System of Classification and Labelling of Chemicals · OEL = Occupational Exposure Limit · PBT/vPvB = Persistent, Bioaccumulative and Toxic / very Persistent, very Bioaccumulative · RAL = Reichsausschuss für Lieferbedingungen (a European colour-matching standard) · SDS = Safety Data Sheet · UPR = Unsaturated Polyester Resin.

Revision Information

SDS Version / Revision No.	01
Issue Date	8 August 2026
Prepared By	Samrat Poly Resins / Regulatory Department
Reason for Issue	Initial official issue

This SDS has been prepared based on available technical data, manufacturer/chemist-reviewed product information, component hazard data, and applicable safety references. The information is provided for safe handling, storage, transport, use, and disposal of the product. This is a master SDS for a multicolour product family; several sections

cannot be completed beyond 'not established' because the manufacturer's general TDS does not disclose colour-specific pigment, carrier, or additive composition. Users are responsible for confirming suitability for their specific application and for compliance with current regulations at the time of use.