

# Ultracold molecule assembly

Yichao Yu


Ni Group/Harvard

Aug 11, 2017

# Molecules in optical tweezer

## Features


- Strong and tunable interaction
- Rich internal energy levels
- High filling fraction
- Single site detection and manipulation



# Molecules in optical tweezer

## Features


- Strong and tunable interaction
- Rich internal energy levels
- High filling fraction
- Single site detection and manipulation



# Molecules in optical tweezer

## Features


- Strong and tunable interaction
- Rich internal energy levels
- High filling fraction
- Single site detection and manipulation



# Molecules in optical tweezer

## Features


- Strong and tunable interaction
- Rich internal energy levels
- High filling fraction
- Single site detection and manipulation



# Molecules in optical tweezer

## Features

- Strong and tunable interaction
- Rich internal energy levels
- High filling fraction
- Single site detection and manipulation



# Applications

- Simulation of many-body system
- Quantum computation

# Applications


- Simulation of many-body system
- Quantum computation




# Applications

- Simulation of many-body system
- Quantum computation


# Setup




# Setup



## Wave function size mismatch



**Molecule**



**Atom**

### Goal of cooling

- Single initial state
- Shrink wavefunction size

# Raman sideband cooling of Sodium

# Raman sideband cooling of Sodium


## Difficulties

- High initial temperature ( $40\mu K$ )
- High recoil heating (High Lamb Dicke parameter)


# Raman sideband cooling of Sodium


## Difficulties

- High initial temperature ( $40\mu K$ )
- High recoil heating (High Lamb Dicke parameter)












## Raman sidebands




## Raman sidebands




# Raman sidebands




# Raman sidebands



## Rabi flopping (radial)





## Rabi flopping (radial)



Good agreement in ground state probability between spectrum and Rabi flopping data.



# Rabi flopping (axial)



## Conclusion


67.6(3.1)% ground state preparation fidelity (79.5(3.6)% without loss)

## Improvements


- Reduce off-resonance scattering from Raman beams
- Reduce magnetic field fluctuation
- Reduce loss during cooling



# Axial matrix element



## Radial 2 matrix element



# Radial 3 matrix element

