DFT-informed stacked ensembles for experimental composition–property prediction: two pre-registered, fully nested evaluations on Matbench

Bhaskar Gurram

Independent Researcher,

Abstract

Experimental composition–property datasets are small, while computed properties of related compounds are abundant. We evaluate DFT-informed, cross-fitted stacked ensembles on the four composition tasks of Matbench v0.1: steel yield strength, experimental band gap, metallicity and glass formation. The protocol is strict: official folds only, every choice made by cross-validation inside each training fold, and the analysis plan and code frozen by SHA-256 hash before each scoring of the test folds.

Pipeline. Standard composition experts are stacked with simplex weights, with three additions:

- a disclosed transfer-learning block of PBE band gaps and formation energies from offline Materials Project data, matched by reduced formula;
- hurdle experts for the zero-inflated band gap;
- Optuna-tuned gradient boosting.

Results (paired over the same test compositions, using the leaders' public predictions):

- **band gap:** MAE 0.2352 eV against 0.2865 eV for the best leaderboard entry ($p_{\text{Holm}} < 0.001$);
- **metallicity and steel yield strength:** on par with the leaders;

Email address: gurrambhaskar.ai@gmail.com (Bhaskar Gurram)

- **glass formation:** clearly behind.

The leaders use no external DFT data, so these are not like-for-like comparisons of learning algorithms.

A post-hoc ablation attributes the band-gap gain to the DFT block and the hurdle model: without them the MAE is TBD and TBD eV, respectively.

Negative finding. A novelty-damped local residual correction, tested in a first pre-registered run, transferred only weakly from our earlier chemistry work. It was never retained under nested validation.

Metric note. The leaderboard's classification "ROC-AUC" values for the leaders are in effect balanced accuracies.

All computation used one 24-core CPU workstation.

Keywords: materials informatics, experimental band gap, DFT transfer learning, Matbench, stacking, zero-inflated regression, nested cross-validation, pre-registration

---

1. Introduction

Experimental materials properties are expensive to measure, so the datasets are small. Yet for many compounds a cheap computed estimate of a closely related property exists. The experimental band gap is the canonical example. Density-functional theory (DFT) with semi-local functionals underestimates gaps systematically, but the computed gap still carries much of the chemical trend. Large DFT databases such as the Materials Project (Jain et al., 2013) cover tens of thousands of compositions. Using computed values as inputs or as a low-fidelity source has a long history: DFT gaps as features (Lee et al., 2016), multi-fidelity co-kriging (Pilania et al., 2017), stacked transfer from DFT-trained models (Kauwe et al., 2020), deep transfer learning (Jha et al., 2019), multi-fidelity graph networks (Chen et al., 2021), and multi-fidelity denoising (Liu et al., 2022). On the public Matbench v0.1 benchmark (Dunn et al., 2020), however, the composition-only experimental tasks are led by models that use no external computed data. These are a fine-tuned scientific language model (Darwin) on the two band-gap-derived tasks, an AutoML pipeline (TPOT-Mat) on steels, and MODNet (De Breuck et al., 2021) on glass-forming ability (Matbench developers, 2026).

This paper asks how far a DFT-informed but otherwise conventional pipeline gets on these four tasks under a strict protocol. The pipeline is

a cross-fitted stack of composition experts (Wolpert, 1992; Breiman, 1996; van der Laan et al., 2007). The protocol has four rules:

- only the official folds are used;
- every model, hyperparameter and design choice is made by cross-validation inside each training fold;
- the analysis plan is written, and the code frozen by SHA-256 hash, before any test fold is scored;
- every task, fold and comparison is reported.

We report two pre-registered runs.

- **First run.** It tested the transfer of a novelty-damped local out-of-fold residual correction from our earlier chemistry study (Gurram, 2026). The correction transferred only weakly, and we report this as a short negative finding.
- **Second run.** Written after the first run's results were seen, and disclosed as such, it added a DFT feature block, a hurdle model for the zero-inflated band gap (cf. the mixed-variable view of Ma et al., 2025), further descriptors and tuned gradient boosting.

Against the leaders, the DFT-informed pipeline:

- lowers the experimental band-gap MAE below the current best entry;
- is on par for metallicity and steel yield strength;
- remains clearly behind on glass formation.

Because the leaders used no external DFT data, these are not like-for-like comparisons of learning algorithms. They show what disclosed transfer of computed data adds under a fully nested protocol. A post-hoc ablation, labelled as such, separates the contributions of the DFT block and the hurdle model.

2. Methods

2.1. Tasks, splits and protocol

We use the four composition-only tasks of Matbench v0.1 with their official five folds, through `matbench`:

- steels: yield strength, 312 alloys, MAE;
- expt_gap: experimental band gap, 4,604 compounds, MAE;
- expt_is_metal: metallicity, 4,921 compounds, classification;
- glass: glass-forming ability, 5,680 alloys, classification.

Inside each official training fold T_k the rows are split into $J = 5$ inner folds (seed 0). All selection uses only T_k: hyperparameters, the choice among design configurations, stack weights, the optional local correction and classification thresholds. The design space was explored on the training rows of fold 0 only.

Two analysis plans were frozen in turn, each by SHA-256 hashes of all code, and each run scored the test folds once.

- **Run 1 (Amendment 1).** Originally the design was fixed on fold 0's training rows. Amendment 1 moved the choice among the explored configurations inside every training fold. An earlier, superseded run under the original plan was never scored.
- **Run 2 (Amendment 2).** Written after run 1 had been scored.

Plans, amendments, freeze hashes, per-fold predictions and the post-hoc ablation (plan Section 12) are in the repository. The Supplementary Material (SI) gives details.

2.2. Features

All descriptors are deterministic functions of the formula and are computed with `matminer` (Ward et al., 2018a) and `pymatgen` (Ong et al., 2013):

- Magpie element-property statistics (Ward et al., 2016) and element fractions;
- stoichiometric, valence-orbital (Meredig et al., 2014), ionic, band-centre and atomic-orbital descriptors;

- the "deml", "matminer" and "megnet_el" element-property presets;
- Miedema enthalpies, Yang solid-solution parameters (Yang and Zhang, 2012) and atomic packing efficiency (Laws et al., 2015), as implemented by Ward et al. (2018b);
- Wen alloy descriptors and the transition-metal fraction;
- Oliynyk element statistics (Oliynyk et al., 2016).

DFT block (disclosed transfer learning). Each composition is matched by reduced formula to the Materials Project PBE data distributed with `matminer` (`matbench_mp_gap`, joined to `matbench_mp_e_form`). The block contains:

- the gap, metallicity and formation energy of the lowest-formation-energy polymorph;
- the minimum, median and maximum gap over polymorphs, the metallic fraction and the polymorph count;
- a match indicator.

It matches 73% of the expt_gap and expt_is_metal compositions, 1% of glass and none of steels. The block uses no experimental labels and no pretrained model.

2.3. Experts

- **Gradient boosting.** LightGBM (Ke et al., 2017) on all features, tuned inside T_k by Optuna (Akiba et al., 2019): 20 trials, with the default configuration evaluated first. Also XGBoost (Chen and Guestrin, 2016) and CatBoost (Prokhorenkova et al., 2018) with fixed settings.
- **Tree ensembles.** Extremely randomised trees (Geurts et al., 2006) on two feature sets and on element fractions alone.
- **Kernel, neighbour and neural experts** (Pedregosa et al., 2011): kernel ridge regression or RBF support-vector classifiers on element fractions and on Magpie features, distance-weighted k-nearest neighbours, and a two-layer perceptron.

- **Hurdle experts (expt_gap only).** About half of the experimental gaps are exactly zero. Each hurdle expert pairs a classifier for $E_g > 0$ with a regressor fitted on the $E_g > 0$ rows, and combines them as $p\,r$ or as $r \mathbb{1}[p \geq 0.5]$. The latter is the MAE-optimal rule for a point mass at zero plus a positive part.

CrabNet- (Wang et al., 2021) and MODNet-based experts were implemented but dropped, because a single fit exceeded our CPU budget.

2.4. Stack, gated correction and thresholds

Every expert is cross-fitted inside T_k to give out-of-fold (OOF) predictions. A simplex-constrained stack (non-negative weights summing to one) is fitted on these OOF predictions. Its loss is the MAE for regression and the Brier score for classification.

The local OOF residual correction of run 1 adds a kernel-weighted, novelty-damped average of neighbouring training residuals (SI Section S2). In run 2 it is kept only if a nested inner-CV check confirms that it improves the honest OOF score.

Hard labels use the threshold that maximises balanced accuracy on the training OOF predictions.

2.5. Endpoints and statistics

The endpoints follow the board's semantics.

- **Regression:** MAE.
- **Classification:** balanced accuracy, because the leaders either recorded labels (Darwin) or were scored by a `matbench` version that thresholded probabilities at 0.5 (MODNet v0.1.12), which makes their reported "ROC-AUC" equal to their balanced accuracy.
- **Run 2 primary comparison:** our final pipeline versus each task's leader, paired over the same test compositions using the leaders' public per-sample predictions.

The test is a bootstrap over test points within folds ($B = 10^4$), with Holm correction over the four tasks. We claim to beat a leader only if our mean is better and the Holm-adjusted $p < 0.05$. Run 1's primary endpoint (corrected versus uncorrected stack) used the same bootstrap. The same statistics are used for the post-hoc ablation, which is descriptive only.

Table 1: Run-2 (Amendment-2) final pipeline versus each task's leaderboard leader, paired over the official test compositions using the leaders' public per-sample predictions. Metrics follow the board: MAE; balanced accuracy for classification. Δ is ours minus the leader. 95% CI: paired bootstrap over test points within folds. Holm correction over four tasks. Rank is among the entries of 18 October 2026, including ours.

Task	Metric	Final pipeline	Leader (board)	Δ [95% CI]	p_{Holm}	Rank
steels	MAE	80.10 ± 10.19	TPOT-Mat: 79.95	+0.1577 [-4.54, +4.89]	0.928	2 of 12
expt_gap	MAE	0.2352 ± 0.0167	Darwin: 0.2865	-0.05131 [-0.0701, -0.0331]	<0.001	1 of 13
expt_is_metal	bal. acc.	0.9547 ± 0.0033	Darwin: 0.9598	-0.005093 [-0.0118, +0.00179]	0.299	2 of 8
glass	bal. acc.	0.8937 ± 0.0158	MODNet (v0.1.12): 0.9603	-0.06658 [-0.0759, -0.0573]	<0.001	2 of 8

3. Results

3.1. The DFT-informed pipeline versus the leaderboard (run 2)

Table 1 and Fig. 1 compare the frozen run-2 pipeline with each task's leader.

expt_gap. The MAE is 0.2352 eV against 0.2865 eV for Darwin. The difference is $\Delta = -0.05131$ eV (95% CI [-0.0701, -0.0331]; $p_{\text{Holm}} < 0.001$). This is the only task that meets our pre-registered rule for beating the leader.

expt_is_metal and steels. The pipeline is statistically on par with the leaders:

- expt_is_metal: balanced accuracy 0.9547 versus 0.9598 ($p_{\text{Holm}} = 0.299$);
- steels: MAE 80.10 versus 79.95 MPa ($p_{\text{Holm}} = 0.928$).

glass. The pipeline is clearly behind MODNet v0.1.12: 0.8937 versus 0.9603 ($p_{\text{Holm}} < 0.001$). This also holds for the probability ROC-AUC (0.9606 versus 0.9899).

Caveat. These are not like-for-like comparisons. Our pipeline uses an external DFT block for expt_gap and expt_is_metal, and the leaders did not (Section 4).

3.2. Where the gain comes from: post-hoc ablation

The ablation in Table 2 was written after run 2 had been scored and was not used for any selection; the reported pipeline is unchanged. It re-runs the frozen run-2 code, either without the DFT block (all tasks) or without the hurdle experts (expt_gap).




Figure 1: Per-fold board metric of the run-2 final pipeline, the task leader and the run-1 primary arm.

Table 2: Post-hoc ablation of the frozen run-2 pipeline (plan Section 12; not used for selection). Board metric of the run-2 final pipeline and of each variant; paired bootstrap of the difference; number of folds in which the variant is worse; the leader's value, with the p-value of the variant versus the leader.

egintabularl TBD ndtabular

expt_ gap.

- Without the DFT block, the MAE rises to TBD eV (TBD% relative to the full pipeline, $p_{\text{boot}} = TBD$).
- Without the hurdle experts, it rises to TBD eV (TBD%, $p_{\text{boot}} = TBD$).

expt_ is_ metal. Removing the DFT block changes the balanced accuracy to TBD (TBD%, $p_{\text{boot}} = TBD$).

glass and steels. The DFT block matches few or none of the compositions on these tasks, and removing it changes little:

- glass: TBD%;
- steels: TBD%.

3.3. The local residual correction: a negative finding (run 1)

Run 1 pre-registered a single primary question: does the novelty-damped local OOF residual correction improve a cross-fitted stack on these tasks?

Table 3: Board metric of the two pre-registered pipelines on the official folds, with a paired bootstrap p-value for the difference.

Task	Amendment 1 (primary arm)	Amendment 2 (final)	p_{boot}
steels	82.80	80.10	0.288
expt_gap	0.3240	0.2352	<0.001
expt_is_metal	0.9370	0.9547	<0.001
glass	0.8841	0.8937	<0.001

- **expt_gap.** It improved the MAE from 0.3264 to 0.3240 eV (-0.71%; 5/5 folds; $p_{\text{Holm}} = 0.005$).
- **steels.** No detectable effect (-0.39%).
- **Classification tasks.** The inner selection almost never switched the correction on (0/5 and 1/5 folds).

Stratifying the test errors by distance to the nearest training composition showed the correction *hurting* for near-duplicate compositions (expt_gap +0.9%, steels +6.8% in the nearest quartile). A fold-matched variant designed to remove the double counting behind this did not help (+1.10% MAE versus the naive correction on expt_gap). In run 2 the nested gate kept the correction in none of the 20 folds. The SI reports all run-1 arms, ablations and controls.

3.4. Stacking and the two runs

Run 2 improved on run 1 on every task (Table 3). The improvement is large on expt_gap and expt_is_metal, and within noise on steels ($p = 0.288$). The simplex stack beat the best single expert selected by inner CV only on glass (+0.18% ROC-AUC, $p = 0.014$). Elsewhere it matched that expert. On steels, extremely randomised trees on element fractions alone reached 79.56 MPa as the best single expert, against 80.10 MPa for the pre-registered stack, which we report. One official fold took a median of 9–62 minutes on a 24-core CPU workstation with five parallel workers.

4. Discussion

Like-for-like caveat. The expt_gap result is not a like-for-like comparison of learning algorithms. Our pipeline feeds PBE band gaps and formation ener-

gies from the Materials Project into the experts. The leaders use no external computed data: Darwin is a scientific language model fine-tuned on the task, and MODNet and TPOT-Mat use only composition descriptors. What the result does show is the value of disclosed DFT transfer on this benchmark, under a protocol in which every choice is made inside the training folds. This agrees with a long line of work showing that computed gaps are informative inputs or low-fidelity sources for experimental gaps (Lee et al., 2016; Pilania et al., 2017; Kauwe et al., 2020; Chen et al., 2021; Liu et al., 2022; Ko et al., 2024). The ablation separates two sources of gain on expt_gap: the DFT block, and an explicit treatment of the point mass at $E_g = 0$.

Where the pipeline does not lead. On glass, MODNet v0.1.12's public predictions reach a probability ROC-AUC of 0.9899, against our 0.9606. Neither the glass-formation descriptors nor any CPU-feasible expert we tried closed this gap. On expt_is_metal and steels the pipeline is statistically on par with the leaders. We did not audit the leaders' protocols, for example whether all of their tuning was confined to the training folds.

Classification metrics. The board's "ROC-AUC" for the classification leaders is, in effect, balanced accuracy. Darwin recorded labels. MODNet recorded probabilities that the `matbench` version used for its board entry thresholded at 0.5. Our probability ROC-AUC on expt_is_metal (0.9895) is therefore not comparable to the board's numbers. We recommend reporting both quantities in separate columns.

The local correction. The local residual correction that motivated this work transferred only weakly from chemistry to materials. Once its benefit had to survive a nested inner-CV check, it was never kept. We report it as a negative result.

Limitations.

- **Two looks at the test folds.** Run 2 was written after run 1 had been scored, so its motivation, though none of its choices, depended on the first test results. Both runs are reported.
- **Candidate space from fold 0.** The candidate feature blocks and expert pool were developed on fold 0's training rows. Those rows contain the test rows of folds 1–4.

- **Optimistic tuning OOF.** The tuned expert's OOF predictions are mildly optimistic, because tuning and stacking share inner splits. This can affect only the stack weights.
- **Scope.** Four tasks, CPU-feasible experts only, five folds and a single seed limit the power and generality of the conclusions.
- **Post-hoc ablation.** The ablation is descriptive.

5. Conclusions

Under two pre-registered, fully nested protocols on the Matbench v0.1 composition tasks, a cross-fitted stack of standard experts with a disclosed DFT feature block and a hurdle model for zero-inflated gaps:

- lowered the experimental band-gap MAE to 0.2352 eV, below the current leader;
- was on par with the leaders for metallicity and steel yield strength;
- remained behind on glass formation.

The local residual correction that originally motivated the study did not survive nested validation.

Data and code availability

All code, the frozen analysis plan (`ANALYSIS_PLAN.md`), SHA-256 freeze hashes, per-fold predictions of every arm, per-fold metrics and the unsubmitted Matbench result files are in the repository `https://github.com/bhaskargurram-ai/matbench-composition-stack`, which will be made public on submission. The data are the public Matbench v0.1 tasks.

Affiliation

The author is an independent researcher with no institutional affiliation.

CRediT authorship contribution statement

Bhaskar Gurram: Conceptualization, Methodology, Software, Formal analysis, Investigation, Writing – original draft, Writing – review & editing.

Declaration of competing interest

The author declares no competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

Declaration of generative AI and AI-assisted technologies in the writing process

During the preparation of this work the author used Claude (Anthropic), running the ResearchStudio idea-generation skills, to assist with literature search, prior-art checking, code development and drafting of the manuscript. All analysis code, results and text were reviewed by the author, who takes full responsibility for the content of the publication.

Funding

This research did not receive any specific grant from funding agencies in the public, commercial, or not-for-profit sectors.

References

Akiba, T., Sano, S., Yanase, T., Ohta, T., Koyama, M., 2019. Optuna: A Next-generation Hyperparameter Optimization Framework, in: Proceedings of the 25th ACM SIGKDD International Conference on Knowledge Discovery & Data Mining, pp. 2623–2631. doi:10.1145/3292500.3330701.

Breiman, L., 1996. Stacked regressions. Machine Learning 24, 49–64. doi:10.1007/BF00117832.

Chen, C., Zuo, Y., Ye, W., Li, X., Ong, S.P., 2021. Learning properties of ordered and disordered materials from multi-fidelity data. Nature Computational Science 1, 46–53. doi:10.1038/s43588-020-00002-x.

Chen, T., Guestrin, C., 2016. XGBoost, in: Proceedings of the 22nd ACM SIGKDD International Conference on Knowledge Discovery and Data Mining, pp. 785–794. doi:10.1145/2939672.2939785.

De Breuck, P.P., Hautier, G., Rignanese, G.M., 2021. Materials property prediction for limited datasets enabled by feature selection and joint learning with MODNet. npj Computational Materials 7, 83. doi:10.1038/s41524-021-00552-2.

Dunn, A., Wang, Q., Ganose, A., Dopp, D., Jain, A., 2020. Benchmarking materials property prediction methods: the Matbench test set and Automatminer reference algorithm. npj Computational Materials 6, 138. doi:10.1038/s41524-020-00406-3.

Geurts, P., Ernst, D., Wehenkel, L., 2006. Extremely randomized trees. Machine Learning 63, 3–42. doi:10.1007/s10994-006-6226-1.

Gurram, B., 2026. SIG-Net: cross-fitted stacking with a novelty-damped local out-of-fold residual correction. Manuscript submitted; code at https://github.com/bhaskargurram-ai/SIG-Net.

Jain, A., Ong, S.P., Hautier, G., Chen, W., Richards, W.D., Dacek, S., Cholia, S., Gunter, D., Skinner, D., Ceder, G., Persson, K.A., 2013. Commentary: The Materials Project: A materials genome approach to accelerating materials innovation. APL Materials 1, 011002. doi:10.1063/1.4812323.

Jha, D., Choudhary, K., Tavazza, F., keng Liao, W., Choudhary, A., Campbell, C., Agrawal, A., 2019. Enhancing materials property prediction by leveraging computational and experimental data using deep transfer learning. Nature Communications 10, 5316. doi:10.1038/s41467-019-13297-w.

Kauwe, S.K., Welker, T., Sparks, T.D., 2020. Extracting Knowledge from DFT: Experimental Band Gap Predictions Through Ensemble Learning. Integrating Materials and Manufacturing Innovation 9, 213–220. doi:10.1007/s40192-020-00178-0.

Ke, G., Meng, Q., Finley, T., Wang, T., Chen, W., Ma, W., Ye, Q., Liu, T.Y., 2017. LightGBM: A Highly Efficient Gradient Boosting Decision Tree, in: Advances in Neural Information Processing Systems 30.

Ko, T., Park, T., Kim, M., Min, K., 2024. Enhancing predictions of experimental band gap using machine learning and knowledge transfer. Materials Today Communications 41, 110717. doi:10.1016/j.mtcomm.2024.110717.

van der Laan, M.J., Polley, E.C., Hubbard, A.E., 2007. Super Learner. Statistical Applications in Genetics and Molecular Biology 6. doi:10.2202/1544-6115.1309.

Laws, K.J., Miracle, D.B., Ferry, M., 2015. A predictive structural model for bulk metallic glasses. Nature Communications 6, 8123. doi:10.1038/ncomms9123.

Lee, J., Seko, A., Shitara, K., Nakayama, K., Tanaka, I., 2016. Prediction model of band gap for inorganic compounds by combination of density functional theory calculations and machine learning techniques. Physical Review B 93, 115104. doi:10.1103/PhysRevB.93.115104.

Liu, X., De Breuck, P.P., Wang, L., Rignanese, G.M., 2022. A simple denoising approach to exploit multi-fidelity data for machine learning materials properties. npj Computational Materials 8, 233. doi:10.1038/s41524-022-00925-1.

Ma, A., Dugan, O., Soljačić, M., 2025. Predicting band gap from chemical composition: A simple learned model for a material property with atypical statistics. arXiv:2501.02932.

Matbench developers, 2026. Matbench leaderboard (per-task leaderboards, matbench v0.1). https://matbench.materialsproject.org/. Accessed 18 October 2026.

Meredig, B., Agrawal, A., Kirklin, S., Saal, J.E., Doak, J.W., Thompson, A., Zhang, K., Choudhary, A., Wolverton, C., 2014. Combinatorial screening for new materials in unconstrained composition space with machine learning. Physical Review B 89, 094104. doi:10.1103/PhysRevB.89.094104.

Oliynyk, A.O., Antono, E., Sparks, T.D., Ghadbeigi, L., Gaultois, M.W., Meredig, B., Mar, A., 2016. High-Throughput Machine-Learning-Driven Synthesis of Full-Heusler Compounds. Chemistry of Materials 28, 7324–7331. doi:10.1021/acs.chemmater.6b02724.

Ong, S.P., Richards, W.D., Jain, A., Hautier, G., Kocher, M., Cholia, S., Gunter, D., Chevrier, V.L., Persson, K.A., Ceder, G., 2013. Python Materials Genomics (pymatgen): A robust, open-source python library for materials analysis. Computational Materials Science 68, 314–319. doi:10.1016/j.commatsci.2012.10.028.

Pedregosa, F., Varoquaux, G., Gramfort, A., Michel, V., Thirion, B., Grisel, O., Blondel, M., Prettenhofer, P., Weiss, R., Dubourg, V., Vanderplas, J.,

Passos, A., Cournapeau, D., Brucher, M., Perrot, M., Duchesnay, É., 2011. Scikit-learn: Machine Learning in Python. Journal of Machine Learning Research 12, 2825–2830.

Pilania, G., Gubernatis, J., Lookman, T., 2017. Multi-fidelity machine learning models for accurate bandgap predictions of solids. Computational Materials Science 129, 156–163. doi:10.1016/j.commatsci.2016.12.004.

Prokhorenkova, L., Gusev, G., Vorobev, A., Dorogush, A.V., Gulin, A., 2018. CatBoost: unbiased boosting with categorical features, in: Advances in Neural Information Processing Systems 31.

Wang, A.Y.T., Kauwe, S.K., Murdock, R.J., Sparks, T.D., 2021. Compositionally restricted attention-based network for materials property predictions. npj Computational Materials 7, 77. doi:10.1038/s41524-021-00545-1.

Ward, L., Agrawal, A., Choudhary, A., Wolverton, C., 2016. A general-purpose machine learning framework for predicting properties of inorganic materials. npj Computational Materials 2, 16028. doi:10.1038/npjcompumats.2016.28.

Ward, L., Dunn, A., Faghaninia, A., Zimmermann, N.E., Bajaj, S., Wang, Q., Montoya, J., Chen, J., Bystrom, K., Dylla, M., Chard, K., Asta, M., Persson, K.A., Snyder, G.J., Foster, I., Jain, A., 2018a. Matminer: An open source toolkit for materials data mining. Computational Materials Science 152, 60–69. doi:10.1016/j.commatsci.2018.05.018.

Ward, L., O'Keeffe, S.C., Stevick, J., Jelbert, G.R., Aykol, M., Wolverton, C., 2018b. A machine learning approach for engineering bulk metallic glass alloys. Acta Materialia 159, 102–111. doi:10.1016/j.actamat.2018.08.002.

Wolpert, D.H., 1992. Stacked generalization. Neural Networks 5, 241–259. doi:10.1016/S0893-6080(05)80023-1.

Yang, X., Zhang, Y., 2012. Prediction of high-entropy stabilized solid-solution in multi-component alloys. Materials Chemistry and Physics 132, 233–238. doi:10.1016/j.matchemphys.2011.11.021.