





↗	0.02	A

GEAR DATA

NUMBER OF TEETH	z	23
NORMAL MODULE	mn	2.5
PRESSURE ANGLE	α	20°
HELIX ANGLE	β	15° RH
FACE WIDTH	b	20
PROFILE SHIFT COEFFICIENT	x	+0.25
GEAR QUALITY		ISO 1328 CLASS 6

NOTES:

1. CASE HARDENED AND TEMPERED. CHD 550 HV1 0.6-0.9 mm.
2. SURFACE HARDNESS 58-62 HRC, CORE HARDNESS 30-42 HRC.
3. TOOTH FLANKS GROUND AFTER HEAT TREATMENT.
4. 100% CRACK DETECTION AFTER GRINDING.
5. BREAK SHARP EDGES 0.2-0.5.

TITLE		MATERIAL	
HELICAL GEAR Z23		16MnCr5 EN ISO 683-3	
PART NO.	DWG NO.	REV	
HG-23-0417	HG-23-0417	B	
HEAT TREATMENT	GENERAL TOLERANCE	MASS	
CASE HARDEN 58-62 HRC	ISO 2768-mK	0.61 kg	
SCALE	DATE	SHEET	CHECKED
1:1	2026-04-02	1 OF 1	T. BAUER